MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES) INSULATING COMPOUND, TYPE IS-MEDIUM-LOW TEMPERATURE, STYRENE-BUTADIENE RUBBER (SBR)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Insulating Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

		WALLS 6 TO 20 MILS THICK	WALLS OVER 20 MILS THICK
UNAGED:			
Tensile strength, minimum psi	=	450	600
Elongation, minimum percent	=	200	250
Set, maximum, inch	=	.500	500
AFTER 95 ± 1/2 HOUR OXYGEN BOMB AGING AT 70°C:			
Tensile strength, minimum percent of original	=	75	75
Elongation, minimum percent of original	=	65	65
OZONE RESISTANCE (AFTER AIR OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):			
At 100°F	=	No visible cracks	No visible cracks
BRITTLENESS TEMPERATURE UNAGED:			
Max C°	=	-40	-40
AFTER OVEN-AGING:			
Max C°	=	-40	-40

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-02)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T22:23Z
Check the source to verify that this is the current version before use.