MILITARY SPECIFICATION SHEET

INSULATING AND JACKETING COMPOUNDS, ELECTRICAL (FOR CABLES, CORDS, AND WIRES), INSULATING COMPOUND, TYPE IL-H-LOW TEMPERATURE, HEAT-RESISTANT, NATURAL RUBBER DEPOSITED FROM A RUBBER-LATEX COMPOUND

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the Insulating Compound described herein shall consist of this specification and the latest issue of MIL-I-3930.

PHYSICAL PROPERTY REQUIREMENTS

UNAGED:		
Tensile strength, minimum psi	=	2500
Elongation, minimum percent	=	600
Set, maximum, inch	=	.063
AFTER 168 ± 1 HOUR OXYGEN BOMB AGING AT 80°C:		
Tensile strength, minimum percent of original	=	50
Elongation, minimum percent of original	=	50
AFTER 20 ± 1/2 HOUR AIR PRESSURE AGING AT 127°C:		
Tensile strength, minimum percent of original	=	50
Elongation, minimum percent of original	=	50
OZONE RESISTANCE (AFTER AIR OVEN CONDITIONING AND 168 ± 1 HOUR IN OZONE):		
At 100° F	=	No visible cracks
BRITTLENESS TEMPERATURE (MAXIMUM °C):		
Unaged	=	-55
Oven aged	=	-55

Custodians:
Army - CR
Air Force - 85

Preparing activity:
Army - CR

(Project 5970-0560-07)

Review Activities:
Army - AR, ME, MI

Agent
DLA-IS

FSC 5970

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil - Downloaded: 2026-10-16T22:24Z
Check the source to verify that this is the current version before use.