MIL-M-43120D
28 June 1988
SUPERSEDING
MIL-M-43120C
15 November 1982

MILITARY SPECIFICATION

MAINTENANCE KIT, ROCKET FUEL HANDLERS' CLOTHING

(RESIN MODIFIED BUTYL RUBBER COATED)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a maintenance kit containing patches, adhesive, abrasive, and protective coating for the repair of rocket fuel handlers' clothing.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

UU-T-595	- Towel, Wiping, Paper: Industrial and Institutional
PPP-B-26	- Bag, Plastic, (General Purpose)
PPP-B-566	- Boxes, Folding, Paperboard
PPP-B-636	- Boxes, Shipping, Fiberboard
PPP-B-676	- Boxes, Setup
PPP-T-45	- Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing
PPP-T-1637	- Tubes, Shipping, Collapsible

MILITARY

MIL-L-35078	- Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For
MIL-C-43062	- Cloth, Coated, Nylon, Resin Modified Butyl Coated, Acid and Fuel Resistant

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members for Containers and Pallets

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

* 3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Components. The maintenance kit shall consist of the following components:

a. 14 patches (10 round patches and 4 rectangular patches)
b. Tube of cement
c. Tube of protective coating
d. Strip of abrasive
e. 2 paper towels
f. Instruction card
g. Plastic film bag

3.3 Materials.

3.3.1 Patches. The patches shall be fully vulcanized coated cloth made from resin modified butyl coated cloth conforming to MIL-C-43062. The patches shall have a contact side and a face side. The contact side shall have a coating of the cement (adhesive) specified in 3.3.2. The dry film thickness of the cement coating shall be 2-1/2 to 5 mils. The cemented side of the patches shall be covered with aluminum foil, 3-1/2 mils thick. The foil shall be in two pieces, each having a 3/8 inch minimum flap to assist in removal. The patches shall measure 1-1/2 inches ± 1/16 inch diameter for round patches and 2-1/2 inches ± 1/16 inch by 4-1/4 inches ± 1/16 inch for rectangular patches.

3.3.2 Cement. The cement (adhesive) shall be made in accordance with the formulation listed below (see 6.4.1). The cement shall be aged at least 48 hours before testing and shall be made up one month or less in advance of the assembly of the maintenance kits.

Hycar 2202 or equal	100 grams
Bakelite CKR 1282 or equal	30 grams
Trichloroethylene	500 grams

A minimum of 25 milliliters of the cement shall be contained in a collapsible tube conforming to 3.3.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

3.3.3 Protective coating compound. The protective coating compound shall be made in accordance with the formulation listed below (see 6.4.1). The compound shall be aged at least 48 hours before testing and shall be made up one month or less in advance of the assembly of the maintenance kits.

Hypalon 40 or equal	100 grams
Bakelite CRK 1282 or equal	30 grams
Trichloroethylene	900 grams

A minimum of 25 milliliters of the protective coating compound shall be contained in a collapsible tube conforming to 3.3.4.

* 3.3.4 Tubes for cement and protective coating compound. The tubes for the cement and protective coating compound shall be collapsible conforming to type I, class 2, style 2 of PPP-T-1637, 7/8 inch tube size, approximately 4-3/4 inch tube length, number 12 diameter orifice code, with cap and liner. The tube shall be securely closed with a crimped number 4 fold, or a double fold with closure sealant suitable for the contents. The tubes shall be permanently and legibly labeled, using letters 1/8 inch minimum height, with the following information:

CEMENT or PROTECTIVE COATING (as applicable)

CAUTION!
Trichloroethylene is a suspected
carcinogen, having been shown to
cause cancer in some animals.
Do not breathe vapors.
Use only in well-ventilated areas.
Avoid skin and eye contact.
May cause skin and eye irritation.

3.3.5 Abrasive. The abrasive strip shall consist of 120 mesh silicon carbide bonded to both sides of a 24 mesh backing in a waterproof grade. The abrasive strip shall measure 3-1/2 inches ± 1/16 inch by 1-1/2 inches ± 1/16 inch (see 6.4.2).

3.3.5.1 Resistance to water. There shall be no appreciable loosening or loss of abrasive particles from the strip when tested as specified in 4.4.3.

3.3.6 Paper towels. The paper towels shall conform to type I of UU-T-595. The towels shall be folded as required to fit neatly into the plastic bag.

* 3.3.7 Instruction card. The instructions shall be printed on index paper, 3 inches by 5 inches minimum, using elite type or equal and shall be inserted into the plastic bag so that the instructions are legible in their entirety without opening the kit. The text of the instructions shall be as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS

MAINTENANCE KIT, ROCKET FUEL HANDLERS' CLOTHING

(RESIN MODIFIED BUTYL RUBBER COATED)

CAUTION: USE ONLY IN WELL-VENTILATED AREA

1. CLEAN AND DRY THE AREA TO BE PATCHED WITH PAPER TOWEL.

2. BUFF AREA LIGHTLY WITH ABRASIVE.

3. APPLY A VERY THIN COAT OF CEMENT OVER THE AREA TO BE PATCHED, SPREAD EVENLY WITH AN APPLICATOR, ALLOW TO DRY 20 TO 30 SECONDS. AVOID BREATHING VAPORS. AVOID SKIN CONTACT.

4. REMOVE BACKING FROM PATCH. DO NOT TOUCH FRESH PATCH SURFACE.

5. APPLY PATCH. PRESS FIRMLY IN PLACE.

6. APPLY CONTINUOUS FILM OF PROTECTIVE COATING OVER EDGES OF PATCH AND THE CEMENT AREA EXTENDING BEYOND.

7. AFTER 10 MINUTES, RECOAT WITH A SECOND HEAVY PROTECTIVE COATING.

Manufacturer's name
Date manufactured (month and year)
Shelf life expiration date (same month - 1 year later)

3.3.8 Bag, plastic. The plastic bag shall conform to type II, style 1, of PPP-B-26. The film shall be natural color and 0.004-inch thick. Size of the bag shall be approximately 5-1/2 by 3-1/2 inches.

* 3.4 Assembly of kit. The components shall be arranged within the plastic bag so that the instructions on the instruction card are legible in their entirety without opening the kit. The abrasive strip, folded paper towels, patches and collapsible tubes shall be evenly and compactly stacked so that the instruction card is held firmly in place. The bag shall be closed by heat sealing. Prior to or during the heat sealing closure operation, excess air within the bag shall be expelled.

3.5 Performance of patch.

3.5.1 Resistance to creep. The average creep of each of the three sets of five specimens shall not exceed 1/8 inch when tested as specified in 4.4.3.

3.5.2 Flexibility of low temperature. The bonded patch shall not crack and shall not separate from the test sheet when tested as specified in 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

3.5.3 Accelerated aging. There shall be no cracking, checking, or lifting of the test patch and there shall be no cracking or checking of the surrounding area of the test fabric into which the cement film extends for a short distance, when tested as specified in 4.4.3.

3.5.4 Application at low temperature. The adhesive shall be spreadable without undue difficulty at 32°F and at least one of the three patches applied and tested as specified in 4.4.3 shall be fully adhered, i.e., without lifting the edge at end of test.

3.6 Workmanship. The maintenance kits shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

* 4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2 and tested for the characteristics specified in 4.4.3. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.1.1 Certification. A certificate of compliance will be acceptable as evidence that the cement and protective coating compound comply with the formulation and volume requirements specified in 3.3.2 and 3.3.3.

4.4.2 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of maintenance kits. The sample unit shall be one complete kit. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

NOTE: This examination shall be performed on repair kits completely sealed within the plastic bag. After the examination of the bag for closure, the bag shall be opened and the contents examined.

TABLE I. End item visual defects

Examine	Defect
General (as applicable to components)	Any component omitted or not as specified Any component defective
Plastic bag	Not transparent Not completely sealed Any hole, cut, or tear

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect
Patches	Brittle Tacky on noncontact side Any hole, cut, tear, or rip Any defect in coating Backing omitted or does not completely cover contact surface of patch Backing not two pieces or the two pieces are not provided with flaps as specified Embedded foreign matter Size not as specified
Tubes	Not type specified Not properly labeled Not folded and crimped as specified Crimping clamp missing Any defect that may result in leakage of contents
Abrasive strip	Not as specified Insufficient abrasive material to perform the function intended Inadequate bond of abrasive material to a degree where the strip will not perform as intended Size not as specified
Paper towels	Not as specified
Instruction card	Missing, incomplete, not legible, size or kind of characters not as specified, not fabricated of index paper, size of card not as specified

* 4.4.3 End item testing. The end item (kit containing all components) shall be tested for the characteristics listed in table II. The lot size shall be expressed in units of completely assembled maintenance kits. The sample unit shall be three complete kits and 1-1/2 yards of the coated fabric conforming to MIL-C-43062. The sample size shall be 5, and the requirements for all characteristics shall be applicable to the sample unit. There shall be no failure of any of the sample units to meet the specified requirements. All test reports shall contain the individual values utilized in expressing the final results.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

TABLE II. End item tests

Characteristic	Requirement	Test method	Number of determinations per sample unit	Results reported as: Pass or fail	Results reported as: Numerically to nearest
Abrasive strip after water immersion	3.3.5.1	4.5.5	1	X	-
Resistance to creep (for each condition)	3.5.1	4.5.1	5	-	1/16 inch
Flexibility at low temperature	3.5.2	4.5.2	3	X	-
Accelerated aging of patched area	3.5.3	4.5.3	3	X	-
Patch application at low temperature	3.5.4	4.5.4	3	X	-

4.4.4 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

Examine	Defect
Content	Number of kits per intermediate pack and number of intermediate packs per shipping container less than required 1/

1/ For this defect, one container in the sample shall be examined.

* 4.4.5 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Resistance to creep. The test surface shall consist of a swatch of the vulcanized coated fabric conforming to MIL-C-43062. Allow patches applied in accordance with kit instructions to condition at 75° ± 5°F for 1 hour minimum. Cut the patches in 1-inch wide strips in either the warp or filling direction.

4.5.1.1 One hour after bonding. After 1-hour conditioning, suspend the test specimens using any suitable horizontal support for securing the coated fabric strip. Peel back the upper edge of the patch for a distance of 1/2 inch, mark that point accurately, and apply 3 ounces of weight (including weight holder) to the patch tab in such a way as to produce a peel force on the adhesive. Arrange the specimens to hang vertically and freely without twist. Allow each weight to hang thus for 4 hours minimum, after which the distance of additional separation of the patch tab shall be measured.

4.5.1.2 One day after bonding. The test specimens shall be tested as described in 4.5.1.1 except that the test shall begin after the bond has been conditioned 24 hours minimum at 75 ± 5°F and a 5-ounce weight shall be used in lieu of a 3-ounce weight.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

4.5.1.3 Test on heat-aged kit. The test specimens shall be prepared from unopened kits that have been maintained at 158° ± 2°F for 7 days in a circulating air oven. The specimens shall be tested as described in 4.5.1.1.

4.5.2 Flexibility at low temperature. Apply a 1-1/2 inch patch from a sample kit to a piece of the vulcanized coated fabric conforming to MIL-C-43062 according to kit instructions. Allow to condition for 72 hours minimum at 75° ± 5°F and then expose to a temperature of minus 20° ± 2°F for not less than 4 hours. While at this temperature, bend the bonded portion, patch outward over a 1/2-inch diameter mandrel. The specimen shall be positioned so that the leading edge of the patch is directly over the center of the mandrel. Examine the patch and adhesive for cracking and lifting.

4.5.3 Accelerated aging of patched area. Wrap a length of the vulcanized, coated fabric conforming to MIL-C-43062 around a 1 inch in diameter mandrel, and clamp the free ends together. Apply three 1-1/2 inch patches in a line along the mandrel in accordance with kit instructions. Allow to stand at 75° ± 5°F for 2 days and then place in a circulating air oven at 158° ± 2°F for 7 days. Remove from oven and examine patch and adjacent area of coated fabric for checking and cracking of the surfaces and for lifting of the patch at the edge.

4.5.4 Patch application at low temperature. Wrap a length of the vulcanized coated fabric conforming to MIL-C-43062 around a 1-inch in diameter mandrel and clamp the free ends together to make a snug wrap. Condition the wrapped fabric and sample maintenance kit for 4 hours minimum at plus 32° ± 2°F. Without removing from this temperature, apply three 1-1/2 inch patches in a line along the wrapped mandrel, following kit instructions, except that before pressing patches into place the cement shall be allowed to dry 1 minute for the first patch, 3 minutes for the second patch, and 5 minutes for the third patch.

4.5.5 Abrasive strip after water immersion. Immerse a 1 inch by 1 inch specimen of the abrasive strip in water at 75° ± 5°F for 10 minutes. Remove specimen from the water, blot dry, and examine for evidence of flaking or looseness of the grit.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A. Ten maintenance kits, assembled as specified in 3.4, shall be packed in an intermediate paperboard box conforming to variety 1, style III, type G, class i of PPP-B-566; or a setup paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676. The maintenance kits shall be arranged on edge, two in length, five in width, and one in depth within a box. Inside dimensions of each box shall be approximately 11 inches in length, 5 inches in width, and 3-1/2 inches in depth. Approximate dimensions are furnished as a guide only. Box closure shall be secured with 2 inches

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

minimum width gummed paper tape conforming to type III, grade B of PPP-T-45 applied at the center of the length opening and extending along the bottom and up the sides at least 2 inches.

* 5.1.2 Commercial. Maintenance kits shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

* 5.2.1 Level A packing. Sixty maintenance kits, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A intermediate packed maintenance kits shall be packed flat, three in length, one in width, and two in depth. Inside dimensions of each shipping container shall be approximately 15-3/4 inches in length, 11-1/4 inches in width, and 7-1/4 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). When unit loads are strapped, strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Sixty maintenance kits, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC, type CF, (variety SW) or type SF, class domestic, grade 275 of PPP-B-636. Level A intermediate packed maintenance kits shall be packed flat, three in length, one in width and two in depth. Inside dimensions of each shipping container shall be approximately 15-3/4 inches in length, 11-1/4 inches in width, and 7-1/4 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall be closed in accordance with method II of the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be V3c, V3s, or V4s, fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.4.

* 5.2.3 Commercial packing. Maintenance kits, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Palletization. When specified (see 6.2), shelters, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 9 in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, intermediate packs and shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

* 5.4.1 Special marking. Each intermediate pack and shipping container shall be marked in accordance with the applicable type I shelf-life item marking requirements specified in MIL-STD-129. The expiration date shall be 1 year after the date the kit is assembled.

6. NOTES

6.1 Intended use. The maintenance kit is for repair of a puncture or small tear in rocket fuel handlers' clothing (resin modified butyl rubber coated).

* 6.2 Ordering data. Acquistion documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.1, 4.3, and 6.3).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. Type and class of unit load required (see 5.2.1).
e. When weather-resistant grade shipping containers are required for level B shipments (see 5.2.2.1).
f. When palletization is required (see 5.3).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.4 Materials.

6.4.1 Adhesive and coating material. The materials specified in 3.3.2 and 3.3.3 are obtainable from the following sources:

Hycar 2202	- B. F. Goodrich Chemical Company
Bakelite CKR 1282	- Union Carbide Chemical Company
Hypalon 40	- E. I. Dupont de Nemours Company

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

6.4.2 Abrasive materials. The following abrasives have been found to conform to the requirements specified in 3.3.5.

Gritcloth C 120	- Bay State Abrasives Company, Westboro, MA
Fabricut 120	- 3M Co., St. Paul, MN

* 6.5 Subject term (key word) listing.

Maintenance kit
Protective clothing
Repair kit

6.6 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activity:

Air Force - 45

Preparing activity:

Army - GL

Project No. 8415-0621

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
MIL-M-43120D	Maintenance Kit, Rocket Fuel Handlers' Clothing (Resin Modified Butyl Rubber Coated)

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b ADDRESS *(Street City State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5 PROBLEM AREAS

a. Paragraph Number and Wording

b Recommended Wording

c Reason/Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c MAILING ADDRESS *(Street, City, State ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T20:44Z
Check the source to verify that this is the current version before use.