MIL-G-48344 (AR)
AMENDMENT 1
24 March 1981

MILITARY SPECIFICATION

GYPSUM, DEAD BURNED

This amendment forms a part of Military Specification MIL-G-48344 (AR) dated 28 May 1974.

Page 2

3.1.2 - Delete as written and substitute:

"3.1.2 Combined Water. The combined water content of the Dead Burned Gypsum shall be 0.3 percent maximum (max) when determined as specified in 4.5.2."

Page 3

4.4.2 Sampling. Delete "Inspection Level II."

Page 4

4.5 Testing. Add: "PRECAUTION - This specification covers testing with toxic or hazardous materials. Accordingly, it is emphasized that all applicable safety rules, regulations, and procedures must be followed in the handling and processing of these materials."

Page 5

4.5.2 - Delete as written and substitute:

"4.5.2 Determination of Combined Water. Approximately 20g of the sample shall be placed in a tared porcelain crucible and dried at 100°C - 125°C to a constant weight, which shall be accurately determined. The crucible and contents shall then be heated in a muffle furnace at 600°C ± 50°C for two hours, cooled in a desiccator, and weighed again. Combined water shall be calculated as shown below.

$$\text{Combined water (percent)} = \frac{A - B}{A - T} \times 100$$

A = weight of crucible and contents after 100°C conditioning, g
B = final weight of crucible and contents, g
T = tare weight of crucible, g"

FSC: 6810

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.

6.3 - Delete "SARPA-QA-A-P" and add "DRDAR-QAR-R".

Custodian:
Army-AR

Preparing Activity:
Army-AR

Project Number: 6810-AB20

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:22Z
Check the source to verify that this is the current version before use.