MIL-P-18080A(SHIPS)
AMENDMENT-1
10 January 1967

MILITARY SPECIFICATION

PLASTIC SHEETS, VINYL, FLEXIBLE, TRANSPARENT

OPTICAL QUALITY

This amendment forms a part of Military Specification MIL-P-18080A(SHIPS), dated 2 March 1956.

Page 1, paragraph 2.1, delete:

"NAVY DEPARTMENT
General Specifications for Inspection of Material."

Page 2, paragraph 2.2, delete:

"CONSOLIDATED CLASSIFICATION COMMITTEE
Consolidated Freight Classification Rules.

(Application for copies should be addressed to the Consolidated Classification Committee, 202 Chicago Union Station, Chicago 6, Ill.) "

Substitute:

"OFFICIAL CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules.

(Application for copies should be addressed to the Official Classification Committee, 1 Park Avenue at 33rd Street, New York, N. Y. 10016)."

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

Page 4, paragraphs 4.1 through 4.3, delete and substitute:

" 4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification. where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

"4.2 Sampling for quality conformance inspection. - Sampling for quality conformance inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for inspection and tests shall consist of all material of the same type, machine run and thickness range submitted for delivery at one time.

"4.2.1 Inspection of materials and components. - In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

"4.2.2 Inspection of the end item. -

"4.2.2.1 Examination of the end item. - Examination of the end item shall be made in accordance with the classification of defects, inspection levels and acceptable quality levels (AQLS) set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of plastic sheets for examination in 4.2.2.1.1, 4.2.2.1.2 and in units of shipping containers for examination in 4.2.2.1.3.

"4.2.2.1.1 Examination of the end item for defects in appearance and workmanship. - The sample unit for this examination shall be one sheet of the specified type plastic material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

Examine	Defects
Appearance and workmanship	Not uniform in transparency
	Any blisters, bubbles, wrinkles, creases, cuts, tears, holes, dents, heat marks, or graininess which will affect serviceability.
	Any scratches, dirt, imbedded particles or other defects which will reduce visibility or affect appearance.
Finish	Not finished to a polished or smooth finish.
Color	Not colorless and transparent.

"4.2.2.1.2 Examination of the end item for dimensional defects. - The sample unit for this examination shall be one sheet of the specified type plastic material.

Examine	Defects
Length and width	Varies by more than minus 0 plus 1/4 inch from size specified.
Thickness	Varies by more than plus or minus the tolerance specified (see Table II).

"4.2.2.1.3 Examination of the preparation for delivery. - An examination shall be made to determine that packaging, packing and markings comply with the requirements of Section 5. The sample unit for this examination shall be one shipping container, fully packed, selected just prior to the closing operation. Shipping containers fully prepared for delivery shall be examined for closure defects.

Examine	Defects
Packaging	Not level specified, not in accordance with contract requirements.
	Packaging material not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

Examine	Defects
Packaging (continued)	Paper interleaves missing, not extending over full area between sheets, or not as specified.
Packing	Not level specified, not in accordance with contract requirements.
	Any nonconforming component, component missing, damaged or otherwise defective, affecting serviceability.
	Container not as specified, closures not accomplished by specified or required methods or materials.
	Inadequate application of components such as: incomplete closure of case liners, container flaps, loose or inadequate strapping, bulged or distorted containers.
Count	Less than specified or indicated quantity of sheets per container.
Weight	Gross or net weight exceeds specified requirements.
Markings	Exterior markings omitted, illegible, incorrect, incomplete or not in accordance with contract requirements.
	Precautionary markings missing or not as specified.

"4.2.3 Inspection levels and acceptable quality levels (AQLS) for examination. - The inspection levels for determining the sample size and the acceptable quality levels (AQLs) expressed in defects per 100 units, shall be as follows:

Examination paragraph	Inspection level	AQL
4.2.2.1.1	I	2.5
4.2.2.1.2	S-3	2.5
4.2.2.1.3	S-2	4.0

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

"4.3 Testing of the end item. - The end item shall be tested for the applicable characteristics as indicated in Table III, on each lot presented for examination. The sample unit shall be one sheet. The inspection level for determining the sample size shall be S-1, except that no less than three sample units shall be randomly selected throughout the lot. The acceptable quality level (AQL) shall be 6.5 expressed in defects per 100 units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

"Table III. - Instructions for testing

Characteristic	Specification reference: Requirement	Test method	Rqmts. appl. to: indiv. unit	lot average	Number determinations per unit	Pass or fail	Numerically to nearest 1/
Physical properties	3.2 and Table I						
Specific gravity	Table I	4.5.1	X	-	Average of 5	-	.01
Tensile strength - lengthwise	Table I	4.5.2	X	-	Average of 5	-	psi
crosswise		4.5.2	X	-	Average of 5	-	psi
Elongation - lengthwise	Table I	4.5.3	X	-	Average of 5	-	percent
crosswise		4.5.3	X	-	Average of 5	-	percent
Brittleness temperature	Table I	4.5.4	X	-	2	-	degree(o)C.
Light transmission A	Table I	4.5.5	X	-	Average of 5	-	percent
Light transmission B		4.5.5	X	-	Average of 5	-	percent
Haze	Table I	4.5.6	X	-	Average of 5	-	0.1 percent

1/ Test results shall include all values on which results are based."

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.

Page 6, delete paragraph 4.6.

Page 7, paragraph 5.2.3, delete and substitute:

" 5.2.3 Level C. - The plastic sheets shall be packed in a manner which will insure acceptance and safe delivery at destination. Containers shall comply with the Uniform Freight Classification Rules or other regulations as applicable to the mode of transportation."

Page 8, delete "Patent notice" paragraph; delete "Custodian: Bureau of Ships".

Preparing activity:
Navy - SH
(Project 9330-N086Sh)

*U.S. GOVERNMENT PRINTING OFFICE: 1967-251-516/4130

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:57Z
Check the source to verify that this is the current version before use.