6 December 1974
SUPERSEDING
MIL-P-62835(MU)
4 April 1968

MILITARY SPECIFICATION

PROJECTILE, 20MM, HEI-T. M242; METAL PARTS

This specificat on is approved for use by all Departments and Agencies of the Department of Defense

1. SCOPE

1.1 This specification covers the body assembly for Projectile, 20mm High Explosive Incendiary-Tracer, M242.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids, or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-C-490 - Cleaning Methods and Pretreatment of Ferrous Surfaces for Organic Coatings

MILITARY

MIL-A-2550 - Ammunition, General Specification For
MIL-S-460T9 - Steel Bar for Projectile Stock

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109 - Quality Assurance Terms and Definitions
MIL-STD-651 - Visual Inspection Standards for 20mm Ammunition and Components
MIL-STD-1168 - Lot Numbering of Ammunition

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

2.1 (Cont)

MIL-STD-1169 - Packaging, Packing, and Marking for Shipment of Inert Ammunition Components
MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

DRAWINGS

ARMAMENT COMMAND

B7258816 - Blank, Rotating Band, for Projectiles, 20mm
F7258861 - Carton for Interplant Shipment of Projectiles, 20mm, Assemblies, and Metal Parts Assemblies (200)
D7259136 - Shipping Container for Inert projectile, 20mm, Assemblies and Metal Parts Assemblies (10,000)
D7259271 - Projectile, 20mm, HEI-T, M242, Metal Parts
IEL 7259271 - Index of Inspection Equipment Lists for: Projectile, 20mm, HEI-T, M242, Metal Parts
D7259275 - Projectile, Metal Parts Test Cartridge, 20mm, M242

PUBLICATIONS

U.S. ARMY MATERIEL COMMAND

AMCR 715-505 - Ammunition Ballistic Acceptance Test Methods, Volume 8, Test Procedures for 20mm Cartridges

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other Publications. -The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM)
ASTM B117-64 -- Method of Test for Salt Spray (Fog) Testing

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Materials. -Materials shall be in accordance with applicable drawings and specifications. Prior to producing projectile bodies from a heat of steel, the contractor shall conduct tests in his own laboratory or other facilities and services acceptable to the Government, to verify that the bar stock meets the requirements of MIL-S-46070.

3.2 Parts and Assembly. -The parts and assemblies shall be in accordance with all the requirements of Drawing (Dwg.) D7259271 and with all requirements of the drawings and specifications shown thereon.

3.3 First Article Sample. -Unless otherwise directed by the contracting officer, a first article sample shall be required.

3.4 Manufacturing Process.-All parts and assemblies shall be manufactured by a process approved by the contracting officer and no deviation from that process shall be made without his prior-approval. (see 6.2)

3.5 Banding-The rotating band blank and the rotating band seat shall be clean and dry at the time of banding. Shot or sandblasting shall not be used to clean the rotating band seat after knurling. The rotating band blank shall fill the band seat.

3.6 Soundness. -Metal discontinuity in the projectile body, as determined by eddy current inspection, shall be less than that represented by Production Check Standard (PCS) No. 1.

3.7 Protective Coating.

3.7.1 Phosphate Coating. -The pretreatment process. used shall be in accordance with applicable requirements of Dwg. D7259271. The phosphate coating shall be in accordance with the requirements of TT-C-490 for appearance and minimum weight, as applicable to the type of phosphate coating used.

3.7.2 Paint Adhesion. -The exterior paint coating shall meet the requirements of TT-C-490 for adhesion.

3.7.3 Corrosion Resistance. -The exterior painted surface of the assembly shall show no evidence of corrosion (red rust) after exposure to a 5% solution of atomized salt spray for 24 hours.

3.8 Metal Parts Security. -The projectile metal parts when charged and assembled as specified by Dwg. D7259275, shall not separate or break up in the test for metal parts security.

3.9 Workmanship. -The requirements for workmanship are as specified by applicable drawings, referenced specifications and the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

3.9.1 Processing Defects.-The projectile, metal parts shall be free of dents, scratches, cuts, sharp edges, burrs, and other forms of substandard workmanship.

3.9.2 Cleanliness. -The projectile, metal parts shall be free of all foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection.-Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as othewise specified in the contract or order, the supplier may use his own or other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Quality Assurance Terms and Definitions.-Reference shall be made to MIL-STD-109 for definition of quality assurance terms.

4.1.2 Bar Stock Verification.-Independent of tests and inspections performed by the steel bar suppliers, an examination shall be made on each lot of bars. The inspections and tests used to verify the bar stock quality shall be as specified by MIL-S-46070, Table IV, using the requirements, acceptance criteria and test methods referenced therein, with the following modifications:

Chemical composition: Sulphur only is required.
Mechanical properties: Unmodified.
Grain size: Unmodified.
Soundness:
Macro-etch
Billet: See Note 1.
Bar: See Note 1.
Magnetic: See Note 1
Surface decarburization: Not required.
Dimensions: Diameter only
Workmanship: See Note 1.

Note 1. The suppliers' macro-etch, magnetic and visual inspection shall be monitored to the extent necessary to assure compliance with MIL-S-46070.

4.2 Classification of Inspections. -The inspection requirements specified herein are classified as follows:

1. First Article Inspection (see 4.3).
2. Quality Conformance Inspection (see 4.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

4.3 First Article Inspection.

4.3.1 First Article Sample.-The sample shall be delivered for inspection in accordance with the first article approval provisions of the contract and MIL-A-2550, and shall consist of:

a. Inspection and nonfiring tests:

3 Standard test panels (see TT-C-490)
32 Rotating band blanks
125 Bodies without rotating bands
125 Assemblies, uncoated and without interior coating
125 Projectile, metal parts

b. Firing test:

4,000 projectile metal parts

The projectile metal parts shall be identified in accordance with MIL-STD-1168.

4.3.1.1 Inspection. -After inspection by the contractor and provisional acceptance by the government activity, the sample will be inspected in accordance with the provisions of MIL-A-2550. Failure of the sample to conform to the initial acceptance criterian will result in sample disapproval. (see 6.3)

4.4 Quality Conformance Inspection.

4.4.1 Submission of Product -The product shall be submitted in accordance with MIL-STD-105 or MIL-STD-1235, as applicable.

4.4.1.1 Lot.-A lot shall consist of projectile, metal parts produced by one manufacturer in one unchanged process, in accordance with the same drawings and drawing revisions, and same specification and specification revision.

4.4.1.2 Lot Identification. -Each projectile, metal parts and each packed lot shall be identified in accordance with applicable drawings and MIL-STD-1168.

4.4.2 Examination. -One hundred percent examination shall be performed by the contractor for all critical defects. Examination for major and minor defects shall be performed as specified herein. Each part and each assembly found to be defective shall be rejected.

4.4.2.1 Sampling and Acceptance Criteria. -The sampling plans and procedures shall be in accordance with MIL-STD-105 or MIL-STD-1235. To determine product acceptability, major or minor defects as listed herein may be considered collectively on a class basis or they may be considered individually. However, where major defects are considered collectively on a class basis, the acceptance number for any individual defect of the class shall be limited by the assigned Acceptable Quality Level (AOL) for individual defect associated with the class (see 4.4.2.2.c.). In addition, where three or less defects

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

4.4.2.1 (cont)

appear in a classification, or where MIL-STD-1235 is used, sampl ing plans applicable to a class shall not be used for major defects. (see 6.4)

4.4.2.2 AQL's.-The following AQL's are assigned to major and minor defects:

a. Individual

Major	0.25%
Minor	0.40%

b. Class basis:

Major	1.50%
Minor	2.50%

c. Individual defects associated with the class basis:

Major	0.40%

4.4.3 Classification of Defects - 1/ The classification of defects shall be as specified herein (see 6.5):

4.4.3.1 Rotating Band Blank (see Dwg. B7258816, covering a detail of Dwg. D7259271)

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Foreign matter	Visual (see 3.5)
102. Defective metal, including lamination	Visual
103. Incomplete or deformed	Visual 2/
Minor:	
201. Width, max.	Gage

4.4.3.2 Body Prior to Banding (see Dwg. D7259272, a detail of Dwg.D7259271).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Knurling missing or imcomplete	Visual
102. Foreign matter in rotating band seat (at time of banding)	Visual (see 3.5)
103. Depth of knurling, min.	Visual 3/
104. Length, mouth to rear of rotating band seat	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

4.4.3.2 (Cont)

Minor:		
201.	Diameter, rotating band seat, knurled	Gage
202.	Width, rotating band seat	Gage
203.	Width, knurling, min.	Visual 3/

4.4.3.3 Body and Rotating Band Assembly, Uncoated (see Dwg. D7259272, a detail of Dwg. 07259271).

Categories and Defects		Method of Inspection
Critical:		
1.	Ferrous metal discontinuity	Soundness
Major:		
101.	Perforation or fracture in tracer cavity	Visual
102.	Length, mouth to rear of rotating band	Gage
103.	Diameter, bourrelet, min.	Gage
104.	Diameter, body rear of rotating band, min.	Gage
105.	Diameter, rotating band	Gage
106.	Runout, body rear of rotating band, with datum surface	Gage
107.	Runout, rotating band with datum surface	Gage
108.	Wall thickness variation	Gage
109.	Width, rotating band	Gage
110.	Location, crimp groove	Gage
111.	Profile, crimp groove	Gage
112.	Radius, rear edge of crimp groove	Gage
113.	Thickness of web between body and tracer cavity	Gage
114.	Depth from metering disc seat to bottom of tracer cavity	Gage
115.	Void, junction rotating band and body	Visual (see 3.5)
116.	Diameter, body cavity	Gage
117.	Diameter, tracer cavity	Gage
118.	Runout, tracer cavity with datum surface	Gage
119.	Diameter, metering disc cavity	Gage
120.	Depth, metering disc cavity	Gage
121.	Radius, metering disc cavity, max.	Gage
122.	Width, crimp lip	Gage
123.	Position, metering disc cavity with datum surface	Gage
124.	Angle of crimp lip	Gage
Minor:		
201.	Foreign matter in metering disc seat	Visual
202.	Finish improper	Visual 4/
203.	Outside diameter, mouth end	Gage

Source: https://assist.dla.mil -- Downloaded: 202640-23T01:00Z
Check the source to verify that this is the currentversion before use.

4.4.3.3 (Cont)

204.	Depth and width of undercut, front and rear of rotating band	Gage
205.	Diameter, thread counterbore, max.	Visual 5/
206.	Depth, thread counterbore	Visual 5/
207.	Overall length	Gage
208.	Break, mouth at ogive	Visual 5/

4.4.3.4 Projectile, Metal Parts (coated, prior to painting) (see Dwg. D7259271).

Categories and Defects		Method of Inspection
Critical:	None defined.	
Major:		
101.	Pitch diameter, thread	Gage
102.	Runout, thread with datum surface	Gage
Minor:		
201.	Minor diameter, thread	Gage
202.	Depth, complete thread	Gage

4.4.3.5 Projectile, Metal Parts, painted (see Dwg. D7259271).

Categories and Defects		Method of Inspection
Critical:	None defined.	
Major:		
101.	Diameter, bourrelet	Gage
102.	Diameter, body, rear of rotating band	Gage
103.	Diameter, metering disc cavity	Gage
104.	Diameter, tracer cavity	Gage
105.	Foreign matter in cavities or threads	Visual 6/
106.	Depth, metering disc seat to bottom of tracer cavity	Gage
107.	Weight	Balance
Minor:		
201.	Paint not dry	Tactile
202.	Marking incorrect, incomplete, illegible or missing	Visual
203.	Paint on rotating band	Visual
204.	Paint on threads	Visual
205.	Rotating band damaged	Visual
206.	Interior or exterior paint inadequate	Visual
207.	Foreign matter on exterior	Visual

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

1/ MIL-STD-651 shall apply in defining and evaluating visual defects.

2/ A rotating band blank which is deformed or judged to lack sufficient metal in any part of its width or thickness to-provide for complete band seat fill and minimum rotating band profile dimensions shall be classed defective.

3/ Measurement of knurling for compliance with the minimum depth and width requirements shall apply where visual inspection indicates that either dimension is borderline.

4/ Measurement of surface roughness shall apply where visual inspection indicates that the specified finish is exceeded.

5/ Measurement of the thread counterbore (if present) for diameter and depth or measurement of break mouth at ogive shall apply where visual inspection indicates that dimensions are excessive.

6/ An assembly that has foreign matter on the exterior or contained in the threads or body shall be classed defective. Particular attention shall be given to the examination of the cavities for steel chips and shavings.

4.4.4 Tests. -The tests listed in Table I shall be conducted in compliance with the test methods and procedures prescribed by 4.5. The sampling plans for these tests shall be as specified by Table I.

Table I

Test		Sample Size	Item	Rqmt. Para.
Band Tightness	1/	315	Body and rotating band Assembly, uncoated	3.5
Automatic inspection effectiveness	2/		PCS No. 1 (see 4.5.3)	--
Soundness verification	3/	315	Body and rotating band assembly, uncoated	3.6
Phosphate coating (appearance & weight)	4/		3 - Standard panels (see TT-C-490)	3.7.1
Paint adhesion	5/	13	Projectile, metal parts	3.7.2
Corrosion resistance	6/	32	Projectile, metal parts	3.7.3
Metal parts security	7/	250	Projectile, metal parts	3.8

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

1/ If two or more units of the sample have an average radial void, between the seated band and the band seat, greater than 0.004 inch, the lot shall be rejected. If one unit of the sample has an average radial void, greater than 0.004 inch, a second sample consisting of the same number of units *as* specified for the first sample shall be tested. If, in the accumulated samples, two or more units have an average radial void greater than 0.004 inch, the lot shall be rejected.

2/ Failure of the flaw detector to reject PCS No. 1 shall be cause for rejection of all assemblies inspected for "soundness" since the preceding test and shall require requalification of the equipment for automatic inspection. (see 4.5.3)

3/ Rejection of one or more units of the sample by the flaw detector in the test for body metal soundness shall be cause for rejection of the lot.

4/ Failure of the phosphate coating on the standard panels to comply with the applicable requirements shall be cause for rejection of all projectiles phosphate since the preceding test.

5/ If two or more units of the sample fail to comply with the requirement for paint adhesion, the lot shall be rejected. If one unit of the sample fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If, in the accumulated samples, two or more units fail to comply with the requirement for paint adhesion, the lot shall be rejected.

6/ If two or more units of the sample fail to comply with the corrosion resistance requirement, the lot shall be rejected. If one unit fails to comply with the requirement, a second sample consisting of the same number of units as specified for in the first sample shall be tested. If in the accumulated samples, two or more units fail to comply with the corrosion resistance requirement, the lot shall be rejected.

7/ The occurrence of one or more of the following casualties, as witnessed by hole(s) in the fragmentation screens, or recovery of the part(s) or fragment(s), shall be cause for rejection of the lot, except as otherwise provided:

a. Body breakup.

b. Complete rotating band separation. This is defined as detachment of all or part of the band having band seat knurling imprint. The following acceptance criteria shall apply to detached band fragments having no visible evidence of band seat knurling imprint:

(1) The lot will be accepted if 2 or less projectiles throw band fragments having length not greater than 0.500 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

(2) The lot will be rejected if three or more assemblies throw band fragments having length not greater than 0.500 inch.

(3) The lot will be rejected if any projectile throws a band fragment having length greater than 0.500 inch (indicative of deep-seated band lamination).

(4) The lot will not be penalized for band particles thrown as a result of normal band fringing or slivering.

4.4.5 Packaging, Packing and Marking Inspection.-Inspection for packaging. packing and marking shall comply with applicable requirements of MIL-STD-1169.

4.4.6 Inspection Equipment.-Index of Inspection Equipment Lists (IEL) 7259271 identifies the applicable inspection equipment lists indicating the equipment required to perform examination and tests prescribed herein. Equipment design shall be in accordance with code designation on the applicable IEL (reference is made to Inspection Equipment Lists for coding definitions, Dwg. B11075228, a detail of IEL 7259271). Provisions of MIL-A-2550 shall apply.

4.5 Test Methods and Procedures.

4.5.1 Band Tightness. -The method of test shall comply with all requirements of the operating instructions for the band tightness tester (Dwg. B7259545, a detail of IEL 7259271). The inspection sample shall be cycled through the tester to determine compliance with the rotating band tightness requirement. The total measurement of radial void (band looseness), registered on the tester indicator at final ram pressure, shall be divided by four (number of indenters) to determine the average radial void.

4.5.2 Soundness. -The method of inspection shall comply with all requirements of Operating Instructions, Eddy Current Flaw Detector, Dwg. D11075203 (a detail of IEL 7259271) for Detecting Metal Discontinuity in Projectile Bodies for 20mm Ammunition, except for those inspection requirements which are reserved for Government application, as specified herein.

4.5.3 Automatic eddy current inspection effectiveness. -Equipment checkout shall be performed as stated in the Operating Instructions at the start of each shift and after any adjustment or shutdown. Upon completion of checkout, cycle the PCS #1, front slot and rear slot standards through the inspection system during automatic operation. All three standards must be rejected to assure correct adjustment for reject level and scan limits. During remainder of shift the PCS #1 shall be cycled through the equipment at intervals of 20 ± 5 minutes during automatic operation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

4.5.4 Soundness Verification. -After equipment checkout and verification as specified in 4.5.3 and 4.5.5 the entire lot sample will be inspected with the equipment operating automatically. Any rejected unit of the sample will be automatically cycled through the equipment with the CAL. button pressed (to lower the sensitivity one step below that used for production inspection). Any unit which is rejected at the lower sensitivity shall be classed as a defective.

4.5.5 Equipment Verification. -The government inspector will maintain, independent of the contractor, a set of standards and may cycle these standards through the equipment at any time. Failure of equipment to reject standards will be evidence that the equipment is not properly adjusted and the contractor will be so notified. (see 6.6)

4.5.6 Phosphate Coating. -The method of test shall be as specified in TT-C-490 for the type of coating used (see Dwg. D7259271). The standard panels shall be processed, with the-projectiles to be represented, at the start of daily production and at four hour intervals, maximum, thereafter. Appearance and weight of the coating shall be recorded.

4.5.7 Paint Adhesion. -The method of test shall be as specified in TT-C-490. The test shall be made on the painted bourrelet of each unit of the sample.

4.5.8 Corrosion Resistance. -The method of test shall be as specified in the American Society for Testing and Materials (ASTM), ASTM B117. All areas not subject to salt spray test may be masked out or plugged for this test. The exposure time shall be as specified by 3.7.3.

4.5.9 Metal Parts Security. -The method of test will be as specified in AMCR 715-505, Volume 8, as applicable. The test sample will be assembled to comply with the requirements of Dwg. D7259275, projectile, Metal parts Test Cartridge, 20mm, M242. The test cartridges, at ambient temperature, will be fired in an M39 gun in bursts of 50 shots. The gun barrel will be at ambient temperature for the firing of each burst. The cyclic rate of fire will be recorded for informational purposes. (see 6.3)

5. PREPARATION FOR DELIVERY

5.1 Packing, Level C.-Each lot of projectile metal parts shall be packed as specified by Dwgs. F7258861 or D7259136.

5.2 Marking, Level C.-Marking of shipping containers shall comply with applicable requirements of MIL-STD-1169.

6. NOTES

6.1 Ordering Data.- Invitations for bids and contracts or orders will specify the following:

6.1.1 Title, number and date of this specification.

6.1.2 place of inspection, if not place of manufacture.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

6.1.3 First article sample requirements (see 3.3, 4.3 and 6.3)

6.1.4 Package, packing and marking instructions. (see 5.1 and 5.2)

6.1.5 Provision for shipment and testing of first article and production lot samples. (see 6.3)

6.1.6 Provision for the supply, maintenance and disposition of mandatory inspection and ball istic test equipment for acceptance inspection purposes.

6.1.7 Provision for the submission and approval of the manufacturing process.

6.2 Process Deviation. -A process deviation is defined as a change in the approved basic method of manufacture, or an operational change which alters the metallurgical or physical properties of the item of contract.

6.3 First Article Sample.- In order to minimize inspection costs, the firing test will be performed after the sample has been approved for all other requirements. Additional projectile, metal parts may be required by the testing facility.

6.4 AQL's. -The optional use of AQL values for either individual defects or classes of defects, with individual major defect limitation, is intended to minimize inspection agency administrative burden which might result from an exclusive assignment of individual defect AQL's. The option also permits flexibility where sampling inspection for acceptance is integrated into the manufacturing process.

6.5 Intermediate Point Inspection. -The classification of defects identifies the defect characteristics (among other things) for acceptance inspection. It may be necessary to modify the sequence of inspection stations to best suit the manufacturing process. Inspection for defect characteristics which will be hidden or altered by subsequent processing operations (including unrelated operations), should be scheduled to prevent premature acceptance which could be detrimental to the attainment of optimum product quality in the end item.

6.6 Defect Standards.-The initial supply of defect standards and instructions for contractor and Government application to the eddy current method of inspection will be furnished with the eddy current inspection equipment. Replacement standards should be requisitioned through normal channels by the Government agency having contract administration responsibility.

NOTE: Asterisks not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodian:

Army - MU

Preparing Activity:

Army - MU

Project No. 1305-A767

☆ U. S. GOVERNMENT PRINTING OFFICE: 1974 -603-113/3638

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
Frankford Arsenal
ATTN: SARFA-MDM
Philadelphia, PA 19137

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers, vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-P-60835A(MU) Projectile, 20MM, HE1-T, M242; Metal Parts

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:00Z
Check the source to verify that this is the current version before use.