[METRIC]

A-A-1802A
March 22, 1993
SUPERSEDING
A-A-1802
September 16, 1983

COMMERCIAL ITEM DESCRIPTION

CARD SET, GUIDE, FILE

The General Services Administration has authorized the use of this commercial item description in preference to Type I, Style A, Class 1 of Federal Specification UU-C-95.

This Commercial Item Description covers buff file guide card sets for use in organization of files.

1. SALIENT CHARACTERISTICS

A. Paper: The file guide cards shall be made of calendered bristol with a basis weight of 366.1 g/m^2 (224 lbs. 25 X 38-500) +/- 5%, when tested in accordance with TAPPI test method T410. The file guide cards shall have a thickness of 0.406 mm, min. to 0.457 mm, max. (0.016 inch, min. to 0.018 inch, max.) when tested in accordance with TAPPI test method T411. The file guide cards shall have a bursting strength of 675.6 kPa (98 lbs. per square inch) min., when tested in accordance with TAPPI test method T403.

B. Card construction: The color of the guide cards shall be buff. The machine direction of the card material shall run vertically in the guide cards.

C. Tab construction: Each guide card shall be furnished with a self tab located along the long dimension of the card. Tabs shall be 9.5 +/- 0.79 mm (3/8 +/- 1/32 inch) high and shall have rounded corners. Tabs shall be one-third cut, second position; one-third cut, all positions; or one-fifth cut, all positions, as specified.

Beneficial comments, recommendations, additions, deletions, clarification's, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278

Distribution Statement A:
Approved for public release; Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:16Z
Check the source to verify that this is the current version before use.

D. Dimensions: The Guide cards shall be 76.2 x 127 mm (3 x 5 in), 127 x 203.2 mm (5 x 8 in), 152.4 x 228.6 mm (6x 9 in), or 82.5 x 187.3 mm (3-1/4 x 7-3/8 in), as specified in the contract or ordering document, exclusive of tabs (vertical dimension cited first). There shall be a dimensional tolerance of +/- 1.5 mm (+/- 1/16 inch). The cards shall be considered square if the difference between the two diagonal measurements is not more than 1.5 mm (1/16 inch).

E. Tab legends: When printed card sets are specified, cards shall be furnished as follows:

Alphabetic - (A through M, Mc, N through W, and XYZ), 25 cards per set.

Numeric - (1 through 31), 31 cards per set or 30 cards per set with the 30th card printed "30/31".

Monthly - (January through December), 12 cards per set.

Unprinted card sets shall consist of 100 cards. All card sets shall be collated.

Workmanship: The guide cards shall have asmooth and uniform finish and shall be free from dirt, foreign matter, wrinkles, holes and any other defects which may affect the serviceability, durability, or appearance. Edges of the cards shall be cleanly cut.

2. **REGULATORY REQUIREMENTS:**

The contractor shall certify that the minimum content standard shall be 50% recovered material, including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definitions of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(a) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:16Z
Check the source to verify that this is the current version before use.

To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3. TABLES AND TESTS:

Table 1. Physical requirements.

	Requirement	Test Method
Basis Weight	366.1 gm/m^2 (224 lbs. 25 X 38-500) +/- 5%	T410
Thickness	0.406 mm, min. to 0.457 mm, max. (0.016 inch, min. to 0.018 inch, max.)	T411
Bursting Strength	675.6 kPa (98 lbs. per square inch) min.,	T403.

4. QUALITY ASSURANCE:

Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government.

The contractor shall certify and maintain substantiating evidence that the product offered meets the salient characteristics of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, and quality assurance practices. The government reserves the right to require proof of conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Each lot of Card Set, Guide, File shall be inspected for conformance to the requirements herein. Inspection shall be in accordance with MIL-STD-105, unless specified otherwise, using the sampling plans specified below.

A. **Visual and dimensional characteristics** - Inspection Level II with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one card set.

B. **Tests** - Sampling shall be in accordance with Plan II of TAPPI T 400, for each of the required tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:16Z
Check the source to verify that this is the current version before use.

C. **Packaging, Packing, and Marking** - Inspection Level S-2 with an AQL of 4.0 percent defective. The sample unit shall be one fully prepared shipping container.

5. **PREPARATION FOR DELIVERY:**

Packaging, packing and marking shall be as specified in the contract or purchase order.

6. **REFERENCED DOCUMENTS:**

The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, P.O. Box 105113
Atlanta, GA 30348
(404) 446-1400

MIL-STD-105 is available from:

STANDARDIZATION DOCUMENTS ORDER DESK
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Copies of Executive Order 12873, dated October 20, 1993 may be obtained from:

The White House Publications Office
New Executive Office Building
White House
Att: Publications
Washington, DC. 20500

(202) 395-7332

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:16Z
Check the source to verify that this is the current version before use.

7. NOTES:

A. Ordering Data:

Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Dimensions.
(2) Cut and tab position.
(3) Color.
(4) Printing.
(5) Whether chlorine or chlorine compound bleaching is acceptable.
(6) Specific packaging, packing, palletization and, marking requirements.

Military interest:

None

Preparing activity:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:16Z
Check the source to verify that this is the current version before use.