[Metric]
A-A-2989
July 25, 1996

COMMERCIAL ITEM DESCRIPTION
TRAY, DESK, WOOD, EXECUTIVE OFFICE TYPE

The General Services Administration has authorized the use of this commercial item description by all federal agencies as a replacement for Federal Specification AA-T-633 which is canceled.

1. Scope: This commercial item description covers executive-office type wood desk trays.

2. Salient Characteristics:

2.1 All exposed wood surfaces of the desk trays shall be of mahogany or walnut as specified and shall be constructed of both solid and veneered parts. Core material for all plywood parts shall be veneer core, fully length strips. Veneer core may consist of mahogany, walnut, red alder, aspen, poplar, maple, or luan. The face veneers shall be grade A, plain-sliced book-matched. The face veneers shall be not less than .16 cm (1/28) inch thick and shall be matched as to figure and color, with invisible joints. All exposed wood surfaces shall be free from defects which may affect serviceability. The moisture content of all wood parts shall be from 5 to 8 %.

2. 2 The felt used for covering the bottom of the desk trays shall be dark brown in color. The felt shall weigh not less than 5 ounces per square yard and shall contain not less than 25 % wood. The felt shall be evenly and securely glued to the bottom of the tray.

2. 3 The glue, filler and lacquer used shall conform to Federal Specifications MMM-A-100D, TT-F-336E, and TT-L-58E.

2.4 Construction.

2.4.1 Design. The design of the desk trays shall be as shown in figure 1.

2.4.2 Side and End Panels. The panels shall be 3-ply 6.350 mm (1/4 inch) plywood, A-A, with vertical grain direction on both faces. The panels shall be grooved to receive the bottom. The corners shall be blind-splined and glued.

2.4.3 Bottoms. The bottom shall be 3-ply 6.350 mm (1/4 inch) plywood, grade A-3, with and shall have a tenon cut on all edges to fit into the grooves in the side and end panels. The bottom shall be glued in place and shall be flush with the bottom edges of the side and end panels.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278.

FSC 7520

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.

2.4.4 **Outside Frame.** The outside frame shall be of 6.350 mm (1/4 inch) thick solid lumber, grade AFE in accordance with Rules and Specifications for Dimensions and Woodwork (see para 6.1.4) with horizontal grain direction. All frame parts shall be shaped and applied as shown in figure 1. The corners shall be blind-splined and glued. The frame shall be securely glued to the side and end panels.

2.4.5 **Finish.** All exposed wood surfaces shall be finished to a smooth surface and stained to match the required color. A filler stain must be applied to fill all open grain and pores. This finish requires the use of sealer and lacquer to produce a smooth, clear product. All sealer and lacquer must be sanded before the next coat is applied. The final coat of lacquer shall produce a flat finish.

2.5 **Workmanship.** The details of construction, including veneering, jointing, assembly, and finishing shall be free from any defects that may affect serviceability or appearance.

3. **Regulatory Requirements:** The offerer/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. **Quality Assurance Requirements:**

4.1 **Product Conformance.** The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards and quality assurance practices and be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

4.2 **Examinations / Sampling.**

4.2.1 Suppliers are encouraged to use quality control (QC) techniques that exhibit control over their processes (e.g. (Statistical Process Control) SPC Techniques) as defined in American National Standards Institute (ANSI) Z1.1, Z1.2 and Z1.3 / American Society for Quality Control (ASQC) B.1, B.2 and B.3 that systematically reduce excess variations. If used, objective evidence shall be available that demonstrates overall measurement adequacy techniques and controls. These techniques shall ensure quality levels equal to, or greater than, those cited in applicable technical document or, herein.

4.2.2 End item inspection/testing may be used by the offerrer or the government representative, as a means to determine the effectiveness of the in process quality controls. While in process controls shall not be substituted for end item performance testing, they may be substituted for visual and dimensional sampling.

4.2.3 For those characteristics for which there are no such controls, lot by lot sampling for inspection shall be required. The sample unit for this item shall be one tray. Sampling shall be in accordance with the American National Standards Institute (ANSI) / American Society for Quality Control (ASQC) Z1.4, Sampling Procedures and Tables for Inspection by Attributes

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:28Z
Check the source to verify that this is the current version before use.

4.2.4 An inspection lot shall consist of all like items submitted for inspection at one time. The inspection level for visual and dimensional inspections shall be S-2 with an AQL of 4.0 percent defective The supplier must provide objective evidence (inspection records) that the presented material meets the requirements of the sampling plan as indicated above.

5. **Packaging:**

5.1 Preservation, packing, and marking shall be specified in the contract or order.

6. **Notes:**

6.1 **Source of Documents.** Issues of the following documents, in effect on the date of invitation for bids or request for proposal form a part of this document to the extent specified herein

6.1.1 Federal Acquisition Regulation (FAR) may be obtained from the Superintendent of Documents, Government Printing Office, Washington. DC 20402.

6.1.2 Application for copies of (ANSI) Z1.1, Z1.2, Z1.3 and (ASQC) B.1, B.2 and B.3 may be obtained from the American Society for Quality Control PO Box 3005, 611 E. Wisconsin Avenue, Milwaukee, WI 53201-4606.

6.1.3 Federal Standards and Specifications may be obtained from the General Services Administration Specifications Section (3FBO-W) in Suite 8100 at 490 L'Enfant Plaza, SW Washington DC 20407.

6.1.4 Copies of Rules and Specifications for Dimension and Wood Work may be obtained from the National Dimension Manufacturers Association at 1000 Johnson Ferry Road, Suite A-130, Marietta, Georgia 30067, phone number 707 565-6660.

6.2 **National Stock Number Listing (NSN).** The following is a list of nsn's assigned which correspond to this CID. The list may not be indicative of all possible nsn's associated with the CID.

7520-00-285-5043

MILITARY INTERESTS:

NONE: DoD has no registered interest in revisions and amendments to this Commercial Item Description until further notice

Preparing Activity:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 202640-26T08:28Z
Check the source to verify that this is the current version before use.