MIL-P-23281(CG)
AMENDMENT 2
11 April 1969
Superseding
AMENDMENT 1
6 March 1964

MILITARY SPECIFICATION

PRIMER, VINYL-RED LEAD (FOR BRUSH OR SPRAY)

This amendment forms a part of Military Specification MIL-P-23281(CG) dated 4 May 1962.

Page 1, paragraph 2.1, Delete: "TT-T-548 Toluene; Technical"
Substitute: "TT-T-548 Toluene; (Toluol) for use in Organic Coatings".

Page 6, paragraph paragraph 5.2, Delete and Substitute:

"5.2 Marking. - Containers shall be marked in accordance with Specification TT-P-143 for military agencies, with the added following data: contract numbers and Federal stock number. Also, marking pertaining to thinning and application instructions shall be as follows:

"Paint must be thoroughly mixed or stirred before and during use. Apply only to a dry clean surface that has been pretreated with a liberal coat of Wash Primer. Never apply over conventional paints or bare metal. Always allow a 30 minutes drying time between coats. The orange Vinyl paint is to be used for initial and final coats; all alternate coats to be brown. Use only Vinyl Paint Thinner for thinning paint or cleaning equipment.

For spraying, gun air pressure should be at least 15 psi above liquid pressure. Always clean gun before and after use, always cover work areas with a vertical and horizontal pass of gun. This paint may be brushed. Spread paint with full brush, do not cross work more than once or attempt to brush out."

Preparing Activity:
U.S. COAST GUARD

Source: https://assist.dla.mil -- Downloaded: 202610-19T16:17Z
Check the source to verify that this is the current version before use.