JAN–C–380

8 AUGUST 1946

JOINT ARMY-NAVY SPECIFICATION

CLOTH, COTTON, SHEETING, COATING-QUALITY

Army Number	Navy Number
G-322A	27C5G

This specification was approved by the War Department and the Navy Department for use of procurement services of the Army and the Navy and supersedes the following specification:

U. S. Army	Navy Department
6–322	.....
19 Nov. 1943	

A. APPLICABLE SPECIFICATIONS AND OTHER PUBLICATIONS

A–1. *Specifications.*—The following specifications, of the issue in effect on date of invitation for bids, form a part of this specification:

U. S. ARMY SPECIFICATION

100–63—Packaging and Packing of Cotton Fabrics (Except Cotton Duck and Coated Cotton Fabrics)[1].

NAVY DEPARTMENT SPECIFICATION

General Specifications for Inspection of Material[2].

FEDERAL SPECIFICATION

CCC–T–191—Textiles; General Specifications, Test Methods, and Supplement Thereto.

A–2. *Other publications.*—The following publication, of the issue in effect on date of invitation for bids, forms a part of this specification:

BUREAU OF SUPPLIES AND ACCOUNTS PUBLICATION

Navy Handbook on Packing and Materials Handling—Packaging, Packing, and Marking of Clothing, Small Stores, and Textiles[2]

B. TYPES AND CLASSES

B–1. *Types.*—Cloth, cotton, sheeting, coating-quality covered by this specification, shall be of the following types, as specified in the contract or order (see par. H–1):

Type I—Unbleached.
Type II—Dyed and finished.

[1] Applicable only to Army purchases.
[2] Applicable only to Navy purchases.

Source: https://assist.dla.m
Check the source to verify th

B–2. *Classes.*—Types I and II shall be of the following classes as specified in the contract or order (see par. H–1):

Class	Commercial designation gray construction	
	Inches	
A	40	56x56
B	40	60x52
C	40	64x64
D	40 to 49	68x64
E	40 to 49	64x56
F	40 to 49	56x56
G	45	68x72

C. MATERIAL AND WORKMANSHIP

C–1. *Material.*—The cotton used in the manufacture of the yarn shall be of a suitable grade and length of staple, thoroughly cleaned and well manufactured into carded single yarns, not finer than 25/1 counts.

C–2. *Workmanship.*—The cloth shall be clean, evenly woven, feeler motion quality suitable for coating, and free from any defects which may affect the appearance or serviceability. Knots, slubs, bunches, hanging threads, etc., shall be carefully burled. Goods shall be free from holes, or torn or tight selvages.

D. GENERAL REQUIREMENTS

D–1. *Standard sample*[a].—Unless otherwise specified, in all respects not specifically covered by this specification, cloth shall be equal to the standard sample (see par. H–3).

D–2. *Weave.*—The weave shall be plain.

D–3. *Length.*—Pieces shall be unspliced and shall be as long as may be consistent with the maintenance of the required standard of quality. Unless otherwise specified in the contract or order the cloth shall be in continuous pieces, each piece not less than 50 yards, but each shipment may contain up to 10 percent of the total yardage of that shipment in pieces between 30 and 50 yards in length. Pieces under 30 yards in length shall not be accepted. For Army purchases, the cloth shall be put up in full width rolls on heavy cardboard tubes of not less than 2 inches inside diameter and a wall thickness of 0.200 inch.

D–4. *Tickets.*—Each bolt or roll shall have a ticket attached to the selvage at one end with not finer than 5 fold cotton string doubled to not less than 8 inches long. The ticket shall be made of heavy cardboard and be provided with a reinforced eyelet for attaching the tying cord. The ticket shall have legibly printed on it the following information:

[a] Not required for Army Air Forces contracts.

Source: https://assist.dla
Check the source to verify

Cloth, cotton, sheeting, coating-quality.....
Weight per square yard.....
Type..... Class..... Width.....
Contractor's name .....
Contract number and date.....
Specification number .....
Stock number .....
Name of contracting bureau or agency.....
Actual yards .....
Net yards .....

In addition, the ticket shall have sufficient blank space for inspector's stamp.

E. DETAIL REQUIREMENTS

E–1. *Physical requirements.*—

E–1a. The physical requirements for Type I shall be as shown in Table I.

TABLE I.—*Physical requirements for Type I.*

Class	Commercial designation gray construction	Weight per square yard		Thread count per inch (min.)		Breaking strength grab method (min.)	
		Minimum	Maximum	Warp	Filling	Warp	Filling
		Ounces	Ounces			Pounds	Pounds
A	40" 56x56 3.60	4.0	5.0	56	56	45	50
B	40" 60x52 3.60	4.0	5.0	60	52	55	50
C	40" 64x64 3.15	4.5	5.5	64	64	55	60
D	40"-49" 68x64	4.3	5.3	68	64	65	60
E	40"-49" 64x56	3.8	4.8	64	56	55	50
F	40"-49" 56x56	3.5	4.5	56	56	45	50
G	45" 68x72 2.45	5.2	6.2	68	72	55	50

E–1b. The physical requirements for Type II shall be as shown in Table II.

TABLE II.—*Physical requirements for Type II.*

Class	Commercial designation gray construction	Weight per square yard		Thread count per inch (min.)		Breaking strength grab method (min.)	
		Minimum	Maximum	Warp	Filling	Warp	Filling
		Ounces	Ounces			Pounds	Pounds
A	40" 56x56 3.60	3.6	4.5	58	50	40	45
B	40" 60x52 3.60	3.6	4.5	62	46	50	45
C	40" 64x64 3.15	4.0	5.0	66	58	50	54
D	40"-49" 68x64	3.8	4.7	70	58	58	54
E	40"-49" 64x56	3.4	4.3	66	50	50	45
F	40"-49" 56x56	3.1	4.0	58	50	40	45
G	45" 68x72 2.45	4.7	5.7	70	66	50	45

Source: https://assist.dla.mi
Check the source to verify tha

E–2. *Width.*—

E–2a. The width of the cloth for Type I shall be as specified in the contract or order, with a plus or minus tolerance of not more than ½ inch for all classes (see par. H–1).

E–2b. The width of the cloth for Type II shall be as follows, unless otherwise specified in the contract or order (see par. H–1):

Unbleached fabrics—40″ to 42″ shall finish 38 inches
44″ to 46″ shall finish 41 inches
47″ to 49″ shall finish 44 inches

A plus or minus tolerance of ½ inch will be allowed on finished width of all classes of cloth.

E–3. *Color.*—The color for Type II shall be as specified in the contract or order (see par. H–1). Unless otherwise specified, cloth shall be dyed with sulfur colors. The use of sulfur black as a component will not be permitted. The pH of the cloth shall be not lower than 7.0, and shall be determined as described in paragraph F–3b.

E–4. *Finish.*—

E–4a. Type I cloth shall not contain more than 8½ percent of sizing, by weight of the fabric.

E–4b. Type II cloth shall be singed, desized, and well scoured before dyeing. The dyed and finished fabric shall contain not more than 0.005 percent copper or 0.001 percent manganese. The finished cloth shall be well calendered to impart a soft handle or feel and unless otherwise specified in the contract or order shall have a suitable water repellent finish. The cloth shall be clean in appearance, free from moats and shall contain in total, not more than 4 percent of sizing and finishing material (including water repellent) by weight of the fabric.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS

F–1. *Sampling.*—

F–1a. *General.*—Samples of any materials, components, etc., not furnished by the Government entering into the manufacture of the article covered herein shall be selected from time to time by the Government inspector, and carefully examined and tests made to determine if they are in accordance with the requirements of this specification.

F–1b. *Preproduction sample approval.*—

F–1b(1). *Army purchases.*—Before production is commenced, the contractor shall submit for approval to the contracting officer, a sample of the cloth he proposes to furnish.

F–1b(2). *Navy purchases.*—Before production is commenced, the contractor shall submit for approval, to the Supply Officer in Command, Naval Clothing Depot, 29th Street and Third Avenue, Brooklyn 32, N. Y., a sample of the cloth he proposes to furnish.

F–2. *Inspection.*—

F–2a. *Contractor's inspection.*—The contractor shall thoroughly inspect the cloth for compliance with the requirements of this specification prior to delivery to the U. S. Government for final inspection.

Source: https://assist.dla.m
Check the source to verify tha

F–2b. *Government inspection.*—Inspection may be made throughout the entire process of manufacture. The passing as satisfactory of any detail of construction or material shall not relieve the contractor of responsibility for faulty workmanship or material which may be discovered at any time prior to final acceptance. Final inspection of the finished article shall be made either at place of manufacture or at point of delivery as specified in the contract or order (see par. H–1). In case of factory inspection, every facility shall be afforded inspectors by the manufacturer, for the prosecution of their work.

F–3. *Tests.*—

F–3a. *General.*—The methods of testing described in Federal Specification CCC–T–191 and supplement thereto, wherever applicable, shall be followed.

F–3b. *Determination of pH.*—The pH of the cloth shall be determined as described in section VII, paragraph 1 of the supplement to Federal Specification CCC–T–191.

G. PACKAGING, PACKING, AND MARKING FOR SHIPMENT

G–1. *Army.*—The cloth shall be packaged, packed and marked for shipment in accordance with the requirements of U. S. Army Specification 100–63.

G–2. *Navy.*—Shipments shall be made in accordance with the requirements of the Navy Handbook on Packing and Materials Handling—Packaging, Packing, and Marking of Clothing, Small Stores, and Textiles.

H. NOTES

H–1. Requests, requisitions, schedules, and contracts or orders should specify the following:

(a) Title, number and date of this specification.
(b) Type of cloth required (see par. B–1).
(c) Class of cloth required (see par. B–2).
(d) Width of cloth required (see par. E–2).
(e) Color and color fastness (when required) (see par. E–3).
(f) Place of final inspection (see par. F–2b).

H–2. *Intended use.*—This cloth is intended to be coated for use in the manufacture of clothing items.

H–3. *Standard sample.*—

H–3a. *Army.*—For access to standard sample, address the procuring office issuing the invitation for bids.

H–3b. *Navy.*—Standard sample may be obtained upon application to the Supply Officer in Command, Naval Clothing Depot, 29th Street and 3rd Avenue, Brooklyn 32, N. Y.

H–4. Applicable sections of the Navy Handbook on Packing and Materials Handling—Packaging, Packing, and Marking of Clothing, Small Stores and Textiles may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C. When requesting, bidders and contractors should state the specification number and the complete nomenclature of the item to be packed so that the proper sections may be forwarded.

Source: https://assist.dla.m
Check the source to verify th

H–5. Copies of Joint Army-Navy specifications and Federal specifications (required for Army purchases) and U. S. Army specifications may be obtained as indicated in the "Index of United States Army, Joint Army-Navy, and Federal Specifications Used by the War Department". Copies of this Index may be obtained from the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Agencies within the War Department, will obtain copies of Joint Army-Navy, United States Army and Federal specifications through established War Department channels. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H–6. Copies of Joint Army-Navy specifications and Federal specifications (required for Navy purchases) and Navy Department specifications may be obtained upon application to the Bureau of Supplies and Accounts, Navy Department, Washington 25, D. C., except that Naval activities should make application to the Supply Officer in Command, Naval Supply Depot, Bayonne, N. J. Both the title and identifying symbol number should be stipulated when requesting copies of specifications.

H–7. Copies of this Joint Army-Navy specification (for Army purchases) may be obtained from the following points:

Chicago Quartermaster Depot, 1819 West Pershing Road, Chicago 9, Ill.
Stockton General Depot, U. S. Army, Stockton 1, Calif.
San Antonio General Depot, U. S. Army, Grayson Street Station, San Antonio, Tex.
Jeffersonville Quartermaster Depot, Jeffersonville, Ind.
Kansas City Quartermaster Depot, 601 Hardesty Avenue, Kansas City 1, Mo.
Philadelphia Quartermaster Depot, 2800 S. 20th Street, Philadelphia 45, Pa.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Army: Q.
Navy: SOGP.

[JAN-C-380]

Source: https://assist.dla.m
Check the source to verify tha