A-A-1244
December 12, 1979

COMMERCIAL ITEM DESCRIPTION

PAPER, WRAPPING, DRY-WAXED (NON-FOOD WRAPPING USES)

The General Services Administration has authorized the use of this commercial item description in lieu of Federal Specification UU-P-270

Salient characteristics:

The waxed paper shall be brown, with a basis weight, bursting strength, tearing resistance, tensile strength, and wax content as indicated in table I. Test methods shall be as follows basis weight - TAPPI T410; bursting strength - TAPPI T403, tearing resistance - TAPPI T414, tensile strength - TAPPI T404, and wax content - TAPPI T405

Paper shall be furnished in rolls or sheets of the dimensions specified ± 1/8 inch Roll length shall be as specified - 0, + unlimited

Rolls of waxed paper shall be smoothly and uniformly wound on a nonreturnable core with a 3-inch ± 1/16 inch inside diameter

TABLE I. Physical requirements

Basis weight (24 x 36-500) plus or minus five percent	Bursting strength average, minimum	Tearing resistance weakest direction, average, minimum	Tensile strength weakest direction, average, minimum	Wax content (24 x 36-500) sheets, min
Pounds	Points	Grams	Pounds per inch width	Pounds
20	16	20	5 5	3
25	20	25	7.5	4
30	24	35	9	5
35	28	40	12	6
40	32	50	13 5	7
50	40	60	17	8
60	48	80	20	10

Workmanship The dry-waxed wrapping paper shall be uniformly waxed and coated, clean, and free from all imperfections which may impair its serviceability

The issue of the TAPPI Test Method in effect on the date of the solicitation shall be used to determine compliance with stated requirements.

Certification The contractor shall certify that the product offered meets the salient characteristics of this description and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices and is the same product offered for sale in the commercial marketplace The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract

Recovered materials The manufacturer shall utilize recovered materials to the maximum extent practicable

Packaging, packing, and marking. The wrapping paper shall be packaged in accordance with normal commercial practice and packed in fiberboard boxes to assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling, and storage. The shipping container shall be in compliance with National Motor Freight Classification and Uniform Freight Classification. Marking shall be as specified in the contract or order.

TAPPI Test Methods are available from the Technical Association of the Pulp and Paper Industry, One Dunwoody Park, Atlanta, GA 30[illegible]

Note. Purchaser should specify form, dimensions, and basis weight of the paper required.

FSC 8135

GSA DC-01003461

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:12Z
Check the source to verify that this is the current version before use.