CORD, ELECTRICAL
(RETRACTILE, 2, 3, AND 4 CONDUCTOR, WD-9/U, WT-2/U, WF-4/U)

1. Paragraph 1.2 - In line 3 correct spelling of "plug" to read "plus".

2. Paragraph 3.6.3 - Replace with the following:

"3.6.3 Low temperature extension.- After conditioning by placing for not less than 20 hours in a compartment maintained at a temperature of minus 40 ± 2°F., a suitable coiled portion of the cord shall permit extension to 4 times its retracted length without fracture of the jacket, conductor insulation, or conductors. Upon release, and while still exposed to the conditioning temperature, the cord shall retract to not more than 200 percent of its original length 30 seconds after being released on a horizontal surface. Frictional restraint shall be relieved by tapping on the surface. Force to extend its retracted length within 5 seconds shall not exceed 20 pounds. The actual values shall be recorded and forwarded with preproduction sample test data."

3. Add the following paragraph after 3.6.3:

"Low temperature extension.- After conditioning by placing for not less than 20 hours in a compartment maintained at a temperature of minus 65°F ± 2°F., a suitable coiled portion of the cord shall permit extension to 4 times its retracted length without fracture of the jacket, conductor insulation, or conductors. Upon release, and while still exposed to the conditioning temperature, the cord shall retract to not more than 200 percent of its original length 30 seconds after being released on a horizontal surface. Frictional restraint shall be relieved by tapping on the surface. Force to extend its retracted length within seconds shall not exceed 20 pounds. The actual values shall be recorded and forwarded with preproduction sample test data."

4. Paragraph 3.6.4 - Replace with the following:

"3.6.4 Retraction after static loading.- At room temperature, 30 minutes after being placed on a flat surface, the retracted length of the finished cord shall be not more than 110 percent of its original retracted length after the coiled portion of a cord has been extended to 250 percent of its original retracted length by the cord being secured at one end and hung vertically with a weight attached to the lower end for 48 hours."

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:20Z
Check the source to verify that this is the current version before use.

5. Add the following Paragraph 3.9:

"3.9 The contractor shall submit 24 each retractile cords of each type with test data, for preproduction test evaluation to determine compliance with the technical requirements of this specification. Failure to meet the requirements of this specification will require corrective action and resubmission of samples and test data."

6. Add the following paragraph 3.10:

"The cords shall comply with Specification MIL-C-3885, Paragraph 3.2.3 - Treatment of Textiles."

7. Add the following:

"High temperature retraction (+150°F ±2°F).- While the coiled portion is extended to 3 times its retracted length the cords shall be conditioned by placing in an air oven maintained at a temperature of +150°F ±2°F for 20 hours. While maintained at this temperature the coiled portion of the cord shall then be capable of complying with the following: After the coiled portion is extended further to 5 times its retracted length and returned to its original retracted length and stretched and returned in this manner for a total of 3 times, the coiled portion shall not exceed 275% of its original retracted length when the cord is held vertically for 15 seconds."

8. Add the following:

"High temperature retraction (+185°F ±2°F).- While the coiled portion is extended to 3 times its retracted length the cords shall be conditioned by placing in an air oven maintained at a temperature of +185°F ±2°F for 20 hours. While maintained at this temperature the coiled portion of the cord shall then be capable of complying with the following: After the coiled portion is extended further to 5 times its retracted length and returned to its original retracted length and stretched and returned in this manner for a total of 3 times, the coiled portion shall not exceed 275% of its original retracted length when the cord is held vertically for 15 seconds."

9. Table II - Government group B inspection. Replace "460-2" with "460-1 and 460-2" under "Drawing" in "Sampling Plan" column.

10. Table III - Government group C inspection. Replace "1 Cord per 100" with "1 Cord per 1000" in "Sampling Plan" column.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:20Z
Check the source to verify that this is the current version before use.

11. Paragraph 4.11 - Replace with the following:

"4.11 Retraction at -40°F.- The finished cord shall be tested to determine compliance with paragraph 3.6.3."

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:20Z
Check the source to verify that this is the current version before use.