INCH-POUND

MIL-DTL-13282C
27 May 2025
SUPERSEDING
MIL-S-13282B
13 July 1973

DETAIL SPECIFICATION

SILVER AND SILVER ALLOYS

REACTIVATED AFTER 13 JULY 2025 AND MAY BE USED FOR NEW AND EXISTING DESIGN AND ACQUISITIONS.

This specification is approved for use by the Department of the Army and is available for use by all Departments and Agencies of the Department of Defense

1. SCOPE

1.1 Scope. This specification covers fine silver and two silver-copper alloys.

1.2 Classification. Silver should be furnished in one of the following grades, forms, and tempers, as specified (see 6.2).

1.2.1 Grades.

A - Fine silver.
B - Sterling silver.
C - Coin or numismatic silver.

1.2.2 Forms.

Plate	Wire	Ingots
Sheet	Rod	Cathodes
Strip	Bar	Anodes

Comments, suggestions, or questions on this document should be addressed to: Director, U.S. Army DEVCOM, Army Research Laboratory (ARL), Army Research Directorate, Specifications & Standards Office, Attn: FCDD-RLA-M, Aberdeen Proving Ground, MD 21005-5069. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil/.

AMSC N/A FSC 9545

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

1.2.3 Tempers.

Annealed

1/8 Hard

1/4 Hard

1/2 Hard

3/4 Hard

Hard

Spring

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-DTL-197	-	Packaging of Bearings, Associated Parts and Subassemblies
MIL-DTL-17667	-	Paper, Wrapping, Chemically Neutral (Non-Corrosive)
MIL-L-10547	-	Liners, Case, Waterproof

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-129	-	Military Marking for Shipment and Storage
MIL-STD-1916	-	DoD Preferred Methods for Acceptance of Product Attributes

(Copies of these documents are available online at https://quicksearch.dla.mil/.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY

NBS Circular 31	-	Copper Wire Tables

(Copies of this document are available online at https://www.govinfo.gov.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

2.2 Non-Government publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the contract or purchase order.

THE AMERICAN NATIONAL STANDARDS INSTITUTE

ANSI/ASQ Z1.4	-	Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available online at https://ansi.org/).

ASTM INTERNATIONAL

ASTM D1974/D1974M	-	Standard Practice for Methods of Closing, Sealing, and Reinforcing Fiberboard Boxes
ASTM D5118/D5118M	-	Standard Practice for Fabrication of Fiberboard Shipping Boxes
ASTM D5168	-	Standard Practice for Fabrication and Closure of Triple-Wall Corrugated Fiberboard Containers
ASTM D6251/D6251M	-	Standard Specification for Wood-Cleated Panelboard Shipping Boxes
ASTM D6880/D6880M	-	Standard Specification for Wood Boxes
ASTM E8/E8M	-	Standard Test Methods for Tension Testing of Metallic Materials
ASTM E55	-	Standard Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition
ASTM E1621	-	Standard Guide for Elemental Analysis by Wavelength Dispersive X-Ray Fluorescence Spectrometry

(Copies of these documents are available online at https://www.astm.org).

INTERNATIONAL STANDARDS

ISO 11427	-	Determination of Silver in Silver Jewellery Alloys - Volumetric (Potentiometric) Method Using Potassium Bromide
ISO 13756	-	Jewellery and Precious Metals - Determination of Silver - Potentiometry Using Sodium Chloride or Potassium Chloride
ISO 15096	-	Jewellery and Precious Metals - Determination of High Purity Silver - Difference Method Using ICP-OES

(Copies of these documents are available online at https://www.iso.org/).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

2.4 Order of precedence. Unless otherwise noted herein or within the contract or purchase order, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Preproduction samples. When specified in the contract, five sample units representative of the material to be produced under the contract will be required to determine compliance with the acceptance test requirements of this specification.

3.2 Chemical composition. The material shall conform to the chemical requirements specified in table I.

3.2.1 Chemical Analysis Report. When specified in the contract or order, a chemical analysis report, showing the percentage of each element, shall be furnished by the contractor.

TABLE I. Chemical composition, percent.

Grade	Silver	Copper	Zinc (max)	Iron (max)	Cadmium (max)	Lead (max)	Other Impurities (max)
A	99.90 min. 1/	0.10 max. 1/	---	0.005	---	0.025	2/
B	92.5 +1.0 - 0.4	7.5 +0.4 - 1.0	0.06	0.05	0.05	0.03	0.06
C	90.0 +1.0 - 0.4	10.0 +0.4 - 1.0	0.06	0.05	0.05	0.03	0.06

1/ For anodes, the silver content shall be 99.95 percent minimum and silver plus copper shall be 99.98 percent minimum. For all other forms, silver plus copper shall be 99.95 percent minimum.

2/ Bismuth - 0.001 percent maximum. For electroplating (anodes), tellurium and selenium shall each be 0.001 percent maximum.

3.3 Mechanical properties.

3.3.1 Tensile requirements for sheet and strip. Silver and silver alloy sheet and strip shall be capable of meeting the requirements of table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

TABLE II Tensile strength requirements, sheet and strip.

Temper	Reduction in Brown and Sharpe Nos.	Percent Reduction	Tensile strength, (ksi)		Elongation, Percent in 2 in.
			Minimum	Maximum	Minimum
Grade A					
Annealed	0	---	24.0	30.0	25
1/2 hard	2	---	30.0	37.0	8
Hard	4	---	37.0	44.0	3
Spring	8	---	44.0	51.0	1
Grade B					
Annealed	0	---	35.0	45.0	20
1/2 hard	2	21	46.0	55.0	4
Hard	4	37	54.0	62.0	2
Spring	8	60	63.0	70.0	1
Grade C					
Annealed	0	---	36.0	47.0	20
1/2 hard	2	21	47.0	57.0	4
3/4 hard	3	29	53.0	63.0	2
Hard	4	37	58.0	68.0	1
Spring	8	60	67.0	75.0	1

3.3.2 Tensile requirements for wire and rod. Silver and silver alloy wire and rod shall be capable of meeting the requirements of table III.

TABLE III. Tensile strength requirements, wire and rod.

Temper	Reduction in Brown and Sharpe Nos.	Percent Reduction	Tensile strength, (ksi)		Elongation, Percent in 2 in. or 4X Diameter
			Minimum	Maximum	Minimum
Grade A					
Annealed	0	---	24.0	30.0	25
1/4 hard	1	21	30.0	37.0	4
Hard	4	60	42.0	49.0	2
Spring	8	84	46.0	54.0	1
Grade B					
Annealed	0	---	35.0	45.0	20
1/4 hard	1	21	47.0	55.0	4
Hard	4	60	63.0	71.0	2
Spring	8	84	72.0	82.0	1
Grade C					
Annealed	0	---	36.0	47.0	20
1/8 hard	0.5	11	42.0	52.0	8
1/4 hard	1	21	47.0	57.0	4
3/4 hard	3	50	61.0	71.0	3
Hard	4	60	65.0	74.0	2
Spring	8	84	74.0	82.0	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

3.3.3 Tensile requirements for other forms. The tensile properties of other forms, when required, shall be as specified in the contract or order, (see 6.2).

3.3.4 Bend requirements for sheet and strip. Sheet and strip, all grades, having a temper of 1/2 hard or less, shall be capable of being bent through 180° around a radius equal to the thickness of the sheet or strip without any signs of flaking or fracture.

3.3.5 Twist requirements for wire and rod. Wire and rod, grades B and C having a temper of 1/4 hard or less shall be capable of being twisted through 7 forward and 7 reverse 360° turns within a length of 3 inches without exhibiting seams, slivers, or other discontinuities that would be detrimental.

3.4 Microstructure. The microconstituents of grades B and C shall be uniformly distributed so that segregations are not present in the material (see 6.6).

3.5 Dimensions. The width, length, thickness and diameter of the material, as applicable, shall be specified in the individual contract.

3.5.1 Dimensional tolerances.

3.5.1.1 Sheet and strip. Thickness, width, and straightness tolerances for sheet and strip shall conform to the requirements of tables IV, V, and VI, respectively. Thickness and width tolerances shall be plus and minus.

TABLE IV. Thickness tolerances, sheet and strip.

Thickness, inch	Tolerance, ±inch		
	Up to 9 in. Wide, incl.	Over 9 to 14 in. Wide, incl.	Over 14 to 20 in. Wide, incl.
Up to 0.004, incl.	0.0003	0.0005	---
Over 0.004 to 0.006, incl.	0.0004	0.0006	---
Over 0.006 to 0.009, incl.	0.0006	0.0008	0.0012
Over 0.009 to 0.013, incl.	0.0008	0.0010	0.0015
Over 0.013 to 0.017, incl.	0.0010	0.0014	0.0018
Over 0.017 to 0.021, incl.	0.0012	0.0016	0.0020
Over 0.021 to 0.026, incl.	0.0015	0.0020	0.0025
Over 0.026 to 0.037, incl.	0.0020	0.0020	0.0025
Over 0.037 to 0.050, incl.	0.0020	0.0020	0.0025
Over 0.050 to 0.073, incl.	0.0025	0.0025	0.0030
Over 0.073 to 0.130, incl.	0.0025	0.0025	0.0030
Over 0.130 to 0.187, incl.	0.0030	0.0030	0.0030
Over 0.187 to 0.205, incl.	0.0030	0.0030	0.0035
Over 0.205 to 0.300, incl.	0.0030	0.0030	0.0035

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

TABLE V. Width tolerance, sheet and strip.

Width, inches	Tolerance, ±inch					
	Slit Metal			Square Sheared Metal	Sawed Metal	
	Up to 0.062 in. Thick, incl.	Over 0.062 in. to 0.125 in. Thick, incl.	Over 0.125 in. Thick		Up to 0.5 in. Thick,	Over 0.5 in. Thick
Up to 2, incl.	0.003	0.008	0.015	0.062	0.031	0.062
Over 2 to 6, incl.	0.003	0.015	0.015	0.062	0.031	0.062
Over 6 to 20, incl.	0.005	0.015	0.015	0.062	0.031	0.062

TABLE VI. Straightness tolerances, sheet and strip (Maximum edgewise curvature in 6 feet).

Width, inches	Tolerance, inch					
	Slit Metal			Square Sheared Metal		Sawed Metal
	Coiled	Flat	Flat and Straightened	Up to 0.125 in. Thick, incl.	Over 0.125 in to 0.250 in. Thick, incl.	
Up to 2, incl.	0.500	0.500	0.250	0.025	0,031	0.031
Over 2 to 6, incl.	0.500	0.500	---	0.025	0.031	0.031
Over 6 to 13, incl.	0.500	0.500	---	0.031	0.062	0.050

3.5.1.2 Wire and rod. Diameter tolerances for wire and rod shall conform to the requirements of table VII. All tolerances shall be plus and minus.

TABLE VII. Diameter tolerances, wire and rod.

Diameter, inch	Tolerance, ±inch
0.012 to 0.030, incl.	0.0002
Over 0.030 to 0.060, incl.	0.0003
Over 0.060 to 0.187, incl.	0.0005
Over 0.187 to 0.250, incl.	0.0010
Over 0.250 to 0.375, incl.	0.0015
Over 0.375 to 0.750, incl.	0.0020

3.5.1.3 Bar, plate, ingots, cathodes and anodes. The dimensional tolerances of bar, plate, ingots, cathodes and anodes as required, shall be as specified in the contract or order, (see 6.2).

3.6 Identification marking. Silver and silver alloys shall be legibly identified with the manufacturer's name, brand or trademark and the grade, temper, and specification number. Identification shall be such as not to adversely affect use of the material.

3.7 Workmanship. Silver and silver alloys furnished under this specification shall be free of dull surfaces, die marks and seams.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. Inspection shall be classified as follows:

(a) Preproduction inspection.
(b) Acceptance inspection of individual lots.

4.2.1 Preproduction inspection. Preproduction inspection, when required (see 3.1) shall consist of the following:

(a) Chemical analysis (see 3.2 and 4.6.1)
(b) Tensile properties (see 3.3.1, 3.3.2, 3.3.3 and 4.6.2)
(c) Bend tests (see 3.3.4 and 4.6.3)
(d) Twist tests (see 3.3.5 and 4.6.4)
(e) Microscopic examination (see 3.4, 4.7, and 6.6)
(f) Dimensions (see 3.5 and 4.5)
(g) Identification marking (see 3.6 and 4.5)
(h) Workmanship (see 3.7 and 4.5)

4.2.2 Lot acceptance inspection. Lot acceptance inspection shall consist of the inspection covered by 4.2.1 plus preparation for shipment (see section 5 and 4.5.2).

4.3 Lot. A lot shall consist of all silver material of the same grade, temper, form, and size in one shipment.

4.4 Sampling.

4.4.1 For preproduction testing. When specified in the contract or order, a representative sample of five units will be required to determine compliance with the requirements of the contract and specification. Preproduction tests will be accomplished at an activity designated by the procuring activity.

4.4.2 For acceptance testing.

4.4.2.1 Sampling for chemical analysis. One sample that is appropriate for the chemical analysis method selected under 4.6.1 shall be taken from each lot of silver material in accordance with ASTM E55. Unless otherwise specified in the contract or order, the sample shall consist of approximately 10 grams of chips.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

4.4.2.2 Sampling for tension tests. Two tension test samples shall be taken from each lot.

4.4.2.3 Sampling for bend and twist tests. Five samples each for the bend and twist tests shall be taken from each lot

4.4.2.4 Sampling for microscopic examination. Two samples for microscopic examination shall be taken from each lot.

4.4.2.5 Sampling for examination. Unless otherwise specified in the contract or order, sampling for dimensional and workmanship examination shall be done in accordance with MIL-STD-1916 and conducted following ANSI/ASQ Z1.4, Level II, AQL 1.0 percent. Samples for dimensional and workmanship examination shall be evaluated separately.

4.5 Examination. Each sample unit selected in accordance with 4.4.2.5 shall be visually and dimensionally examined to determine compliance with the requirements for dimensions (see 3.5), identification marking (see 3.6), and workmanship (see 3.7). Straightness of each sample unit shall be determined as specified in 4.5.1.

4.5.1 Straightness. Straightness shall be determined by placing the piece on a level surface so that the arc or departure from straightness is horizontal. The maximum depth of arc shall be measured to the nearest 1/32 inch by means of a straightedge and a steel scale.

4.5.2 Preparation for shipment. Examination of the packing and marking for shipment shall be made for conformance to the requirements of section 5.

4.6 Tests.

4.6.1 Chemical analysis. The samples selected in accordance with 4.4.2.1 shall be analyzed using inductively coupled plasma atomic emission spectroscopy (ICP-AES) also known as inductively coupled plasma optical emission spectroscopy (ICP-OES) in accordance with ISO 15096. Wavelength dispersive X-ray fluorescence spectrometry (XRF) in accordance with ASTM E1621 and wet chemical analysis in accordance with ISO 11427 or ISO 13756 are acceptable alternate methods to determine conformance to 3.2. In case of dispute, analysis using ICP-AES/OES shall be the final basis for acceptance or rejection.

4.6.2 Tension tests. All tension tests shall be conducted in accordance with ASTM E8.

4.6.3 Bend test. Samples selected in accordance with 4.4.2.3 shall be bent 180° around a radius equal to the thickness of the sheet or strip. Bends shall be made 90° to the direction of rolling. The material shall be examined for conformance to 3.3.4.

4.6.4 Twist test. Samples of grades B or C silver alloy having a temper of 1/4 hard or less, selected in accordance with 4.4.2.3 shall be subjected to 7 forward and 7 reverse 360° turns within a length of 3 inches. The material shall be examined for conformance to 3.3.5.

4.7 Microscopic examination. Samples selected in accordance with 4.4.2.4 shall be examined at a suitable magnification to determine compliance with 3.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

4.8 Rejection.

4.8.1 Examination defects. Any sample unit having one or more defects shall be rejected. If the number of nonconforming sample units in the sample exceeds the acceptance number specified in contract or purchase order for that sample size, the entire lot shall be rejected.

4.8.2 Test failures. A lot shall be rejected for failure to meet any of the test requirements when tested in accordance with 4.6 and 4.7.

5. PACKAGING

5.1 Internal Packaging. Packaging shall be as specified (see 6.2).

5.1.1 Wrapping paper. The silver material shall be wrapped using chemically neutral and noncorrosive paper conforming to MIL-DTL-17667.

5.1.2 Coiling and spools. Unless otherwise specified on the contract or order, the inside diameter of material supplied in coils or on spools shall be in accordance with the supplier's standard practice.

5.1.3 Manufacturers' practice. When requested in the contract or purchase order, silver material shall be packaged in accordance with the manufacturers' standard commercial practice.

5.2 Packing. Packing shall correspond to levels A or B in accordance with MIL-DTL-197, or to level C as agreed upon in the contract or purchase order (see 6.2).

5.2.1 Level A. The silver material packaged as specified in 5.1 shall be packed in close fitting boxes of the overseas class or type, conforming to one of the following specifications listed in table VIII. Exterior shipping containers shall be multi-application type containers designed to protect silver forms within a given fragility and size range. Intermediate containers shall provide weather resistant case liners (see 5.2.1.1), closed and sealed in accordance with military practices. Boxes shall be closed, strapped, or banded in accordance with the applicable box specification, except that ASTM D5118/D5118M boxes shall be closed, sealed, and reinforced using any method in ASTM D1974/1974M. Unless otherwise specified (see 6.2), the gross weight of wood or wood-cleated boxes shall not exceed 200 pounds; fiberboard boxes shall not exceed the weight limitation of the applicable box specification.

5.2.1.1 Level A liners. Unless otherwise specified, wood and wood-cleated containers shall be lined with a case liner conforming to MIL-L-10547 and sealed in accordance with the appendix of that specification. Fiberboard boxes closed, waterproofed and reinforced in accordance with the appendix of the box specification will not require case liners.

5.2.1.2 Gross packaged weight. Unless otherwise specified in the contract or order, the gross weight of wood or wood cleated boxes shall not exceed 200 pounds, and the gross weight of fiberboard boxes shall not exceed the limitations of the applicable box specification. If a gross weight exceeding 200 pounds is authorized for wood or wood cleated boxes, the boxes shall be provided with skids and securely strapped.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

5.2.1.3 Closing and reinforcement. Strapping and closure shall be in accordance with the appendix to the applicable container specification.

5.2.2 Level B. The silver material packaged as specified in 5.1 shall be packed in close fitting boxes of the overseas class or type, conforming to one of the following specifications listed in table VIII. Box closures, sealing, and reinforcement shall be as specified in the applicable box specification or as specified in ASTM D1974/D1974M.

TABLE VIII. Packaging options for shipment and storage of silver materials.

Packaging Specification	Class	Description	Level A	Level B
ASTM D6251/D6251M	class 1	Domestic Boxes	---	✓
	class 2	Overseas Boxes	✓	✓
ASTM D6880/D6880M	class 2	Heavy Duty	✓	✓
ASTM D5118/D5118M	N/A	Weather Resistant, Corrugated, and Solid Fiberboard	---	✓
ASTM D5168	N/A	Weather Resistant	---	✓

5.2.3 Level C. All silver material, packaged as otherwise specified in the contract or purchase order (see 6.2), shall be packed in containers to provide a compact and non-shifting load and to insure acceptance at destination. Containers, shipments and container closures shall comply with carrier regulations as applicable to the mode of transportation.

5.3 Marking. Unless otherwise specified in the contract or order, marking of shipments shall be in accordance with MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. This silver is intended for use in the following types of applications:

6.1.1 Electrical. All types of electrical contacts such as headed rivets, springs, wire, composite forms, slip rings, and special assemblies for make and break and sliding contact applications.

6.1.2 Mechanical. Applications where mechanical strength and hardness are required with high thermal and electrical conductivity.

6.1.3 Anodes. Anodes are for use in electroplating.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Grade, form, and temper required (see 1.2).
(c) When preproduction samples are required (see 3.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

(d) When a chemical analysis report is required (see 3.2.1).
(e) When required, mechanical properties of bar, plate, ingots, and cathodes (see 3.3).
(f) Dimensions required (see 3.5).
(g) When strip is to be furnished in lengths, other than random flat lengths or supplied in coils or on spools in accordance with supplier's standard practice (see 3.5).
(h) Dimensional tolerances of bar, plate, ingots, cathodes and anodes (see 3.5.1.3).
(i) When a sample for chemical analysis of other than 10 grams is required (see 4.4.2.1).
(j) When sampling for examination other than in accordance with 4.4.2.5 is required (see 4.4.2.5).
(k) Maximum gross weight of containers with contents.
(1) Special marking, if required (see 5.3).
(m) Packaging and packing level required (see 5.1 and 5.2).

6.3 Alternate Terminologies. Grade A silver is commercially known as "999.0 fine silver", grade B as sterling or “925.0 fine", and Grade C as "coin silver", “numismatic silver”, or "900.0 fine".

6.4 Resistivity and electrical conductivity of silver materials. The resistivity and electrical conductivity of the silver materials covered by this specification are shown in table IX for information only.

6.5 Packaging Costs. In the interest of economy, it is desired in packing that fiberboard boxes be used to the greatest extent practicable.

6.6 Microscopy techniques for silver. The article: *Metallographic Procedures for Precious Metals*, by G. Vander Voort, July 2012, provides helpful instructions for the preparation of various grades of silver including abrasives, etchants, and example pictures of microstructures. This article is available for reference at: https://vacaero.com/information-resources/metallography-with-george-vander-voort/1251-metallographic-procedures-for-precious-metals.html.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

TABLE IX. Resistivity and electrical conductivity.

Form	Grade	Temper	ρ, Resistivity, microohms/cm^3 (max)	Percent Electrical Conductivity IACS [1/] (min)
Sheet and strip	A	Annealed	1.724	100
		1/2 hard	1.749	98
		Hard	1.777	97
		Spring	1.796	96
	B	Annealed	2.155	80
		1/2 hard	2.211	78
		Hard	2.298	75
		Spring	2.298	75
	C	Annealed	2.052	84
		1/2 hard	2.102	82
		3/4 hard	2.128	81
		Hard	2.155	80
		Spring	2.298	75
Wire and rod	A	Annealed	1.724	100
		1/4 hard	1.749	98
		Hard	1.796	96
		Spring	1.815	95
	B	Annealed	2.155	80
		1/4 hard	2.211	78
		Hard	2.298	75
		Spring	2.298	75
	C	Annealed	2.052	84
		1/8 hard	2.102	82
		1/4 hard	2.102	82
		3/4 hard	2.128	81
		Hard	2.155	80
		Spring	2.298	75

[1/] International Annealed Copper Standard (Set to Copper = 100% Conductivity). See Bureau of Standards Circular No. 31.

6.7 Subject term (key word) listing.

Bars
Conductors
Contacts
Currency
Electrical
Electronics
Foil
Ingot
Plating
Precious metals
Reflectivity
Wire

6.8 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army - MR
Air Force - 84
Navy - AS

Preparing activity:
ARMY - MR

(Project 9545-2025-001)

Review activities:
Army - AV, CR4, MI
Air Force - 11

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T00:21Z
Check the source to verify that this is the current version before use.