INCH-POUND

MIL-P-52905A
31 January 1994
SUPERSEDING
MIL-P-52905(ME)
7 July 1976

MILITARY SPECIFICATION

PAINT, CAMOUFLAGE, REMOVABLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a quick-drying camouflage paint that can be easily removed when applied on previously painted military equipment. The paint is lead and chromate free, contains no more than 3.5 pounds per gallon (420 grams per liter) of volatile organic compounds (VOC), as applied.

1.2 Classification.

1.2.1 Colors. The coating shall be furnished in the following colors as specified (see 6.2).

1.2.1.1 Camouflage. White 37875 and Tan 686A, 33446.

1.2.1.2 Others. Brown 30219, Brown 30279, Green 34095, Grey 35327, Grey 36320, Grey 36375, and, Black 37038.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US ARMY BELVOIR RDE CTR, ATTN SATBE TSE, 10101 GRIDLEY RD STE 104, FT BELVOIR VA 22060-5818 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8010

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

TT-S-735 - Standard Test Fluids, Hydrocarbon.
PPP-P-1892 - Paint, Varnish, Lacquer, and Related Materials, Packaging, Packing, and Marking of.

MILITARY

MIL-C-46168 - Coating, Aliphatic Polyurethane, Chemical Agent Resistant.

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.
FED-STD-313 - Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities.
FED-STD-595 - Colors Used in Government Procurement.

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from: STDZN DCMNT ORDER DESK, BLDG 4D, 700 ROBBINS AVE, PHILADELPHIA PA 19111-5094.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DoDISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 34 - Chemical Analysis of White Pigments.
D 562 - Consistency of Paints Using the Stormer Viscometer.
D 1210 - Fineness of Dispersion of Pigment-Vehicle Systems.
D 1308 - Effect of Household Chemicals on Clear and Pigmented Organic Finishes.
D 1729 - Visual Evaluation of Color Differences of Opaque Materials.
D 2369 - Volatile Content of Coatings.
D 2698 - Determination of the Pigment Content of Solvent-Reducible Paints by High-Speed Centrifuging.
D 3951 - Standard Practice for Commercial Packaging.
D 3960 - Determining Volatile Organic Compound (VOC) Content of Paints and Related Coatings.
E 70 - Ph of Aqueous Solutions With The Glass Electrode.
E 308 - Computing the Colors of Objects By Using the CIE System.
G 26 - Operating Light-Exposure Apparatus (Xenon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to: AMERCN SCTY & MTRLS, 1916 RACE STRET, PHILADELPHIA PA 19103.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, (except for related associated detail specifications, specification sheets or MS standards), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Formulation. The method of formulation and choice of materials is optional with the contractor, except as noted in 3.3 below, provided that the final product conforms to all requirements of the specification.

3.2 Color. The coating shall impart to the substrate the required spectral reflectance properties in the ultraviolet (350-360 nanometers), visible (380-700 nanometers) and the near infrared (700-900 nanometers) spectral regions. All reflectance values shall meet the limits specified in table I, and the color shall fall within 2.5 CIELAB units of the listed chromaticity coordinates, when calculated using the average brightness of an allowable range or the minimum brightness if no range is specified. All non-camouflage colors shall visually match the appropriate chip from FED-STD-595.

TABLE I. Reflectance requirements of applied coating.

Color, FED-STD-595 No.	Ultraviolet 1/	Visual (Y)	Infrared 2/	Chromaticity x	Chromaticity y
White, 37875	Min - 75%	Min - 85%	Min - 85%	0.310	0.315
Tan 686A, 33446	-	36.0 - 40.0%	62.0 - 72.0%	0.368	0.364

1/ From 350-360 nanometers, the percent reflectance shall be not less than the minimum required.
2/ Average for wavelengths specified. See table IV.

3.3 Composition.

3.3.1 Pigment.

3.3.1.1 White. The primary hiding pigment shall be either chemically pure zirconium oxide or cubic structured antimony oxide. The average maximum particle size shall be no greater than 2.0 microns. The extender pigment shall consist of one or more of barium sulfate (blanc fixe), natural ground or synthetic calcium carbonate, amorphous and diatomaceous silica, or magnesium silicate. Titanium

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the currentversion before use.

ed specimens shall be at least ten times ... lation resistance of the set of coat

dioxide or aluminum silicate shall not be employed alone, but is permissible as a component part of any pigment, provided these additional pigments do not affect the spectral requirements in table I. Small amounts of shading pigments may be used to increase opacity, but must not affect the required characteristics of table I.

3.3.1.2 Tan 686A. Hiding pigments shall be limited to chromium oxide, titanium dioxide, carbazole dioxazine violet, iron oxides, zinc/magnesium ferrites or other mixed metal oxides. Extenders shall be siliceous and are limited to 65 percent by weight of the pigment.

3.3.2 Vehicle. The vehicle shall be a low molecular weight, thermoplastic acrylic resin dispersed in ammonia water. Small amounts of antioxidants, wetting agents, anti-sag agents, and stabilizers may be present.

3.4 Qualitative requirements.

3.4.1 Condition in container. When tested as specified in 4.3.10, the paint shall be free of grit, seeds, skins, lumps, or livering and shall show no more pigment settling or caking than can be readily re-incorporated to a smooth homogenous state.

3.4.2 Storage stability.

3.4.2.1 Partially full container. When tested as specified in 4.3.11.1, the paint shall show no skinning. After aging as specified in 4.3.11.1, the coating shall show no livering, curdling, hard caking or gummy sediment. It shall mix readily to a smooth homogeneous state, and any skin formation shall be continuous and easily removed.

3.4.2.2 Full container. When tested as specified in 4.3.11.2, the paint shall show no skinning, livering, curdling, hard-dry caking or tough gummy sediment. The coating shall remix readily to a smooth homogeneous state and must be usable. The consistency of the coating after storage shall be not more than 95 KU.

3.4.3 Dilution stability. When thinned as specified in 4.3.12, the paint shall remain stable and uniform showing no precipitation, curdling, or separation. Slight pigment settling shall be permitted.

3.4.4 Brushing properties. When tested as specified in table III, the paint shall brush satisfactorily and shall dry to a smooth, uniform film, free from seeds, runs, sags or streaks. The dried film shall show no discernible brush marks.

3.4.5 Spraying properties. When tested as specified in table III, the paint shall spray satisfactorily in all respects, and shall show no running, sagging, streaking, or pronounced orange peel. The air dried film shall show no seeding, dusting, floating, fogging, mottling, hazing, or other film defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

3.4.6 Recoatability. When tested as specified in table III, recoating of dried film shall produce no film irregularity.

3.4.7 Water resistance. When tested as specified in 4.3.13, a film of the paint shall not be removed, but slight wrinkling or blistering is allowed when examined immediately after removal from the distilled water. When examined 2 hours after removal, there shall be no excessive softening and no blisters shall be observed. After 24 hours air drying, the portion of the panel which was immersed shall be practically the same, with regard to hardness and adhesion, compared to a panel prepared at the same time, but not immersed.

3.4.8 Hydrocarbon resistance. When tested as specified in 4.3.14, a film of the paint shall show no blistering or wrinkling when examined immediately after removal from the hydrocarbon test fluid. When examined 2 hours after removal, there shall be no excessive softening, whitening, or dulling. After 24 hours drying, the part of the panel which was immersed shall be practically the same, with regard to hardness, adhesion, and general appearance, compared to a panel prepared at the same time but not immersed.

3.4.9 Accelerated weathering. When tested as specified in 4.3.15, samples of the paint shall show no chalking, cracking, or loss of adhesion. The colors and spectral reflectance values after weathering shall remain within those limits originally specified in table I, except the visual reflectance for white may be as low as 80 percent.

3.4.10 Removability. When tested as specified in 4.3.19, the paint shall be easily removed by washing with the specified solution (see 6.5). There shall be no deleterious effect on the underlying paint film or substrate. Time period for immersion shall be not more than 2 minutes.

3.4.11 Freeze conditions. When tested as specified in 4.3.18, the paint shall not gel nor show phase separation which cannot be easily dispersed. The condition of the paint shall be the same as before this exposure condition; the brushing and spraying properties shall be the same as specified in 3.4.4 and 3.4.5.

3.4.12 Weather resistance. A film of the paint, prepared and exposed as specified in 4.3.17, shall show no cracking, or appreciable film deterioration. There shall be not more than light chalking. For the white color, the minimum values may be as much as 5 percentage points less than the values specified in table I. For the tan color, all values shall remain within the limits specified. The paint shall be easily removed when tested as specified in 4.3.19.

3.4.13 Photographic test (white only). When tested as specified in 4.3.16, the paint shall appear comparable to standard panels of calcium carbonate. There shall be no greying of the test panels.

3.5 Quantitative requirements. The quantitative requirements shall be as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

TABLE II. Quantitative requirements of the coating.

Characteristics	Requirements Min	Max
Total solids, percent by wt. of coating	50	--
Pigment solids, percent by wt. of coating	34	38
Vehicle solids, percent by wt. of coating	15	--
85 degree gloss	--	3
60 degree gloss	--	2.0
Fineness of grind	5	--
Dry opacity (2.0 mil dry film) control ratio		
White, 37875	90	--
Tan 686A, 33446	99	--
Viscosity, Krebs units	85	95
Drying time		
Set to touch, min.	--	30 min
Dry hard, hours	--	4 hours
pH of enamel	7.5	8.0
VOC of enamel (pounds per gallon)	--	3.5
Lead content, percent	--	0.06

3.6 Toxic ingredients. The manufacturer shall certify that the primer contains no hexavalent chromium (chromate), benzene (benzol), chlorinated solvents, or ethylene based glycol ethers and their acetates.

3.7 Material Safety Data Sheet. A Material Safety Data Sheet shall be included with each shipment of the material covered by this specification and submitted to pertinent Government agencies as stated in FED-STD-313, appendix B (see 6.7).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Sampling and inspection. Unless otherwise specified herein, sampling, inspection, and testing shall be in accordance with FED-STD-141, method 1022.

4.1.3 Material Safety Data Sheet. Material Safety Data Sheets not prepared in accordance with FED-STD-313 shall be cause for rejection.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. Quality conformance inspection (see 4.2.1).
b. Inspection of packaging (see 4.4).

4.2.1 Quality conformance inspection. Quality conformance inspection for individual lots shall be as follows: VOC, condition in container, hiding power, total solids, infrared reflectance, viscosity, fineness of grind, spraying properties, drying time, and specular gloss.

4.3 Test methods.

4.3.1 Test conditions. The testing conditions shall be in accordance with FED-STD-141, section 9 or in accordance with the appropriate ASTM method except as otherwise specified herein.

4.3.2 Tests. The following tests shall be conducted. The right is reserved to make any additional tests deemed necessary to determine that the paint meets the requirements of this specification. Failure of any test result to fall within the ranges specified shall constitute failure of the applicable test.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the currentversion before use.

TABLE III. Test and methods.

Test	Requirements paragraph	ASTM	FED-STD-141	Test paragraph
Enamel:				
Color	3.2	E 308	--	4.3.3
Condition in container	3.4.1	--	3011	4.3.10
Storage stability	3.4.2	--	3021, 3022	4.3.11
Dilution stability	3.4.3	--	4203	4.3.12
Brushing properties	3.4.4	--	4321	--
Spraying properties	3.4.5	--	4331	--
Recoatability	3.4.6	--	4061	--
Water resistance	3.4.7	D 1308	--	4.3.13
Hydrocarbon resistance	3.4.8	D 1308	--	4.3.14
Accelerated weathering	3.4.9	G 26	6352	4.3.15
Removability	3.4.10	--	--	4.3.19
Freeze conditions	3.4.11	--	--	4.3.18
Weather resistance	3.4.12	--	--	4.3.17
Photographic test	3.4.13	--	--	4.3.16
Total solids	Table II	D 2369	--	--
Pigment solids	Table II	D 2698	--	--
Vehicle solids	Table II	D 2698	6103	--
Specular gloss (85° & 60°)	Table II	--	6101	4.3.9
Dry opacity (hiding power)	Table II	--	4122	4.3.8
Fineness of grind	Table II	D 1210	--	--
Viscosity	Table II	D 562	--	--
Drying time	Table II	--	4061	--
Spectral reflectance	3.2, Table I	--	6241	4.3.7
VOC of enamel	Table II	D 3960	--	--
pH of enamel	Table II	E 70	--	--
Lead content	Table II	D 3335	--	--
Pigment:				
Prime pigment	3.3.1	--	--	4.3.4
Extender pigment	3.3.1	D 34	--	4.3.4
Particle size	3.3.1	--	--	4.3.6
Vehicle:				
Composition	3.3.2	D 2369	--	4.3.5

4.3.3 Color. The applied coating shall be tested for color in accordance with ASTM E 308, using standard illuminant C. For the color test, the average of the measurements from 3 samples shall be used, none of which shall deviate more than 2.5 CIELAB units from the center value and the average of which shall meet those requirements indicated in table I. Failure to conform to these shall constitute

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

failure of this test. For non-camouflage colors, prepare samples with a minimum dry film thickness of 2 mils. Nonconformance to 3.2 shall constitute failure of this test.

4.3.4 Pigment analysis. By the most suitable method, analyze the pigment composition. Extender pigments shall be tested in accordance with ASTM D 34. Nonconformance to 3.3.1 shall constitute failure of this test.

4.3.5 Non-volatile vehicle analysis. Extract the non-volatile vehicle by the following procedure:

a. Place 1-2 g of the coating into a 6 cm diameter aluminum weighing pan and dry the sample for several hours in a 105 °C oven.
b. Strip the film from the pan, place it in a 25 mL glass stopped flask, add 10 mL of ACS acetone, and agitate frequently over a period of 1 hour.
c. Transfer the sample to a 15 Ml centrifuge tube and centrifuge to remove the pigment.
d. Place the supernatant liquid into a 50 mL beaker and evaporate to dryness on a warm hot plate.
e. Redissolve the resin in 1-2 mL of ACS acetone and spread an even film of this solution on a salt plate.
f. Dry the plate in an 80 °C vacuum oven for 30 minutes and scan the infrared spectrum for 4000 to 650 cm^{-1}. The film thickness should be such that the carbonyl band at 1730 cm^{-1} shows a transmission of 10 to 20 percent.
g. The spectrum shall be consistent with material requirements specified in 3.3.2.

Nonconformance to 3.3.2 shall constitute failure of this test.

4.3.6 Prime pigment particle size. Using a portion of the prime pigment sample, determine the particle size of the prime pigment with a Fisher sub-sieve sizer. Nonconformance to 3.3.1 shall constitute failure of this test.

4.3.7 Spectral reflectance. The spectral reflectance of the coating shall be determined as follows.

4.3.7.1 Applied coating characteristics. Prepare specimens for the coating reflectance test on a black and white Morest chart. Apply the coating to a dry mil thickness that possesses 98 percent opacity with a Boston-Bradley or a doctor blade. Determine the spectral reflectance for the coating in all applicable regions of the spectrum using the spectrophotometer method in accordance with FED-STD-141, method 6241.

4.3.7.2 Spectrophotometer method. For method 6241, infrared reflectance values shall be obtained by averaging the reflectance percentage at the wavelength ordinates specified in table IV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

TABLE IV. Selected ordinates for determining infrared values from spectrophotometric curves.

Nanometers	
720.0	800.0
740.0	810.0
760.0	830.0
770.0	840.0
780.0	860.0

Nonconformance to 3.2 shall constitute failure of this test.

4.3.8 Hiding power (contrast ratio). Determine the hiding power (contrast ratio) in accordance with FED-STD-141, method 4122, using a film applicator which will deposit a 3-inch-wide film with a dry film thickness of 0.002 inch maximum. Air-dry for 24-hours, then determine the reflectance and verify the film thickness in the area which the reflectance was measured. Calculate the contrast ratio. Nonconformance to table II shall constitute failure of the test.

4.3.9 Specular gloss. Draw down the paint as in 4.3.7.1. Test as specified in FED-STD-141, methods 6103 and 6101. Nonconformance to table II shall constitute failure of this test.

4.3.10 Condition in container. Determine package condition of the paint in accordance with FED-STD-141, method 3011. Reseal and then agitate the can for 3 minutes on a paint shaker. Re-examine the contents. Evidence of any gel bodies or undispersed pigment or nonconformance to 3.4.1 shall constitute failure of this test.

4.3.11 Storage stability.

4.3.11.1 Partially full container. Determine skinning after 48 hours in accordance with FED-STD-141, method 3021, except use a 3/4-filled, 1/2 pint, multiple-friction top can. Reseal and store for 7 days at 140 °F. Nonconformance to 3.4.2.1 shall constitute failure of this test.

4.3.11.2 Full container. In accordance with FED-STD-141, method 3022, allow a full standard quart can of the paint to stand undisturbed for 1 year and then examine the contents. Evaluate pigment settling or caking, but agitate the can for 5 minutes on the paint shaker prior to re-examination. Nonconformance to 3.4.2.2 shall constitute failure of this test.

4.3.12 Dilution stability. Reduce 6 parts of paint as packaged with 1 part by volume of water. Then test in accordance with MIL-STD-141, method 4203. Nonconformance to 3.4.3 shall constitute failure of this test.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the currentversion before use.

4.3.13 Water resistance. Prepare by drawdown a 2 mil dry film of the paint as in method 4061 onto a pretreated aluminum panel previously painted with a suitable primer and a topcoat conforming to MIL-C-46168, color green 383. Air-dry the coating for 72 hours, then immerse in distilled water at 23 ±1 °C for 18 hours in accordance with ASTM D 1308. At the end of the test period, remove and examine. Nonconformance to 3.4.7 shall constitute failure of this test.

4.3.14 Hydrocarbon resistance. Prepare a film of the paint as in 4.3.13. Air-dry the panels for 72 hours at 23 ±1 °C, then immerse for 4 hours in a hydrocarbon fluid conforming to TT-S-735, type III in accordance with ASTM D 1308. At the end of the test period remove and examine. Nonconformance to 3.4.8 shall constitute failure of this test.

4.3.15 Accelerated weathering. Prepare a film of the paint as in 4.3.13 and air-dry for 72 hours. Expose the panel for 300 hours to accelerated weathering in accordance with ASTM G 26, method A, type BH. Examine the exposed panel for chalking. Nonconformance to 3.4.9 shall constitute failure of this test.

4.3.16 Photographic test. Panels shall be prepared as specified in 4.3.17. The panels shall be placed horizontally to the ground with standard calcium carbonate coated panels. The photographs shall be taken with the sun directly behind the photographer. The film shall be normal black and white film, but an ultraviolet filter will be placed over the lens. Nonconformance to 3.4.13 shall constitute failure of this test.

4.3.17 Weather resistance. Spray the paint to a dry film thickness of 2.0 mils or to complete hiding on three 4 x 12-inch steel panels previously coated as in 4.3.13. Air-dry for 72 hours, and place on outdoor exposure for 9 months at an angle of 45 degrees facing south in the climate of Washington, DC. The exposure time must include the months of November to March. Nonconformance to 3.4.12 shall constitute failure of this test.

4.3.18 Freeze conditions. Fill a screw-top jar of not less than 2-ounce capacity with the paint and place it in a cold-box chamber at 0 °F for 48 hours. After returning to room temperature, disperse, spray and brush the paint. Nonconformance to 3.4.11 shall constitute failure of this test.

4.3.19 Removability. Prepare and dry a panel as in 4.3.17. Brush on remover solution (see 6.5) or immerse in 5 percent ammonia-water solution. Rinse under running water with light scrubbing. Nonconformance to 3.4.10 shall constitute failure of this test.

4.4 Inspection of packaging. Packaging inspection shall be in accordance with the quality assurance provisions of PPP-P-1892 or ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation, packing and marking. Preservation, packing and marking shall be level A, B, C, or commercial as specified (see 6.2). Level A, B, and C requirements shall be in accordance with PPP-P-1892. Commercial requirements shall be in accordance with ASTM D 3951. The paint shall be preserved in quantities as specified (see 6.2).

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. This paint is a quick-drying, water dispersible acrylic type intended to be used as a removable camouflage coating for use over previously painted surfaces. The paint is a lusterless coating meeting reflectance requirements in the ultraviolet, visual and infrared regions as appropriate for the specified color.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of the specification.
b. Issue of DoDISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. Color of coating required (see 1.2.1).
d. Degree of preservation and degree of packing required (see 5.1).
e. Size of container required (see 5.1).

6.3 Basis of purchase. The coating covered by this specification should be purchased by volume, the unit being 1 U.S. gallon of 231 cubic inches at 68 °F (20 °C).

6.4 Sample formula. The white coating procured under this specification is contemplated to be comparable in performance for the color spectral and physical requirements to the following formulation. However, the Government assumes no responsibility for the acceptance of a product to be manufactured under an identical formulation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

Constituents		Percentages
Acrylic resin solutions 1/		38.12
Zirconium oxide 2/ and/or antimony oxide 3/		25.41
Natural ground $CaCO_3$ 4/		4.57
Synthetic $CaCO_3$ 5/		2.29
Water		19.31
Methyl isobutyl ketone		9.53
Suspension agent		0.76
Ammonium hydroxide	Adjust pH to	8.00

1/ Carboset 514H - B.F. Goodrich Corporation
2/ ZS-2 Grade - Magnesium Elektron, Inc.
3/ KR Grade - Harshaw Chemical Corp.
4/ Chem Carb 11 - Engelhard
5/ Multifex MM - Diamond Shamrock

6.5 Remover. The solution below, or similar, when applied to the coating described within this specification, will remove it without affecting the base coat. A commercial product is manufactured by McGean-Rochco under the name CEE BEE A-276.

Constituents	Percentages
5% Ammonium hydroxide solution	90%
2% Methocel solution	10%

6.6 Dry film thickness. The paint must be applied with at least two coats at a total dry film thickness of not less than 2 mils.

6.7 Material Safety Data Sheets. Contracting officers should identify those activities requiring copies of completed Material Safety Data Sheets prepared in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in FED-STD-313, appendix B.

6.8 Color chips. Tan 686A color chips are available from: US ARMY RSRCH LAB, ATTN AMSRL MA E, FT BELVOIR VA 22060-5818. All other color chips may be obtained by color number from the GENERAL SERVICES ADMN, SPCFCTN SECT, 7TH & D STRETS SW, WASHINGTON DC 20407.

6.9 Subject term (key word) listing.

Removable
VOC compliant

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the current version before use.

6.10 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - ME
Navy - AS

Review activity:
Army - MR

Preparing activity:
Army - ME

Project 8010-A373

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-P-52905A	2. DOCUMENT DATE (YYMMDD) 940131

3. DOCUMENT TITLE
PAINT, CAMOUFLAGE, REMOVABLE

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (if applicable) (2) DSN	7. DATE SUBMITTED

8. PREPARING ACTIVITY

a. NAME Carolyn B. Johnson	b. TELEPHONE (Include Area Code) (1) Commercial (703) 704-3468	(2) DSN 654-3468
c. ADDRESS (Include Zip Code) US ARMY BELVOIR RDE CTR ATTN SATBE TSE 10101 GRIDLEY RD STE 104 FT BELVOIR VA 22060-5818	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: DEFNS QLTY & STDZN OFC 5203 LEESBURG PIKE STE 1403 FLS CHURCH VA 22041-3466 Telephone (703) 756-2340 DSN 289-2340	

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:11Z
Check the source to verify that this is the current version before use.