MILITARY SPECIFICATION

SHIPPING AND STORAGE CONTAINER, ROCKET: XM626

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification establishes the requirements for the manufacture and acceptance of the fully reusable Fiberglass Reinforced Plastic (FRP) Shipping and Storage Container, Rocket: XM626, for M130, high explosive, 345mm rockets and M131, 345mm, training rockets.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-P-514	- Plates, Identification, Instruction and Marking, Blank.
MIL-T-704	- Treatment and Painting of Materiel.
MIL-W-21157	- Weldment, Steel, Carbon and Low Alloy (Yield Strength 30,000-60,000 psi).
MIL-R-21607	- Resin, Polyester Low Pressure Laminating, Fire Retardant.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: USA Belvoir Research and Development Center, ATTN: STRBE-DS, Fort Belvoir, VA 22060-5606 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8140

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

STANDARDS

FED-STD-101	- Test Procedures for Packaging Materials.

MILITARY

MIL-STD-105	- Sample Procedure and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-130	- Identification and Marking of US Military Property.
MIL-STD-248	- Welding and Brazing Procedure and Performance Qualifications.
MIL-STD-648	- Design Criteria for Specialized Shipping Containers.
MIL-STD-889	- Dissimilar Metals.

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein.

DRAWINGS

TA13226E5600	- Shipping and Storage Container, Rocket: XM626.

(Copies of specifications, standards, and drawings required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 256 -	Impact Resistance of Plastics and Electrical Insulating Materials.
ASTM D 638 -	Tensile Properties of Plastics.
ASTM D 790 -	Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials.
ASTM D 2583 -	Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:12Z
Check the source to verify that this is the current version before use.

AMERICAN WELDING SOCIETY

AWS A5.2 - Specification for Iron & Steel Gas Welding Rods.

(Application for copies should be addressed to the American Welding Society, 345 East 47th Street, New York, NY 10017.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Description. The Shipping and Storage Container, Rocket: XM626 (hereafter called container) shall be in accordance with TA13226E5600 and as specified herein. This fully reusable container shall handle, ship, store, and protect the M130 and M131 rockets throughout the logistic cycle. This unsealed container is comprised of upper and lower FRP shells. Five rockets are held in place by polyethelene foam which is bonded to each shell. The upper shell is held to the lower shell by eight overcenter fasteners. Each fastener strike is attached to a steel band which terminates on the opposite side of the upper shell and forms the opposite side fastener strike. Upper shell alignment to the lower shell is controlled by steel alignment pins.

3.1.1 Drawings. The drawings forming a part of this specification are end product drawings. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer. Where tolerances could cumulatively result in incorrect fits, the contractor shall provide tolerances within those prescribed on the drawings to insure correct fit, assembly and stacking of the containers. Any data (e.g., shop drawings, layouts, flow sheets, processing procedures, etc.) prepared by the contractor or obtained from a vendor to support fabrication and manufacture of the production item shall be made available, upon request, for inspection by the contracting officer or his designated representative.

3.1.2 Container fabrication. The container shall be fabricated by either the handlay, resin transfer or match metal mold processes.

3.2 First articles.

3.2.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 4.3 and 6.3).

3.2.2 Material samples. In addition to the first article models, samples (12 x 12 x .25) of molded sections of material as used in the fabrication shall be furnished and tested by the supplier prior to the time the first article

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:12Z
Check the source to verify that this is the current version before use.

model is furnished. Tests shall be those specified in section 4. The selection of samples and the tests shall be monitored by the Defense Contract Administration Services Office.

3.3 Material. Material shall be as specified on the drawings and herein.

3.3.1 Fiberglass reinforced plastic (FRP). The FRP shall be a 35 percent fiberglass reinforcement. The resin shall be in accordance with MIL-R-21607, grade 2, class A. The following properties shall be exhibited:

Tensile Strength 18,000-20,000 psi
Flexural Strength (Dry) 30,000-32,000 psi
Hardness, Barcol Units 50 to 60 scale
Impact Strength (IZOD) 23-25 ft. lb/in.

3.3.2 Metal parts. The procedures and fabrication specification to be used in the manufacture of the metal parts for this container are specified on the appropriate drawings. Welding specifications for steel weldments, carbon and low alloy, weld in accordance with MIL-W-21157, class 5 using with process shield metal arc wire AWS A5.2, class RG 60. Positional qualification of welders shall be in accordance with MIL-STD-248.

3.3.2.1 Material deterioration and control. Metal parts shall be fabricated from compatible materials, inherently corrosion resistant or treated to provide protection against the various forms of corrosion and deterioration that may be encountered in any of the applicable operation and storage environment to which the item may be exposed.

3.3.2.2 Dissimilar metals. Dissimilar metals shall not be used in intimate contact with each other unless protected against galvanic corrosion. Dissimilar metals and methods of protection are defined and detailed in MIL-STD-889.

3.3.2.3 Identification of materials and finishes. The contractor shall identify the specific material, material finish or treatment for use with components and sub-components, and shall make information available upon request to the contracting officer or designated representative.

3.3.3 Finish and color. Clean all exterior surfaces with a suitable mold release solvent. Remove gloss by sanding as required. Apply paint in accordance with MIL-T-704, type G; except the epoxy primer is not required.

3.4 Interface. The lower body assembly and the cover assembly of the container shall mate over the guide pins provided and all latches shall operate, without application of any mechanical force beyond normal body pressure when tested as specified in 4.6.4.

3.4.1 Interchangeability. Each cover assembly shall be interchangeable with any container body when tested as specified in 4.6.4.

3.5 Cover removal. The force necessary to remove the cover shall not be more than the weight of the cover plus 40 pounds, when tested as specified in 4.6.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

3.6 Handles. Container covers shall be provided with four handles for use in removing the cover. Each handle shall be capable of supporting the total container cover when tested as specified in 4.6.6

3.7 Transportation shock and vibration. The containers ordered under this specification shall provide protection to the contents from damage resulting from exposure to the applicable shock or vibration as specified herein.

3.7.1 Repetitive shock (vibration). Containers shall not exhibit any of the appropriate damage criteria of 5.2.1.1 of MIL-STD-648 after being subject to the subjected repetitive shock test of 4.6.7.

3.7.2 Resonance strength and dwell. Containers shall not exhibit any of the appropriate damage criteria of 5.3.1.1 of MIL-STD-648 after being subjected to the resonance strength and dwell test of 4.6.8. In addition, peak transibility (as measured during the resonance search portion of the test) shall not exceed 5.0 if the resonant frequency is less than 15 Hz; 8.0 if the resonant frequency is between 15 Hz and 25 Hz; and 10.0 if from 25 Hz to 50 Hz.

3.7.3 Impact. Containers shall not exhibit any of the appropriate damage critera of 5.2.1.1 of MIL-STD-648 after being subjected to the impact test of 4.6.9 at ambient and extreme temperatures of 160° F ±5° F (71° C ±2.8° C) and -65° F ±5° F (-54° C ±2.8° C).

3.7.4 Cornerwise-drop (rotational). Containers shall not exhibit any of the appropriate damage criteria of 5.2.1.1 of MIL-STD-648 after being subjected to cornerwise-drop test of 4.6.10 at ambient and extreme temperatures of 160° F ±5° F (71° C ±2.8° C) and -65° F ± 5° F (-54° C ±2.8° C).

3.8 Lifting and tie-down fittings. Suitable lifting rings shall be located on the base of the container as specified on the drawings and each fitting shall be suitable for lifting two loaded containers stacked and bound together. The fittings shall pass the performance test as specified in 4.6.11.

3.9 Superimposed-load (stackability). Containers shall be suitable for stacking one upon the other in such a manner as not to interfere with forklift access. Each container shall be capable of supporting seven similarly loaded containers in a superimposed (i.e., stacked eight high) condition. Provisions shall be made for indexing and interlocking stacked containers to each other. Both lateral and longitudinal restraint shall be provided. Stacking provisions shall meet performance testing of 4.6.12.

3.10 Forklift truck compatibility. The container unit load shall be compatible for safe lifting, transporting, pushing and towing by forklift truck. Testing in accordance with 4.6.13 shall not cause failure or permanent deformation to the container so as to prevent continued transit in the logistic cycle.

3.11 Government-loaned property. Unless otherwise specified (see 6.2), the following property in the quantity indicated will be loaned by the Government (see 6.4):

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:12Z
Check the source to verify that this is the currentversion before use.

Description	Identification	Quantity
Rocket, Training 345 millimeter	M131	15

3.12 Identification markings.

3.12.1 Identification plate. The container shall be identified in accordance with MIL-STD-130 on identification plates furnished and permanently affixed by the contractor as specified on the drawings.

3.12.2 Instruction plates. Instruction plates shall be furnished and permanently affixed by the contractor as specified on the drawings.

3.13 Workmanship. The container including components, assemblies, and subassemblies shall be clean and free from dirt, burrs, sharp edges, cracks, breaks, dents, loose attaching parts, misalignment of parts, peeled or blistered painted surfaces, or any condition that would render the container unsuitable for the purpose intended. Exterior surface coatings shall be continuous except for slight scratches not exposing the base material.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Component and material inspection. The contractor is responsible for insuring that components and materials used are manufactured, examined, and tested in accordance with referenced specifications, standards and drawings, as applicable.

4.1.2 Parts and components. Parts and componets detailed on the drawings shall be inspected in accordance with the Quality Assurance Provisions (QAP's) shown on the drawings. The drawings specify the characteristics requiring QAP inspection, the sampling plan, and the basis for acceptance and rejection (see 6.5 and 6.6.2)

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).
c. Inspection of packaging (see 4.7).

Source: https://assist.dla.mil -- Downloaded: 202640-26T04:12Z
Check the source to verify that this is the currentversion before use.

4.3 First article inspection.

4.3.1 Examination. The first article container shall be examined as specified in 4.5.1. Presence of one or more defects shall be cause for rejection.

4.3.2 Material acceptance. Samples of molded section of material as used in this contract shall be tested as specified in 4.6.3 to assure that the physical and mechanical property requirements of 3.3.1 are met (see 3.2.2). Failure of any test shall be cause for rejection.

4.3.3 Tests. The first article container shall be subjected to the tests marked "X" in column 2 of table II. Failure of any test shall be cause for rejection.

4.4 Quality conformance inspection.

4.4.1 Sampling. Sampling for examination and tests shall be in accordance with MIL-STD-105.

4.4.2 Examination. Samples selected in accordance with 4.4.1 shall be examined for characteristics specified in 4.5.1. AQL shall be 1.0 percent defective for major characteristics and 4.0 percent defective for minor characteristics.

4.4.3 Tests.

4.4.3.1 Individual. Each container shall be subjected to the tests marked "X" in column 3 of table II, and in the order shown. Failure of any test shall be cause for rejection.

4.4.3.2 Samples. Samples selected in accordance with 4.4.1 shall be subjected to the tests marked "X" in column 4 of table II, and in the order shown. AQL shall be 2.5 percent defective.

4.5 Inspection schedule.

4.5.1 Examination. The container shall be examined as specified herein for the defects listed in table I.

TABLE I. Examination schedule.

Number	Characteristic	Requirement Paragraph
Major		
101.	Dimensions that affect form, fit, or function not as shown on the drawings.	3.1.1
102.	Material not as specified.	3.3

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

TABLE I. Examination schedule. (Cont'd)

Number	Characteristic	Requirement Paragraph
103.	The metal parts are not resistant to corrosion and deterioration nor treated to be made resistant to corrosion and deterioration for applicable storage and operating environment.	3.3.2.1
104.	Dissimilar metals as defined in MIL-STD-889 are not effectively insulated from each other.	3.3.2.2
105.	The contractor does not have documentation available for identification of material, material finishes or treatments.	3.3.2.3
Minor		
201.	Treatment and painting not as specified.	3.3.3
202.	Identification marking not as specified.	3.12
203.	Workmanship not as specified.	3.3.2 & 3.13

4.6 Tests.

4.6.1 Test schedule.

TABLE II. Test schedule.

Order	First article	Quality Conformance		Test	Test paragraph	Requirement paragraph
		Individual	Sample			
1	2	3	4	5	6	7
1	X	-	-	FRP	4.6.3	3.3.1
2	X	X	-	Interface.	4.6.4	3.4
3	X	-	X	Interchangeability.	4.6.4	3.4.1
4	X	-	-	Cover removal.	4.6.5	3.5
5	X	-	-	Handles.	4.6.6	3.6
6	X	-	-	Repetitive shock (vibration).	4.6.7	3.7.1
7	X	-	-	Resonance strength and dwell.	4.6.8	3.7.2
8/10*	X	-	-	Single container impact.	4.6.9	3.7.3
12	X	-	-	UL impact.	4.6.9	3.7.3
13	X	-	-	Single container cornerwise Drop (rotational).	4.6.10	3.7.4
9/11*	X	-	-	UL cornerwise-drop (rotational).	4.6.10	3.7.4

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

TABLE II. Test schedule. (Cont'd)

Order	First article	Quality Conformance		Test	Test paragraph	Requirement paragraph
		Individual	Sample			
1	2	3	4	5	6	7
14	X	-	-	Lifting and tiedown.	4.6.11	3.8
15	X	-	X	Superimposed-load (stackability).	4.6.12	3.9
16	X	-	-	Forklift truck compatibility.	4.6.13	3.10

* 8/10 Hot/cold.
* 9/11 Hot/cold.

4.6.2 Test conditions. Unless otherwise specified in a test, tests shall be performed at the climatic conditions existing at the place of test. When required, the container shall be loaded with five Government loaned M131 training rockets. Any test failure attributable to Government furnished equipment shall not constitute a failure of any test specified herein.

4.6.3 FRP test. Material samples shall be tested in accordance with the following:

Tensile Test ASTM D638.
Flexural Test ASTM D790.
Hardness Test ASTM D2583.
Impact Strength Test ASTM D256.

Nonconformance to 3.3.1 shall constitute failure of test.

4.6.4 Interface and interchangeability. Assemble the container by placing the cover on the lower body assembly. The alignment pins on the lower body assembly must mate with the corresponding holes on the cover. All covers shall be interchanged with all lower bodies. Latching devices must be secured without the use of tools or excessive body pressure. Nonconformance with 3.4 and 3.4.1 shall constitute failure of this test.

4.6.5 Cover removal. Release the cover assembly latches. Attach a weight-equalizing sling to the cover assembly. Attach a tension scale or dynameter to the sling and lift the cover assembly and clear the cover assembly guide pins on the container. Observe the lifting force necessary on the scale and subtract the weight of the cover assembly, spreader bars and sling. Nonconformance to 3.5 shall be cause for rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

4.6.6 Handles test. Each handle shall be capable of supporting the total container cover load for a total of five minutes when cover is lifted by an overhead hoist from an individual handle. Nonconformance to 3.6, breakage, permanent deformation of the fittings or structure adjacent thereto, or loosening of attachment shall be cause for rejection.

4.6.7 Repetitive shock (vibration) test. This test shall be conducted using a stack of four containers (two unit loads) in accordance with MIL-STD-648, 5.2.2. Nonconformance to 3.7.1 shall be cause for rejection.

4.6.8 Resonance strength and dwell test. This test shall be conducted in accordance with MIL-STD-648, 5.3.2 except UL configuration shall be tested instead of a single container. Nonconformance with 3.7.2 shall be cause for rejection.

4.6.9 Impact test. This test shall be conducted for single loaded container and unit load containers in accordance with either the procedures of method 5023 (Incline-Impact Test) or method 5012 (Pendulum-Impact Test) of FED-STD-101. Impact velocity shall be 7 ft./sec. (2.13 in./sec.) on all sides of the container. Nonconformance with 3.7.3 shall be cause for rejection.

4.6.9.1 Single container impact. The single container test loaded with five M131 training rockets shall be conducted at extreme temperatures of 160° F ±5° F (71° C ±2.8° C) and -65° F ±5° F (-54° C ±2.8° C).

4.6.9.2 Unit load impact. The unit load test shall be conducted at ambient temperature and optional timber shall be used.

4.6.10 Cornerwise-drop (rotational). This test shall be conducted for single loaded container and unit loaded containers in accordance with method 5005 of FED-STD-101. Nonconformance with 3.7.4 shall be cause for rejection.

4.6.10.1 Single container cornerwise-drop. The single container test loaded with five M131 training rockets shall be conducted at ambient temperature.

4.6.10.2 Unit load cornerwise-drop. The unit load test shall be conducted at extreme temperatures of 160° F ±5° F (71° C ±2.8° C) and -65° F ±5° F (-54° C ±2.8° C).

4.6.11 Lifting and tie-down test. The hoisting fittings shall individually lift the gross weight of two loaded containers banded together by single suspension and maintain the lift for not less than 1 hour. Each fitting shall be so tested. In additon, the set of hoisting fittings shall withstand a loading of five times the gross weight of the loaded containers when tested with a sling. The duration of the test shall be at least 1 hour. Breakage, permanent deformation of the fittings or structure adjacent thereto, or loosening of attachment is nonconformance to 3.8 and shall constitute failure of this test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

4.6.12 Superimposed-load (stackability). Proof of adequate stacking strength shall be determined by testing in accordance with the procedure of method 5016 of FED-STD-101 except the constant "S" of method 5016 used to calculate the load shall be 1.0. Any breakage or deformation sufficient to result in any unsafe stacking configuration or condition or nonconformance to 3.9 shall be cause for rejection.

4.6.13 Forklift truck compatibility. This test shall be conducted in accordance with MIL-STD-648, 5.9. Unit load configuration shall be used. Nonconformance to 3.10 shall be cause for rejection.

4.7 Inspection of packaging. Each container shall be examined for closure, latching, and marking as specified in section 5. Noncompliance with any requirement shall be cause for rejection.

5. PACKAGING

5.1 Preservation and packaging. Each container, with the two halves closed together and secured with the latches as intended, shall be packed or unitized in a manner which will assure carrier acceptance and delivery to the destination without damage at the lowest rates (see 6.8).

5.2 Marking. Each container shall be marked for shipment in accordance with MIL-STD-129 (see 6.8).

6. NOTES

6.1 Intended use. The containers are intended for use as domestic and overseas shipping and storage containers for M130 and M131 rockets.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of the specification.
b. Timeframe required for submission of first article model and number of containers required (see 3.2.1 and 3.2.2).
c. When Government-loaned property is not required (see 3.11).

6.3 First article. When a first article inspection is required, the items should be initial production units. The first article should consist of four units. The contracting officer should include specific instructions in acquisition documents regarding arragnements for examinations, tests and approval of the first article test results and disposition of the document's first articles.

6.4 Government-loaned property. The contracting officer should arrange to furnish the property as specified in 3.11 when applicable (see 6.2).

6.5 Quality assurance provisions (QAP). The contracting officer should require the contractor to maintain records of all QAP inspections. A suggested paragraph is as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

"The contractor shall maintain complete records of all examinations and tests performed to verify the requirements of classified QAP characteristics. The records shall include as a minimum, lot size, sample size, drawing requirements, actual measurements, number and type of deficiencies found, quantity approved, quantity rejected, and corrective action taken when applicable."

6.6 Definitions.

6.6.1 Unit load definition. Two loaded containers stacked one on the other and banded together constitute a unit load (UL). It is the principal shipping and storage condition of the XM-626 container.

6.6.2 Quality assurance provisions (QAP). A QAP is a contractual requirement that supplements section 4 of the specification. A QAP indicates the minimum requirements which must be inspected on the product drawings to verify the design objectives of the product.

6.7 Recycled material. It is encouraged that recycled material be used, when practical, as long as it meets the requirements of this specification (see 3.3).

6.8 Packaging. Degrees of preservation and packing are not appropriate for this item as there is but one realistic way to package containers for shipment from the supplier to the point where rockets will be loaded into them. For purposes of preservation and packing level marking, the container shall be marked A/A.

Custodian:
Army - ME

Review activity:
Army - AL

Preparing activity:
Army - ME

Project 8140-A633

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
USA Belvoir R&D Center
STRBE-DS
Fort Belvoir, VA 22060-5606

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
'FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
USA Belvoir R&D Center
STRBE-DS
Fort Belvoir, VA 22060-5606

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-53041(ME)	Shipping and Storage Container, Rocket: XM626

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:12Z
Check the source to verify that this is the current version before use.