MILITARY SPECIFICATION

TANK, FABRIC, COLLAPSIBLE, PILLOW

TYPE (FOR POTABLE WATER)

This specification is approved for use by the Mobility Equipment Research and Development Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers collapsible, pillow type, synthetic rubber impregnated nylon fabric tanks for storing potable water.

1.2 Classification. The tanks shall be of the following sizes, as specified (see 6.2):

500 - gallon
1500 - gallon
3000 - gallon

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

L-P-378 - Plastic Sheet and Strip, Thin Gauge, Polyolefin.

FSC 5430

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Mobility Equipment Research and Development Command, ATTN: DRDME-DS Fort Belvoir, VA 22060 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the current version before use.

QQ-S-781	- Strapping, Steel, and Seals.
PPP-B-601	- Boxes, Wood, Cleated-Plywood.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-T-60	- Tape: Packaging, Waterproof.
PPP-T-97	- Tape, Pressure-Sensitive Adhesive, Filament Reinforced.

MILITARY

MIL-A-8625	- Anodic Coatings, For Aluminum and Aluminum Alloys.
MIL-R-22368	- Repair Kit and Repair Kit Components, For Collapsible Fabric Tanks and Boats.

STANDARDS

FEDERAL

FED. STD. No. 191	- Textile Test Methods.
FED. STD. No. 601	- Rubber: Sampling, and Testing.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables For Inspection By Attributes.
MIL-STD-129	- Marking For Shipment and Storage.
MIL-STD-130	- Identification Marking of US Military Property.

DRAWINGS

ME

TA13222E3564	- Tank, Fabric, Collapsible, Pillow Type (For Potable Water), 500 Gallon Capacity.
TA13222E3565	- Tank, Fabric, Collapsible, Pillow Type (For Potable Water), 1500 Gallon Capacity.
TA13222E3566	- Tank, Fabric, Collapsible, Pillow Type (For Potable Water), 3000 Gallon Capacity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN PUBLIC HEALTH ASSOCIATION, INC.

Standard Methods For The Examination Of Water And Wastewater.

(Application for copies should be addressed to the American Public Health Association, Inc., 1740 Broadway, New York, NY 10019.)

CODE OF FEDERAL REGULATIONS

21 CFR 121.2562 - Rubber Articles Intended For Repeated Use.

(Application for copies should be addressed to the Superintendent of Documents, Government Printing Office, Washington, DC 20402.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

B 26 - Aluminum-Alloy Sand Castings.
B 85 - Aluminum-Alloy Die Castings.
B 209 - Aluminum-Alloy Sheet and Plate.
D 412 - Tension Testing Of Vulcanized Rubber.
D 413 - Adhesion Of Vulcanized Rubber (Friction Test).
D 573 - Accelerated Aging Of Vulcanized Rubber By The Oven Method.
D 751 - Testing Coated Fabrics.
D 2000 - Classification System For Elastomeric Materials For Automotive Applications.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the Uniform Classification Committee, ATTN: Tariff Publishing Officer, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification.

(Application for copies should be addressed to the American Trucking Associations, Inc., ATTN: Traffic Department, 1616 P Street NW, Washington, DC 20036.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Description. Tanks shall be in accordance with TA13222E3564 for the 500-gallon tanks, TA13222E3565 for the 1500-gallon tanks, and TA13222E3566 for the 3000-gallon tanks, and as specified herein.

3.1.1 Drawings. The drawings forming a part of this specification are end product drawings. No deviation from the prescribed dimensions or tolerances is permissible without prior approval of the contracting officer. Where tolerances could cumulatively result in incorrect fits, the contractor shall provide tolerances within those prescribed on the drawings to insure correct fit, assembly, and operation of the tanks. Any data (e.g., shop drawings, layouts, flow sheets, processing procedures, etc.) prepared by the contractor or obtained from a vendor to support fabrication and manufacture of the production item shall be made available, upon request, for inspection by the contracting officer or his designated representative.

3.2 First article (preproduction model). The contractor shall furnish one or more tanks as specified (see 6.2), for examination and testing within the time frame specified (see 6.2), to prove prior to starting production that his production methods will produce tanks that comply with the requirements of this specification. Examination and tests shall be as specified in Section 4 and shall be subject to surveillance and approval by the Government (see 6.3).

3.3 Material. Material shall be as specified herein and as shown on the applicable drawings. Materials not specified shall be selected by the contractor and shall be subject to all provisions of this specification (see 6.5). The finished fabric tank shall contain no materials or substances which might leach out or disintegrate and cause the water to be nonpotable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to this effect shall be referred by the procuring activity to the appropriate departmental medical service who will act as an advisor to the procuring agency. Materials shall be listed in the Code of Federal Regulations 21 CFR 121.2562 as acceptable for food contact.

3.3.1 Aluminum plate. Aluminum plate shall conform to ASTM B 209, Alloy 6061 Temper T6 or ASTM B 209, Alloy 2024, Temper T3 or T4.

3.3.2 Aluminum-alloy castings. Aluminum sand castings shall conform to ASTM B 26, Alloy 356.0 Temper T6 or ASTM B 85, Alloy 360.0 for die castings.

3.4 Tank body construction. The tank body shall be fabricated of a single ply of the nylon cloth impregnated and coated on both sides with the synthetic rubber compound. Seams may be either the lap or butt type. Curing shall be accomplished in a suitable steam or air autoclave. Adhesion of seams and cemented areas shall be not less than 12 pounds per inch of width. Seam areas shall not slip or fail while supporting a load of 40 pounds per inch (pi) at a temperature of 158° Fahrenheit (F) $\pm$ 3° F.

3.4.1 Nylon cloth. Nylon cloth for the tank body shall be low twist, square woven, or 2 x 2 basket weave, high tenacity, heat set and shrunk, and shall have a weight of not less than 8 ounces per square yard. The nylon cloth shall be free from defects that interfere with coating, such as bagginess or uneven warp tension, tight or drawn selvage, and defects that reduce the breaking strength or hydrostatic resistance of the impregnated fabric, such as smashes, oil spots, gouts, kinky filling, floats, shuttle marks, two continuous threads missing, soiling, or tear in selvage. All such defects shall be corrected, cut out, or marked for future elimination. When material is to be eliminated after impregnation and coating, marking shall be such that it shall be visible in the impregnated cloth.

3.4.2 Synthetic rubber compound. The compound for impregnating and coating the nylon cloth, for the molded fittings, and for gum strips, sheets, and reinforcements shall meet the requirements specified herein. The compound used on the inner surface of the tank and on parts in contact with the potable water shall meet the requirements of ASTM D 2000, Compositions 2AA 615 F17 or 2BA 615 F17 or 5BC 615 F17 and the potability requirements of 3.3 herein. The compounds shall not impart toxic or disagreeable tastes or oders to water stored in the tank to the extent that the water is unsuitable for human consumption. Water absorption and water extractable ingredients shall be held to a minimum. The tensile strength of the cured compound shall be not less than 1500 psi, and the ultimate elongation shall be not less than 275 percent. When subjected to accelerated weathering and aging

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

tests, the cured rubber compound shall retain not less than 75 percent of the original tensile strength and not less than 65 percent of the original ultimate elongation.

3.4.3 Impregnated tank fabric. The impregnated fabric shall be constructed by calendar coating both surfaces of the nylon cloth with the synthetic rubber compound. The surface facing the inside of the tank shall be impregnated with a total thickness of not less than 0.018 inch, and the opposite (exterior) surface shall have one coat of a thickness not less than 0.012 inch. The combined total thickness of the impregnated and coated fabric shall be not less than 0.038 inch. Adhesion of the coatings, and of the coating to the cloth, shall be not less than 12 pounds per inch of width. Breaking strength of the cured impregnated fabric shall be not less than 400 pounds per inch of width. Tear strength shall be not less than 30 pounds per inch of width in both the warp and fill direction. All cut edges shall be sealed with strips or sheets or with rubber cement.

3.4.4 Cement. The synthetic rubber cement used in fabrication of the tank shall be compatible with the rubber compound and shall be a vulcanizing type.

3.4.5 Molded fittings. Molded synthetic rubberized fabric flange fittings shall be as shown on the applicable drawings, installed before the tank is cured, and in such a manner as to prevent leakage between the tank wall and the fittings. Fittings containing gum voids, cracks, or tears shall not be used. Molded fittings shall not be adversely affected by the additional cure necessary when they are vulcanized with the tank body. Repaired fittings shall meet the requirements of a new fitting.

3.4.6 Repairs. Damage occurring before curing shall be repaired before curing. The hotpatch method shall be used to repair damages after curing. Patches shall have an adhesion not less than that specified in 3.4.3 for the synthetic rubber compound. Not more than eight repairs will be permitted in each tank body and each ground cloth, and only minor damages, such as cuts or bruises having a longest dimension not greater than 6 inches, or a seam separation not longer than 12 inches may be patched. Repairs shall restore the full strength of the impregnated fabric, or the seam, as applicable, and the tank shall not leak.

3.5 Fitting assemblies. The components, dimensions, and details of the filler and discharge assemblies, the overflow pipe assembly, shall be as shown on the applicable drawings. Antiseize compound shall be used on all threaded surfaces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

3.6 Ground cloth. When specified (see 6.2), a ground cloth shall be furnished. The ground cloth shall be fabricated of a single ply of square woven nylon cloth weighing not less than 4.5 ounces per square yard impregnated on both sides with the synthetic rubber compound as specified in 3.4.2. The impregnated fabric shall weigh not less than 28 ounces per square yard. The finished ground cloth shall be sized as follows:

(a) 9 feet x 9 feet ± 3 inches on edge for the 500-gallon tank.
(b) 13 feet x 13 feet ± 3 inches on edge for the 1500-gallon tank.
(c) 15 feet x 15 feet ± 3 inches on edge for the 3000-gallon tank.

All cut edges and stitching shall be sealed with strips or sheets or with rubber cement.

3.7 Performance.

3.7.1 Leakage. Tank and fittings shall not leak when the tank is filled with water to 110 percent of capacity, or when the tank is subjected to 1 psi internal air pressure. The filler, overflow, and discharge assemblies shall not leak or rupture when subjected to a hydrostatic pressure of 15 psi. The pressure relief cap shall open to relieve excess pressure and protect the tank from rupture at 1.5 psi.

3.7.2 Mildew resistance. The impregnated fabric of the tank body, after exposure to soil burial for 1 month, shall have a retained breaking strength of not less than 200 pounds per inch of width.

3.7.3 Temperature range. The tank shall be suitable for storage in a temperature range from -40° F to +160° F. The tank body material shall not flake or crack in an ambient temperature of -40° F and shall develop no damage or abnormal tackiness in an ambient temperature of +160° F.

3.8 Emergency repair assembly. One emergency repair assembly, consisting of one each of three sizes of clamping devices as shown in Figure 1 of MIL-R-22368 shall be furnished with each tank.

3.9 Vulcanizing repair items. When specified (see 6.2), the vulcanizing repair items shown in Table I shall be furnished with each tank.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the currentversion before use.

TABLE I. Vulcanizing Repair Items

Item	Description	Quantity
Patching, 12 by 48 inches	Cured impregnated fabric conforming to 3.4.3, buffed one side	1 piece
Sealing strip, 1 by 144 inches	Cured gum strip conforming to 3.4.2, buffed one side	1 strip
Cement	Room temperature curing	4-1/2-pint cans
Instructions	(In waterproof package)	1 copy

3.10 Color. Unless otherwise specified (see 6.2), color of the exterior surfaces of the tank shall be lusterless green. The color may be integral with the rubber compound, or may be obtained by painting with a suitable ozone resistant synthetic rubber base paint of the correct color. Dry film thickness of the paint coating shall be not less than 1 mil.

3.11. Metallic component finish. Unless otherwise specified (see 6.2), all exterior aluminum parts shall have a dyed, anodized coating conforming to MIL-A-8625, Type I. The color shall be lusterless green or buff to correspond with tank color.

3.12 Cleaning. The interior surface of the tank shall be free of dirt, talc, separation sheet, excess material used in construction of tank, and other foreign material. The interior of the tank shall be flushed out using a mild detergent solution followed by a final flushing with potable water, then drained and air dried.

3.13 Interchangeability. All fittings of a given size and shape shall be completely interchangeable with like fittings with respect to installation and performance.

3.14 Markings. Identification and information markings shall be on labels vulcanized to the tank during the fabrication curing process. Letters shall be 1/2 inch high, indented. When ground cloth is furnished, identification markings shall be stenciled on the ground cloth in letters not less than 3/4 inch in height, so as to be visible when the tank is rolled in the ground cloth for shipment or storage. Identification markings shall be in accordance with MIL-STD-130. Information markings shall be provided at each tank opening and on each corresponding assembly fitting.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

3.15 Workmanship. Workmanship on the tank shall be of the highest quality and shall not permit air cells, bruises, or abrasions, poor adhesion, buckling, heater damage, bleeding, uneven coating, or similar defects adversely affecting strength, tightness, or serviceability. Boltholes shall be accurately punched or drilled and shall have the burrs removed. Metal used in the fabrication shall be free from sharp edges and projections which could damage the fabric. Shearing and chipping shall be done neatly and accurately.

3.15.1 Machine work. Tolerances and gages for metal fits shall conform to the limitations specified herein and on the drawings, and otherwise to the standards of good commercial practice.

3.15.2 Castings. Castings shall be sound and free from patching, blowholes, porosity, hard spots, misplaced coring, warping, or other defects which might render the casting unsound for use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to the prescribed requirements.

4.2 Preproduction inspection.

4.2.1 Examination. Each tank shall be examined for compliance with the requirements of Section 3 of this specification. Examinations shall be conducted as specified in Table II. Noncompliance with any specified requirement or presence of one or more defects shall constitute cause for rejection.

TABLE II. List of Defects

Paragraph Number	Category
3.1	Tank not fabricated as specified. Dimensions not as specified on the applicable drawings.
3.3 through 3.3.2	Materials not as specified and obviously damaged or defective, affecting serviceability and reliability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

TABLE II. List of Defects (Cont'd)

3.4 through 3.4.2	Tank body construction not as specified.
3.4.3	Impregnated fabric not constructed as specified.
3.4.4	Cement not as specified.
3.4.5	Molded fittings not as shown on applicable drawings.
3.4.6	Repairs not as specified, presence of more than eight patches on tank body and each ground cloth.
3.5	Dimensions and details of fitting assemblies not as shown on applicable drawings. Antiseize compound not used on threaded surfaces.
3.6	Ground cloth, when required, not as specified.
3.8	Emergency repair assembly not provided, incomplete or not as specified.
3.9	Vulcanizing repair items, when required, not as specified.
3.10 and 3.11	Color of exterior tank surfaces and metallic parts not as specified.
3.12	Tank interior not cleaned as specified.
3.13	Fittings of a given size and shape not interchangeable as specified.
3.14	Identification and information marking missing, incorrect, illegible, or otherwise not as specified.
3.15	Workmanship not as specified. Presence of defects adversely affecting strength, tightness or serviceability. Boltholes rough and burred; bolts missing or not type or size specified. Metal components not free from sharp edges and projections.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

TABLE II. List of Defects (Cont'd)

3.15.1	Tolerances and gages for metal fits not within the limitations specified.
3.15.2	Castings not as specified; evidence of blowholes, patches, porosity, fins, or other defects impairing the serviceability or reliability of the component part or assembly.

4.2.2 Tests. The preproduction tank shall be tested as specified in the test procedures of 4.3 and the tests of 4.4. Failure of any test shall be cause for rejection.

4.3 Test procedures.

4.3.1 First article. The first article shall be subjected to the tests specified in 4.4.2 through 4.4.15 to verify compliance with this specification. Failure to pass any phase of this inspection shall constitute cause for rejection.

4.3.2 Production Unit. Each production unit shall be subjected to the air leakage test specified in 4.5.1 to verify compliance with specified requirements and to assure presentation of usable items.

4.3.2.1 Production unit sampling procedure. Production unit sampling for test purposes shall be as specified herein. Failure to pass any phase of the designated tests shall constitute cause for rejection of the applicable production units.

4.3.2.1.1 Nylon cloth. A random sample of the nylon cloth used in the tank body fabric shall be selected from each 2000 linear yards or fraction thereof. Samples shall be at least 1-1/2 feet long and the full width of the roll.

4.3.2.1.2 Synthetic rubber compounds. One square foot of each impregnating compound used in the tank body shall be selected from each 2000 yards or fraction thereof. The sample shall be in sheet form not less than 0.012 inch thick and shall be cured simultaneously or identically with the tanks fabricated from the material represented by the sample.

4.3.2.1.3 Impregnated fabric. A random sample shall be selected from each 2000 linear yards or fraction thereof. The sample shall be not less

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

than 1-1/2 feet long and the full width of the fabric. The sample shall be cured simultaneously or identically with the tanks fabricated from the material represented by the sample.

4.3.2.1.4 Seams. Not less than two seam samples shall be furnished for each 10 tanks. Seam samples shall be the same as used in the tank and shall be fabricated and cured identically and simultaneously with the tank.

4.3.2.2 Tests for production unit samples. Samples selected in accordance with 4.3.2.1.1 through 4.3.2.1.4 shall be subjected to the applicable tests specified in 4.4.2 through 4.4.4 and 4.4.7 through 4.4.11 as indicated in Table III.

4.3.3 Test schedule. A test schedule for use in determining applicable test requirements is contained in Table III.

TABLE III. Test Schedule

Tests	First article (para. number)	Complete production unit (para. number)	Production samples (see 4.3.2.1) (para. number)
1	2	3	4
Complete tank assembly: Air leakage test (hydrostatic test in case of question)	-	4.4.1	-
Nylon cloth: Weight test	4.4.2	-	4.4.2
Synthetic rubber compound:			
Tensile strength test	4.4.3	-	4.4.3
Ultimate elongation test	4.4.4	-	4.4.4
Taste and odor test	4.4.5	-	-
Accelerated weathering test	4.4.6	-	-
Coated fabric:			
Thickness test	4.4.7	-	4.4.7
Adhesive test	4.4.8	-	4.4.8
Slippage test	4.4.9	-	4.4.9
Breaking strength test	4.4.10	-	4.4.10
Tear strength test	4.4.11	-	4.4.11
Mildew resistance test	4.4.12	-	-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

TABLE III. Test Schedule (Cont'd)

1	2	3	4
Tank:			
Temperature test	4.4.13	-	-
Water leakage test	4.4.14	-	-
Fittings:			
Hydrostatic test	4.4.15	-	-

4.4 Tests.

4.4.1 Air leakage. The tank shall be pressurized to a 1 psi internal air pressure and allowed to stand for 1 hour. At the end of this period, the internal air pressure shall be adjusted to 1 psi. All fittings and external seams shall be covered with soapsuds solution, and the tank shall be examined for leaks. Any evidence of leakage shall constitute failure of this test. In the event of a suspected leak that cannot be readily defined, place the tank on newsprint paper and fill with the rated capacity of water and check after 1 hour for wet spots.

4.4.2 Weight. Weight of the nylon cloth shall be determined in accordance with FED. STD. No. 191, Method 5040. Weights less than those specified in 3.4.1 shall constitute failure of this test.

4.4.3 Tensile strength. Tensile strength of the synthetic rubber compound shall be determined for conformance to 3.4.2 in accordance with ASTM D 412.

4.4.4 Ultimate elongation. The ultimate elongation of the synthetic rubber compound shall be determined for conformance to 3.4.2 in accordance with ASTM D 412.

4.4.5 Taste and odor. Samples of cured synthetic rubber compounds shall be immersed for 70 hours in distilled water having 0.2 parts per million of total available chlorine at the start of the 70-hour test. The samples shall be large enough to expose 36 square centimeters of compound to 1 liter of chlorinated distilled water. The water shall be tested for taste and odor in accordance wtih procedures outlined in APHA Standard Methods for the Examination of Water and Wastewater.

4.4.6 Accelerated weathering and aging.

4.4.6.1 Accelerated weathering of rubber compound. Accelerated weathering of the synthetic rubber compound shall be in accordance with FED. STD. No. 601, Method 7311, except that alternate filters shall be removed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

4.4.6.2 Accelerated aging of rubber compound. Accelerated aging of the synthetic rubber compound shall be in accordance with ASTM D 573.

4.4.7 Thickness. Minimum thickness of coatings and impregnated fabric shall be determined for conformance to 3.4.3 in accordance with FED. STD. No. 601, Method 2011.

4.4.8 Adhesion. Adhesion of seams, cemented areas, and coatings shall be determined for conformance to 3.4 and 3.4.3 in accordance with ASTM D 413 (MACHINE METHOD) and ASTM D 751 using a 1 inch wide sample and a rate of travel for the power grip of 2 inches per minutes. Break shall be away from the splice.

4.4.9 Slippage. The seam slippage shall be determined for conformance to 3.4 by suspending a 1 inch wide seam sample in an air circulating oven with a 40-pound deadweight hanging freely from the unattached end. The temperature of the oven shall be +158° F and the conditioning period shall be 22 hours.

4.4.10 Breaking strength. Breaking strength of the impregnated fabric shall be determined for conformance to 3.4.3 in accordance with the grab method specified in FED. STD. No. 191, Method 5100.

4.4.11 Tear strength. Tear strength of the impregnated fabric shall be determined for conformance to 3.4.3 in accordance with the tongue tear method specified in FED. STD. No. 191, Method 5134.

4.4.12 Mildew resistance. Mildew resistance of the impregnated fabric for the tank body shall be determined for conformance to 3.7.2 in accordance with FED. STD. No. 191, Method 5762, the specimen being buried horizontally for a period of 1 month. Method of determining breaking strength shall be as specified in 4.4.3.

4.4.13 Temperature. The tank shall be rolled up and placed in a dry temperature environment of +160° F for 24 hours. At the end of this period, the tank shall be removed from the environment and within 45 minutes unrolled and examined for evidence of tackiness or damage. The tank shall then be re-rolled and placed in a dry cold temperature environment of -40° F for 24 hours. The tank shall then be removed from the low temperature and unrolled within 45 minutes and examined for evidence of cracking, flaking, or other damage to the tank body.

4.4.14 Water leakage. After completion of the temperature tests, the tank shall be filled with 110 percent of capacity of clean potable water and shall remain filled for a period of 1 hour without evidence of leakage, rupture, or other damage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

4.4.15 Hydrostatic. The filler vent and discharge assemblies shall be subjected to an internal hydrostatic pressure of 15 psi. Evidence of rupture or leakage shall be cause for rejection.

4.5 Inspection of packaging.

4.5.1 Quality conformance inspection of pack.

4.5.1.1 Unit of product. For the purpose of inspection a completed pack prepared for shipment shall be considered a unit of product.

4.5.1.2 Sampling. Sampling for examination shall be in accordance with MIL-STD-105.

4.5.1.3 Examination. Samples selected in accordance with 4.5.1.2 shall be examined for the following defects. Acceptable quality level shall be 2.5 percent defective.

101.	Containers not as specified.
102.	Tank openings not closed for Level A.
103.	Attached fittings not protected as specified for Level A.
104.	Fiberboard boxes not closed as specified for Level A.
105.	Wood boxes not lined as specified for Level A or B.
106.	Strapping not as specified for Level A or B.
107.	Marking illegible, incorrect, or incomplete.

5. PACKAGING

5.1 Preservation. Preservation shall be Level A or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Tanks. All openings into the tank shall be closed with caps or plugs. All permanently attached fittings shall be covered or protected with a noncorrosive, water-resistant cushioning material secured in place with tape conforming to PPP-T-60, Type IV. The tank shall be collapsed and folded or neatly rolled and the bundle secured with cord or tape, PPP-T-97, Type IV.

5.1.1.2 Accessories. The detached fittings and accessories for each tank shall be preserved together in a box conforming to PPP-B-636, Class Weather-Resistant and closed in accordance with Method V of the appendix to the box specification.

5.1.2 Commercial. The complete tank shall be preserved to afford protection against deterioration and damage during shipment from the contractor to initial destination.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the currentversion before use.

5.2 Packing. Packing shall be Level A, Level B, or Commercial (see 6.2).

5.2.1 Level A. Each complete tank shall be packed in a close-fitting box conforming to PPP-B-601, Overseas Type, Grade B. The box shall be lined with polyethylene material conforming to L-P-378, Type I, Class 1, minimum thickness 0.0060 inches. Strapping shall conform to QQ-S-781, Class 1, Type I or IV, size as applicable and, unless otherwise specified, shall be Finish B. When specified, (see 6.2), Finish A strapping shall be used. The contents shall be blocked to prevent movement.

5.2.2 Level B. The complete tank shall be packed as specified in 5.2.1 for Level A, except the box shall be Domestic Type and strapping shall be either Finish A or B.

5.2.3 Commercial. Each complete tank shall be packed to meet common carrier acceptance and provide safe delivery to destination at lowest rates in compliance with Uniform Freight Classification rules or National Motor Freight Classification rules.

5.3 Marking.

5.3.1 Military. Marking shall be in accordance with MIL-STD-129.

5.3.2 Commercial. Marking for commercial packaging shall be by any means which provides legibility and shall include the National Stock Number (NSN) or part number, nomenclature, quantity and unit of issue, contract or delivery order number, and address.

6. NOTES

6.1 Intended use. The synthetic rubber coated fabric pillow tank is intended for storing potable water in remote or temporary areas of operation.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Size required (see 1.2).
(c) Time frame required for submission of preproduction model, and number of tanks required (see 3.2).
(d) When a ground cloth is required (see 3.6).
(e) When vulcanizing repair items are required (see 3.9).
(f) The color of the exterior surfaces of tank (see 3.10).
(g) The color of the exterior surfaces of metallic parts (see 3.11).
(h) Degree of preservation and packing required (see 5.1 and 5.2).
(i) When Finish A strapping is required (see 5.2.1).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

6.3 Preproduction model. Any changes or deviations of production tanks from the approved preproduction model during production will be subject to the approval of the contracting officer. Approval of the preproduction model will not relieve the contractor of his obligation to furnish tanks conforming to this specification.

6.4 For Army procurement, the Surgeon General of the Army will act as advisor to make the necessary determination on health hazards (see 3.3).

6.5 Recycled material. It is encourage that recycled material be used when practical as long as it meets the requirements of the specification (see 3.3).

Custodian:
Army - ME

Review activity:
Army - MD

Preparing activity:
Army - ME

Project 5430-A115

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE: MIL-T-52943(ME) Tank, Fabric, Collapsible, Pillow Type (For Potable Water)

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1426 1 OCT 76

EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:11Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
US Army Mobility Equipment Research and
Development Command
ATTN: DRDME-DS
Fort Belvoir, VA 22060

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:11Z
Check the source to verify that this is the current version before use.