The documentation and process conversion measures necessary to comply with this document shall be completed by 12 October 2012.

INCH-POUND

MIL-PRF-19500/533J
w/AMENDMENT 1
12 July 2012
SUPERSEDING
MIL-PRF-19500/533J
4 September 2007

PERFORMANCE SPECIFICATION SHEET

SEMICONDUCTOR DEVICE, DIODE, SILICON, VOLTAGE REGULATOR, TYPES 1N6309 THROUGH 1N6355; 1N6309US THROUGH 1N6355US, PLUS C AND D TOLERANCE SUFFIX, JAN, JANTX, JANTXV, AND JANS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-PRF-19500.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for microminiature 500 mW, silicon, metallurgically bonded, voltage regulator diodes with voltage tolerances of 5 percent, 2 percent (C), and 1 percent (D). Four levels of product assurance are provided for each encapsulated device type as specified in MIL-PRF-19500.

1.2 Physical dimensions. See figure 1 (DO-35) and figure 2 (surface mount).

1.3 Maximum ratings. Maximum ratings are as shown in maximum and primary test ratings (see 3.11 herein) and as follows:

a. P_{TL} = 500 mW (DO-35) at T_L = + 75°C, L = .375 inch (9.53 mm); both ends of case or diode body to heat sink at L = .375 inch (9.53 mm). (Derate I_Z to 0.0 mA dc at +175°C.)

b. P_{TEC} = 500 mW (surface mount) at T_{EC} = 125°C. (Derate to 0 at 175°C.)

c. P_{TPCB} = 500 mW, T_A = +55°C.

d. -65°C ≤ T_J ≤ +175°C; -65°C ≤ T_{STG} ≤ +175°C.

* Comments, suggestions, or questions on this document should be addressed to DLA Land and Maritime, ATTN: VAC, P.O. Box 3990, Columbus, OH 43218-3990, or emailed to Semiconductor@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Primary electrical characteristic are shown in maximum and primary test ratings (see 3.11 herein) and as follows:

a. 2.4 V dc ≤ V_Z ≤ 200 V dc (nominal).

b. 1N6309D through 1N6355D, and US devices are 1 percent voltage tolerance.

c. 1N6309C through 1N6355C, and US devices are 2 percent voltage tolerance.

d. 1N6309 through 1N6355, and US devices are 5 percent voltage tolerance.

e. L = .375 inch (9.53 mm) (DO-35) non-surface mount.

(1) 1N6309 – 1N6320, $R_{\Theta JL}$ = 150°C/W (maximum). See figure 3 for derating.

(2) 1N6321 – 1N6355, $R_{\Theta JL}$ = 95.5°C/W (maximum). See figure 4 for derating.

f. $R_{\Theta JL}$ = 50°C/W (maximum) at L = 0 inch non-surface mount.

g. Surface mount (US).


(1) 1N6309US – 1N6320US, $R_{\Theta JEC}$ = 35°C/W (maximum). See figure 5 for derating.

(2) 1N6321US – 1N6355US, $R_{\Theta JEC}$ = 21°C/W (maximum). See figure 6 for derating.

h. $R_{\Theta JA}$ = 240°C/W junction to ambient including PCB see note below.

NOTE: See figure 7 for derating curves. T_A = +55°C before derating for both axial and MELF (US) on printed circuit board (PCB), PCB = FR4 .0625 inch (1.59 mm) 1-layer 1-Oz Cu, horizontal, still air, pads (US) = .067 inch (1.70 mm) x .105 inch (2.67 mm); pads (axial) = .092 inch (2.34 mm) diameter, strip = .030 inch (0.76 mm) x 1 inch (25.4 mm) long, axial lead length L ≤ .187 inch (≤ 4.75 mm); $R_{\Theta JA}$ with a defined thermal resistance condition included is measured at I_Z = as defined in the characteristics and ratings table herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




Ltr	Dimensions				Notes
	Inches		Millimeters		
	Min	Max	Min	Max	
BD	.060	.090	1.52	2.29	
BL	.120	.200	3.05	5.08	5
LD	.018	.022	0.46	0.56	
LL	1.000	1.500	25.40	38.10	
LL_1		.050		1.27	3

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Lead diameter not controlled in this zone to allow for flash. Lead finish build-up and minor irregularities other than slugs.
4. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.
5. The BL dimension shall include the entire body including slugs.

FIGURE 1. Physical dimensions (DO-35).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.



Symbol	Dimensions			
	Inches		Millimeters	
	Min	Max	Min	Max
BD	.070	.085	1.78	2.16
BL	.165	.195	4.19	4.95
ECT	.019	.028	0.48	0.71
S	.003 min		0.08 min	

NOTES:
1. Dimensions are in inches.
2. Millimeters are given for general information only.
3. Dimensions are pre-solder dip.
4. In accordance with ASME Y14.5M, diameters are equivalent to Φx symbology.

FIGURE 2. Physical dimensions surface mount device,

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-750 - Test Methods for Semiconductor Devices.

* (Copies of these documents are available online at https://assist.dla.mil/quicksearch or https://assist.dla.mil or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

* 2.3 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 General. The individual item requirements shall be as specified in MIL-PRF-19500 and as modified herein.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows.

C	2 percent voltage tolerance.
D	1 percent voltage tolerance.
EC	End-cap.
T_{EC}	Temperature of end-cap.
US	Unleaded square end-cap.

3.4 Interface and physical dimensions. Interface and physical dimensions shall be as specified in MIL-PRF-19500 and on figure 1 (DO -35) and figure 2 (surface mount) herein.

3.5 Construction. All devices shall be metallurgically bonded, thermally matched, non-cavity, double-plug construction in accordance with MIL-PRF-19500.

3.5.1 Metalurgical bond for diodes with V_Z greater than 6.8 V dc. Category I bonds, as defined in accordance with MIL-PRF-19500, shall be utilized.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

3.5.2 Metalurgical bond for diodes with V_Z less than or equal to 6.8 V dc. Category I or category III bonds, as defined in accordance with MIL-PRF-19500, shall be utilized.

3.6 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.6.2 Polarity. The polarity shall be indicated with a contrasting color band to denote the cathode end. Alternately, for surface mount (US) devices, a minimum of three evenly spaced contrasting color dots around the periphery of the cathode end may be used. No color coding will be permitted.

3.7 Lead finish. Lead finish shall be solderable as defined in MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.8 Selection of tight tolerance devices. The C and D suffix devices shall be selected from JAN, JANTX, JANTXV, and JANS devices which have successfully completed all applicable screening, and tables I, II, and III testing herein as 5-percent tolerance devices. All sublots of C and D suffix devices shall pass table I, subgroup 2, at tightened tolerances. Tighter tolerances for mounting clip temperature shall be maintained for reference purposes to establish correlation. For C and D tolerance levels, T_L = 25°C, +1°C, -3°C at .375 inch (9.53 mm) from body or equivalent.

3.9 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, tables I, II, III, and table IV.

3.10 Electrical test requirements. The electrical test requirements shall be the subgroups specified in table I and II herein.

3.11 Maximum and primary test ratings. Maximum and primary test ratings for voltage regulator diodes are specified in table III herein.

3.12 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3).

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500 and herein. Lot accumulation period shall be 3-months in lieu of 6-weeks.

4.2.1 Group E qualification. Group E inspection shall be performed for qualification or requalification only. In case qualification was awarded to a prior revision of the specification sheet that did not request the performance of table II tests, the tests specified in table II herein that were not performed in the prior revision shall be performed on the first inspection lot to this revision to maintain qualification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

* 4.3 Screening (JANTXV, JANTX, and JAN levels). Screening shall be in accordance with table E-IV of MIL-PRF-19500 and as specified herein. Specified electrical measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table E-IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTXV and JANTX level
1a 1b	Required Required	Not required Required (JANTXV only)
2	Not required	Not required
3a 3b (1) 3c	Required Not applicable Required (see 4.3.1)	Required Not applicable Required (see 4.3.1)
4, 5, and 6	Not applicable	Not applicable
8	Required	Not required
9	Required on nom V_Z > 10 V I_{R1}, V_{Z2} and Z_Z	Not applicable
10	Required on nom V_Z > 10 V	Not applicable
11	Required I_{R1}, V_{Z2}; $\Delta I_{R1} \leq$ 100 percent of value or 50 nA dc, whichever is greater. $\Delta V_{Z2} \leq \pm$1 percent of initial value	Required I_{R1} and V_{Z2}
12	Required, see 4.3.2	See 4.3.2
13	Required Scope display, see 4.5.7 Subgroup 2 and 3 of table I herein; $\Delta I_{R1} \leq$ 100-percent of initial reading or 50 nA whichever is greater; $\Delta V_{Z2} \leq$ 1 percent of initial reading	Subgroup 2 of table I herein; $\Delta I_{R1} \leq$ 100 percent of initial reading or 50 nA whichever is greater; $\Delta V_{Z2} \leq$ 1 percent of initial reading
15	Required	Not required
16	Required	Not required

* (1) Shall be performed anytime after temperature cycling, screen 3a; TX and TXV do not need to be repeated in screening requirements.

4.3.1 Thermal impedance. The thermal impedance measurements shall be performed in accordance with method 3101 or 4081 as applicable of MIL-STD-750 using the guidelines in that method for determining I_M, I_H, t_H, t_{MD} (and V_C where appropriate) see table II, subgroup 4 (see figures 8 through 11).

LS = lead spacing = .375 inch (9.53 mm) for non-surface mount devices and 0 inch for surface mount devices as defined on figure 9. See figure 12 for mounting conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

4.3.2 Power burn-in conditions. Power burn-in conditions are as follows (see 4.5.8): $I_{Z(min)}$ = 50 percent of column 7 of table IV. T_A = 75°C maximum. Test conditions in accordance with method 1038 of MIL-STD-750, condition B. Adjust I_Z or T_A to achieve the required T_J. T_J = 125°C minimum. With approval of the qualifying activity and preparing activity, alternate burn-in criteria (hours, bias conditions, T_J, mounting conditions) may be used for JANTX and JANTXV quality levels. A justification demonstrating equivalence is required. In addition, the manufacturing site's burn-in data and performance history will be essential criteria for burn-in modification approval.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500, and as specified herein.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with appendix E, table E-V of MIL-PRF-19500 and table I herein.

* 4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VIa (JANS) and table E-VIb (JAN, JANTX, and JANTXV) of MIL-PRF-19500 and 4.4.2.1 herein. Electrical measurements (end-points) and delta requirements shall be in accordance with table I, subgroup 2 and table III herein.

* 4.4.2.1 Group B inspection, table E-VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1056	0°C to +100°C, 25 cycles, n = 22, c = 0.
B3	1051	-55°C to +175°C, 100 cycles, n = 22, c = 0.
B3	4066	T_A = room ambient as defined in the general requirements of 4.5 of MIL-STD-750. I_{ZSM} = column 9 of table IV herein (shall be performed on each sublot).
B3	1071	Condition E.
B3	2101	Decap analysis scribe and break only.
B4	1037	I_Z = shall be equal to 100 percent of column 7 of table IV minimum, 2,000 cycles.
B5	1027	I_Z = 50 percent of column 7 of table IV minimum for 96 hours; adjust T_A or I_Z to achieve T_J minimum.
		Option 1: T_A = +100°C max; T_J = +275°C minimum; t = 96 hours. n =22, c = 0.
	or	Option 2: T_A = +55°C max; T_J = +175°C minimum; t = 1,000 hours. n = 45, c = 0.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

* 4.4.2.2 Group B inspection, table E-VIb (JAN, JANTX, and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	1056	0°C to +100°C, 10 cycles, n = 22, c = 0.
B2	1051	-55°C to +175°C, 25 cycles, n = 22, c = 0.
B2	1071	Condition E.
B3	1027	I_Z (min) shall be equal to 50 percent of column 7 of table IV minimum. Adjust I_Z to achieve T_J = 150°C minimum (see 4.5.8). T_A = 75°C max.
B4	2101	Decap analysis scribe and break only.

* 4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 and table III herein.

Subgroup	Method	Condition
C2	1056	0°C to +100°C, 10 cycles, n = 22, c = 0.
* C2	2036	Condition A; 6 pounds; t = 15 seconds ±3 s (not applicable to "US" suffix devices). Condition E, 8 ounces, t = 15 seconds ±3 s (not applicable to "US" suffix devices).
C2	1071	Condition E.
C5	4081	$R_{\Theta JL}$; see 1.4.e $R_{\Theta JEC}$; n = 22, c = 0 (see 4.3.1), see 1.4.g.
C6	1027	I_Z (min) shall be equal to 50 percent of column 7 of table IV. Adjust I_Z to achieve T_J = 150°C minimum (see 4.5.8). T_A = 75°C max.
C7		Not applicable.
C8	4071	(For JAN, JANTX, and JANTXV only); I_{Z2} = column 4 of table IV; T_1 = +25°C ±5°C, T_2 = +125°C (see 4.5.5); αV_Z = col. 14 of table IV; n = 22 devices, c = 0.

* 4.4.4 Group E inspection. Group E inspection shall be conducted in accordance with the conditions specified for subgroup testing in table E-IX of MIL-PRF-19500 and as specified in table II herein. Electrical measurements (end-points) shall be in accordance with table I, subgroup 2 herein. See table III for delta limits when applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows:

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Surge current (I_{ZSM}). The peak currents shown in column 9 of table IV shall be applied in the reverse direction and these shall be superimposed on the current (I_Z = column 4 of table IV); a total of five (5) surges at 1 minute intervals. Each individual surge shall be 0.5 square-wave-pulse of 8.3 ms duration, or an equivalent sine wave, with the same effective rms current.

4.5.3 Regulator voltage measurements. The test current shall be applied until thermal equilibrium is attained (90 ±2 seconds minimum) prior to reading the breakdown voltage. For this test, the diode shall be suspended by its leads with mounting clips whose inside edge is located at .375 inch (9.53 mm) from the body and the mounting clips shall be maintained at a temperature of +25°C +8°C, -2°C. US suffix devices shall be mounted at the end-caps. This measurement may be performed after a shorter time following application of the test current than that which provides thermal equilibrium if correlation to stabilized readings can be established to the satisfaction of the qualifying activity.

4.5.4 Voltage regulation. For values of V_{Z2} (nominal) from 6.8 V dc to 200 V dc, current at 10 percent of I_{ZM} (column 7 of table IV) shall be maintained for a period of 90 ±5 seconds, and then V_Z shall be recorded. The current shall then be increased to 50 percent of I_{ZM} (column 7 of table IV) and maintained for a period of 90 ±5 seconds, then V_Z shall be recorded. The voltage change shall not exceed the applicable limits as shown in column 8 of table IV. During this test, the diode shall be suspended by its leads with mounting clips whose inside edge is located between .375 inch (9.53 mm) and .500 inch (12.70 mm) from the device body and the mounting clips shall be maintained at a temperature of +25°C +8°C, -2°C. US suffix devices shall be mounted by the end-caps. For values of V_{Z2} (nominal) from 2.4 V dc to 6.2 V dc, the lower test current shall be 2 mA dc and the higher current shall be 20 mA dc.

4.5.5 Temperature coefficient of regulator voltage (αV_Z). The device shall be temperature stabilized with current applied prior to reading regulator voltage at the specified ambient temperature.

4.5.6 Noise density. Noise density shall be measured using a noise density test circuit as shown on figure 13. Place a low-noise resistor, equivalent in value to the dynamic impedance of the device under test (DUT), in the test clips and adjust test current (I_{ZT}) to 250 μA dc and measure output noise voltage. Remove the resistor, insert DUT in test clips, readjust test current to 250 μA dc and measure output noise voltage again. To obtain noise density (N_D), subtract rms resistor output noise voltage from rms diode output noise voltage and divide by product of overall system gain and square root of bandwidth. All measurements shall be made at +25°C.

4.5.7 Scope display evaluation. Scope display evaluation shall be stable in accordance with method 4023 of MIL-STD-750, condition A. Scope display may be performed on ATE (automatic test equipment) for screening only with the approval of the qualifying activity. Scope display in table I, subgroup 4 shall be performed on a scope. The reverse current over the knee shall be 500 μA peak.

4.5.7.1 Scope display option. At the suppliers option, 100-percent scope display evaluation may be discontinued after three consecutive lots are 100-percent tested with zero failures. Any table I failure shall require 100-percent scope display to be reinvoked.

4.5.8 Free air power burn-in and life tests. The use of a current limiting or ballast resistor is permitted provided that each DUT still sees the full P_t (minimum) and that the minimum applied voltage, where applicable, is maintained throughout the burn-in period. Use method 3100 of MIL-STD-750 to measure T_J.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits 2/		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical examination	2071					
Subgroup 2						
Thermal impedance	3101	See 4.3.1	$Z_{\Theta JX}$			°C/W
Forward voltage	4011	I_F = 1 A dc, pulsed (see 4.5.1)	V_F		1.4	V dc
Reverse current leakage	4016	DC method; V_R = column 10 of table IV	I_{R1}		Column 11	µA dc
Regulator voltage (see 4.5.3)	4022	I_{Z1} = 250 µA dc	V_{Z1}	Column 3		V dc
Regulator voltage (see 4.5.3)	4022	I_{Z2} = column 4 of table IV	V_{Z2}	Column 2 -5, -2, -1 percent	Column 2 +5, +2, 1 percent	V dc
Subgroup 3						
High-temperature operation		T_A = +150°C				
Reverse current	4016	DC method; V_R = column 10 of table IV	I_{R2}		Column 12	µA dc
Subgroup 4						
Small-signal reverse breakdown impedance	4051	I_Z = column 4 of table IV, I_{SIG} = 10 percent of I_{Z2}	Z_{ZT}		Column 5	ohms
Knee impedance	4051	I_{ZK} = 250 µA dc, I_{SIG} = 25 µA rms	Z_{ZK}		Column 6	ohms
Noise density (see 4.5.6)		I_{Z1} = 250 µA dc	N_D		Column 13	$\mu V/\sqrt{Hz}$

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits 2/		Unit
	Method	Conditions		Min	Max	
Subgroup 4 - continued						
Scope display evaluation	4023	See 4.5.7, n = 116, c = 0				
Subgroup 5						
Not applicable						
Subgroup 6						
Surge current	4066	T_A = +25°C ±5°C (see 4.5.2); I_{ZSM} = column 9 of table IV herein (shall be performed on each sublot)				
Electrical measurements		See table I, subgroup 2 herein				
Subgroup 7						
Not applicable						
Subgroup 8		n = 22, c = 0				
Voltage regulation		See 4.5.4	$V_{Z(reg)}$		Column 8	V dc
Temperature coefficient of regulator voltage	4071	JANS level, I_Z = column 4 of table IV, T_1 = +25°C ±5°C; T_2 = +125°C (see 4.5.5)	α_{VZ}		Column 14	%/°C

1/ For sampling plan, see MIL-PRF-19500.
2/ Column references are to table IV herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE II. Group E inspection qualification and requalification (all product assurance levels).

Inspection	MIL-STD-750		Sampling plan
	Method	Conditions	
Subgroup 1			n = 22, c = 0
Thermal shock	1056	20 cycles, condition D except low temperature shall be achieved using liquid nitrogen (-195°C). Do a visual for cracked glass	
Electrical measurements		See table I, subgroup 2	
Subgroup 2			n = 22, c = 0
Intermittent operating life	1037	$I_Z = I_{ZM}$(column 7 of table IV) at T_A = room ambient for 10,000 cycles. No forced air cooling on the device shall be permitted	
Electrical measurements		See table I, subgroup 2	
Subgroup 4			
Thermal impedance curves		See MIL-PRF-19500	Sample size N/A
Subgroups 5 and 6			
Not applicable			
Subgroup 7			n = 45
Resistance to glass cracking	1057	Step stress to destruction by increased cycles or up to a maximum of 25 cycles	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE III. Group A, B, and C electrical and delta end-point measurements. 1/ 2/ 3/

Step	Inspection	MIL-STD-750		Symbol	Limits 4/		Unit
		Method	Conditions		Min	Max	
1.	Forward voltage	4011	I_F = 1 A dc, pulsed (see 4.5.1)	V_F		1.4	Vdc
2.	Reverse current	4016	DC method; V_R = column 10 of table IV	I_{R1}		Column 11	µA dc
3.	Regulator voltage (see 4.5.3)	4022	I_{Z1} = 250 µA dc	V_{Z1}	Column 3		V dc
4.	Regulator voltage (see 4.5.3)	4022	I_{Z2} = column 4 of table IV	V_{Z2}	Column 2; -5, -2, -1 percent	Column 2; -5, -2, -1 percent	V dc
5.	Thermal impedance	3101	See 4.3.1	$\Delta Z_{\Theta JX}$		10 percent of initial reading max.	°C/W
6.	Regulator voltage	4022	I_Z = column 4 of table IV (see 4.5.3)	ΔV_{Z2}	±1 percent of initial value.		
7.	Reverse current	4016	DC method, V_R = column 10 of table IV	ΔI_{R1}	100 percent of initial value or 50 nA dc, whichever is greater.		
8.	Small-signal breakdown impedance	4051	I_Z = column 4 of table IV, I_{SIG} = 10 percent of I_Z	ΔZ_Z	±35 percent of initial value or 2 ohms, whichever is greater.		

1/ The electrical measurements for Group B Inspections in table E-VIa (JANS) of MIL-PRF-19500 are as follows: Subgroup 3, see table III herein, steps 2, 3, 4, 5, 6, 7, and 8.
2/ The electrical measurements for Group B Inspections in table E-VIb (JAN, JANTX and JANTXV) of MIL-PRF-19500 are as follows:
a. Subgroup 2, see table III herein, steps 1, 3, 4, and 5.
b. Subgroup 3, see table III herein, steps 2, 3, 4, and 6.
c. Subgroup 6, see table III herein, steps 2, 3, and 4.
3/ The electrical measurements for Group C Inspections in table E-VII of MIL-PRF-19500 are as follows: Subgroup 2, see table III herein, steps 1, 3, 4, and 5.
4/ Column references are to table IV herein.
5/ Devices which exceed

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE IV. Characteristics and ratings.

Col 1	Col 2	Col 3	Col 4	Col 5	Col 6	Col 7	Col 8	Col 9	Col 10	Col 11	Col 12	Col 13	Col 14
Type	V_{Z2} nom at I_{Z2} 1/	V_{Z1} min at I_{Z1} 250 µA	I_{Z2} test current	Z_{ZT} at I_{Z2}	Z_{ZK} at 250 µA	I_{ZM}	$V_{Z(reg)}$	I_{ZSM} surge	V_R	I_{R1} at +25°C	I_{R2} at T_A = +150°C	N_D at 250 µA 1-3 kHz	α_{VZ}
	V	V	mA	Ω	Ω	mA	V	A	V	µA	µA	$\mu v\sqrt{Hz}$	%/°C
1N6309	2.4	1.1	20	30	1,200	177	1.50	2.50	1.0	100	200	1	-.085
1N6310	2.7	1.2	20	30	1,300	157	1.50	2.20	1.0	60	150	1	-.080
1N6311	3.0	1.3	20	29	1,400	141	1.50	2.00	1.0	30	100	1	-.075
1N6312	3.3	1.5	20	27	1,400	128	1.60	1.80	1.0	5	20	1	-.070
1N6313	3.6	1.8	20	25	1,400	117	1.60	1.65	1.0	3	12	1	-.065
1N6314	3.9	2.0	20	23	1,700	108	1.60	1.50	1.0	2	12	1	-.060
1N6315	4.3	2.4	20	20	1,700	99	0.90	1.40	1.0	2	12	1	-.045 +.020
1N6316	4.7	2.8	20	17	1,500	90	0.50	1.27	1.5	5	12	1	-.028 +.032
1N6317	5.1	3.3	20	14	1,300	83	0.40	1.17	2.0	5	12	1	-.020 +.035
1N6318	5.6	4.3	20	8	1,200	76	0.40	1.10	2.5	5	10	2	+.050
1N6319	6.2	5.2	20	3	800	68	0.30	0.97	3.5	5	10	5	+.060
1N6320	6.8	6.0	20	3	400	63	0.35	1.23	4.0	2	50	5	+.062
1N6321	7.5	6.6	20	4	400	57	0.40	1.16	5.0	2	30	5	+.068
1N6322	8.2	7.5	20	5	400	52	0.40	1.07	6.0	1	10	20	+.075
1N6323	9.1	8.4	20	6	500	47	0.50	0.97	7.0	1.00	10	40	+.076
1N6324	10.0	9.1	20	6	500	43	0.50	0.89	8.0	1.00	10	80	+.079
1N6325	11.0	10.0	20	7	550	39	0.50	0.83	8.5	1.00	10	100	+.082
1N6326	12.0	11.0	20	7	550	35	0.55	0.77	9.0	1.00	10	100	+.083
1N6327	13.0	11.9	9.5	8	550	33	0.55	0.71	9.9	0.05	10	100	+.083
1N6328	15.0	13.8	8.5	10	600	28	0.70	0.62	11.0	0.05	10	100	+.084
1N6329	16.0	14.7	7.8	12	600	27	0.75	0.58	12.0	0.05	10	100	+.084
1N6330	18.0	16.6	7.0	14	600	24	0.85	0.52	14.0	0.05	10	100	+.085
1N6331	20.0	18.5	6.2	18	500	21	0.95	0.47	15.0	0.05	10	100	+.086
1N6332	22.0	20.4	5.6	20	500	19	1.05	0.43	17.0	0.05	10	100	+.087
1N6333	24.0	22.3	5.2	24	500	18	1.15	0.39	18.0	0.05	10	100	+.088
1N6334	27.0	25.2	4.6	27	500	16	1.30	0.35	21.0	0.05	10	100	+.090
1N6335	30.0	28.0	4.2	32	500	14	1.45	0.31	23.0	0.05	10	100	+.091
1N6336	33.0	30.9	3.8	40	600	13	1.60	0.28	25.0	0.05	10	100	+.092
1N6337	36.0	33.7	3.4	50	600	12.0	1.75	0.260	27.0	0.05	10	100	+.093
1N6338	39.0	36.6	3.2	55	700	11.0	1.90	0.240	30	0.05	10	100	+.094
1N6339	43.0	40.4	3.0	65	800	9.9	2.10	0.220	33	0.05	10	80	+.095
1N6340	47.0	44.2	2.7	75	900	9.0	2.25	0.200	36	0.05	10	80	+.095

See footnote at end of table.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TABLE IV. Characteristics and ratings - Continued.

Col 1	Col 2	Col 3	Col 4	Col 5	Col 6	Col 7	Col 8	Col 9	Col 10	Col 11	Col 12	Col 13	Col 14
Type	V_{Z2} nom at I_{Z2} 1/	V_{Z1} min at I_{Z1} 250 µA	I_{Z2} test current	Z_{ZT} at I_{Z2}	Z_{ZK} at 250 µA	I_{ZM}	$V_{Z(reg)}$	I_{ZSM} surge	V_R	I_{R1} at +25°C	I_{R2} at T_A = +150°C	N_D at 250 µA 1-3 kHz	α_{VZ}
	V	V	mA	Ω	Ω	mA	V	A	V	µA	µA	$\mu v\sqrt{Hz}$	%/°C
1N6341	51.0	48.0	2.5	85	1,000	8.3	2.50	0.180	39	0.05	10	80	+.096
1N6342	56.0	52.7	2.2	100	1,200	7.6	2.70	0.170	43	0.05	10	80	+.097
1N6343	62.0	58.4	2.0	125	1,300	6.8	2.90	0.150	47	0.05	10	80	+.099
1N6344	68.0	64.1	1.8	155	1,500	6.3	3.20	0.130	52	0.05	10	80	+.101
1N6345	75.0	70.8	1.7	180	1,600	5.7	3.40	0.125	56	0.05	10	80	+.103
1N6346	82.0	77.4	1.5	220	1,800	5.2	3.80	0.115	62	0.05	10	80	+.105
1N6347	91.0	86.0	1.4	270	2,100	4.7	4.20	0.100	69	0.05	10	80	+.108
1N6348	100.0	94.5	1.3	340	2,400	4.3	4.40	0.095	76	0.05	10	80	+.110
1N6349	110.0	104.0	1.1	500	2,800	3.9	4.80	0.085	84	0.05	10	80	+.110
1N6350	120.0	113.0	1.0	600	3,200	3.5	5.20	0.080	91	0.05	10	80	+.110
1N6351	130.0	122	0.95	850	4,100	3.3	5.60	0.070	99	0.05	10	80	+.110
1N6352	150.0	141	0.85	1,000	4,500	2.8	7.00	0.065	114	0.05	10	80	+.110
1N6353	160.0	151	0.80	1,200	5,000	2.7	7.50	0.060	122	0.05	10	80	+.110
1N6354	180.0	170	0.68	1,500	5,600	2.4	9.00	0.050	137	0.05	10	80	+.110
1N6355	200.0	189	0.65	1,800	6,500	2.1	12.00	0.045	152	0.05	10	80	+.110

1/ 1N6309D through 1N6355D are 1 percent voltage tolerance. 1N6309C through 1N6355C are 2 percent voltage tolerance. 1N6309 through 1N6355 are 5 percent voltage tolerance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




NOTES:

1. All devices are capable of operating at $\leq T_J$ specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperature ($T_J \leq 175°C$) and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at $T_J \leq 150°C$, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at $T_J \leq 125°C$, and 110°C to show current rating where most users want to limit T_J in their application.

FIGURE 3. Temperature-power derating curve (DO-35).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




NOTES:

1. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperature (T_J ≤ 175°C) and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ 150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ 125°C, and 110°C to show current rating where most users want to limit T_J in their application.

FIGURE 4. Temperature-power derating curve (DO-35).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TEMPERATURE- POWER DERATING CURVE
1N6309US - 1N6320US




NOTES:

1. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperature (T_J ≤ 175°C) and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ 150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ 125°C, and 110°C to show current rating where most users want to limit T_J in their application.

FIGURE 5. Temperature-power derating curve (surface mount).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TEMPERATURE- POWER DERATING CURVE
1N6321US - 1N6355US




NOTES:

1. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperature (T_J ≤ 175°C) and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ 150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ 125°C, and 110°C to show current rating where most users want to limit T_J in their application.

FIGURE 6. Temperature-power derating curve (surface mount).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

TEMPERATURE- POWER DERATING CURVE
1N6309, US - 1N6355, US



NOTES:

1. All devices are capable of operating at ≤ T_J specified on this curve. Any parallel line to this curve will intersect the appropriate power for the desired maximum T_J allowed.
2. Derate design curve constrained by the maximum junction temperature (T_J ≤ 175°C) and power rating specified. (See 1.3 herein.)
3. Derate design curve chosen at T_J ≤ 150°C, where the maximum temperature of electrical test is performed.
4. Derate design curve chosen at T_J ≤ 125°C, and 110°C to show current rating where most users want to limit T_J in their application.

FIGURE 7. Temperature-power derating curve.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




FIGURE 8. Axial thermal impedance graph ($R_{\Theta JL}$ = 150°C/W) for 1N6309 through 1N6320.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




FIGURE 9. Thermal impedance surface mount graph ($R_{\Theta JEC}$ = 35°C/W) for 1N6309US through 1N6320US.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.




FIGURE 10. Axial thermal impedance graph ($R_{\Theta JL}$ = 95°C/W) for 1N6321 through 1N6355.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.





FIGURE 11. Thermal impedance surface mount graph ($R_{\Theta JEC}$ = 21°C/W) for 1N6321US through 1N6355US.


Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.



NOTES:

1. The lead temperature, T_L shall be measured on a lead at a point adjacent to the heat sink clamp (reference point).
2. The device under test (DUT) shall be shielded from drafts.
3. The heat sink clamps shall be placed equal distance from each end of the diode body.
4. For surface mount devices, the end-caps shall be clamped to the heat sinks.

FIGURE 12. Mounting conditions.



NOTES:

1. Input voltage and lead resistance should be high so that zener can be driven from a constant current source.
2. Input impedance of band pass filter should be high compared with the dynamic impedance of the DUT.
3. Filter bandwidth characteristics shall be as follows:
   a. f_o = 2,000 Hz.
   b. Shape factor, -40 db to -3 db, approximately 2.
   c. Passband at the -3 db is 1,000 Hz ±□50 Hz to 3,000 Hz±□150 Hz.
   d. Passband at the -40 db is 500 Hz ±50 Hz to 6,000 Hz ±□600 Hz.

FIGURE 13. Circuit for determination of noise density.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the Military Service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory. The notes specified in MIL-PRF-19500 are applicable to this specification.)

6.1 Intended use. Semiconductors conforming to this specification are intended for original equipment design applications and logistic support of existing equipment.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.

b. Packaging requirements (see 5.1).

c. Lead finish (see 3.7).

d. Product assurance level and type designator.

* 6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List (QML 19500) whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from DLA Land and Maritime, ATTN: VQE, P.O. Box 3990, Columbus, OH 43218-3990 or e-mail vqe.chief@dla.mil. An online listing of products qualified to this specification may be found in the Qualified Products Database (QPD) at https://assist.dla.mil .

6.4 Substitution information.

6.4.1 Substitutability of 2 percent and 1 percent tolerance devices. Devices of tighter tolerance are a direct one way substitute for the looser tolerance devices (example: JANTX1N6309D substitutes for JANTX1N6309).

* 6.5 Amendment notations. The margins of this specification are marked with asterisks to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.

Custodians:
Army - CR
Navy - EC
Air Force - 85
NASA - NA
DLA - CC

Review activities:
Navy - AS
Air Force - 19, 99

Preparing activity:
DLA - CC

(Project 5961-2012-031)

* NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T02:51Z
Check the source to verify that this is the current version before use.