COMMERCIAL ITEM DESCRIPTION

SHEET, BED

(Nonwoven)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for MIL-S-36834B which is cancelled.

This Commercial Item Description covers a nonwoven fabric, disposable bedsheet.

Salient characteristics:

The bedsheet shall be a nonwoven fabric, disposable sheet, rectangular in appearance with all edges straight and even. The sheet shall be furnished in the following sizes and colors:

Size 1 - 96 inches long by 60 inches wide, white

Size 2 - 72 inches long by 40 inches wide, aqua or blue

Size 3 - 84 inches long by 40 inches wide, aqua or blue

Tolerances on the above bedsheet dimensions shall be plus or minus 4 inches.

The nonwoven fabric shall be fabricated from any of the following compositions at the manufacturer's option. The finished nonwoven fabric shall be soft, have good draping and hand (feel). The finished nonwoven fabric shall not have an objectionable odor and shall be non-irritating and non-toxic.

a. The nonwoven fabric shall consist of 60 plus or minus 5 percent bleached chemical pulp tissue, 15 plus or minus 5 percent viscose rayon fibers (2 inch average staple length) and 25 plus or minus 5 percent plastisol bonding and fire retardant agents. The fabric shall be constructed by laminating two layers of tissue having sandwiched between them two layers of oriented rayon fibers. One layer of the rayon fiber shall be placed in the cross direction.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

b. The nonwoven fabric shall consist of 40 plus or minus 5 percent viscose rayon fibers and 60 plus or minus 5 percent bleached chemical pulp tissue bonded with a resin adhesive and fire retardant agents. The fabric shall be made from a carded web or randomized web structure.

c. The nonwoven fabric shall consist of 45 plus or minus 5 percent bleached chemical pulp tissue, 20 plus or minus 5 percent synthetic fibers, 35 plus or minus 5 percent polymeric bonding and fire retardant agents. The fabric shall be constructed by laminating two layers of nonwoven tissue having sandwiched between them one layer of random or oriented continuous synthetic filament fibers.

d. The nonwoven fabric shall consist of 100, plus 0, minus 5 percent viscose rayon fibers bonded with a resin adhesive and fire retardant agents. The fabric shall be an all-textile product made from a carded web or randomized web structure.

e. The nonwoven fabric shall consist of 87 plus or minus 5 percent chemical pulp tissue, 1-1/2 plus or minus 1/2 percent oriented continuous synthetic yarns in a nonwoven scrim and 11-1/2 plus or minus 5 percent bonding and fire retardant agents. The fabric shall be constructed by laminating one or two layers of tissue on each side of the scrim reinforcing network.

f. The nonwoven material shall consist of 60 plus or minus 5 percent bleached chemical pulp tissue, 15 plus or minus 5 percent rayon and polyester fiber blend (2 inch average staple length), and 25 plus or minus 5 percent plastisol bonding and fire retardant agents. The material shall be constructed by laminating two layers of tissue having sandwiched between them one layer of random or oriented fibers. One layer of the fibers shall be placed in the cross direction.

g. The nonwoven material shall consist of 60 plus or minus 5 percent bleached chemical pulp tissue, 15 plus or minus 5 percent synthetic fibers (2 inch average staple length), and 25 plus or minus 5 percent plastisol bonding and fire retardant agents. The material shall be constructed by one layer or by laminating two layers of nonwoven tissue having sandwiched between them two layers of oriented or random synthetic fibers. One layer of the synthetic fiber may be placed in the cross direction.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

h. The fabric shall be nonwoven (saturation bonded wet laid) manufactured from cellulosic or synthetic fiber or a combination of both. The nonwoven fabric shall be resin saturated.

1. The nonwoven material shall be spunbonded polypropylene.

The nonwoven fabric shall have the following properties:

Weight (minimum) - 39.3 grams per square meter or 1.15 ounces per square yard.

Tensile strength.

Machine direction	-	3.5 pounds per inch minimum
Cross direction	-	1.0 pounds per inch minimum
Flame resistance	-	8 seconds minimum
Color fastness to:		
Water	-	Good
Crocking Wet and Dry	-	Not lower than Munsel Value 8.0

Each bedsheet shall be clean, free from any break, tear, hole, wrinkle, uneven or ragged edge, foreign material, spot, stain, mend, or patch. The bedsheet shall not contain any spot of oil or grease, fiber clump, insect, smudge, dirt, sharp object, bonding material strike-through, congealed mass of the bonding material, or spot or stain resulting from excess bonding material.

The bedsheet shall be tested using the following standards from American Society for Testing and Materials (ASTM), Technical Association of the Pulp and Paper Industry (TAPPI), and National Fire Protection Association (NFPA):

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

Property	Test
Weight	ASTM D-1910-64
Tensile strength	TAPPI-T494 OM81
Flame resistance	NFPA 702
Toxicity	Any standard method

Certificates of quality, supplied by the manufacturer of the materials, may be furnished in lieu of actual performance of such testing by the contractor. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the item identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements. A certificate of compliance shall be acceptable in lieu of a certificate of quality, provided the manufacturer can establish that adequate controls were applied to assure compliance with the specification requirements.

The sheets shall be uniformly and neatly folded. Multiple quantities of sheets may be bundled, banded, or bagged in unit package at the option of the contractor.

Workmanship. The nonwoven bedsheet shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Package (PG). One package containing one hundred sheets of one color, and size, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, with an AQL of 4.0 (percent defective) and an inspection level of II. The unit of product for examination purposes shall be one nonwoven bed sheet.

Sampling for tests (bedsheet). Sampling for dimensional tests shall be conducted in accordance with MIL-STD-105, with an AQL of 4.0 (percent defective) and an inspection level of S-3. The unit of product for test purposes shall be one nonwoven bed sheet.

Sampling for tests (fabric). Sampling for the testing of the fabric shall be as follows:

Lot size (yards)	Sample size
800 or less	2
801 and up to and including 22,000	3
22,001 and over	5

The sample unit of fabric for test purposes shall be one linear yard of the fabric. The samples shall be taken from the beginning of each roll. The lot shall be unacceptable if one or more sample units fail to meet any of the fabric property requirements.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

7210-00-144-6082 (Size 1)

7210-00-498-0512 (Size 2)

7210-00-139-6376 (Size 3)

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
USPHS
FDA-MPQAS

Project No. 7210-0282

Location: CID/SHEET/BED/H13-37

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in putting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

EFENSE LOGISTICS AGENCY

)FFICIAL BUSINESS
ENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4956 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-RSTE
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
A-A-54212	SHEET, BED, (Nonwoven)

3a NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5 PROBLEM AREAS

a Paragraph Number and Wording

b Recommended Wording

c Reason/Rationale for Recommendation

6 REMARKS

7a NAME OF SUBMITTER *(Last, First, MI)* – Optional	b WORK TELEPHONE NUMBER *(Include Code)* – Optional
c MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8 DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:30Z
Check the source to verify that this is the current version before use.