METRIC
MIL-C-51047B
15 July 1987
SUPERSEDING
MIL-C-51047A
28 March 1969

MILITARY SPECIFICATION

COMPOUND, ANTISEEPAGE, FOR COOLING SYSTEM,

INTERNAL COMBUSTION ENGINE (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type and grade of antiseepage compound for use in the cooling system of internal combustion engines (see 6.1).

1.2 Military part number. Antispeepage compound furnished under this specification shall be identified by a military part number consisting of the "M" prefix, and the basic specification number followed by a two-digit number 02 indicating a 42.5 gram unit container as shown in the following example:

M51047-02

"M" prefix and basic specification

Dash number indicating a 42.5 gram quantity

2. APPLICABLE DOCUMENTS

2.1 Government documents.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: USA Belvoir Research, Development, and Engineering Center, ATTN: STRBE-TSE, Fort Belvoir, VA 22060-5606 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 6850

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

RR-S-366	- Sieves, Standard for Testing Purposes.
PPP-B-601	- Box, Wood, Cleated-Plywood.
PPP-B-621	- Box, Wood, Nailed and Lock-Corner.
PPP-B-636	- Box, Fiberboard.
PPP-C-55	- Cans, Fiberboard and Paperboard (With Paper and Metal Ends).

MILITARY

MIL-A-46153	- Antifreeze, Ethylene Glycol, Inhibited, Heavy Duty, Single Package.

STANDARDS

FEDERAL

FED-STD-313	- Material, Safety Data Sheets, Preparation and Submission of.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.

(Copies of specifications, standards, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DoDISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 664 - Method of Test for Neutralization Number by Potentiometric Titration.
D 836 - Specification for Industrial Grade Bentene.
D 3147 - Stop-Leak Additives for Engine Coolants.
D 3951 - Standard Practice for Commercial Packaging.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Non-Government standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. The cooling system antiseepage compound shall be in the form of a loose granular material and shall be composed of a mixture of ground almond and ground roasted peanut shells, a polyvinyl alcohol and a small amount of antidust material such as castor oil (see 6.3). The mixture shall be furnished in unit containers with a net content of 42.5 grams. The material shall be nonabrasive and free of any material which may have a harmful effect on the radiator or other components of the cooling system of an internal combustion engine. The compound shall not clog the tubes of the radiator or heater, and shall be readily removable from the cooling system by means of cooling system cleaners. The contractor shall certify that no carcinogenic or potentially carcinogenic constituents are present as defined under the Hazard Communication Standard (HCS) 29 CFR 1910.1200. Certification to this effect shall be made available to the contracting officer or the contracting officer's representative.

3.1.1 Safety data sheet. Material safety data sheets shall be prepared in accordance with FED-STD-313 (see 6.4). The form used for submission of data shall be OSHA-20, DD Form 1813, or one essentially similar and approved by OSHA.

3.2. Chemical requirements. The compound shall conform to the chemical requirements specified in table I.

3.3 Physical requirements. The compound shall conform to the physical requirements specified hereinafter.

3.3.1 Compatibility with water and inhibited ethylene glycol. The compound shall be compatible with water and with borax inhibited ethylene glycol solutions within the temperature range between the freezing point of the engine coolant to 120 °C. The mixtures of the compound with these substances shall show no gelling or gumming and all phases of the mixture shall pass through a US No. 30 standard testing sieve when tested in accordance with 4.6.7.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical requirements.

Characteristic	Requirements Min	Requirements Max	Test paragraph
pH value of water mixture.	5.1	5.6	4.6.1.1
pH value of ethylene glycol mixture.	7.4	7.9	4.6.1.2
Water insoluble material, percent by weight.	75.0		4.6.2
Volume of water insoluble material, milliliters (mL).		45	4.6.6
Ash content of water insoluble material, percent.	0.5	1.0	4.6.4
Apparent density of water insoluble material.	1.10	1.15	4.6.5
Polyvinyl alcohol, percent by weight.	13.5		4.6.3.1
Water extractable material (other than polyvinyl alcohol), percent by weight.		10.0	4.6.3.2
Neutralization number.		4.0	4.6.9
Rosin test.		Negative	4.6.10

3.3.2 Leak stoppage. The compound shall effectively stop leakage through a 0.762 millimeter (mm) diameter hole and a 0.127 mm crack within 120 seconds and it shall retain its seal under a pressure of 103 kPa gage, when the compound is employed with water and inhibited glycol-water solution when tested in accordance with 4.6.8.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

a. Quality conformance inspections (see 4.4 thru 4.6).
b. Inspection of packaging (see 4.7).

4.3 Material safety data sheets. The manufacturer shall provide certification of noncarcinogenicity (i.e. materials material safety data sheets (see 3.1.1).

4.4 Sampling.

4.4.1 Sampling for tests. For purpose of test, one sample per five thousand units but not less than twelve samples shall be taken for a given lot. A lot shall consist of all the compound produced by one manufacturer and offered for delivery at one time.

4.4.2 Sampling for examination of filled containers. A random sample of filled containers shall be taken from each lot in accordance with MIL-STD-105 at inspection level I and acceptable quality level (AQL) shall be 1.0 percent defective to verify compliance with all stipulations of the specification regarding fill, closure, marking and other requirements not involving tests.

4.5 Examination of filled containers. Each sample filled container selected in accordance with 4.4.2 shall be examined for defects of the container and the closure, and for unsatisfactory marking; each sample filled container shall also be weighed to determine the amount of contents. Any container in the sample having one or more defects, or under required fill, shall be rejected; and if the number of defective containers in any sample exceeds the acceptance number for the appropriate sampling plan of MIL-STD-105, the lot represented by the sample shall be rejected.

4.6 Test methods. The test methods specified hereafter shall be used in determining compliance of the material under test, with the corresponding requirement specified in section 3 of this specification.

4.6.1 pH value of compound.

4.6.1.1 Water mixture. Place 5 grams of the well mixed compound in a 237 mL screw-cap glass jar. Add 200 mL of distilled water to the jar; cover it, shake its contents, allow the jar to stand for 10 minutes and filter. Determine the pH value of the filtrate, using the glass electrode and reference calomel electrode specified in ASTM D 664. Values outside of the range of 5.1 to 5.6 shall constitute a failure.

4.6.1.2 Inhibited ethylene glycol mixture. Place 5 grams of the well mixed compound in a 237 mL screw-cap glass jar. Add 200 mL of 1:1 mixture by volume of inhibited ethylene glycol conforming to MIL-A-46153 and distilled water or water of equal purity to the jar; cover it, shake its contents, allow to stand for 10 minutes and filter. Determine the pH value of the filtrate using the glass electrode and reference calomel electrode specified in ASTM D 664. Values outside of the range of 7.4 to 7.9 shall constitute a failure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

4.6.2 Percentage of solid material. Place 45 to 90 grams of the well mixed compound in an evaporation dish and dry for two hours in an oven at 110° C. Cool the compound to room temperature in a desiccator. Weigh 20 gram duplicate samples to the nearest 0.1 gram in a tared paper extraction thimble, 43 mm by 123 mm. Place the thimble in a soxhlet extractor apparatus. Place a small piece of glass rod beneath the thimble. The extractor shall be of a large size and a 1000 mL flask shall be employed. Add 300 mL of distilled water or water of equal purity to the extraction apparatus and bring the water to boiling. Continue extraction for sixteen hours. Remove the thimble with its contents, balance on the concavity of a Gooch crucible, and permit the excess water to drain from the thimble for approximately thirty minutes. (Retain the contents of the flask for the test of 4.6.3.) Place the crucible and thimble in a forced draft oven at 110 °C and dry until a constant weight is achieved (approximately 16 hours). Cool in a disiccator, weigh, and calculate the percent of solid material. Retain the dried material for use in the tests of 4.6.4 and 4.6.5. A percent by weight of less than 75 shall constitute failure.

4.6.3 Percent of water-extractable material.

4.6.3.1 Polyvinyl alcohol. Distill approximately 150 mL of water from the flask in 4.6.2 into the extractor. Take care to prevent excessive foaming of the liquid. Remove the flask containing the water extractable material and slowly pour the hot contents into a 500 mL wide mouth Erlenmeyer flask which contains 200 mL of reagent grade acetone. Slowly swirl the liquid in the Erlenmeyer flask during the pouring. Cool the mixture to room temperature and filter the suspended solids through a Buchner funnel with suction using a tared No. 50 Whatman filter paper. Use a portion of the filtrate to rinse the flask thoroughly. Remove the paper and contents and dry at 110 °C for 2 hours. Cool in a desiccator, weigh, and calculate percent of polyvinyl alcohol. A percent by weight of less than 13.5 shall constitute a failure.

4.6.3.2 Water extractable material from solid material. Transfer part of the water-acetone mixture to a tared crystallizing dish and evaporate to near dryness in oven at 110 °C. Add the remaining portions of the mixture to the crystallizing dish. Rinse the flask with three, ten milliliter portions of hot distilled water. Dry the dish and contents to constant weight at 110 °C. Cool in a desiccator, weigh, and calculate the percent of water extractable material from solid material. A percent by weight of more than 10 shall constitute a failure.

4.6.4 Ash content of solid material. Weigh approximately 3 grams, to the nearest 0.1 gram, of the solid material (see 4.6.2) into a tared porcelain crucible. Partly cover the crucible, place it in a muffle furnace and heat it at 750 +50 °C until all carboniferous matter has been removed, taking care that no solid particles are removed from the crucible by the draft during the heating period. Heat the crucible to constant weight. Place in a dessicator until cool, and weigh. Calculate the percent ash in the solid material. The weight percent shall be between 0.5 and 1.0. Values other than these shall constitute failure.

4.6.5 Apparent density of solid material. Weigh approximately 3 grams, to the nearest 0.1 gram, of the dried solid material, (see 4.6.2) and place the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

sample in a 50 mL stoppered graduated cylinder. Add 25 mL of distilled water with a transfer pipette. Wet the solids thoroughly by shaking the cylinder at various intervals over a 15 minute period. Add 10 mL of distilled water with a transfer pipette, washing all adhering solids from the sides of the cylinder. Swirl the cylinder to thoroughly mix the solids. Allow the mixture to stand for 15 minutes, and then record the volume. Calculate the apparent density of the solids as follows:

$$\text{Apparent density of solids} = \frac{M}{R-35}$$

Where M = weight of dried solid material used, in grams
R = final volume reading, in milliliters

Failure of the density to fall between 1.10 and 1.15 shall constitute failure.

4.6.6 Volume of water insoluble material. Wash approximately 250 grams of the well mixed compound with 100 mL of carbon tetrachloride. Filter through coarse filter paper. Place the washed material in an evaporating dish and dry for 4 hours in an oven at 99 °C, stirring occasionally during the drying period. Weigh 10 grams ±0.1 gram of the dried material into a 100 mL stoppered graduated cylinder. Fill the cylinder with 1 N NaOH to the 100 mL mark. Stopper the cylinder and shake thoroughly. Swirl the cylinder gently to wash adhering solids from the top of the cylinder into the liquid layer. Allow the cylinder to sit undisturbed for 16 hours at room temperature. Record the volume of the solid material. Values over 45 mL shall constitute failure.

4.6.7 Compatibility.

4.6.7.1 With water. Place 5 grams of the well mixed compound in a 237 mL screw cap glass jar. Add 200 mL of distilled water to the jar. Cover it, shake its contents, and allow the jar to stand for 10 minutes. Again shake the jar contents until thoroughly mixed, and pour them through a US No. 30 standard sieve conforming to RR-S-366. Rinse the jar and sieve with 200 to 300 mL of distilled water. Observe the sieve for any retained material, and for evidence of gumming or gelling of the water-compound mixture. Any evidence of retained material or evidence of gumming or gelling shall constitute failure of this test.

4.6.7.2 With inhibited ethylene glycol mixture. Place 5 grams of the well-mixed compound in a 237 mL screw cap glass jar. Add 200 mL of a 1:1 mixture by volume of inhibited ethylene glycol, conforming to type 1, MIL-A-46153 and distilled water to the jar, cover it, shake its contents and allow to stand for 10 minutes. Again shake the jar contents until thoroughly mixed and pour them through a US No. 30 standard sieve conforming to RR-S-366. Rinse the jar and sieve with 200 to 300 mL of distilled water. Observe the sieve for any retained material and for evidence of gumming or gelling of the ethylene glycol-compound mixture. Any evidence of retained material or evidence of gumming or gelling shall constitute failure of this test.

4.6.8 Leak test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

4.6.8.1 Apparatus. The leak test unit shall be constructed according to ASTM D 3147.

4.6.8.2 Procedure with water as a coolant. After throughly cleaning the unit, reassemble with a test plate (side B) that contains a slit of 0.127 mm width and a test plate (side A) that contains three holes 0.762 mm diameter. Fill the unit to the top with distilled water and observe that all openings show leakage. Remove 500 mL of water and slowly add 20 to 22 grams of the well-mixed antiseepage compound. Bolt the reservoir cover plate to the test unit and seal the 103 kPa pressure cap in place. Start the circulation pump and turn on the heating unit. Leakage at the 0.762 mm holes shall cease after 120 seconds. Only slight seepage at the 0.127 mm slit shall be permitted. When the temperature reaches 88 $\pm$3 °C, adjust the pressure to 103 $\pm$14 kPa gage. Operate the unit at this temperature and pressure for 2 hours and then turn off the motor and heater. Leave the system under pressure for 16 $\pm$4 hours. During this period no seepage or leakage is permitted. Restart the unit and operate for 1 hour at 88 $\pm$3 °C and 103 $\pm$4 kPa gage. Again no seepage or leakage is permitted.

4.6.8.3 Procedure with antifreeze as a coolant. The procedure as outlined in 4.6.8.2 shall be conducted using a 1:1 mixture by volume of antifreeze meeting MIL-A-46153.

4.6.9 Neutralization number. Accurately weigh approximately 5 grams of the well mixed compound into a 300 mL Erlenmeyer flask. Add 50 mL of distilled water and 50 mL of 95 percent ethyl alcohol which has previously been neutralized to pH 7.0. Heat the contents of the flask to boiling. Agitate thoroughly and filter through coarse filter paper. Wash the filter paper with 20 mL of a hot 50/50 mixture of distilled water and 95 percent ethyl alcohol. Combine filtrates and titrate rapidly while warm with 0.1 N aqueous KOH until a pH of 9.0 persists for 30 seconds after the addition of one drop of KOH. Compute the equivalent number of mL of 0.1000 N KOH which would be required for the titration. Calculate the neutralization number as follows:

$$\text{Neutralization number} = \frac{\text{mL of 0.1000 N KOH X 5.61}}{\text{weight of sample}}$$

A neutralization number above 4.0 shall constitute failure.

4.6.10 Rosin test. Extract approximately 5 grams of the well mixed compound with 25 mL of benzene conforming to ASTM D 836. Filter into small evaporating dish and dry for 2 hours in an oven at 99 °C. Cool and add 0.5 mL of acetic anhydride and 2 drops of concentrated H_2SO_4 (reagent grade). A fugitive red or violet color indicates rosin. A positive test shall constitute failure.

4.7 Inspection of packaging.

4.7.1 Quality conformance inspection of packaging.

4.7.1.1 Unit of product. For the purpose of inspection only, a complete package of compound that has been prepared for shipment shall be considered a unit of product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

4.7.1.2 Sampling. Sampling for examination of the unit of product specified in 4.7.1.1 shall be in accordance with MIL-STD-105.

4.7.1.3 Examination. In addition to the sampling and examination of the unit containers as specified in 4.4.2 and 4.5, unit of product samples selected in accordance with 4.7.1.2 shall be examined for the following defects. AQL shall be 1.0 percent defective.

Major	Defect	A	B	Comm
101.	Unit containers not as specified.	5.1.1.1		5.1.2.1
102.	Intermediate containers not as specified.	5.1.1.2		5.1.2.2
103.	Quantity of unit containers in intermediate container not as specified.	5.1.1.2		5.1.2.2
104.	Shipping container not as specified.	5.2.1	5.2.2	5.2.3
105.	Quantity of intermediate containers per shipping container not as specified.	5.2.1	5.2.2	5.2.3
106.	Marking not as specified.	5.3.1	5.3.1	5.3.2

5. PACKAGING

5.1 Preservation. Preservation shall be level A or commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit containers. The unit containers, of the net content capacity specified in 3.1, shall conform to the requirements of PPP-C-55.

5.1.1.2 Intermediate containers. Forty-eight unit containers (see 5.1.1.1) shall be placed in a close-fitting box conforming to PPP-B-636, grade W5c, style RSC. Box closure shall be method IV in accordance with the requirements of the appendix to the box specification.

5.1.2 Commercial.

5.1.2.1 Unit containers. The unit containers, of the net content capacity specified in 3.1, shall be of the type normally used for a product of this nature, providing that there will be no interaction chemically or physically with the contents so as to damage the container or alter the strength, quality or purity of the contents. The filled containers shall be closed in a manner to assure that the contents will not spill or leak from the container during shipment, handling, storage, and redistribution.

5.1.2.2 Intermediate containers. Forty-eight unit containers (see 5.1.2.1) shall be placed in a close-fitting fiberboard box in a manner to satisfy the requirements of ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, level B, or commercial as specified (see 6.2).

5.2.1 Level A. Eight intermediate containers, each containing forty-eight unit containers as specified in 5.1, shall be packed in a snug-fitting box conforming to PPP-B-601, overseas type, or PPP-B-621, class 2. Box style shall be optional. Box closure and strapping shall be as specified in the box specification or the appendix thereto except that strapping shall be flat and the finish B. Tops for style A and B overseas boxes will be constructed with a unnailed closure.

5.2.2 Level B. Eight intermediate containers shall be packed as specified for level A in 5.2.1 except that the boxes shall be domestic type or class and the strapping shall be finish A or B.

5.2.3 Commercial. The intermediate containers specified in 5.1, each containing forty-eight unit containers as specified in 5.1, shall be packed in accordance with ASTM D 3951. Eight intermediate containers shall be packed in each shipping container (see 6.2).

5.3 Marking.

5.3.1 Levels A and B packing. In addition to any special or identification markings required by the contract or purchase order, each container shall be marked in accordance with MIL-STD-129 (see 6.2).

5.3.2 Commercial. Commercial marking shall be in accordance with ASTM D 3951. Additionally, each exterior container shall be marked with the cube and gross weight.

6. NOTES

6.1 Intended use. The antiseepage compound is intended for sealing cracks and crevices in the cooling system of internal combustion engines, especially wet sleeve engines, and for stopping seepage of the coolant into the cylinder combustion chamber and into the crankcase of the engine. The compound is also intended for sealing small pinhole leaks in the radiator and cooling system of internal combustion engines. The compound is not intended to stop seepage of the coolant at the circulating pump shaft.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Degree of preservation and packing required (see 5.1 and 5.2 respectively).
c. Any special marking (see 5.3.1).
d. Quantity (see 3.1).

6.3 Suggested formulation. The antiseepage compound is contemplated to be comparable in performance to the following approximate composition. However, the Government assumes no responsibility for the acceptance of a product claimed to be manufactured under the identical formula:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

Ground almond shells	Percent by weight
Through No. 30 sieve and retained on No. 40 sieve.	6.0 - 8.0
Through No. 40 sieve and retained on No. 45 sieve.	6.0 - 8.0
Through No. 45 sieve and retained on No. 50 sieve.	12.0 - 16.0
Through No. 50 sieve and retained on No. 80 sieve.	27.0 - 30.0
Through No. 80 sieve.	9.0 - 12.0

Ground roasted peanut shells	Percent by weight
Through No. 40 sieve and retained on No. 45 sieve.	6.0 - 8.0
Through No. 45 sieve and retained on No. 50 sieve.	11.0 - 13.0
Through No. 50 sieve and retained on No. 80 sieve.	3.0 - 4.0
Low viscosity polyvinyl alcohol	13.0 - 14.0
Raw castor oil	3.0 - 4.0

6.4 Material safety data sheets. A copy of the data sheet must be forwarded with the application for acceptance to the addresses in FED-STD-313.

6.5 Key words

Antileak compound
Antiseepage compound
Stop leak compound

6.6 Changes from previous issue. Asterisks (or vertical lines) are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - ME
Air Force - 68

Review activities:
Army - EA, AL
DLA - GS

User activities:
Army - AT, SM

Preparing activity:
Army - ME

Project 6850-0791

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-51047B	Compound, Antiseepage, for Cooling System, Internal Combustion Engine (Metric)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:04Z
Check the source to verify that this is the current version before use.