MIL-L-51131A (PA)
31 July 1974
SUPERSEDING
MIL-L-51131 (MU)
30 August 1963

MILITARY SPECIFICATION

LITHIUM STEARATE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers two types of lithium stearate.

1.2 Classification. - Lithium Stearate shall be of the following types as specified (see (6.1).

Type I - Maximum moisture content of 0.1 %
Type II - Maximum moisture content of 0.2 %

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids, or request for proposals, form a part of this specification to the extent specified herein.

SPECIFICATION

FEDERAL

UU-S-48 - Sacks, Shipping, Paper.
RR-S-366 - Sieves, Standard for Testing Purposes.
PPP-D-723 - Drums, Fiber.
PPP-D-729 - Drums, Metal, 55 Gallon (for shipment of noncorrosive material).

MILITARY

MIL-P-112 - Packaging and Packing for Overseas Shipment Drums, Plywood (for drums whose weight of contents does not exceed 200 pounds).
MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification For

STANDARDS

FEDERAL

FED-STD-141 - Paint, Varnish Lacquer, and Related Material, Methods of Inspection, Sampling and Testing.

FSC: 6810

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-109 - Inspection Terms and Definitions.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-1168 - Lot Numbering of Ammunition.
MIL-STD-1235 - Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes.

(Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. - The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) STANDARDS

E324 - Relative Initial and Final Melting Points, and the Melting Range of Industrial Organic Chemicals, Test for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19130).

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal Agencies).

UNIFORM FREIGHT CLASSIFICATION RULES

(Application for copies of these freight classification rules should be addressed to Consolidated Classification Committee, 202 Chicago Union Station, Chicago, Ill.)

AMERICAN TRUCKING ASSOCIATION PUBLICATION

National Motor Freight Classification Rules and Container Specifications. (Application for copies should be addressed to the American Trucking Association, 1424 16th Street N.W., Washington, D.C.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:05Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 The requirements for lithium stearate shall comply with Table I when determined as specified in the applicable paragraphs of section 4.5.

Table I

Tests	Requirements	
	Type I	Type II
Moisture percent, maximum (max.)	0.1	0.2
Water soluble material, percent, max.	1.5	0.5
pH Value	8 to 10	8 to 10
Lithium content, percent	2.2 to 2.8	2.2 to 2.8
Stearate content, percent	94.6 to 97.8	94.6 to 97.8
Melting point, degree Centigraded (°C) minimum (min)	200	200
Melting point of fatty acid degree C., min	55	55
Iodine number of fatty acid, max	5.0	5.0
Free alkali calculated as $LiOH \cdot H_2O$	___	None
Free acid (calculated as stearic acid) percent max.	___	0.5
Chloride percent, max.	___	0.01

3.2 Granulation. - The granulation of lithium stearate type I and II shall be 99 percent, min. through United States Standard sieve number 100 when determined as specified in paragraph 4.5.7.

3.3 Workmanship. - The standard of workmanship shall be such as to insure the production of material meeting the requirements of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection and Standard Quality Assurance Provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification.

4.2 Classification of Inspections. The following types of inspection shall be conducted on this item:

a. First Article Inspection
b. Quality Conformance Inspection

4.3 First Article Inspection

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall be obtained as described in 4.4.3. The samples shall be obtained from a production batch which has been produced by the contractor using the same production processes, procedures and equipment as will be used in fulfilling the contract. All materials shall be obtained from the same sources of supply as will be used in regular production.

4.3.2 Inspections to be Performed. The sample will be subjected by the Government to any or all of the examinations or tests specified in 4.5 of this specification

4.3.3 Rejection. See MIL-A-48078 (PA).

4.4 Quality Conformance Inspection

4.4.1 Inspection Lot Formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078. For the material covered by this specification, a lot shall consist of one or more batches of lithium stearate produced by one manufacturer, in accordance with the same specification, or same specification revision, under one continuous set of operating conditions. Each batch shall consist of that quantity of lithium stearate that has been subjected to the same unit chemical or physical process.

4.4.2 Examination. - See MIL-A-48078.

a. Sampling Plans. Unless otherwise specified in the Classification of Defects and Test Tables, sampling plans for major and minor defects shall be in accordance with MIL-STD-105, Inspection Level II.

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:05Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.1	Drums, prior to filling (Polyethylene liner)		NA
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Liner cut, torn or punctured		0.40%	5.1	Visual
Minor	None defined				

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.1.1	Drums, prior to filling (Alternative method)				NA
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Laminations on coatings incomplete		0.40%	5.1	Visual
Minor	None defined				

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER NA
4.4.2.2	Drums, prior to closing (Polyethylene liner)				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Liner not completely sealed		0.40%	5.1	Visual
Minor	None defined				

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER NA
4.4.2.3	Drum sealed (Steel)				NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Closing ring damaged or not properly positioned so it does not close drum properly		0.40%	5.1	Visual
Minor					
201	Marking misleading or unidentifiable		0.65%	5.2	Visual

NOTES:

SARPA-QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE		SHEET 1 OF 1		DRAWING NUMBER
4.4.2.4	Drum, sealed (fiber)				NA
					NEXT HIGHER ASSEMBLY
CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Weight of contents		0.40%	5.1	Scale
132	Closure incomplete or damaged to the extent that contents sift out		0.40%	5.1	Visual
Minor					
201	Marking misleading or unidentifiable		0.65%	5.2	Visual

NOTES:

SARPA-OA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

10

CLASSIFICATION OF DEFECTS & TESTS

MIL-L-51131A

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.5	Drum, sealed (plywood)		NA
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined				
Major B					
131	Weight of contents		0.40%	5.1	Scale
132	Strapping missing or broken		0.40%	5.1	Visual
Minor					
201	Strapping mislocated		0.65%	5.1	Visual
202	Marking misleading or unidentifiable		0.65%	5.2	Visual

NOTES:

SARPA QA FORM 2567 FEB 74

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

4.4.3 Testing

4.4.3.1 Sampling. Samples from individual containers shall be selected in accordance with ASTM E300, using a sampling thief. Samples shall be identified to provide identification of the containers used to provide the sample. For the tests given in 4.5.1 through 4.5.9 the containers in the lot shall be divided into two (2), approximately equal groups. For each of these 2 groups, an individual sample shall be prepared in the following manner: Randomly select containers for sampling in accordance with MIL-STD-105. However, if each group contains less than (5) containers, select all containers. Approximately equal portions of the material shall be taken from each selected container, in such quantity that the aggregate weight of the portions of the samples shall be approximately one (1) pound. Combine these portions and thoroughly mix. Use the two sample formed to performed the tests described in 4.5.1 through 4.5.9. For the test given in 4.5.10 the containers in the lot shall be divided into four (4), approximately equal groups. For each group, a sample shall be prepared in the same manner as described above. If any of the above samples fail to meet any of the requirements specified in Section 3, the lot shall be rejected.

4.4.4 Inspection Equipment.-The government reserves the right to inspect the contractor's equipment and determine that he has available and utilizes correctly, measuring and test equipment of the required accuracy and precision and that the instruments are of the proper type and range to make measurements of the required accuracy.

TABLE II

Tests	Requirement	Test Method	Defect Classification
Moisture	3.1	4.5.1	Major B
Water soluble material	3.1	4.5.2	Major B
pH value	3.1	4.5.3	Major B
Lithium content	3.1	4.5.4.1	Major B
Stearate content	3.1	4.5.4.2	Major B

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

Table II (cont.)

Tests	Requirement	Test Method	Defect Classification
Melting point of fatty acid	3.1	4.5.5	Major B
Iodine number of fatty acid	3.1	4.5.6	Major B
Granulation	3.2	4.5.7	Major B
Free Alkali	3.1	4.5.8	Major B
Free acid	3.1	4.5.8	Major B
Chloride	3.1	4.5.9	Major B
Melting point	3.1	4.5.10	Major B

4.5 Test Methods and Procedures. The tests in 4.5.1 through 4.5.10 shall be performed using prescribed analytical procedures for duplicate determinations given in standard analytical textbooks.

4.5.1 Moisture. - A 10 gram (gm) portion of the sample shall be weighed in a tared glass or other suitable dish about 5 centimeters (cm) in diameter and 2 centimeters (cm) deep. Place the dish and contents in an oven maintained at 95 degrees to 100 degrees C. for 2 hours. Cool in a desiccator and weigh. Calculate the loss in weight as percent moisture.

4.5.2 Water-soluble matter. - A weighed portion of 5 grams (gms) of the sample shall be placed in a 500-ml Erlenmeyer flask and 200 ml of water added. Insert a rubber stopper and allow to stand 15 to 30 minutes with occasional shaking. Dilute to 500 ml, shake, and then allow to stand about 5 minutes. Filter 250 ml of the solution through a Whatman 11-cm No. 42 filter paper into a tared 250-ml beaker. Evaporate the filtrate in the 250-ml beaker to dryness on a steam bath and then heat in an oven at 110°C for 1 hour. Cool in a desiccator and weigh.

Calculate as follows:

$$\% \text{ Water-soluble matter} = \frac{\text{grams of residue}}{\text{grams of sample in aliquot}} \times 100$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

4.5.3 pH value. - Transfer a weighed portion of about 20 gm. of the sample to a 400 ml. beaker and add 40 ml. of 95 percent ethyl alcohol previously neutralized to phenolphthalein. Stir the mixture and break up any lumps in the material with a stirring rod. Add 200 ml. of cold, freshly boiled distilled water to the beaker and stir the mixture vigorously for about 2 minutes. Determine the pH of the solution electrometrically to the nearest 0.1 pH.

4.5.4 Purity

4.5.4.1 Total lithium content.-Transfer an accurately weighed sample of approximately 2 gm. of the material to a 250-ml. beaker. Thoroughly wet the sample with 95 percent ethyl alcohol and break up any lumps which remain with a stirring rod. Add to the beaker 100 ml. of distilled water and then 10 ml. of concentrated nitric acid. Stir the mixture for about 2 minutes and transfer to a 250-ml. separatory funnel using a stream of cold distilled water to make certain that all solid matter is transferred to the funnel. To the separatory funnel, add 50 ml. of ethyl ether. Stopper the funnel and shake it vigorously for a few seconds, then invert the funnel and release the pressure which has been built up in the funnel by carefully opening the stopcock. Close the stopcock and again shake the funnel vigorously releasing the pressure as described herein. Continue shaking the funnel and releasing any pressure which builds up in the funnel until all the lithium stearate in the mixture appears to have been dissolved. Place the funnel upright and allow the two layers to separate. Draw off the lower aqueous layer into a 400 ml. beaker, being careful not to allow any of the ether layer to run into the beaker. Add 10 ml. of distilled water to the funnel and without shaking it, draw of the aqueous layer. Repeat this procedure and then add 25 ml. of distilled water. Stopper the funnel and shake vigorously, releasing the pressure as directed above. Draw off the aqueous layer and repeat the washing with 25 ml. of distilled water. Retain the ether layer for the determination of total stearate (see 4.5.4.2). Combine all the washing with the original aqueous layer in the 400 ml. beaker. Evaporate the solution on a hot plate under a hood to a small volume and transfer to a tared platinum dish. Add 5 ml. of concentrated sulfuric acid and cautiously evaporate the solution to dryness. Ignite the dry residue until fumes cease to come off. Cool, add 5 ml. of concentrated sulfuric acid and again cautiously evaporate to dryness and then ignite until fumes cease to come off. Cool, add 5ml. of concentrated sulfuric acid and again cautiously evaporate to dryness and then ignite until fumes cease to come off. Cool in a desiccator and weigh.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

Repeat the evaporation and ignition after the addition of 5 ml. portions of concentrated sulfuric acid until constant weight is obtained. Calculate the total lithium content as follows:

$$\text{Total lithium content} = 12.62 \frac{A}{W}$$

where:
A = weight of residue in platium dish.
W = weight of sample.

4.5.4.2 Total stearate contents.-Transfer the ether layer obtained as specified in 4.5.4.1 to a tared 150 ml. beaker, washing the separatory funnel three times with 15 ml. portions of ether. Evaporate the ether on a steam bath, and place the beaker and contents in an oven at 100° to 105°C. until constant weight is attained, cool in a desiccator and weigh. Calculate the gain in weight as percent total stearic acid.

4.5.5 Melting point of fatty acid.-Use the fatty acids obtained as described in 4.5.4.2. Determine the melting point using the method described in 4.5.10.2 except that the sample shall not be dried at 70° plus or minus 2°C. or passed through a number 200 mesh sieve. Record as the melting point the temperature at which the material appears to become completely liquified.

4.5.6 Iodine number of fatty acid

4.5.6.1 Iodine number of fatty acid.- Determine the iodine number of fatty acid in accordance with method No. 506.1 of Federal Standard 141 except a weighed portion of 0.12 gram to 0.16 grams of fatty acid shall be used.

4.5.7 Granulation.-Transfer a weighed portion of 10 gm. of the sample to a 600 ml. beaker and wet thoroughly with 95-percent ethyl alcohol, breaking up all lumps with a stirring rod. Add to the beaker about 500 ml. of a 1 : 1 water-alcohol mixture and stir vigorously to suspend the solid material in the liquid. Pour the suspension on a tared 3 inch, number 100 U. S. Standard sieve, catching the material going through the sieve in a large dish. Wash any of the sample remaining in the beaker on the sieve by means of a stream of 1 : 1 water-alcohol mixture. Wash the residue on the sieve by brushing and washing with 1 : 1 alcohol-water mixture until the washings come through with only a slight turbidity. Rinse the sieve once with 95-percent ethyl alcohol and then air-dry the sieve. Place the sieve in an

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

oven at 95° to 100°C. for one-half hour, cool in a desiccator and weigh. Calculate the gain in weight of the sieve to percent lithium stearate retained on the sieve.

4.5.8 Free acid or alkali. - A weighed portion of 2 grams of the sample shall be placed in a 500-ml Erlenmeyer flask. Add 100 ml of 95% ethyl alcohol (or Formula 3A denatured alcohol) that has been made neutral to phenolphthalein with 0.1N sodium hydroxide. Reflux for 30 minutes, detach the flask from the condenser, and add 6 drops of phenolphthalein solution (0.1%). If the solution is colorless, determine the acidity by titration (while hot) to a pink end point with 0.1N sodium hydroxide solution; if the solution is pink, determine the free alkali by titrating (while hot) to a colorless end point with 0.1N hydrochloric acid solution.

Calculate as follows:

$$\% \text{ Free acid (calculated as stearic acid)} = \frac{28.4 \times \text{ml of NaOH} \times \text{normality of NaOH}}{\text{grams of sample}}$$

or

$$\% \text{ Free alkali (calculated as } LiOH \cdot H_2O) = \frac{4.2 \times \text{ml of HCl} \times \text{normality of HCl}}{\text{grams of sample}}$$

4.5.9 Chloride. - A weighed portion of 5 grams (gm.) of the sample shall be placed in a 500-ml Erlenmeyer flask and 200 ml of water added. Insert a rubber stopper and allow to stand 15 to 30 minutes with occasional shaking. Dilute to 500 ml, shake, and allow to stand about 5 minutes. Filter 250 ml of the solution through a Whatman 11-cm No. 42 filter paper into a 400-ml beaker. Add 5 ml of nitric acid to the beaker and heat to boiling. Add 5 ml of silver nitrate solution (1%) and boil for about 1 minute. Allow to stand in a dark place overnight. Filter through a tared sintered glass crucible of fine porosity and transfer and wash with 1% nitric acid solution. Dry at 110°C for 1 hour, cool in a desiccator, and weigh.

Calculate as follows:

$$\% \text{ Cl} = \frac{24.7 \times \text{grams of precipitate}}{\text{grams of sample in aliquot}}$$

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

4.5.10 Melting point

4.5.10.1 Apparatus. - The apparatus shall be as specified in ASTM E324 using a calibrated thermometer in accordance with American Standard Testing Method No. 69C.

4.5.10.2 Determination.-Grind a small portion (about 2 gm.) of the material so that it will pass a number 200 U.S. Standard sieve and spread it over the bottom of a glass dish which is about 2 inches in diameter. Dry the material in an oven maintained at 70 degrees C. for 2 hours or in a vacuum desiccator over sulfuric acid for at least 16 hours. Use a thin-walled capillary tube long enough to extend above the top of the bath, having an inside diameter of about 1 millimeter and sealed at one end. Fill the tube with the dried, ground sample to a depth of about 5mm., compacting the sample by tapping. Fasten the tube to the standarized thermometer so that the lower end of the tube is in contact with the bulb of the thermometer. Start the stirrer and heat the bath rapidly to about 15 degrees C. below the prescribed melting point, then adjust the heat source so that the rise in temperature does not exceed 1 degree C. per minute. Observe and record the temperature at which the material in the tube first appears to become completely liquified. When a total immersion thermometer is used and part of the liquid column is not immersed, add the following correction to the observed melting point:

Correction, degrees C. = N(T-t) X.00016

where:

N = number of degress in the exposed mecury column.
T = uncorrected melting point.
t = average temperature of the exposed column as indicated by the second thermometer.

5. PREPARATION FOR DELIVERY

5.1 Packing

5.1.1 Drums.-Unless otherwise specified in the contract or purchase order, lithium stearate shall be packed in a fiber, plywood or metal drum in accordance with Specification PPP-D-723 (Type III, Grade A), MIL-P-112, and PPP-D-729 (Type III, Full Removable Head Type), respectively. Fiber and plywood drums shall be furnished with a nominal 0.004 inch thick polyethylene liner, properly heat sealed or otherwise closed to afford protection to the contents equivalent to that given by a heat seal closure. (Alternately, an equivalent degree of protection may be furnished by suitable laminations or coatings of the inner surface of the drum.) The drums shall be closed in accordance with Specifications PPP-D-723, PP-D-729 and MIL-P-112 as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

5.1.1.2 Alternate method.-Lithium Stearate may be packed in paper shipping sacks in accordance with Table 1, Construction No. 2X of Specification UU-S-48. Closure of sacks shall be in accordance with above Specification.

5.1.2 Level C.-Lithium Stearate shall be packed to afford protection against damage during direct shipment from supply source to the first receiving activity for immediate use. Containers shall comply with Uniform Freight Classification Rules and Container Specifications for rail shipments or National Motor Freight Rules and Container Specifications for truck shipments, as applicable.

5.2 Marking.-In addition to any special marking required by the contract or purchase order, containers shall be marked in accordance with Standard MIL-STD-129.

6. NOTES

6.1 Intended Use.-The lithium stearate covered by this specification is intended for use as a lubricant in ammunition.

6.2 Ordering Data.-See MIL-A-48078 (PA).

6.3 Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, Picatinny Arsenal, ATTN: SARPA-QA-A-P, Dover, New Jersey 07801. This description should include but not be limited to the accuracy and precision of the method, test data to demonstrate the accuracy and precision and drawings of any special equipment required.

Custodian:
Army - PA

Preparing activity:
Army - PA

Project No. 6810- AA36

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T04:05Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T04:05Z
Check the source to verify that this is the currentversion before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD – 314

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

COMMANDER
Picatinny Arsenal
ATTN: SARPA-QA-A
Dover, New Jersey 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-26T04:05Z
Check the source to verify that this is the current version before use.