MIL-C-22785B
28 December 1977
SUPERSEDING
MIL-C-22785A
2 September 1971

MILITARY SPECIFICATION

CAN, BEVERAGE DISPENSER

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of 5-gallon (18.9 liters) beverage can for use in refrigerated dispensers (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

QQ-B-654	-	Brazing Alloys, Silver.
QQ-S-571	-	Solder; Tin Alloy; Lead-Tin Alloy; and Lead Alloy.
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-F-320	-	Fiberboard, Corrugated and Solid Sheet Stock (Container Grade), and Cut Shapes.

Beneficial comments (recommendations, deletions, additions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Command, Natick, MA 01760, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 7330

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-175 - Minimum Sanitary Standards, for the Equipment and Methods for the Handling of Milk and Milk Products in Bulk Milk Dispensing Operations.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

LAWS AND REGULATIONS

21 CFR 121 - Federal Food, Drug, and Cosmetic Act and Regulations Promulgated Thereunder

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402. When indicated, reprints of certain regulations may be obtained from the Federal agency responsible for the issuance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, Washington, DC 20036.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) STANDARD

A 167 - Stainless and Heat-Resisting Chromium Nickel Steel Plate, Sheet and Strip

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Standard product. The cans delivered under this specification shall be the manufacturer's current standard commercial product, except for any changes necessary to comply with specification requirements.

3.2 Materials. Materials not definitely specified shall be of the quality normally used by the manufacturer for beverage dispenser cans, provided the completed items comply with all provisions of this specification. Materials shall have no adverse effect on the health of personnel when used for the intended purpose (see 6.3 and 6.4).

3.2.1 Stainless steel. Stainless steel shall conform to the chemical composition of type 302, 303, or 304 of ASTM A167.

3.2.2 Solder. Solder shall conform to composition Sn40 of QQ-S-571.

3.2.3 Silver solder. Silver solder shall conform to grade 1 of QQ-B-654.

3.3 Design and construction. The design and construction of the beverage can and cover shall conform to the requirements and dimensions specified herein. The body, hoops, handles, cup, and nipple shall be stainless steel conforming to 3.2.1. Cans with false bottoms (more than one bottom) are not permitted. When spot welding is used, all crevices between welded parts in contact with the beverage shall be completely filled with silver solder conforming to 3.2.3 Use of solder conforming to 3.2.2 may be used on the exterior wherever necessary, provided there is no contact with the beverage. The complete dispenser shall conform to Federal Food, Drug, and Cosmetic Act (see 6.6).

* 3.3.1 Body. The can body shall be a one piece unit of seamless welded construction. The top edge shall be furnished with a closed bead. The can shall be reinforced on the outside with a continuous horizontal hoop, not less than 1-1/2 inches (38 mm) wide, spot or seam welded over the junction of the breast and cyclinder portion of the body. A hoop, containing four equally spaced drainage holes approximately 7/16-inch (11 mm) diameter, shall be spot or seam welded over the junction of the body cyclinder and bottom to form the base of the can.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

3.3.1.1 Hose nipple and hose cup. A dispensing nipple suitable for use with a 5/16-inch (8 mm) inside diameter dispensing tube conforming to MIL-STD-175, shall be silver soldered, smooth and flush to the inside bottom of the body and shall be located to provide drainage of the contents in accordance with 3.4.1. The nipple shall have a uniform, straight, smooth bore 5/16-inch, plus or minus 1/64-inch (8 plus or minus 0.4 mm) in diameter. The dispensing nipple shall be physically protected from possible damage by bumping. The cup shall be recessed behind the base hoop and spot or seam welded to the hoop.

3.3.1.2 Capacity and weight. The can shall have a liquid capacity to the capacity line of not less than 5 gallons U.S. liquid measure (18.9 liters), and shall weigh not more than 14 pounds (6.35 kg) when empty. The location of the 5-gallon (18.9 liters) level shall be indicated on the outside of the can by an indented line marked as follows: "Fill to Here".

3.3.1.3 Dimensions. The maximum outside diameter of the body can shall be 10-1/2 inches (267 mm). The maximum overall height over the cover shall be 20-3/4 inches (527 mm). The inside neck diameter shall be 7 inches plus or minus 0.010 inches (178 plus or minus 0.25 mm). The minimum thickness for stainless steel parts shall be as shown in table I.

TABLE I. Minimum thickness of stainless steel parts

Part	(Inches)	(millimeters)
Body assembly	0.036	0.91
Breast hoop	0.059	1.50
Bottom hoop	0.084	2.13
Handles	0.059	1.50
Hose cup	0.036	0.91

3.3.1.4 Handles. Each can shall be equipped with two stamped handles, spot or seam welded to the breast of the can diametrically opposite each other and within the maximum overall diameter of the can. The handles shall be shaped to permit the hand to be easily inserted and permit lifting the can, filled with liquid, without cutting or squeezing the hand. The handles shall withstand the test specified in 4.3.2 without failure or permanent deformation.

3.3.2 Cover. The cover shall be umbrella type made of a drawn cup, tapered 2° maximum for friction fit, securely spot or seam welded to a shaped top plate with a closed, rolled beaded edge. An unobstructed vent hole, 3/16-inch plus or minus 1/16-inch (4.8 plus or minus 1/6 mm) in diameter, shall be located in the cup at a maximum of 7/8-inch (22 mm) downward from the inside of the cover top. Two holes, 3/8-inch plus or minus 1/16-inch (9.5 plus or minus 1.6 mm) in diameter, shall be located diametrically opposite each other in the curved portion of the top plate.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

3.4 Performance requirements.

3.4.1 Drainage test. Liquid in the can shall drain to within 3 ounces (0.089 liters) when tested as specified in 4.3.1.

3.4.2 Durability test. The can and cover shall be capable of withstanding the test specified in 4.3.3 without breakage or separation of any kind which may cause a leak or otherwise impair efficiency.

3.5 Finish. The inside and outside surfaces of the can and cover shall have the equivalent of a number 2B mill finish or better.

3.6 Marking for identification. Each can shall be die stamped with 1/4 inch (6.4 mm) letters with the manufacturer's name or trade name, date and capacity. The surface opposite the markings shall show no signs of penetration nor shall the markings cause distortion of the adjacent surfaces.

3.7 Workmanship. All continuous welds shall be well rounded, smooth and finished equal to the adjacent surfaces. All soldered seams shall be filled, well rounded, and smooth. There shall be no sharp edges or burrs.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to insure supplies and services conform to prescribed requirements.

4.2 Inspection. Except as otherwise specified herein, sampling for inspection shall be made in accordance with MIL-STD-105.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.2.2 End item inspection. The lot shall consist of all completely fabricated cans offered for inspection at one time. The sample unit shall be one completely finished can with cover.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

4.2.2.1 Visual examination. Visual examination of the cans and covers shall be in accordance with table II. Inspection level shall be II, with an acceptable quality level (AQL) of 2.5 for major defects and 6.5 for total defects, expressed in terms of defects per hundred units.

TABLE II. Classification of visual defects

Examine	Defect	Classification Major	Minor
Finish	Can or cover not finished as specified		
	(Food contact surfaces)	X	
	(Other than food contact surfaces)	X	
	Stained, discolored, not uniform	X	
	Deep scratches or tool marks on the inner surface clearly noticeable	X	
	Pitted, scratched, or tool marks on the exterior surface, clearly noticeable	X	
	Dirt, smudge, grease or foreign matter	X	
Construction and workmanship	Any component not attached as specified	X	
	Split, crack, fracture, dent, puncture, or wrinkle affecting serviceability	X	
	Dent or wrinkle not affecting appearance	X	
	Any crack, crevice, hole or opening on inside surface of can	X	
	Sharp edges or burrs	X	
	Component missing	X	
	Handle loose, damaged, or not welded in proper location	X	
	Breast hoop omitted	X	
	Bottom hoop omitted	X	
	Drainage holes in bottom hoop not as specified	X	
	Hose cup not as specified	X	
	Cover does not fit snugly in neck can	X	
	Any hole in cover not as specified	X	
	Cover top and collar not joined by welding	X	
	5-gallon (18.9 liter) liquid level not identified	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

TABLE II. Classification of visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Welding or soldering	Visible seam weld	X	
	Not fused	X	
	Cracked or fractured	X	
	Excess flux or splatter not removed	X	
	Excess material not ground smooth	X	
	Broken or burned through	X	
Identification marking	Missing, illegible		X
	Incorrect or incomplete		X
	Wrong location		X

4.2.2.2.2 Dimensional and weight examination. Examination shall be made of the end item for defects in dimensions and weight. Any deviation from specified requirements shall constitute a defect. The inspection level shall be S-2 with an (AQL) of 4.0 expressed in terms of defects per hundred units.

4.2.2.3 End item testing. The initial production unit shall be tested in accordance with 4.3.1 through 4.3.3. Any nonconformance shall be cause for rejection of the lot. The contractor shall perform tests on production units in accordance with 4.3.1 through 4.3.3. The inspection level shall be S-2 with an AQL of 2.5 expressed in terms of defects per hundred units.

4.2.3 Packaging inspection. An inspection shall be made to determine that packing and marking as required by section 5 are complied with. Defects shall be as indicated in table III. The sample unit shall be one shipping container fully prepared for delivery except it need not be closed. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 2.5, expressed in terms of defects per hundred units.

TABLE III. Examination of packaging

Examine	Defect
Markings	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Component missing, damaged, or otherwise defective.
Contents	Number per container is more or less than required,
Workmanship	Bulged or distorted containers.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

4.3 Test methods.

4.3.1 Drainage test. An empty can shall be placed on a level plane and a measured amount of water at least 1 gallon (3.8 liters) poured into the can. The water shall then be drained through the dispenser nozzle and measured. A differential of more than 3 liquid ounces (0.089 liters) between the measurements shall be considered noncompliance with 3.4.1.

4.3.2 Handle test. The container shall be suspended by one handle, with a load of 80 pounds (36 kg) suspended from the other handle for at least 15 minutes. Failure of any weld, or permanent deformation or rupture of either handle or of the can body shall be considered noncompliance with 3.3.1.4.

4.3.3 Durability test. The can shall be filled with water to rated capacity, covered, and tested in a machine that will permit the container to fall free through a trap door device from a height of not less than 2 feet (610 mm) onto a flat stone, brick, or concrete floor. The covered can shall be placed in an identical position for each drop and shall be dropped a total of five times as follows: The can shall be level for the first drop; thereafter, a 3-inch (76 mm) cube of wood shall be positioned under the bottom rim of the can to vary the angle of each fall. For each successive drop, the cube of wood shall be moved 90 degrees in a clockwise direction from the previous drop. No restraining guide lines shall be used. Opening of seams, breakage of any part, cover dropping off, or leakage will be considered as noncompliance with 3.4.2.

5. PACKAGING

5.1 Packing. Packing shall be level A, B, or C as specified (see 6.2).

* 5.1.1 Level A packing. Four cans, with covers securely in place, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type SF, grade V2s of PPP-B-636. The cans shall be separated by means of a full height partition fabricated from fiberboard conforming to class WWVR, grade V3c of PPP-F-320. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

5.1.2 Level B packing. Four cans, with covers securely in place, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF, variety SW or SF, class domestic, grade 200 of PPP-B-636. The cans shall be separated by means of a full height partition fabricated from fiberboard conforming to type CF, variety SW, class domestic, grade 200 of PPP-F-320. Each shipping container shall be closed in accordance with method II of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

5.1.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the fiberboard shipping container shall be grade V3c, V3s, or V4s, fabricated and closed in accordance with method III as specified in the appendix of PPP-B-636.

5.1.3 Level C packing. The cans, with covers, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall be in accordance with Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.2 Marking. In addition to any special marking required by the contract or order, shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The beverage can covered by this specification is intended for use with refrigerated bulk milk dispensers of the type covered by OO-D-450.

6.2 Ordering data. Procurement documents shall specify the following:

(a) Title, number, and date of this specification.
(b) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.1.2.1).
(c) Selection of the applicable level of packing (see 5.1).

6.3 Material and health. Questions pertaining to the adverse effect of materials (see 3.2) on the health of personnel shall be referred to the medical department of the Service for which the dispensers are being procured.

6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.2).

6.5 Approval. The contracting officer should contact any of the regional offices of the Department of Health, Education and Welfare to arrange for Public Health Service approval.

6.6 Metric equivalents. Metric equivalents, indicated in parentheses throughout this document, are based on practices, conversion factors, and symbols specified in ASTM E 380 Standard for Metric Practice, and are for information only. In each instance, the value stated in US customary units shall be controlling.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

6.7 Changes from previous issue. The margins of this specification have been marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - YD
Air Force - 99

Preparing activity:

Army - GL

Project No. 7310-0429

Review activity:

DLA - GS

User activity:

Navy - MC

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-22785B - Can, Beverage Dispenser

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1426 1 OCT 76 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK RESEARCH and DEVELOPMENT COMMAND
NATICK, MASSACHUSETTS 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
DRXNM-TD G

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD-314

U.S. MAIL

Commander
US Army Natick Research and Development Command
ATTN: DRXNM-TD G
Natick, MA 01760

NATICK OP 1 JUL 77

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:59Z
Check the source to verify that this is the current version before use.