INCH-POUND
MIL-DTL-43307C
3 March 2025
SUPERSEDING
MIL-C-43307B
28 January 1972

DETAIL SPECIFICATION

CORD, NYLON, SOLID BRAID, GENERAL PURPOSE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a solid braided nylon cord.

1.2 Classification. The cord is braided in the size (diameter) specified (see table I and 6.2).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specification and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

FEDERAL STANDARDS

FED-STD-191 - Textile Test Methods

COMMERCIAL ITEM DESCRIPTIONS

A-A-59622 - Tags, Shipping and stock

(Copies of these documents are available online at https://assist.dla.mil).

Comments, suggestions, or questions on this document should be addressed to DLA Troop Support – Construction and Equipment (C&E) (ATTN: Code FCSB), 700 Robbins Avenue Philadelphia, PA 19111-5096 or e-mail to CE_Standardization@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 4020

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AMERICAN SOCIETY FOR QUALITY (ASQ)

ASQ-Z1.4 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of this documents are available online at https://www.asq.org or the American Society for Quality, 600 North Plankinton Avenue, Milwaukee, WI 53203.)

2.4 Order of Precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.2.

3.2 Government and contractor purchases. The requirements specified in 3.8 and 3.9 apply only to cord purchased directly by the Government. All other requirements apply both to cord purchased by a contractor as a component for an end item and to cord purchased directly by the Government.

3.3 Standard sample. The cord shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6. 4).

3.4 Material. The yarn used in the fabrication of the cord shall be a bright, multi-filament nylon yarn. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.5 Construction and physical requirements. The cord shall be of solid braid construction (see 6.4) and the natural or dyed cord shall conform to the requirements specified in table I when tested as specified in 4.3.3.

TABLE I. Physical requirements.

Diameter (size) ±.0156 inches	Number of strands (minimum)	Breaking Strength Pounds (minimum)	Length per pound feet (minimum)
.0938	9	250	380
.125	9	400	220
.1563	12	540	144
.1875	12	720	99
.2188	12	900	72
.250	12	1100	57
.3125	12	1900	36
.375	12	2700	24

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

3.6 Color. Unless otherwise specified, the color of the cord shall be natural. When a specific color is required, it shall be as specified (see 6.2) and shall match the standard sample when available for the applicable shade when tested as specified in 4.3.3.

3.6.1 Colorfastness. The dyed cord shall show fastness to weathering equal to or better than the standard sample when tested as specified in 4.3.3. When no standard sample has been established the dyed cord shall show good fastness to weathering when tested as specified in 4.3.3.

3.7 Put-up and length. Unless otherwise specified (see 6.2), the cord shall be furnished without knots or splices on spools (reels) in the minimum lengths specified in table II. Each spool (reel) shall contain no more than three pieces, and no piece shall be less than 100 feet in length or no more than two pieces with no minimum length applicable. The cord shall be wound on the spools (reels) so that each turn and layer is free from entanglement. The ends of the cord shall be heat sealed to prevent fraying. A plus tolerance of 10.0 percent shall be allowed on the length of spool (reel) specified.

3.8 Identification. Each spool (reel) of cord shall have a ticket (identification tag) or label attached to it for identification purposes. The ticket shall be in accordance with A-A-59622. When labels are used, the label shall be attached in such a manner as to remain in place and be clearly legible until all cord has been removed. All ticket or label entries shall be legibly printed, stamped, or typed with water insoluble ink. The ticket or label shall contain the following information:

Stock Number
Nomenclature
Size (diameter)
Specification number
Length
Contract number and date
Contractor's name

3.9 Workmanship. The end item shall conform to the quality of product established by this specification.

TABLE II. Put-up spool reel length.

Diameter In inches	Length of spool (reel) feet (minimum)
.0938	3000
.125	3000
.1563	3000
.1875	3000
.2188	2000
.250	2000
.3125	1000
.375	1000

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2).
b. Conformance inspection (see 4.3).

4.2 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.3.2.1 and 4.3.2.2 and tested for the characteristics specified in 4.3.3.

4.3 Conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with ASQ-Z1.4.

4.3.1 Component and material inspection. Components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3.1.1 Component and material certification. A certificate of compliance may be acceptable as evidence that the material conforms to the requirements specified in 3.4.

4.3.2 End item examination.

4.3.2.1 End item visual examination. The cord shall be examined for the defects listed in table III. All defects shall be counted regardless of their proximity to each other. The lot size shall be expressed in units of spools or reels of cord. The sample unit shall be one spool or reel of cord. Ten percent of the total footage, but not less than 100 feet, shall be examined on each spool or reel of cord in the sample. The inspection level shall be I.

Table III. End item visual defects.

Examine	Defect	Classification Major	Classification Minor
Appearance and workmanship	Any cut	101	
	Abraded surface, chafed or damaged	102	
	Kinks or unevenly braided resulting in open places, breaks in continuity of braids, or soft spots	103	
	Loosely braided	104	
	Broken, loose, or projecting strand or end	105	
	Not equal to standard sample for roundness and firmness	106	
Color	Other than specified	107	
	Not uniform		201
Cleanness	Spot or stain clearly visible 1/		202
Identification ticket or label	Omitted, incorrect, illegible, insecurely attached		203
	Ticket or label not as specified		204

1/ At normal inspection distance (approximately 3 feet).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

4.3.2.2 Length and winding examination. The end item shall be examined for the defects listed below. The lot size shall be expressed in units spools or reels of cord. The sample unit shall be one spool or reel of cord. For lots consisting of 500 or fewer units, the sample size shall be 10. Defects shall be as listed below. The inspections level shall be S-3.

Defects

Length less than specified or more than 10 percent in excess of length specified.

Length of cord on the spool (reel) is less than marked on the ticket or label.

Improperly or not firmly wound resulting in kinking, knotting, entangling, or slippage during unwinding, or otherwise affecting free unhampered unwinding of cord.

Put-up not as specified.

Any end not heat sealed.

Any spool (reel) found to contain more than three pieces.

Any piece less than 100 feet in length (except when there are only two pieces per spool).

Any knot or splice.

4.3.3 End item testing. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table IV shall be followed. When the data in the "Number of determinations" and "Results reported as" columns are not specified in table IV, they shall be as required by the referenced test method. The physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The lot size shall be expressed in units of spools or reels of cord, as applicable. The sample unit shall be one spool or reel of cord. The sample size shall be in accordance with table V. All test reports shall contain the individual values utilized in expressing the final results. The lot shall be unacceptable if one or more units fail to meet any requirement specified. Tests to determine compliance with specification requirements, including quantity of delivery, may be made under prevailing atmospheric conditions. In cases of dispute, tests shall be made upon material which has reached equilibrium under standard conditions as defined in FED-STD-191.

4.3.3.1 Determination of color matching. The shade of the dyed cord shall match the standard sample under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin (see 6.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

TABLE IV. End Item tests.

Characteristics	Requirement paragraph	Test method	No. of deter. per sample unit	Results reported as
Construction (solid braid without core)	3.5	Visual	1	Pass or fail
Diameter	3.5	6002	-	-
Number of strands	3.5	Visual	1	Pass or fail
Breaking strength	3.5	6016	-	-
Length per pound	3.5	6004	-	-
Color matching	3.6	5671.1 1/	-	Pass or fail
Colorfastness to weathering	3.6.1	5671.1/	-	Pass or fail

1/ The time of exposure shall be 40 standard fading hours.

.

TABLE V. Sample size.

Lot size (spools or reels)	Sample size (sample units)
800 or less	2
801 up to and including 22,000	3
22,000 and over	5

5. PACKAGING

5.1. Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of material is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. Cordage covered by this specification is intended for use in miscellaneous tentage and equipage applications.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Size (diameter) required (see 1.2).
c. Color (shade) required if other than natural (see 3.6).
d. Put-up if other than specified (see 3.7).
e. Length required if other than specified (see 3.7).
f. Packaging requirements (see 5.1).

6.3 First article. When a first article is required, it should be inspected and approved under the appropriate provisions of FAR 52.209-4. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Standard Sample. For access to the standard sample, address the contracting activity issuing the invitation for bids or request for proposal.

6.5 Filler core yarns. Suppliers may use filler core yarns in the construction of the cord as long as the finished cord is constructed to form a round, even, solid cord conforming to all other specified requirements.

6.6 Subject term (key word) listing.

Cordage
Equipage
Tent

6.7 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - GL
Navy - SH
DLA - CQ

Review activities:
Army - AR, CR4, EA, MD, MI
Navy - MC

Preparing Activity:
DLA – CQ

(Project 4020-2025-004)

NOTE: The activities listed above were interested in this document as of the date of document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:07Z
Check the source to verify that this is the current version before use.