MIL-P-43325A
5 September 1969
SUPERSEDING
MIL-P-43325(GL)
6 April 1965

MILITARY SPECIFICATION

PAPER, BOOK

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope.- This specification covers groundwood offset book paper, opacified book paper and vellum-finish book paper, and reflects requirements parallel to the Government Paper Specification Standards of the Joint Committee of Printing (see 6.1).

1.2 Classification.- Book paper covered by this specification shall be of the following types, as specified (see 6.2).

Type I - Groundwood offset book (JCP-A-70).
Type II - Opacified book (JCP-A-80).
Type III - Vellum-finish book (JCP-A-90).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards.- The following specifications and standards, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of specifications, standards and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 9310

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated the issue in effect on date of invitation for bids or request for proposal shall apply.

JOINT COMMITTEE ON PRINTING PUBLICATIONS

GOVERNMENT PAPER SPECIFICATION STANDARDS

(Application for copies should be addressed to the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.)

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY (TAPPI) PUBLICATIONS:

T 401 m-60	-	Fiber Analysis of Paper and Paperboard.
T 402 m-49	-	Conditioning Paper and Paperboard for Testing.
T 403 ts-63	-	Bursting Strength of Paper.
T 408 os-61	-	Rosin in Paper and Paperboard.
T 409 os-61	-	Machine Direction of Paper.
T 410 os-68	-	Weight per Unit Area (Basis Weight or Substance) of Paper and Paperboard.
T 411 os-68	-	Thickness (Caliper) of Paper and Paperboard.
T 417 os-68	-	Proteinaceous Nitrogenous Materials in Paper (Qualitative).
T 423 su-68	-	Folding Endurance of Paper (Schopper Tester).
T 425 m-60	-	Opacity of Paper.
T 435 su-68	-	Hydrogen for Concentration (pH) of Paper Extracts - Hot Extraction Method.
T 452 m-58	-	Brightness of Paper and Paperboard.
T 459 su-65	-	Wax Pick Test of Paper.

(Application for copies should be addressed to the Technical Association of the Pulp and Paper Industry, 360 Lexington Avenue, New York, New York 10017.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Standard sample.- The color, finish, formation and cleanliness of the paper must conform to the standard sample as adopted by the Joint Committee on Printing and furnished by the contracting officer.

3.2 Material.- The three types of book paper covered by this specification shall conform to the requirements of the Joint Committee on Printing Publications, Government Paper Specification Standards as follows:

Type I conforming to JCP-A-70.
Type II conforming to JCP-A-80.
Type III conforming to JCP-A-90.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

3.3 Workmanship.- All types of paper covered by this specification shall be clean and free from any dirt, oil spot, sliver, shive, scale, scab, mottle, hole, tear, cut, wrinkle, fold, chafe mark, scuff mark, slime spot, lump, corrugation, dog ear, foreign or undigested matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection.- In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended or qualified in this specification or applicable purchase documents.

4.2.2 Inspection of the end item.-

4.2.2.1 Examination of the end item.- The end item shall be examined for the defects set forth in the applicable subparagraphs at the inspection levels and acceptable quality levels (AQL's) set forth in 4.2.2.1.7. Random samples shall be drawn from each lot of the end item for examination of visual, workmanship, dimensional, count and preparation for delivery defects. The lot size shall be expressed in units of reams of one type and size of book paper for examination in 4.2.2.1.1 through 4.2.2.1.4 and in units of shipping containers for examination in 4.2.2.1.5.

4.2.2.1.1 Examination for visual defects.- The sample unit for this examination shall be one sheet. Both sides of the sheet shall be examined.

Examine	Defects
Appearance	Cleanliness, finish or formations (as applicable) not equal to or better than standard sample. Color not uniform on both sides; not equal to standard sample. Presence of dirt or oil spots, slivers, shives, scales, shiners, scabs or mottle larger than or more in number than in the standard sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

4.2.2.1.2 Examination for defects in workmanship.- The sample unit for this examination shall be one sheet.

Examine	Defects
Workmanship	Edges not trimmed clean; ragged, torn, uneven or crushed edges. Paper curls, does not lie flat, i.e., not flat after reasonable flexing. Any hole, tear, cut, wrinkle, fold, chafe mark, scuff mark, slime spot, lump, corrugation or dog ear. Presence of lint, fuzz or any particles which will pick, lift, fluff or pile on the press blanket. Any foreign or undigested matter. Splice within a sheet. Partial sheet.

4.2.2.1.3 Examination for defects in dimensions.- The sample unit for this examination shall be one sheet.

Examine	Defects
Sheet size	Less than specified in either direction.
Sheets 8-1/2 by 14 inches or less	Oversize by more than 1/16 inch in either dimension from size specified.
Sheets over 8-1/2 by 14 inches	Oversize by more than 1/8 inch in either dimension from size specified.
Squareness	Dimensional variation exceeds 1/32 inch for sheets 32 inches or less in length, or exceeds 1/16 inch for sheets over 32 inches in length.

4.2.2.1.4 Examination for count.- The lot shall be unacceptable if the average count per package or quantity between marker, when paper is skid packed, is less than the specified or indicated quantity.

4.2.2.1.5 Examination for color uniformity.- The sample unit for this examination shall be one shipping container.

Examine	Defects
Color uniformity	Color not uniform throughout shipping container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

4.2.2.1.6 Examination of preparation for delivery.- An examination shall be made in accordance with the provisions of PPP-P-25 to determine that packaging, packing and marking comply with the requirements of Section 5 of this specification.

4.2.2.1.7 Inspection levels and acceptable quality levels (AQL's) for examinations.- The inspection levels, for purposes of determining the sample size, and the acceptable quality levels (AQL's) expressed in defects per 100 units shall be as follows:

Examination paragraph	Inspection level	AQL
4.2.2.1.1	I	2.5
4.2.2.1.2	III	0.25
4.2.2.1.3	S-2	2.5
4.2.2.1.4	S-2	N.A.
4.2.2.1.5	S-2	2.5

4.2.3 Testing of the end item.- The end item shall be tested for the applicable characteristics in table I. The tests shall be performed in accordance with the TAPPI test method specified. All specimens shall be conditioned to equilibrium in accordance with TAPPI method T 402 m-49. The sample unit shall be 1,000 square inches of paper. The lot size shall be expressed in units of reams of paper of one type and size. The sample size shall be drawn at inspection level S-1 of MIL-STD-105. There shall be no failure to meet the composite, sample unit or lot average requirements. A composite shall consist of small portions taken from all sample units and combined in a single sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING OF THE END ITEM

TABLE I

CHARACTERISTIC	Specification Reference		Requirements Applicable To		Number Determinations Per Sample Unit	Results Reported As		Inspect Level	AQL
	Requirement	Test Method	Individ Unit	Lot Aver		Pass or Fail	Numerically to Nearest		
Stock	3.2	T401m-60		X	2 on composite		5 percent		
Acidity (except type I)	3.2	T435su-68		X	1 on composite		0.1 pH		
Basis weight	3.2	T410os-68		X	2 on composite		0.1 pound		
Bursting strength (except type II)	3.2	T403ts-63		X	10		point		
Folding endurance (type II only)	3.2	T423su-68		X	10		fold		
Thickness	3.2	T411os-68		X	20		0.0001 inch		
Opacity	3.2	T425m-60		X	5		0.1 percent		
Brightness (except type I)	3.2	T452m-58		X	6		0.1 percent		
Pick	3.2	T459su-65	X		1	X			
Grain	3.2	T409os-61	X		1	X			
Sizing (except type I)	3.2	T408os-61 or T417os-68 as applicable	X		1	X			

AMXRE Form 598
8 February 1965

Source: https://assist.dla.mil -- Downloaded: 20260-21T21:10Z -
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging, packing and marking.- Packaging, packing and marking for levels A, B, and C shall be in accordance with PPP-P-25 (see 6.2), except that in table III add the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

REAM						SHIPPING CONTAINER			
Nomenclature	Size inches	Weight pounds	Approx thickness inches	Wrapped	Ream marked w/marker placed length-wise	Approx inside length and width (inside of liner)	Quantity	Approx net weight pounds	Type
Paper, Book MIL-P-43325 Type I (25 x 38 - 50/500)	42 x 32	70	2	No	Yes	42 x 32	3 reams	210	Fiberboard
Paper, Book MIL-P-43325 Type II (25 x 38 - 60/500)	21 x 16	21	2.25	No	Yes	21 x 32	8 reams	168	Fiberboard
	42 x 32	84.5	2.25	No	Yes	42 x 32	2 reams	169	Fiberboard
Paper, Book MIL-P-43325 Type III (25 x 38 - 50/500)	8 x 10-1/2	4.5	2.1	No	Yes	16 x 10-1/2	12 reams	54	Fiberboard
	21 x 16	17.5	2.1	No	Yes	21 x 32	8 reams	140	Fiberboard
	38 x 25	50	2.1	No	Yes	38 x 25	4 reams	200	Fiberboard
	42 x 32	70.5	2.1	No	Yes	42 x 32	2 reams	141	Fiberboard

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use.-

6.1.1 Type I papers are intended to be used for minimum quality face and back offset printing of books, pamphlets, catalogs, folders, circulars, etc., of a temporary nature. Printed matter may include text and line illustrations.

6.1.2 Type II papers are intended to be used for high quality multicolor face and back letterpress and offset printing of books, pamphlets, folders, etc. Printed matter may include text, line illustrations, halftones up to 133-line screen and solid reverses. Not suitable for halftone production by letterpress printing.

6.1.3 Type III papers are intended to be used for high quality face and back letterpress and offset printing of books, pamphlets, folders, etc. Printed matter may include text, line illustrations, halftones up to 133-line screen and solid reverses. Not suitable for halftone production by letterpress printing.

6.2 Ordering data.- Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type weight and size required (see 1.2).
(c) Grain direction.
(d) Pressroom conditions.
(e) Selection of the applicable levels of packaging and packing (see 5.1).

6.3 Standard comparison samples may be obtained upon application to the procuring activity issuing the invitation for bids.

Custodians:

Army - GL
Air Force - 84

Review activities:

Army - CE, ME

User activities:

Army - MD
Navy - SA

Preparing activity:

Army - GL

Project No. 9310-0064

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development
Laboratories
ATTN: DRDNA-ES (Mr. D. Luppino)
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.