INCH-POUND

MIL-P-43325B
31 December 1990
SUPERSEDING
MIL-P-43325A(GL)
5 September 1969

MILITARY SPECIFICATION

PAPER, BOOK

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers white groundwood offset book paper, opacified book paper and vellum-finish book paper, and reflects requirements parallel to the Government Paper Specification Standards of the Joint Committee of Printing (see 6.1).

1.2 Classification. The book paper shall be of the following types and sizes, as specified (see 6.2).

Type I	-	Groundwood offset book (JCP-A-70)
Type II	-	Opacified book (JCP-A-80)
Type III	-	Vellum-finish book (JCP-A-90)
Size 1	-	8-1/2 inches by 11 inches (type III only)
Size 2	-	21 inches by 16 inches (types II and III only)
Size 3	-	38 inches by 25 inches (type III only)
Size 4	-	42 inches by 32 inches (types I, II, and III)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5019 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 9310

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

PPP-P-25 - Printing and Stationery Paper, Packaging and Packing of

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CONGRESS OF THE UNITED STATES, JOINT COMMITTEE ON PRINTING PUBLICATIONS, GOVERNMENT PAPER SPECIFICATION STANDARDS

JCP-A-70 - Recycled Offset Book
JCP-A-80 - Opacified Offset Book
JCP-A-90 - Vellum-Finish Book, White and Colored

(Copies may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402-0001.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY (TAPPI) PUBLICATIONS:

T 401	-	Fiber Analysis of Paper and Paperboard
T 402	-	Conditioning and Testing Atmospheres for Paper, Board, Pulp Handsheets, and Related Products
T 403	-	Bursting Strength of Paper
T 408	-	Rosin in Paper and Paperboard
T 409	-	Machine Direction of Paper and Paperboard
T 410	-	Grammage of Paper and Paperboard (Weight Per Unit Area)
T 411	-	Thickness (Caliper) of Paper and Paperboard and Combined Board
T 417	-	Proteinaceous Nitrogenous Materials in Paper (Qualitative)
T 423	-	Folding Endurance of Paper (Schopper Type Tester)
T 425	-	Opacity of Paper
T 435	-	Hydrogen Ion Concentration (pH) of Paper Extracts - Hot Extraction Method
T 452	-	Brightness of Pulp, Paper and Paperboard (Directional Reflectance at 475 nm)
T 459	-	Surface Strength of Paper (Wax Pick Test)

(Copies may be obtained from the Technical Association of the Pulp and Paper Industry, (TAPPI) Standards, Technology Park/Atlanta, P.O. Box 105113, Atlanta, GA 30348).

(Non-Government standards and other publications are normally available from organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3), in accordance with 4.3.

3.2 Standard sample. The color, finish, formation and cleanliness of the paper must conform to the standard sample as adopted by the Joint Committee on Printing and furnished by the contracting officer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

3.3 Material. The three types of book paper covered by this specification shall conform to the requirements of the Joint Committee on Printing Publications, Government Paper Specification Standards as follows:

Type I conforming to JCP-A-70
Type II conforming to JCP-A-80
Type III conforming to JCP-A-90

It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.4 Workmanship. The book paper shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)
b. Quality conformance inspection (see 4.4)

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3, and shall be tested for the characteristics specified in 4.4.5.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 End item visual examination. The end items shall be examined for the defects listed below. Both sides of the paper shall be examined. The lot size shall be expressed in units of sheets of paper. The sample unit shall be one sheet of paper. The inspection level shall be I, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Appearance	Cleanliness, finish or formations (as applicable) not equal to or better than standard sample
	Color not uniform on both sides; not equal to standard sample
	Presence of dirt or oil spots, slivers, shives, scales, shiners, scabs or mottle larger than or more in number than in the standard sample
Workmanship	Edges not trimmed clean; ragged, torn, uneven or crushed edges
	Paper curls, does not lie flat, i.e., not flat after reasonable flexing
	Any hole, tear, cut, wrinkle, fold, chafe mark, scuff mark, slime spot, lump, corrugation or dog ear
	Presence of lint, fuzz or any particles which will pick, lift, fluff or pile on the press blanket
	Any foreign or undigested matter
	Splice within a sheet
	Partial sheet

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

4.4.3 End item dimensional examination. The end items shall be examined for the defects listed below. The lot size shall be expressed in units of sheets of paper. The sample unit shall be one sheet of paper. The inspection level shall be S-2, and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Sheet size	Less than specified in either direction
Sheets 8-1/2 by 14 inches or less	Oversize by more than 1/16 inch in either dimension from size specified
Sheets over 8-1/2 by 14 inches	Oversize by more than 1/8 inch in either dimension from size specified
Squareness	Dimensional variation exceeds 1/32 inch for sheets 32 inches or less in length, or exceeds 1/16 inch for sheets over 32 inches in length

4.4.4. End item examination for color uniformity. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2, and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Color uniformity	Color not uniform throughout shipping container

4.4.5 Testing of the end item. The end item shall be tested for the applicable characteristics in table I. The tests shall be performed in accordance with the TAPPI test methods specified. All specimens shall be conditioned to equilibrium in accordance with TAPPI method T 402. The sample unit shall be 1,000 square inches of paper. The lot size shall be expressed in units of reams of paper of one type and size. The sample size shall be drawn at inspection level S-1 of MIL-STD-105. There shall be no failure to meet the composite, sample unit or lot average requirements. A composite shall consist of small portions taken from all sample units and combined in a single sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS FOR TESTING OF THE END ITEM

TABLE I

CHARACTERISTIC	Requirement Paragraph	Test Method	Requirement Applicable To: Individ unit	Requirement Applicable To: Lot aver	Number of determinations per sample unit	Results reported as	Inspect Level	AQL
Stock	3.3	T401		X	2 on composite	to nearest 5 percent		
Acidity (except type I)	3.3	T435		X	1 on composite	to nearest 0.1 pH		
Basis weight	3.3	T410		X	2 on composite	to nearest 0.1 pound		
Bursting strength	3.3	T403		X	10	to nearest point		
Thickness	3.3	T411		X	20	to nearest 0.0001 inch		
Opacity	3.3	T425		X	5	to nearest 0.1 percent		
Brightness (except type I)	3.3	T452		X	6	to nearest 0.1 percent		
Pick	3.3	T459	X		1	pass or fail		
Grain	3.3	T409	X		1	pass or fail		
Sizing (except type I)	3.3	T408 or T417 as applicable	X		1	pass or fail		

AMXRE Form 598
9 February 1965

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

4.5. Packaging inspection. An examination shall be made in accordance with the provisions of PPP-P-25 to determine that packaging, packing, and marking comply with the requirements of section 5.

5. PACKAGING

5.1 Packaging, packing and marking. Packaging, packing and marking for levels A, B, and C shall be in accordance with the applicable requirements of PPP-P-25 (see 6.2), except that the following shall be added to table II (packaging and packing printed papers) of PPP-P-25:

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

TABLE II. Packaging and packing printing paper

Nomenclature	Ream					Shipping container			
	Size	Weight	Approximate thickness	Wrapped	Ream marked with marker placed length-wise	Approximate inside length and width (inside of liners)	Quantity	Approximate net weight	Type
	Inches	Pounds	Inches			Inches		Pounds	
Paper, Book MIL-P-43325 Type I (25 x 38 - 50/500)	42 x 32	70	2	No	Yes	42 x 32	3 reams	210	Fiberboard
Paper, Book MIL-P-43325 Type II (25 x 38 - 60/500)	21 x 16	21	2.25	No	Yes	21 x 32	8 reams	168	Fiberboard
	42 x 32	84.5	2.25	No	Yes	42 x 32	2 reams	169	Fiberboard
Paper, Book MIL-P-43325 Type III (25 x 38 - 50/500)	8-1/2 x 11	4.9	2.1	No	Yes	17 x 11	12 reams	59	Fiberboard
	21 x 16	17.5	2.1	No	Yes	21 x 32	8 reams	140	Fiberboard
	38 x 25	50	2.1	No	Yes	38 x 25	4 reams	200	Fiberboard
	42 x 32	70.5	2.1	No	Yes	42 x 32	2 reams	141	Fiberboard

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use.

6.1.1 Type I. Papers are intended to be used for minimum quality face and back offset printing of books, pamphlets, catalogs, folders, circulars, etc., of a temporary nature. Printed matter may include text and line illustrations.

6.1.2 Type II. Papers are intended to be used for high quality multi-color face and back letterpress and offset printing of books, pamphlets, folders, etc. Printed matter may incude text, line illustrations, halftones up to 133-line screen and solid reverses. Not suitable for halftone production by letterpress printing.

6.1.3 Type III. Papers are intended to be used for high quality face and back letterpress and offset printing of books, pamphlets, folders, etc. Printed matter may include text, line illustrations, halftones up to 133-line screen and solid reverses. Not suitable for halftone production by letterpress printing.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Type, weight, and size (see 1.2).
c. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
d. When a first article is required (see 3.1, 4.3, and 6.3).
e. Grain direction (see 3.3).
f. Pressroom conditions (see 3.3).
g. Selection of the applicable levels of packaging and packing (see 5.1).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Sample. For access to samples, address the contracting activity issuing the invitation for bids or request for proposal.

Source: https://assist.dla.mil -- Downloaded: 20260-21T21:10Z
Check the source to verify that this is the current version before use.

6.5 Subject term (key word) listing.

Groundwood
Information
Manual
Opacified
Vellum

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Air Force - 99
Navy - SA

Review activities:

Army - MD, ME
Air Force - 84

Preparing activity:

Army - GL

(Project 9310-0108)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-P-43325B	1990 December 31

3. DOCUMENT TITLE
PAPER, BOOK

4. NATURE OF CHANGE (*Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.*)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)

7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

NAME	b. TELEPHONE (Include Area Code)
U.S. Army Natick RD&E Center	(1) Commercial: 508-651-4532 (2) AUTOVON: 256-4532
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-IRT Natick, MA 01760-5019	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 20240-21121:102
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:10Z
Check the source to verify that this is the current version before use.