MIL-S-43317B

29 July 1977

SUPERSEDING
MIL-S-43317A(GL)
3 March 1972

MILITARY SPECIFICATION

SCARF, NECKWEAR, WOMAN'S, ACRYLIC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for one type and size of woman's acrylic neckwear scarf.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

V-T-276	-	Thread, Cotton
PPP-B-566	-	Boxes, Folding, Paperboard
PPP-B-636	-	Boxes, Shipping, Fiberboard
PPP-B-665	-	Boxes: Paperboard, Metal Edged and Components
PPP-B-676	-	Boxes, Setup
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing

Beneficial comments (recommendations, additions, deletions, and any pertinent data which may be used in improving this document should be addressed to: US Army Natick Research and Development Command, Natick, MA 01760, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8445

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods
FED-STD-751 - Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105 - Sampling Producures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Associations, Inc., Traffic Department, 1616 P Street, N.W., Washington, DC 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

3. REQUIREMENTS

3.1 Samples.

3.1.1 Guide sample . Guide samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this specification may appear in the sample, in which case this specification shall govern.

3.1.2 Standard sample. The scarfs shall match the standard sample for shade, and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3) .

3.2 Materials.

3.2.1. Fiber. The fiber shall be acrylic, semi-dull and of a suitable staple length and shall conform to the requirements of table 1. Testing shall be as specified in 4.2.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

3.2.2 Yarns. The warp and filling shall be 2 ply yarns of a suitable twist and shall conform to the requirements of table I (see 6.4). Testing shall be as specified in 4.2.1.

3.3 Color of cloth. The finished cloth shall be chemically bleached white and may be supplemented with optical brighteners which fluoresce to the blue region. The degree of whiteness shall match the standard sample. The finished bleached cloth shall not discolor to a degree greater than that shown by the standard sample when tested as specified in 4.2.1. When no standard sample is available, the discoloration shall be not less than "good" rating when tested as specified in 4.2.1.

3.3.1. Matching. The color of the finished cloth shall match the standard sample under artificial daylight having a color temperature of 7500 kelvin and shall be a good approximation of the standard sample under incandescent lamplight at 2800 kelvin.

3.3.2. Colorfastness. The finished cloth shall show colorfastness to light equal to or better than the standard sample when tested as specified in 4.2.1. The finished bleached cloth shall not discolor to a degree greater than that shown by the standard sample. When no standard sample is available, the discoloration shall not be less than "good" rating.

3.4 Physical requirements. The finished cloth shall conform to the physical requirements specified in table I when tested as specified in 4.2.1.

TABLE I. Physical requirements

Characteristic	Minimum
Weight, ounces per square yard (g/m^2)	3.8 (129)
Yarns per inch (yarns/cm.)	
Warp	28 (11)
Filling	20 (8)
Breaking strength pounds (N)	
Warp	40 (178)
Filling	25 (111)

3.5 Weave. The weave shall be a crowfoot satin, repeating on 4 ends and 4 picks. Testing shall be as specified in 4.2.1 (see 6.5 for diagram of weave).

3.6 Finish. The finish of the cloth shall match the finish of the standard sample. When no standard sample is available, the finish must be approved by the contracting officer prior to approval.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

3.6.1 Nonfibrous materials. The starch and protein content of the finished cloth, including chloroform-soluble and water-soluble material shall be not more than 2.0 percent when tested as specified in 4.2.1.

3.7 pH. The pH value of the finished cloth shall be not less than 5.0 percent nor more than 8.5 percent when tested as specified in 4.2.1.

3.8 Thread, cotton. The cotton thread for seaming the edges of the scarf shall be ticket number 00, 3 ply, conforming to type IC1 of V-T-276. The color of the thread shall be white A.H. C.A. 66050. The colorfastness to light of the finished bleached thread shall be equal to or better than the standard sample. When no standard sample is available, the colorfastness to light shall be not less than "good". The exposure time shall be 20 standard fading hours.

3.9 Design. The scarf is made of one piece single thickness material with fringed ends and overedge stitched side edges.

3.9.1 Construction. The scarf shall be manufactured in accordance with the operational requirements specified in table II. The contractor is not required to follow the exact sequence of operations.

3.9.2 Stitches, seams and stitchings. Stitches, seams and stitchings types specified in table II shall conform to FED-STD-751. Whenever two or more methods of stitch types are given for the same part of the operation, any one of them may be used.

3.9.3 Stitches per inch (Stitches/cm). The minimum and maximum number of stitches per inch (Stitches/cm) shall be as specified in table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE II

NO.	MANUFACTURING OPERATIONS REQUIREMENTS	STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH (/cm)	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
1.	Cutting. Cut the material across the warp to a scarf length permitting even fringing at each end. Cut the material in the direction of the warp to a scarf width so as to finish to the specified size (see 3.10).						
2.	Fringing. Ravel both ends of the scarf to form a fringe at each end 3/4 ± 1/8 inch (19 ± 3 mm) long.						
3.	Overedge stitching. Overedge stitch continuously the full length of each side edge of scarf. The chain at each end of overedge stitching shall be the same length as fringe, minus 1/4 inch (6 mm) tolerance. The width of the overedge stitching shall be 1/8 to 3/16 inch (3 to 5 mm). NOTE: The knife of the overedge machine shall be kept at peak sharpness in order to cut the side edges of the scarf cleanly.	504 or 505	EFd-1	21-24 (8-9)	00	00	
4.	Cleaning. Remove all spots and stains. Trim thread ends, and remove loose threads from scarfs.						
5.	Pressing. Press scarf flat with heated pressing iron.						

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

3.10 Finished dimensions. The finished dimensions of the scarf shall be 46-1/2 to 48 inches (1181 to 1220 mm) long (including fringe), and 10-1/2 to 11 1/4 inches (266 to 286 mm) wide (including overedge stitching).

3.11 Workmanship. The finished scarf shall conform to the quality of product established by this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. When certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all requirements of referenced specifications, drawings, and standards unless otherwise excluded amended, modified or qualified in this specification or applicable purchase document. In addition to testing provisions contained in subsidiary specifications, testing shall be performed on the component listed in table III for the characteristics noted. Unless otherwise indicated, testing shall be conducted in accordance with FED-STD-191. All test reports shall contain the individual values used in expressing the final result. The lot shall be unacceptable if one or more sample units fail to meet any of the test requirements specified. Testing for all requirements listed in table III are applicable to the sample unit. The lot size and sample size shall be as specified below, and the sample unit for testing shall be 2 yards (1.8 m) full width.

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE III. Fabric component tests

Component	Characteristics	Requirement reference	Test method
Woven cloth, acrylic	Material identification and fiber content.	3.2.1	1/
	Yarn ply:		
	Warp	3.2.2	Visual
	Filling	3.2.2	Visual
	Discoloration	3.3	5660 2/
	Colorfastness to:		
	Light	3.3.2	5660
	Weight	3.4	5041
	Yarns per inch: (yarns/cm)		
	Warp	3.4	5050
	Filling	3.4	5050
	Breaking strength:		
	Warp	3.4	5100
	Filling	3.4	5100
	Weave	3.5	Visual 1/
	Nonfibrous material	3.6.1	2611
	pH	3.7	2811

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

2/ Method 5660 shall be used except that exposure of the specimen and standard sample shall be for 20 standard fading hours. One determination shall be made for each sample unit and the result reported as "pass" or "fail".

4.2.2 End item examination. Defects found during this examination shall be classified in accordance with 4.2.2.1 and 4.2.2.2. The sample unit for these examinations shall be one scarf. The lot size shall be expressed in units of one finished scarf. The inspection levels and acceptable quality levels for these examinations shall be in accordance with 4.2.2.3.

4.2.2.1 Visual examination. The scarf shall be examined for defects in finish, design, material, and workmanship as listed in table IV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects

Examine	Defect	Classification Major	Minor
Material defects	Hole, cut, tear, or smash; one or more floats, or loose and weakening slub.	X	
	Needle chew.	X	
	Thin or weak area.	X	
	Shade bar or streak, clearly visible . 1/	X	
	Wrong color.	X	
	Character of finish not equal to standard.	X	
Cutting construction	Length not cut in direction of warp.	X	
	Constructed of more than one piece of material.	X	
	Width of overedge stitching:		
	- less than 1/8 inch (3 mm).	X	
	- more than 3/16 inch (5 mm).		X
	Overedge stitching wavy, affecting appearance.	X	
	Overedge stitching missing.	X	
Fringe	Missing on one or both ends.	X	
	Ragged or uneven (clearly noticeable).		X
	Less than 5/8 inch (16 mm) long.		X
	More than 7/8 inch (22 mm) long.		X
Thread	Wrong color.	X	
	Not size or type specified.		X
Stitching	Break in overedge stitching.	X	
	Runoff.	X	
	Chain at either end of overedge stitching more than 1/4 inch (6 mm) less than length of fringe.		X
Stitch type	Wrong stitch type.	X	
Stitch tension	Loose tension (resulting in loosely exposed loops to lower or top thread).	X	
	Tight tension, resulting in puckering.	X	
Stitches per inch	One stitch less than minimum specified.		X
	Two or more stitches less than minimum specified.	X	
	One or more stitches in excess of maximum specified.	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Cleanness	Spot or stain clearly visible. 1/	X	
	Thread ends not trimmed as specified.		X
Pressing	Burned or scorched.	X	
	Omitted.	X	
	Crease or wrinkle.	X	
	Poorly pressed.		X

1/ At normal inspection distance (approximately 3 feet).

4.2.2.2 Dimensional examination. The scarf shall be examined for defects in dimensions. Any dimension not within the established tolerances shall be classified as a defect.

4.2.2.3 Inspection and AQLs. The inspection levels and (AQLs) expressed in defects per 100 units shall be as follows:

Examination	Inspection level	AQLs Major	Total
For defects applicable to 4.2.2.1	II	2.5	6.5
For defects applicable to 4.2.2.2	S-3	(One class)	4.0

4.3 Packaging inspection. An examination shall be made to determine that preservation-packaging, packing and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be closed. Examination for the closure defects listed below shall be made on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged or not as specified.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, loose strapping, improper taping or inadequate stapling. Bulged or distorted container. Open and non-continuous heat sealed seams and closure of polyethylene bag. Alternative closure of polyethylene bag not provided with tuck or reverse flap. Omission of vent hole in polyethylene bag. Incorrectly fabricated bag.
Content	Number is intermediate packages per shipping container is more or less than required. Number of scarfs per intermediate package is more or less than required. 1/

1/ For this defect, three (3) intermediate packages shall be examined from each shipping container in the sample.

5. PACKAGING

5.1 Preservation-packaging. Preservation-packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit packaging. Each scarf shall be folded in half the length. The scarf shall then be folded twice more in half the length. The completely folded scarf shall measure approximately 11 by 6 inches. (280 by 152 mm). Each folded scarf shall be inserted in a snug-fitting flat-style clear polyethylene film bag of 0.00125 inch (0.03 mm) thickness (± 25 percent tolerance). The polyethylene bag shall be formed with heat sealed seams that are straight, continuous and parallel to each other, and the formed edges of the bag. The bag closure shall be effected by heat sealing with the heat seal as close as possible to the open end. A 1/4-inch (6 mm) diameter hole shall be made at one corner of each polyethylene bag to allow the excess air to escape. Alternatively, the final closure of the polyethylene bag may be accomplished by means of a tuck or reverse flap.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

5.1.1.2 Intermediate packaging. Six scarfs, unit packaged as specified in 5.1.1.1, shall be preserved-packaged flat within a folding paperboard box conforming to variety 1, style III, type G, class 1, group I of PPP-B-566; a setup paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676; or a metal-stayed paperboard box conforming to class 1, style A of PPP-B-665. Inside dimension of each paperboard box shall be 11-1/2 inches (292 mm) in length, 6-1/4 inches (159 mm) in width, and 3 inches (76 mm) in depth. The box closure shall be secured with 2-inch (51 mm) minimum width gummed paper tape conforming to type III, grade A of PPP-T-45, applied at the center of the length opening and extending along the bottom and up the sides at least 2 inches (51 mm).

5.1.2 Level-C packaging. The scarfs shall be preserved-packaged to afford adequate protection against physical damage during shipment from the contractor to the first receiving activity. The package and the quantity per package shall be the same as that normally used by the contractor for retail distribution.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A packing. One hundred and forty-four scarfs, preserved-packaged as specified in 5.1 shall be packed in a fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Level A packages shall be packed flat two in length, three in width, and four in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches (597 mm) in length, 20 inches (510 mm) in width, and 12-3/4 inches (324 mm) in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.3.

5.2.2 Level B packing. One hundred and forty-four scarfs, preserved-packaged as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 200 of PPP-B-636. Level A packages shall be packed flat two in length, three in width, and four in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches (597 mm) in length, 20 inches (508 mm) in width, and 12-3/4 inches (324 mm) in depth. Approximate dimensions are furnished as a guide only. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.3.

5.2.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

5.2.3 Level C packing. The scarfs preserved-packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the Uniform Freight Classification or National Motor Freight Classification, as applicable.

5.3 Marking. In addition to any special marking required by the contract, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.1 Polyethylene bagged packages. Polyethylene bagged packages shall have the stock number and nomenclature information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification.

6. NOTES

6.1 Intended use. The scarf is intended for use by female personnel of the Department of Defense.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of preservation-packaging and packing (see 5.1 and 5.2).
(c) When weather-resistant grade, fiberboard shipping containers are required for level B packing (see 5.2.2.1).

6.3 Sample. For access to a guide or standard shade sample, address the procuring activity issuing the invitation for bids.

6.4 Yarns. The standard sample was woven with 16, 2 ply warp and filling yarns. The ply yarn was twisted with 6-9 turns per inch (2.4-3.6 per cm), Z twist. The ply yarn consisted of two single yarns, each with 5-9 turns per inch (2-3.6 per cm), S twist.

6.5 Weave. The diagram for the weave is as shown below.

			X
	X		
		X	
X			

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

6.6 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire coutent irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - SA

Preparing activity:

Army - GL

Project No. 8445-0069

Review activities:

Army - MD
DLA - CT

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
US ARMY NATICK RESEARCH and DEVELOPMENT COMMAND
NATICK, MASSACHUSETTS 01760

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
DRXNM-TDC

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD-314

U.S. MAIL

Commander
US Army Natick Research and Development Command
ATTN: DRXNM-TDC
Natick, MA 01760

NATICK OP 1 JUL 77
FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-S-43317B SCARF, NECKWEAR, WOMAN'S, ACRYLIC

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.