INCH-POUND

MIL-S-43317C(NU)
14 June 1989

SUPERSEDING
MIL-S-43317B
29 July 1977

MILITARY SPECIFICATION

SCARF, NECKWEAR, WOMAN'S, ACRYLIC

This specification is approved for use by the Navy Clothing and Textile Research Facility, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for one type and size of woman's acrylic neckwear scarf.

2. APPLICABLE DOCUMENTS

* 2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760-2490 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8445

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

V-T-276	- Thread, Cotton
* NN-P-71	- Pallet, Material Handling, Wood, Stringer Construction, 2 Way and 4 Way (Partial)
PPP-B-566	- Box, Folding, Paperboard
PPP-B-636	- Box, Shipping, Fiberboard
PPP-B-665	- Boxes, Paperboard, Metal Edged and Components
PPP-B-676	- Boxes, Setup
PPP-T-45	- Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing

MILITARY

* MIL-P-15011	- Pallet, Material Handling, Wood, Post Construction, 4 Way Entry

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods
FED-STD-751	- Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	- Sampling Producures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
* MIL-STD-147	- Palletized Unit Loads
* MIL-STD-2073-1	- Department of Defense Materials Procedures for Development and Applications of Packaging Requirements
* MIL-STD-2073-2	- Packaging Requirement Codes

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

U.S. POSTAL SERVICE MANUAL

(Superintendent of Documents, U.S. Government Printing Office, Washinghton, DC 20402-0001).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

* 2.2 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Association, ATTN: Traffic Department, 1616 P Street, N.W., Washington, DC 20036-1404).

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606-5808).

THE COLOR ASSOCIATION OF THE UNITD STATES

Department of Defense Standard Shades for Sewing Thread

(Application for copies may be obtained from the Color Association of the United States, 343 Lexington Ave., New York, NY 10016).

* (Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Guide sample. Samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variations from this specification may appear in the sample in which case this specification shall govern.

3.2 First article. When specified, the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.3 and 6.2).

3.3 Material (see 6.6).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

3.3.1 Basic cloth. The fiber for the basic cloth shall be acrylic, semi-dull and of a suitable staple length conforming to the requirements of Table I. The warp and filling yarns shall be 2 ply yarns of a suitable twist conforming to the requirements of Table I (see 6.4). Testing for the fiber and the warp and filling yarns shall be as specified in 4.4.1.

* 3.3.1.1 Color of cloth. The finished cloth shall be chemically bleached white and may be supplemented with optical brighteners which fluoresce to the blue region. The degree of whiteness shall match the standard sample.

* 3.3.1.2 Matching. The color of the finished cloth shall match the standard sample under artificial daylight having a color temperature of 7000 (± 500) kelvin and shall be a good approximation of the standard sample under incandescent lamplight at 2850 (± 100) kelvin.

3.3.1.3 Physical requirements. The finished cloth shall conform to the physical requirements specified in Table I when tested as specified in 4.4.1.

TABLE I. Physical requirements

Characteristic	Minimum
Weight, ounces per square yard	3.8
Yarns per inch	
Warp	28
Filling	20
Breaking strength pounds	
Warp	40
Filling	25

3.3.1.4 Weave. The weave shall be a crowfoot satin, repeating on 4 ends and 4 picks. Testing shall be as specified in 4.4.1 (see 6.5 for diagram of weave).

* 3.4 Finish. The finish of the cloth shall match the finish of the standard sample.

3.4.1 Nonfibrous materials. The starch and protein content of the finished cloth, including chloroform-soluble and water-soluble material shall be not more than 2.0 percent when tested as specified in 4.4.1.

3.5 pH. The pH value of the finished cloth shall be not less than 5.0 percent nor more than 8.5 percent when tested as specified in 4.4.1.

3.6 Thread, cotton. The cotton thread for seaming the edges of the scarf

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

shall be ticket number 00, 3 ply, conforming to type IC1 of V-T-276. The color of the thread shall be white A.H. C.A. 66050 in accordance with the Department of Defense Standard Shades for Sewing Threads. The colorfastness to light of the finished bleached thread shall be equal to or better than the standard sample. As a limit of acceptability or when no standard sample is available, the colorfastness to light shall be not less than "good". The exposure time shall be 20 standard fading hours.

3.7 Design. The scarf is made of one piece single thickness material with fringed ends and overedge stitched side edges.

3.7.1 Construction. The scarf shall be manufactured in accordance with the operational requirements specified in Table II. The contractor is not required to follow the exact sequence of operations.

* 3.7.2 Stitches, seams and stitchings. Stitches, seams and stitchings types specified in Table II shall conform to FED-STD-751. Whenever two or more methods of stitch types are given for the same part of the operation, any one of them may be used. The bight of the overedge stitching shall be 3/16 inch. The guide and knife shall be set to trim only the ravelled ends of the fabric.

3.7.3 Stitches per inch. The minimum and maximum number of stitches per inch shall be as specified in Table II.

* 3.7.3 Abbreviations in table of operations. The abbreviations used in Table II are as follows:

Stch	-	Stitch
in	-	inch
Ndl	-	Needle
Bob	-	Bobbin
Lpr	-	Looper
Mchne	-	Machine
Brtck	-	Bartack
Comrcl	-	Commercial
smlr	-	similar
Btnhl	-	Buttonhole
incl	-	including
dbl	-	double
chnstch	-	chainstitch

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE II - Construction of Scarf

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH IN	THREAD NDL	THREAD BOB/ LPR
*1.	Cutting. The scarf shall be cut from the material so the length direction of the scarf is in the warp direction of the material. The scarf shall be cut so as to allow it to be finished to the specified size (see 3.9) and permit even fringing.					
*2.	Fringing. Fringing shall be accomplished by raveling each end of the scarf or by using a dead box in the loom and weaving without the filling yarns for a distance of 1-1/2 to 2 inches. The length of the fringe at each end of the scarf shall be 3/4 (+1/4/-1/8) inch.					
*3.	Overedge stitching. Overedge stitch continuously the full length of each side edge of scarf. The chain at each end of overedge stitching shall be the same length as fringe, minus 1/4 inch tolerance. The width of the overedge stitching shall be 3/16 inch. NOTE: The knife of the overedge machine shall be kept at peak sharpness in order to cut the side edges of the scarf cleanly.	504 or 505	EFd-1	16-18	00	00
4.	Cleaning. Remove all spots and stains. Trim thread ends, and remove loose threads from scarfs. * NOTE: Care shall be taken when trimming thread ends that damage to the fabric does not result.					

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

3.9 Finished dimensions. The finished dimensions of the scarf shall be 46-1/2 to 48 inches long (including fringe), and 10-1/2 to 11-1/4 inches wide (including overedge stitching).

3.10 Workmanship. The finished scarf shall conform to the quality of product established by this specification.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

* 4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When required, the first article submitted in accordance with 3.2 shall be inspected for compliance with design, construction, workmanship, appearance, and dimensional requirements.

4.4 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents. In addition to testing provisions contained in subsidiary specifications, testing shall be performed on the component listed in Table III for the characteristics noted. Unless otherwise indicated, testing shall be conducted in accordance with FED-STD-191. All test reports shall contain the individual values used in expressing the final result. The lot shall be unacceptable if one or more sample units fail to meet any of the test requirements specified. Testing for all requirements listed in Table III are applicable to the sample unit. The lot size and sample size shall be as specified below, and the sample unit for testing shall be 2 yards full width.

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE III. Fabric component tests

Component	Characteristics	Requirement reference	Test method
Woven cloth, acrylic	Material identification and fiber content.	3.3.1	1/
	Yarn ply:		
	Warp	3.3.1	Visual
	Filling	3.3.1	Visual
	Weight	3.3.1.3	5041
	Yarns per inch:		
	Warp	3.3.1.3	5050
	Filling	3.3.1.3	5050
	Breaking strength:		
	Warp	3.3.1.3	5100
	Filling	3.3.1.3	5100
	Weave	3.3.1.4	Visual 1/
	Nonfibrous material	3.4.1	2611
	pH	3.5	2811

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirements.

4.4.2 Examination of the end item. Examination of the end item shall be in accordance with 4.4.2.1 through 4.4.2.3.

4.4.2.1 Visual examination. The scarf shall be examined for defects in finish, design, material, and workmanship as listed in Table IV.

TABLE IV. Classification of visual defects

Examine	Defect	Classification Major	Minor
Material defects	Hole, cut, tear, or smash; one or more floats, or loose and weakening slub.	X	
	Needle chew.	X	
	Thin or weak area.	X	
	Shade bar or streak, clearly visible. 1/	X	
	Wrong color.	X	
Cutting construction	Length not cut in direction of warp.	X	
	Constructed of more than one piece of material.	X	
	Width of overedge stitching:		
	- less than 1/8 inch	X	
	- more than 3/16 inch		X
	Overedge stitching wavy, affecting appearance.	X	
	Overedge stitching missing.	X	
Fringe	Missing on one or both ends.	X	
	Ragged or uneven (clearly noticeable).		X
	Less than 5/8 inch long.		X
	* More than 1 inch long.		X
Thread	Wrong color.	X	
	Not size or type specified.		X
Stitching	Break in overedge stitching.	X	
	Runoff.	X	
	Chain at either end of overedge stitching more than 1/4 inch less than length of fringe.		X
	* Chain at either end of overedge stitching is longer than fringe		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Stitch type	Wrong stitch type.	X	
Stitch tension	Loose tension (resulting in loosely exposed loops to lower or top thread).	X	
	Tight tension, resulting in puckering.	X	
Stitches per inch	One stitch less than minimum specified.		X
	Two or more stitches less than minimum specified.	X	
	One or more stitches in excess of maximum specified.	X	
Cleanness	Spot or stain clearly visible. 1/	X	
	Thread ends not trimmed as specified.		X
Finish	Does not match standard sample	X	

1/ At normal inspection distance (approximately 3 feet).

4.4.2.2 Dimensional examination. The scarf shall be examined for defects in dimensions. Any dimension not within the established tolerances shall be classified as a defect.

4.4.2.3 Inspection and AQLs. The inspection levels and (AQLs) expressed in defects per 100 units shall be as follows:

Examination	Inspection level	AQLs Major	AQLs Total
For defects applicable to 4.2.2.1	II	2.5	6.5
For defects applicable to 4.2.2.2	S-3	(one class)	4.0

* 4.4.3 Examination of packaging requirements. An examination shall be made to determine that packaging, packing, and marking comply with Section 5 requirements of this specification. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be on the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the acceptable quality level (AQL) shall be 2.5 defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, improper taping, inadequate stapling, bulged or distorted container. Open and non-continuous heat sealed seams and closure of polyethylene bag. Alternative closure of polyethylene bag not provided with tuck or reverse flap. Omission of vent hole in polyethylene bag. Incorrectly fabricated bag.
Content	Number of intermediate packs per shipping container is more or less than required. 1/ Number of scarfs per intermediate pack is more or less than required. 1/

1/ For this defect, three (3) intermediate packs from each shipping container in sample shall be examined.

* 4.4.4 Palletization examination. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully packaged. The lot size shall be the number of palletized unit loads in the end item inspected lot. The inspection level shall be S-1 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 6.5 in accordance with MIL-STD-105.

Examine	Defect
Finished dimensions	Length, width,or height exceeds specified maximum requirements.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application.

5. PACKAGING

* 5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

* 5.1.1.1 Unit pack. Each scarf shall be folded in half the length. The scarf shall then be folded twice more in half the length. The completely folded scarf shall measure approximately 11 by 6 inches. Each folded scarf shall be inserted in a close-fitting flat-style clear polyethylene film bag having a thickness of 0.00125 inch (± 25 percent tolerance). The bag shall be formed with heat sealed seams that are straight, continuous and parallel to each other and the formed edges of the bag. The final closure of the bag shall be heat sealed with the heat seal as close as possible to the open end. A 1/4-inch diameter hole shall be made at one corner of the polyethylene bag to allow the excess air to escape. Alternately, the final closure of the polyethylene bag may be accomplished by means of a tuck or reverse flap.

* 5.1.1.2 Intermediate pack. Six scarfs, unit packed as specified in 5.1.1.1, shall be placed flat within a folding paperboard box conforming to variety 1, style III, type G, class 1, group I of PPP-B-566; a setup paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676; or a metal-stayed paperboard box conforming to class 1, style A of PPP-B-665. Inside dimension of each paperboard box shall be 11-1/2 inches in length, 6-1/4 inches in width, and 3 inches in depth. The box closure shall be secured with 2-inch minimum width gummed paper tape conforming to type III, grade A of PPP-T-45, applied at the center of the length opening and extending along the bottom and up the sides at least 2 inches.

* 5.1.2 Level C. The scarfs shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The package and the quantity per package may be the same as that normally used by the supplier for retail distribution when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

* 5.2.1 Level A. One hundred and forty-four scarfs, packed as specified in 5.1 shall be packed in a corrugated fiberboard shipping container conforming to style RSC, grade V15c, type CF, class weather resistant, variety DW of PPP-B-636. Level A packages shall be packed flat two in length, three in width, and four in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches in length, 20 inches in width, and 12-3/4 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3.

* 5.2.2 Level B. One hundred and forty-four scarfs, packed as specified in 5.1, shall be packed in a fiberboard shipping container conforming to style RSC, type CF, variety DW, class domestic, grade 200 of PPP-B-636. Level A packages shall be packed flat two in length, three in width, and four in depth within a shipping container. Inside dimensions of each shipping container shall approximate 23-1/2 inches in length, 20 inches in width, and 12-3/4 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

5.2.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3.

* 5.2.3 Level C. Item packaged, as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the US Postal Service Manual, Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

* 5.3 Marking. In addition to any special marking required by the contract or order, unit packs, intermediate or exterior containers, and palletized unit loads shall be marked in accordance with MIL-STD-129.

* 5.4 Palletization. When specified (see 6.2) item packed as specified shall be palletized on a 4-way entry pallet in accordance with load type 1A of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C, K, and L or O or P. Pallet pattern shall be in accordance with the appendix of MIL-STD-147.

The pallet shall be 4-way, Type IV; Type V, Class 1, Size 2; or Type VIII, fabricated from wood group I, II, III or IV, Grade A of NN-P-71, or 4-way, Style 1, Size A, Type I, Class 1 fabricated from wood groups specified of MIL-P-15011. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the patterns specified in MIL-STD-147, the pallet pattern used shall be approved by the contracting officer.

* 5.5 MIL-STD-2073. When specified (see 6.2), Preservation and Packing shall be in accordance with MIL-STD-2073-1 and MIL-STD-2073-2.

6. NOTES

* (This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The scarf is intended for wear by female personnel of the Department of Navy.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.


* 6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When first article sample is required (see 3.2). The item will be tested and should be a first article sample. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examination, quantity, testing and approval of the first article.
d. Levels of packaging and packing required (see 5.1 and 5.2).
e. When palletization is required (see 5.4).
f. When all packaging data is to be found in MIL-STD-2073-1 and MIL-STD-2073-2 (See 5.5).

6.3 Samples. For access to samples, address the procuring activity issuing the invitation for bids (see 3.1).

6.4 Yarns. The standard sample was woven with 16, 2 ply warp and filling yarns. The ply yarn was twisted with 6-9 turns per inch, Z twist. The ply yarn consisted of two single yarns, each with 5-9 turns per inch, S twist.

6.5 Weave. The diagram for the weave is as shown below.



6.6 Recycled materials. It is encouraged that recycled materials be used when practical as long as it meets the requirements of this specification (see 3.3).

* 6.7 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

* 6.8 Subject term (key word) listing.

Neckwear, woman's acrylic
Neckwear, woman's scarf

Custodian:
Navy - NU

Preparing Activity:
Navy - NU

Review Activity:
DLA - CT

Project No. 8445-N107

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Navy Clothing and Textile Research Facility
21 Strathmore Road, Code 50
Natick, MA 01760-2490

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-43317C(NU)	SCARF, NECKWEAR, WOMAN'S, ACRYLIC

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:09Z
Check the source to verify that this is the current version before use.