MIL-T-43333C
31 October 1988
SUPERSEDING
MIL-T-43333B
12 December 1973

MILITARY SPECIFICATION

TENT LINER, GENERAL PURPOSE, SMALL AND ARCTIC, 10 MAN

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a tent liner for use with small general purpose and 10-man arctic tents. The tent liner is fabricated from natural color, fire resistant oxford cotton cloth.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

T-T-871	-	Twine, Cotton, Wrapping
T-T-911	-	Twine, Fibrous, Jute
V-F-106	-	Fasteners, Slide Interlocking
V-T-285	-	Thread, Polyester

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

CCC-C-429	-	Cloth, Osnaburg, Cotton
CCC-C-467	-	Cloth, Burlap, Jute (or Kenaf)
DDD-L-20	-	Label: For Clothing, Equipage and Tentage, (General Use)
PPP-B-601	-	Boxes, Wood, Cleated-Plywood
PPP-B-1055	-	Barrier Material, Waterproofed, Flexible
PPP-S-760	-	Strapping, Nonmetallic, (and Connectors)

MILITARY

MIL-B-543	-	Buckles, Tongueless and Web Strap
MIL-C-2399	-	Cement, Liquid, Tent Patching
MIL-R-3390	-	Rings, Dee
MIL-C-10859	-	Cloth, Oxford, Cotton, (Permeable)
MIL-G-16491	-	Grommet, Metallic
MIL-T-43566	-	Tape, Textile, Cotton or Polyester, General Purpose, Natural or in Colors
MIL-W-43638	-	Webbing, Textile, Woven, for Tent Framing
MIL-W-44049	-	Webbing, Textile and Tape, Textile, Polypropylene, General Purpose, Natural or in colors

STANDARDS

FEDERAL

FED-STD-751	-	Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads
MIL-STD-731	-	Quality of Wood Members for Containers and Pallets

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of solicitation.

Department of the Army Field Manual FM 10-16 -
General Repair of Tents, Canvas and Webbing

(Copies may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:11Z
Check the source to verify that this is the current version before use.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

5-4-930	-	Tent Liner, General Purpose, Small and Artic, 10-Man; Assembly and Details
5-4-931	-	Side and Details
5-4-932	-	Front and Rear Liner and Details
5-4-933	-	Maintenance, Striking and Folding Instructions

(Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

D 3951 - Standard Practice for Commercial Packaging

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2 and 6.3).

3.2 Materials and components. Materials and components shall be as specified herein (see 6.4).

3.2.1 Cloth, oxford, cotton. The cloth shall conform to type I, class 2 of MIL-C-10859.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

3.2.2 Tape, textile, cotton. The tape shall be 1/2 inch, 3/4 inch and 2 inch widths conforming to type I, class 1b of MIL-T-43566. Alternatively, the tape shall be polypropylene conforming to type I, class 3 of MIL-W-44049.

3.2.3 Webbing, low elongation. The webbing shall be 1 inch wide conforming to type I of MIL-W-43638.

3.2.4 Thread, polyester.

3.2.4.1 Liner. The thread shall be natural and shall conform to type I or II, class 1, subclass A, natural in color of V-T-285.

3.2.4.2 Sizes. Thread sizes shall be as follows:

For all stitching except stitching indicated by "Z" on drawings	- Size E for needle and size B for bobbin
For stitching indicated by "Z" on drawings	- Size E for needle and size B for looper
Bartacking	- Size E for needle and bobbin

3.2.5 Fasteners, slide, interlocking. The slide fasteners shall conform to type III, style 1, size H, brass chain and brass slider with double wire stirrup pull of V-F-106. Alternatively, the slide fastener chain shall be polyester continuous monofilament in a ladder or coil type configuration. Color of the chain, slider, pull and stops shall approximately match the tape color. The slide fastener tape shall be natural in color prior to the water repellent and mildew resistant treatment. Tape made of 100 percent polyester need not be treated for mildew resistance.

3.2.6 Rings, dee. The dee rings shall conform to class 1 or 2, configuration K, size 1 x 3/4 of MIL-R-3390.

3.2.7 Buckles, tongueless, 2 bar. The buckles shall conform to type II, style 1, class 3 of MIL-B-543.

3.2.8 Grommets, metallic. The grommets shall conform to type III, class 3, size No. 2 of MIL-G-16491.

3.3 Construction. The construction shall conform in all respects to the drawings listed in section 2 and as specified herein.

3.3.1 Stitching, machine.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

3.3.1.1 Types of stitching. All stitching, except bartacking, shall conform to FED-STD-751 as follows:

For all stitching, except stitching indicated by "Z" on drawings	- Type 301, 6 to 8 stitches per inch
For stitching indicated by "Z" on drawings and for attachment of slide fasteners	- Type 401, 6 to 8 stitches per inch Chain portion of stitching shall not appear on outside of tent liner
For bartacking	- Bartack, 3/4 ± 1/8 inch long with 1/8 ± 1/32 inch bight and shall contain 42 stitches

3.3.1.2 Type 301 stitching. Ends of all stitching shall be backstitched or overstitched 1/2 inch minimum except when caught in other stitching or turned under in a hem. Thread tension shall be maintained so that there will be no loose stitching resulting in puckering of material sewn. The lock shall be embedded in the material sewn.

3.3.1.2.1 Repairs of type 301 stitching. The ends of the stitching are not required to be backstitched. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of one inch behind the end of the stitching.

b. Thread breaks, two or more consecutive skipped stitches or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of one inch before the defective area (1/2 inch on Box, Box and Cross and W-W stitching) and continue a minimum of one inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and restitching in the required manner.

3.3.1.3 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching. Both ends of all seams or stitching produced with a 401 stitch type, when not turned under in a hem or held down by other stitching, shall have a 1/2 to 3/4 inch chain extending beyond each end. The looper (under thread) shall always be on the inside of the tent or cover. All repairs shall be made in accordance with 3.3.1.3.1a or 3.3.1.3.1b. Repairs may be made using 301 stitch type.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

3.3.1.4 Automatic stitching. Automatic stitching machines may be used to perform any of the required stitch patterns provided the requirements of the stitch pattern, stitches per inch, size and type of thread are met, and at least three tying, overlapping or backstitches are used to secure the ends of the stitching.

3.3.1.5 Thread ends. All thread ends that are visible on the finished item shall be trimmed to a length of not more than 1/4 inch.

3.3.1.6 Stitching margins. Unless otherwise specified, all stitch margins shall be 1/8, +1/16 -0 inch.

3.3.1.7 Bartacking. Bartacking shall be free of thread breaks or loose stitching.

3.3.2 Setting of grommets. Holes punched to receive the grommets shall be smaller than the outside diameter of the grommet barrel so that the barrel must be forced through the hole. The grommets shall be securely clinched without cutting the materials.

3.3.3 Attachment of slide fasteners. Care shall be exercised to trim all thread ends to 1/4 inch or less and maintain specified distances between edges of fabric attached to slide fastener tape so that there will be no interference with the operation of the slider. The length of the slide fastener shall be such that after the slide fastener is sewed on, the tape shall not be puckered and the slider shall operate freely.

3.3.4 Splicing of webbing. If required, the webbing shall be spliced as shown on Drawing 5-4-931. A maximum of one splice per gore shall be permitted. The minimum distance between splices in webbing in the remainder of the liner shall be 5 feet.

3.3.5 Splicing of cloth. There shall be no splicing of the cloth in the roof or wall panels.

3.3.6 Fusing of ends of synthetic webbing and tape. All ends of synthetic webbing and tape shall be fused. The apparatus used to fuse the ends shall be capable of providing sufficient heat to provide a smooth edge and with the cut ends of the yarns all fused together. Fusing of the ends shall be accomplished prior to being assembled for stitching.

3.3.7 Replacement of defective components. During the spreading, cutting and manufacturing process, components of the liner having material defects or damages that are classified as defects in 4.4.2 or 4.4.3 shall be removed from production and replaced with non defective and properly matched components.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

3.3.8 Repairs. Repairs, whenever necessary, shall be effected in accordance with Department of the Army Field Manual FM 10-16 except that hand sewn patches, or cemented patches other than as specified herein, will not be acceptable. Holes, cuts or tears not more than 1 inch in diameter or length may be repaired with cemented patches. The cement shall be as specified in MIL-C-2399. A maximum of three cemented patches per tent will be acceptable without prior authorization from the contracting officer. All other repairs shall require contracting officer authorization.

3.4 Marking. All labels and markings shall conform to DDD-L-20.

3.4.1 Special marking. The letters "US" and repair kit marking on the tent liner shall conform to type IV, class 9 in the size characters and in the locations shown on the drawings. Class 9 markings shall be clearly legible after subjection to accelerated weathering.

3.4.2 Identification label. The identification label shall conform to type VI, class 6 and shall be 3-1/2 inches by 5-1/2 inches minimum and a blank space of at least 1-1/4 inches shall be provided on the bottom of the label for the Department of Defense inspector's stamp. The identification label shall be stitched to the tent liner in the location shown on the drawing.

3.4.3 Label of care and maintenance instructions. The label of care and maintenance instructions shall conform to type VI, class 7 and shall be stitched to the tent liner in the location shown on the drawing. The size of the label shall be, borderline to borderline, 15 $\pm$ 1/4 inches in the longer dimension with a minimum 1/2 inch margin outside of the borderline on all sides. The information on the label shall be a proportionate copy of Drawing 5-4-933.

3.5 Workmanship. The liner shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels. Thread tension shall be maintained so that there is no loose stitching, and seam allowances shall be maintained with seams properly sewn so that no runoffs, twists, pleats or open seams result. Care shall be taken to see that no needle chews occur. Cloth components shall be clean and free of holes, cuts, tears or cloth defects such as multiple floats or broken or missing yarns. Webbing and tapes shall contain no frayed or scalloped edges. Metal components shall be free of burrs, sharp edges, corroded areas and shall not be broken or malformed. Care shall be exercised to maintain proper tension when attaching the slide fastener tape to the tent.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:11Z
Check the source to verify that this is the currentversion before use.

herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 In-process inspection. Inspection shall be made of the following operations or assemblies to establish conformance to specified requirements. Whenever nonconformance is noted, correction shall be made to the items affected and to the operation. Items which cannot be corrected shall be removed from production.

a. Verification that holes punched to receive grommets conform to 3.3.2

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:11Z
Check the source to verify that this is the currentversion before use.

4.4.3 End item visual examination. The end item shall be in an erected position so that both the inside and outside of the liner can be examined for defects listed in table I. The lot size shall be expressed in units of liners. The sample unit shall be one liner. The inspection level shall be I, and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 25 for major defects, 65 for major and minor A combined defects and 150 for total (major, minor A and minor B combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Fabric	Cut, tear, or hole:			
	- greater than 1/4 inch in length or diameter	X		
	- greater than 1/8 inch but not greater than 1/4 inch in length or diameter		X	
	- more than 5 holes 1/8 inch or less in length or diameter			X
	Broken or missing yarn, multiple floats, clearly visible at normal inspection distance (approximately 3 feet)		X	
Webbing and tie tapes	Edge frayed or scalloped			X
	Splice (when necessary) not as indicated on Drawing 5-4-931		X	
	More than one splice per gore on seams joining panels of liner; distance between splices on all reinforced places of liner less than 5 feet		X	
Hardware	Broken	X		
	Malformed:			
	- fails to perform intended function	X		
	- but will perform intended function		X	
	Corroded area			X
	Burr or sharp edge which may cause injury in handling or damage to fabric	X		

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:11Z
Check the source to verify that this is the currentversion before use.

TABLE I. End item visual defects(cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Grommets	Improperly set; two or more teeth exposed (except where grommet is set as specified but is in an area of unequal thickness which prevents uniform clinching)			X
	Clinched loosely, allowing grommet to rotate in hole			X
	Clinched excessively tight, cutting fabric	X		
	Insecurely clinched; i.e., grommet washer becomes disengaged	X		
Seams and stitchings	Open seam on stitch type 301:			
	- for more than 1/4 inch but not more than 1 inch			X
	- for more than 1 inch		X	
	Open seam on stitch type 401:			
	- one row of stitching open for 1 inch or less			X
	- one row of stitching open for more than 1 inch		X	
	- both rows of stitching open (not necessarily at same location)	X		
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken, or when two or more consecutive skipped or runoff stitches occur. On double-stitched seams, a seam shall be classified as open when either one or both sides of seam are open.			
	Raw edges caught in stitching:			
	- more than 1 inch but not more than 3 inches			X
	- more than 3 inches		X	
	Pleated seams			X
	Thread breaks:			
	- overstitched less than 1 inch on stitch type 401 or 301			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects(cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Seams and stitchings (cont'd)	NOTE: Thread breaks not overstitched shall be classified as open seams. Needle chews resulting in cut, tear or hole (see cut, tear or hole under fabric examination).			
	Skipped stitches overstitched: - less than 1 inch on stitch type 301 or 401 (where 2 or more stitches are skipped consecutively)			X
	NOTE: Skipped stitches not over-stitched shall be classified as open seams.			
	One or more required rows of stitching omitted (except on boxstitching)	X		
	Boxstitching incomplete: - one row of stitching omitted			X
	- two or more rows of stitching omitted	X		
Seam type	Wrong seam type	X		
Stitch type	Wrong stitch type	X		
Stitch tension	Loose, resulting in an exposed bobbin or top thread for more than 6 inches		X	
	Tight as evidenced by puckering on seams for more than 6 inches		X	
Stitches per inch	Less than minimum specified: - one stitch			X
	- two or more stitches		X	
	More than maximum specified: - one stitch			X
	- two or more stitches		X	

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:11Z
Check the source to verify that this is the currentversion before use.

TABLE I. End item visual defects(cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Boxstitching	Any boxstitching less than specified length by more than 1/8 inch			X
	Incomplete:			
	- Two or more rows of stitching omitted		X	
	- One row of stitching omitted			X
Bartack	Any bartacking less than specified by more than 1/8 inch			X
	NOTE: Variation in the number of stitches per inch, caused by the operator's speeding up the machine and pulling the fabric in order to sew over heavy seams or heavy places or turning corners shall be classified as follows:			
	a. Within the minor "A" defect classification - minor B defect			
	b. Within the minor "B" defect classification - no defect			
Stitching gage	Not as specified			X
Stitching margin	Larger than specified:			
	- for more than 2 inches but not more than 4 inches in length			X
	- for more than 4 inches in length		X	
	Less than specified:			
	- for more than 2 inches but not more than 4 inches in length			X
	- for more than 4 inches in length		X	
Stitching ends	Overstitched less than 1/2 inch on stitch type 301 (except where ends are held down by other stitching, turned under in a hem or where stitching is performed automatically)			X
	Secured with less than 3 tying, overlapping or backstitches when automatic stitching is performed			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Stitching indicated by "Z" on drawings	Chain portion of stitching shows on outside of liner		X	
Mends, darns, or patches	Repairs not in accordance with Department of the Army Field Manual FM 10-16 or not authorized by the contracting officer (see 3.3.8)	X		
Component and assembly	Any component not fabricated of applicable referenced material	X		
Construction details:				
Hems	Twisted or pleated			X
	Constructed with partial turnunder when double turnunder is required		X	
Splicing of cloth	Splice in roof or wall panels	X		
Reinforcements	Improperly applied, causing excessive fullness on reinforcement or reinforced parts			X
Binding	Improperly or loosely applied			
Slide Fasteners	Slider jams or fails to interlock chain	X		
	Any tape improperly assembled causing failure of chain to effect a smooth and secure closure	X		
	Wrong length	X		
	Width not as specified	X		
	Puckering of tape	X		
	Broken or missing scoops	X		
	Thong omitted	X		

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Slide fasteners (cont'd)	NOTE: The inspector shall pull slide fasteners three or four times to an open and closed position to determine proper function and effectiveness of each fastener.			
General	Any other construction detail not performed as specified		X	
Labels	Omitted, incorrect, illegible or misplaced:			
	- erection or maintenance instructions		X	
	- identification			X
Marking: "US" and identification	Omitted, incorrect, illegible or misplaced			X
Cleanness	Grease or oil stains			X
	Thread ends not trimmed to 1/4 inch or less throughout (except in slide fastener area)			X
	Thread ends not trimmed to 1/4 inch or less in slide fastener area		X	

4.4.4 End item dimensional examination. The end item shall be in an erected position so that both the inside and outside of the liner can be examined for defects listed in table II. The lot size shall be expressed in units of liners. The sample unit shall be one liner. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects, 15 for major and minor A combined defects and 40 for total (major, minor A and minor B combined) defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

TABLE II. End item dimensional defects

Examine	Defect	Classification Major	Minor A	Minor B
Overall dimensions	Smaller than specified dimensions less applicable minus tolerance indicated on drawings	X		
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			X
Location and components dimensions (unless otherwise specified)	Smaller than specified dimensions less applicable minus tolerance indicated on drawings but not smaller than specified dimensions less twice the applicable minus tolerance			X
	Smaller than specified dimensions less twice the applicable minus tolerance indicated on drawings		X	
	Larger than specified dimensions and applicable plus tolerance indicated on drawings			X
Tent liner openings	Smaller than specified dimensions by more than 1/2 inch			X
	Larger than specified dimensions by more than 1/2 inch			X
Reinforcement webbing	Edges of stovepipe opening webbing reinforcement uneven with finished edge of opening by more than 1/8 inch			X
Peak of wall door opening	Peak of wall halves joined to roof with edges of door opening less than 7/8 inch apart, failing to provide clearance for top of slide fastener			X
	One inch space at top of wall halves not securely closed by bottom end of roof reinforcement webbing		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as incomplete closure of cloth wrapping or loose stitching.
Content	Number per container is more or less than required.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each liner, with slide fasteners closed, shall be smoothly folded flat to measure approximately 30 by 44 inches. Care shall be taken during the folding operation to expel entrapped air. Five liners shall be neatly stacked in a bundle and completely wrapped with waterproofed kraft wrapping paper conforming to class B-1 or B-2 of PPP-B-1055. The wrapped bundle shall be secured by cross-strapping with 3/8 by 0.020-inch strapping conforming to type II of PPP-S-760.

5.1.2 Commercial. Liners shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Five liners, preserved as specified in 5.1, shall be packed in a close-fitting wood-cleated plywood box conforming to overseas type, style A of PPP-B-601. Each box shall be closed and strapped with flat steel strapping in accordance with the box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

5.2.2 Level B packing. Five liners, preserved as specified in 5.1, shall be wrapped in cotton osnaburg cloth conforming to class 2 of CCC-C-429; or burlap cloth conforming to class 3 of CCC-C-467. The wrapping shall be securely hand sewn with type I or II, 16-ply cotton twine conforming to T-T-871, or type I, size No. 2 jute twine conforming to T-T-911, with approximately one stitch to the inch and every third stitch knotted or alternatively, the seams of the wrap may be machine sewn. A minimum of 5 inches of wrapping material or tubing shall be gathered together on each of the four corners and securely sewn into ears for handles. The polyester thread used to manufacture the tent liners shall be used for effecting the machine sewn closure of the wrapping or tubing.

5.2.3 Commercial. Liners, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipments shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The tent liner is designed to be used with the small general purpose and arctic 10-man tents and is intended to provide insulation in cold climates and protection from solar radiation in hot weather.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number and date of this document.
b. When a first article is required (see 3.1, 4.3 and 6.3).
c. Selection of the applicable levels of preservation and packing (see 5.1 and 5.2).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangments for selection, inspection, and approval of the first article.

6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document (see 3.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

6.5 International standardization agreements. Certain provisions of this document are the subject of international standardization agreement as cited in NATO, STANAG NO. 2882, relative to camouflage requirements for tents, shelters and subsidiary components. When amendment, revision, or cancellation of this document is proposed which will affect or violate the international agreement concerned, the contracting activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

6.6 Subject term (key word) listing.

Liner
Tent, General Purpose, Small and Arctic

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensivensss of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activities:

Navy - YD
Air Force - 45

Preparing activity:

Army - GL

Project No. 8340-0515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:11Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-T-43333C	Tent Liner, General Purpose, Small and Arctic, 10 Man

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426 PREVIOUS EDITION IS OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 20240-21121:11Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)* mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATE

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:11Z
Check the source to verify that this is the current version before use.