MIL-S-21472C
31 October 1988
SUPERSEDING
MIL-S-21472B
5 October 1971

MILITARY SPECIFICATION

SCREW, SHOULDER, HEXAGON SOCKET-HEAD
AND SLOTTED-HEAD
GENERAL SPECIFICATION FOR

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers hexagon socket-head shoulder screws and slotted-head shoulder screws.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

QQ-B-637 - Brass, Naval: Rod, Wire, Shapes, Forgings and Flat Products with Finished Edges (Bar, Flat, Wire, and Strip).
QQ-B-728 - Bronze Manganese; Rod, Shapes, Forgings, and Flat Products (Flat Wire, Strip, Sheet, Bar, and Plate).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to Commander, US Army Armament Research, Development and Engineering Center, ATTN: SMCAR-ESC-S, Picatinny Arsenal, NJ 07806-5000 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is limited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

QQ-B-750 - Bronze, Phosphor; Bar, Plate, Rod, Sheet, Strip, Flat Wire and Structural and Special Shaped Sections.
QQ-C-00465 - Copper-Aluminum Alloys (Aluminum Bronze) (Copper Alloy Numbers 606, 614, 630, 632M, and 642); Rod, Flat Products with Finished Edges (Flat Wire, Strip, and Bar) Shapes, and Forgings.
QQ-C-591 - Copper-Silicon, Copper-Zinc-Silicon, and Copper-Nickel-Silicon Alloys: Rod, Wire, Shapes, Forgings, and Flat Products (Flat Wire, Strip, Sheet, Bar, and Plate).
QQ-N-281 - Nickel-Copper Alloy Bar, Rod, Plate, Sheet, Strip, Wire, Forgings, and Structural and Special Shaped Sections.
QQ-N-286 - Nickel-Copper-Aluminum Alloy, Wrought.
QQ-P-35 - Cleaning Methods and Passivation Treatments for Corrosion Resisting Steel.
QQ-P-416 - Plating, Cadmium (Electrodeposited).

MILITARY

MIL-H-6875 - Heat Treatment of Steel, Process for.
MIL-S-7742 - Screw Threads, Standard, Optimum Selected Series, General Specification for.
MIL-C-81562 - Coatings, Cadmium, Tin-Cadmium and Zinc (Mechanically Deposited).

STANDARDS

FEDERAL

FED-STD-H28/20 - Screw-Thread Standards for Federal Services, Section 20, Inspection Methods for Acceptability of UN, UNR, UNJ, M and MJ Screw-Threads.
FED-STD-123 - Marking for Shipment (Civil Agencies).
FED TEST METHOD STD NO. 151 - Metals; Test Methods.
FED-STD-H28/2 - Screw-Thread Standards for Federal Services, Section 2, Unified Inch Screw threads- UN and UNR Thread Forms.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-1312 - Fasteners, Test Methods.
MIL-STD-1949 - Inspection, Magnetic Particle.
MIL-STD-6866 - Inspection, Liquid Penetrant.
MS51575 - Screw, Shoulder, Slotted-Head, Corrosion-Resistant Steel.
MS51576 - Screw, Shoulder, Socket-Head, Hexagon, Corrosion-Resistant Steel.
MS51975 - Screw, Shoulder-Socket-Head, Hexagon, Alloy Steel, Cadmium Plated, UNC-3A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY OF MECHANICAL ENGINEERS (ASME)/AMERICAN NATIONAL STANDARDS INSTITUTE (ANSI)

ASME/ANSI B18.3 - Socket Cap, Shoulder and Set Screws - Inch Series
ANSI B18.6.3 - Machine Screws and Machine Screw Nuts
ANSI/ASME B46.1 - Surface Texture (Surface Roughness, Waviness, and Lay)

(Application for copies should be addressed to The American National Standards Institute, 1430 Broadway, New York, NY 10018 or The American Society of Mechanical Engineers, United Engineering Center, 345 E. 47th Street, New York, NY 10017.)

ASTM

ASTM A 370 - Mechanical Testing of Steel Products
ASTM A 493 - Stainless and Heat-Resisting Steel for Cold Heading and Cold Forging-Bar and Wire
ASTM A 574 - Alloy Steel Socket-Head Cap Screws
ASTM A 582 - Free Machining Stainless and Heat Resisting Steel Bars, Hot Rolled or Cold Finished.
ASTM B 633 - Electrodeposited Coatings of Zinc on Iron and Steel
ASTM D 3951 - Standard Practice for Commerical Packaging
ASTM F 606 - Conducting Tests to Determine the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets
ASTM F 788 - Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series

(Application for copies should be addressed to ASTM, 1916 Race Street, Philadelphia, PA 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein (except for associated detail specifications, specification sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 MS sheets. The individual item requirements shall be as specified herein and in accordance with the applicable MS sheet. In the event of any conflict between requirements of this specification and the MS sheet, the latter shall govern (see 6.2).

3.2 Material. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable. Screws shall be made of alloy steel in accordance with 3.2.1, corrosion-resistant steel in accordance with 3.2.2 or 3.2.3, or non-ferrous material in accordance with 3.2.4, as specified (see 6.2 and 6.3). Mechanical properties shall be as specified in 3.3 and Tables I and II as applicable.

3.2.1 Alloy steel. Alloy steel screws shall be of a chemical composition which can be heat treated in accordance with MIL-H-6875, to meet the mechanical properties specified in 3.3.1 and 3.3.1.1.

3.2.2 Free-machining corrosion-resistant steel. Unless otherwise specified (see 6.2), screws shall be manufactured from free-machining corrosion-resistant steel conforming to Type 303 (UNS S30300), Condition A, of ASTM A 582.

3.2.3 Cold-finished corrosion-resistant steel. When specified in the contract (see 6.2), screws shall be manufactured from Type 304 (UNS S30400) or Type XM-7 (UNS S30430) in accordance with ASTM A 493.

3.2.4 Non-ferrous material. Non-ferrous screws shall be manufactured from an alloy conforming to the mechanical properties specified in Table II.

3.3 Mechanical properties.

3.3.1 Alloy steel. Alloy steel screws shall meet the mechanical property requirements specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

TABLE I. MECHANICAL PROPERTIES OF ALLOY STEEL SHOULDER SCREWS

SIZE NOM	THREAD SIZE UNC-3A NOM	MINIMUM AREA SQUARE INCHES		SHEAR STRENGTH POUNDS-MIN		TENSILE STRENGTH LBS-MIN 1/
		THREAD NECK	SHOULDER	SINGLE 2/	DOUBLE 3/	
.250	.190-24	.0139	.0475	1,170	7,980	1,950
.3125	.250-20	.0260	.0748	2,180	12,550	3,640
.375	.3125-18	.0441	.1081	3,700	18,150	6,170
.500	.375-16	.0665	.1932	5,580	32,450	9,310
.625	.500-13	.1238	.3029	10,400	50,900	17,300
.750	.625-11	.1979	.4371	16,600	73,400	27,700
1.000	.750-10	.2980	.7791	25,000	130,900	41,700
1.250	.875-9	.4140	1.2194	34,800	204,850	58,000

1/ Ultimate tensile strength is based on a stress of 140,000 PSI Min and the minumim thread neck area.
2/ Single shear strength is based on a stress of 84,000 PSI Min and the minimum thread neck area.
3 Double shear strength is based on a stress of 84,000 PSI Min and twice the minimum shoulder area.

3.3.1.1 Hardness (after heat treatment). Screws shall have a hardness range of 32 to 43HRC at the surface.

3.3.2 Free-machining corrosion-resistant steel. Free-machining corrosion-resistant steel screws shall meet the hardness requirement specified in ASTM A 582 for Type 303, Condition A.

3.3.3 Cold-finished corrosion-resistant steel. Cold-finished corrosion-resistant steel screws shall meet the tensile strength requirements specified in ASTM A 493 for Type 304 or Type XM-7.

3.3.4 Non-ferrous material. Non-ferrous screws shall meet the mechanical property requirements specified in Table II.

3.4 Protective coating or surface treatment Screws shall be furnished uncoated or with a protective coating or surface treatment as specified herein (see 6.2. and 6.3).

3.4.1 Cleaning, descaling and passivation. Corrosion-resistant steel shoulder screws shall be cleaned, descaled and passivated in accordance with QQ-P-35, Type I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

3.4.2 Cadmium plating. When specified, screws shall be cadmium plated by electrodeposition in accordance with QQ-P-416, Type II, Class 2 or by mechanical plating in accordance with MIL-C-81562, Type II, Class 2.

3.4.3 Zinc coating. When specified, screws shall be zinc coated by electrodeposition in accordance with ASTM B 633, Type II, Class Fe/Zn5 or by mechanical plating in accordance with MIL-C-81562, Type II, Class 6.

3.4.4 Other finishes. When protective finishes other than those listed in the previous paragraphs are required, they shall be as specified (see 6.2 and 6.3).

3.5 Metallographic requirements.

3.5.1 Carburization and decarburization limits. The depth of carburization, total decarburization, and partial decarburization shall be in accordance with ASTM A 574. A carbon content throughout the threads equivalent to that of the core is desirable.

3.5.2 Discontinuities. Alloy steel screws shall meet the discontinuities limitations specified in ASTM A 574. Discontinuities for corrosion-resistant steel screws shall meet the requirements specified in ASTM F 788.

3.6 Design.

3.6.1 Dimensions and tolerances. Unless otherwise specified, slotted head dimensions and slot dimensions of screws shall conform to the dimensions and tolerances specified in ANSI B18.6.3. Unless otherwise specified, all other dimensions and tolerances specified in ASME/ANSI B18.3. Dimensions shall apply after plating or coating.

3.6.2 Broaching chips. Broached sockets of screws shall have all loose chips removed. Remaining chips shall be firmly attached.

3.6.3 Threads. Unless otherwise specified (see 6.2), socket-head shoulder screws shall be Class 3A-UNC Series in accordance with with FED-STD-H28/2. Plated and coated Class 3A threads shall be as specified in the requirements covering material limits for Class 3A coated threads in FED-STD-H28/2. Unless otherwise specified (see 6.2 and 6.3), slotted-head shoulder screws shall be Class 2A UNC and UNF Series in accordance with FED-STD-H28/2. Acceptability of screw threads shall be in accordance with FED-STD-H28/20, System 22.

3.7 Surface texture. The surface roughness height of the shoulder diameter and threads of the screws before plating shall not exceed 0.8µm (32 µ in.) roughness average Ra. The surface roughness height of all other surfaces of the screw, excluding the top and side of the head and flat point, shall not exceed 3.2µm (125 µ in.) roughness average Ra values shall be interpreted in accordance with ANSI/ASME B46.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

3.8 Workmanship. Screws shall be free from burrs, cracks, seams, laps, nicks, pits, loose scale, irregular surfaces, chips and other defects that will adversely affect life or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of Sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Quality conformance inspection.

4.2.1 Lot. A lot shall consist of all screws of the same type, made from the same heat of material, heat treatment, protective coating, surface finish, size, length, and threads produced by the same suppliers facility and offered for acceptance at the same time.

4.2.2 Sampling for examination. A random sample of screws shall be taken from each lot in accordance with MIL-STD-105, Inspection Level II. The acceptable Quality Level (AQL) shall be as specified in Table III. For small lot procurement, see 4.2.7.

4.2.3 Sampling for mechanical properties and metallographic tests. A random sample of screws shall be taken from each lot in accordance with MIL-STD-105, Inspection Level S-1 for destructive testing. The AQL shall be 4.0 percent defective. For small lot procurement, see 4.2.7.

4.2.4 Sampling for protective coating or surface treatment tests. Sampling for tests of protective coating or surface treatment shall be in accordance with the applicable specification as specified (see 3.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

TABLE II. MECHANICAL PROPERTIES OF NON-FERROUS SCREWS

MATERIAL	APPLICABLE DOCUMENT	COMPOSITION CLASS OR ALLOY NUMBER	CONDITION OR TEMPER	ULTIMATE TENSILE STRENGTH PSI MIN	YIELD STRENGTH PSI MIN	ELONGATION 1/ PERCENT MIN
Manganese Bronze	QQ-B-728	Class A (UNS N05500)	Soft	55,000	22,000 3/	20
Nickel-Aluminum Bronze	QQ-C-00465	Copper Alloy No. 632 M (UNS C63200)	Quench and Temper, Heat Treatment	90,000	50,000 3/	15
Phosphor Bronze	QQ-B-750	Composition A	Hard	80,000 (dia= under .250) 70,000 (dia= .250 to .500) 60,000 (dia= over .500 to 1.000) 55,000 (dia= 1.000 to 3.000) 50,000 (dia= over 3.000)	Not Specified	Not Specified 13 15 18 18
Silicon Bronze	QQ-C-591	Copper Alloy No. 651	Hard	60,000	40,000 3/	10
Naval Brass	QQ-B-637	Copper Alloy No. 464	Half	60,000	27,000 3/	22 (dia= .500 and under) 25 (dia= over .500)
Nickel-Copper Alloy	QQ-N-281	Class A (UNS N05500)	Hot Finished (as Hot Finished or Stress Relieved)	80,000	40,000 2/	30
Nickel-Copper Aluminum Alloy	QQ-N-286	Class A (UNS N05500)	Annealed and age hardened	130,000	90,000 2/	20

1/ In 4D gage length.
2/ 0.2 percent offset.
3/ 0.5 percent extension under load.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

4.2.5 Sampling for chemical analysis. A random sample of screws shall be taken from each lot in accordance with MIL-STD-105, Inspection Level S-1 for destructive testing. The AQL shall be 4.0 percent defective. For small lot procurement (see 4.2.7).

4.2.6 Sampling for discontinuities. A random sample of screws shall be taken from each lot in accordance with MIL-STD-105, Inspection Level II for non-destructive testing. The AQL shall be 2.5 percent defective. For small lot procurement (see 4.2.7).

4.2.7 Sampling for small lots. For small lot procurement of less than 51 screws, sampling and acceptance/rejection criteria for mechanical properties, metallographic, chemical analysis, and discontinuity tests shall be as follows:

LOT SIZE	SAMPLING SIZE	NUMBER OF DEFECTIVES	
		ACCEPT	REJECT
2 TO 10	1	0	1
11 TO 50	2	0	1

4.2.8 Inspection of packaging. The sampling and inspection of the preservation, packing and container marking shall be as specified (see 5).

4.2.9 Examination.

4.2.9.1 Visual and dimensional. Each screw taken as specified in 4.2.2 shall be examined to verify conformance with this specification. Examination shall be conducted in accordance with Table III and ASME/ANSI B18.3. Any screw in the sample containing one or more defects shall be rejected, and if the number of defective screws in any sample exceeds the acceptance for that category, the lot represented by the sample shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

TABLE III. CLASSIFICATION OF DEFECTS.

CATEGORY	DEFECT	INSPECTION
CRITICAL	NONE DEFINED	METHOD
Major	AQL = 2.5	
101	Discontinuities (see 3.5.2)	CIE 1/
102	Socket dimensions (see 3.6.1)	CIE 1/
103	Threads (see 3.6.3)	CIE 1/
104	Concentricity (see 3.6.1)	CIE 1/
105	Shoulder diameter (see 3.6.1)	CIE 1/
106	Shoulder length (see 3.6.1)	CIE 1/
Minor	AQL = 4.0	
201	Protective coating or surface treatment (see 3.4)	Visual/ CIE 1/
202	Surface texture (see 3.7)	Visual/ CIE 1/
203	Head diameter (see 3.6.1)	CIE 1/
204	Head chamfer (see 3.6.1)	CIE 1/
205	Head height (see 3.6.1)	CIE 1/
206	Head side height (see 3.6.1)	CIE 1/
207	Head fillet extension (see 3.6.1)	CIE 1/
208	Head fillet radius (see 3.6.1)	CIE 1/
209	Bearing surface (see 3.6.1)	CIE 1/
210	Shoulder neck diameter (see 3.6.1)	CIE 1/
211	Shoulder neck width (see 3.6.1)	CIE 1/
212	Edge of shoulder (see 3.6.1)	CIE 1/
213	Thread neck diameter (see 3.6.1)	CIE 1/
214	Thread neck width (see 3.6.1)	CIE 1/
215	Thread neck fillet (see 3.6.1)	CIE 1/
216	Thread length (see 3.6.1.)	CIE 1/
217	Screw Length (see 3.6.1)	CIE 1/
218	Screw point chamfer (see 3.6.1)	CIE 1/
219	Broaching chips (see 3.6.2)	Visual/ CIE 1/

1/ Commercial Inspection Equipment

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

4.3 Test methods.

4.3.1 Mechanical property test. The hardness test as specified in 4.3.1.1, axial tension test as specified in 4.3.1.2, and double shear strength test as specified in 4.3.1.3 shall be mandatory tests of finished screws and specimens as applicable to determine compliance to meet the mechanical property requirements of 3.3.

4.3.1.1 Hardness test. Samples selected as specified in 4.2.3 shall be subjected to a hardness test conducted in accordance with ASTM F 606 at room temperature on a clean, flat surface, capable of sustaining the load imposed by the hardness tester. Non-ferrous screws shall be excluded from this test.

4.3.1.2 Axial tension test. Samples selected as specified in 4.2.3 shall be subjected to a full-size tension test conducted in accordance with ASTM F 606. The minimum required length for tension testing shall be 3D. The speed of testing, as determined with a free running crosshead shall be a maximum of 1 in./min.

4.3.1.3 Double shear strength test. Samples selected as specified in 4.2.3 shall be subjected to a double shear strength test conducted in accordance with MIL-STD-1312, Test No. 13, with the following requirements. The shear plane shall be at least one screw diameter away from the end of the screw shoulder. Clearance between the loading and supporting members shall be 0.005 in. maximum. Hardness of the loading and supporting members shall be 55HRC minimum. The holes for the screws shall have sharp edges and shall be the same size as the shoulder diameter of the screw.

4.3.1.4 Single shear strength test. This test shall be conducted on those fasteners that cannot be tested in double shear. Samples selected as specified in 4.2.3 shall be subjected to a single shear strength test conducted in accordance with MIL-STD-1312, Test No. 20.

4.3.2 Metallographic test. Samples selected as specified in 4.2.3 shall be subjected to a metallographic test conducted in accordance with ASTM A 574 to determine conformance with 3.5.

4.3.3 Ductility test (non-ferrous screws). Samples selected as specified in 4.2.3 shall be tested for elongation to determine compliance with 3.3.3. The test shall be conducted in accordance with ASTM A 370 on a turned shank specimen having dimensions equal to the largest practical specimen which can be made from the screw.

4.3.4 Protective coating or surface treatment tests. Protective coating or surface treatment tests shall be conducted in accordance with the applicable specification, as specified in 3.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

4.3.5 Chemical analysis. Samples selected as specified in 4.2.5 shall be subjected to a chemical analysis in accordance with Federal Test Method Standard No. 151, Method 111.2 or Method 112.2. In case of dispute Method 111.2 shall be the basis for acceptance. When a mill certificate covering chemical requirements can be furnished, it will be accepted in lieu of the chemical analysis required by 4.2.5 (see 6.2).

4.3.6 Discontinuity inspection test. For sizes .250 and smaller, samples selected as specified in 4.2.6 shall be subjected to the method of inspection in accordance with ASTM F 788 to meet the requirements of 3.5.2. Marking of inspected parts shall be optional. For sizes .3125 and larger, samples selected as specified in 4.2.6 shall be subjected to MIL-STD-1949 or MIL-STD-6866 inspection methods as applicble to meet the requirements of 3.5.2.

5. Packaging.

5.1 Packaging requirements. The requirements for packaging shall be in accordance with ASTM D 3951.

5.2 Marking for civil agencies. Marking for all containers shall be in accordance with FED-STD-123.

6. Notes.

6.1 Intended use. Shoulder screws are intended for use in punch and die operations such as location and retention of spring strippers of press tools, and as fulcrums or pivots in machine design that involve links, levers, or other oscillating parts.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number and date of this specification.
b. Title, number and date including part number specified in accordance with military document (see 6.3).
c. Material certification, if required (see 3.2 and 4.3.5).
d. Cold-finished corrosion-resistant steel, if required (see 3.2.3).
e. Protective coating or surface treatment, if required (see 3.4).
f. Thread series and class (see 3.6.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

6.3 Military acquisition. Items acquired under this specification for military use are to be limited to the variety shown on the applicable Military Standards as specified herein:

MS51575 -Screw, Shoulder, Slotted-Head, Corrosion-Resistant Steel.
MS51576 -Screw, Shoulder, Socket-Head, Hexagon, Corrosion-Resistant Steel.
MS51975 -Screw, Shoulder-Socket Head, Hexagon, Alloy Steel, Cadmium Plated, UNC-3A.

6.4 Subject term (key word) listing.

Heaxagon socket-head shoulder screw
Shoulder screw
Slotted shoulder screw
Slotted-head shoulder screw
Socket-head shoulder screw

6.5 Changes from previous issue. Asterisks (or vertical lines) are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army-AR
Navy-AS
Air Force-99

Review Activities:
Army-ME
Navy-OS
Air Force-82
NASA-86

User Activities:
NSA-NS

Preparing Activity:
Army-AR

Agent:
DLA-IS

(Project 5305-1585)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-S-21472C	

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T09:38Z
Check the source to verify that this is the current version before use.