GGG-N-71C
July 23, 1976
SUPERSEDING
Fed. Spec. GGG-N-71B
August 2, 1963

FEDERAL SPECIFICATION

NAIL SET

This specification was approved by the Commissioner, Federal Supply Service General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers nail sets used for setting finishing nails below the surface of the wood.

1.1.1 Federal specification coverage. Federal specifications do not include all varieties of the commodity indicated by the title of the specification, but are intended to cover only those generally used by the Federal Government.

1.2 Classification.

1.2.1 Type. Nail sets covered by this specification shall be of the one type.

1.2.2 Sizes. Size shall be defined as meaning the diameter at the point. Nail sets shall be furnished in the following sizes as specified (see 6.1) 1/32, 1/16, 3/32, 1/8, and 5/32 inch.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-40 - Packaging and Packing of Hand Tools.

Federal Standard:

Fed. Std. No. 358 - Sampling Procedures.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles, and Seattle WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:37Z
Check the source to verify that this is the current version before use.

American Society for Testing and Materials (ASTM) Standard:

E 18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Tests For.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

3. REQUIREMENTS


3.1 Illustrations. The illustrations shown on figure 1 are for convenience of identification and are not intended to preclude purchase of nail sets which are otherwise in accordance with the requirements of this specification.

3.2 Material and construction. Nail sets shall be fabricated of steel, and have either a circular cross section throughout, a square body with a circular head, or a circular body with a square head. The body and head shall be not less than 1/4 nor more than 3/8 inch in diameter, or across the flat of the square portion. Nail sets shall have an overall length of not less than 3-7/8 inches nor more than 4-1/4 inches. The body portion of the nail set shall be neatly knurled or impressed. The head, body, and punch end shall be concentric with the longitudinal axis.

3.3 Punch end. The punch end shall be neatly cupped and chamfered. The punch end of all nail sets shall be of circular cross section and tapered from the body portion to the tip. The tapered portion shall be not less than 1-5/16 inches in length. The cup edge shall not distort, crack, fracture, spall, flatten, or bend when tested as specified in 4.4.2. The punch end shall be heat treated within a minimum of 1/2 inch from the cupped point to a hardness of Rockwell C 53 to C 63 (see 4.4.1).



Circular cross section throughout



Circular body, square head.



Square body, circular head.

FIGURE 1. Nail sets

3.4 Head end. The head end shall be rounded or chamfered. The head shall not distort, crack, upset, fracture, or spall when tested as specified in 4.4.2. The head shall be heat treated within a minimum of 1/2 inch from the end to a hardness of Rockwell C 35 to C 61 (see 4.4.1).

3.5 Coatings. Each nail set shall be furnished with a protective coating of paint, lacquer, oxide, or zinc plating in accordance with good commercial practices (see 6.1).

3.6 Identification marking. Each nail set shall be marked in a plain and permanent manner with the size and the manufacturer's name or with a trademark of such known character that the source of manufacture may be readily determined.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:37Z
Check the source to verify that this is the currentversion before use.

3.7 Workmanship. The finished nail sets shall be clean, and free from scale, pits, burrs, cracks, or any imperfections which may affect their appearance, durability or serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Inspection of materials and components. In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified herein, or, if none, in accordance with this specification.

4.2 Sampling procedures. Sampling procedures shall be in accordance with FED-STD-358.

4.3 Testing. Each sample unit shall be tested in accordance with 4.3.1 and 4.4.1 thru 4.4.2 as applicable.

4.3.1 Hardness. Hardness tests shall be conducted in accordance with ASTM E 18. When grinding is necessary to prepare the test surface, the amount of material removed must not exceed 0.007 inches on the surface contacted by the indentor.

4.4 Tests.

4.4.1 Hardness test. The hardness test shall be in accordance with the applicable requirements to determine compliance to the requirements of 3.3 and 3.4. Impressions shall be taken 1/8 and 3/8 inch from both the head and punch ends.

4.4.2 Striking test. The nail sets shall be held firmly by hand in a vertical position with the cupped punch end resting on a steel plate having a hardness of Rockwell C 26 to C 30. The nail set shall be struck 15 blows, each blow to be of sufficient force to produce a full circle impression of at least 0.005 inch deep to determine compliance with 3.3 and 3.4.

4.5 Inspection of preparation for delivery requirements. An inspection shall be made to determine that the preservation, packaging, packing, and marking comply with the requirements in section 5.

5. PREPARATION FOR DELIVERY

5.1 Preservation, packaging, packing, and marking. Preservation, packaging, packing, and marking shall be in accordance with the requirements of PPP-P-40.

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Size required (see 1.2).
(c) Type coating required (see 3.5).
(d) Level of preservation, packaging, packing, and marking (see 5.1).

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:37Z
Check the source to verify that this is the current version before use.

Military Interests:

Army - GL, ME, EL
Navy - SH, YD, MC
Air Force - 99

PREPARING ACTIVITY: GSA - FSS

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See Section 2 of this specification to obtain extra copies and other documents referenced herein. Price 25 each.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:37Z
Check the source to verify that this is the currentversion before use.