W-T-1553/04
August 12, 1996

FEDERAL SPECIFICATION SHEET

TAPE, INSTRUMENTATION RECORDING, MAGNETIC OXIDE-COATED, 800 OERSTEDS COERCIVITY, 2 DROPOUTS PER 100 FOOT (FT) 30 METERS (M)) OF TAPE, WITH 76.2 MILLIMETER (MM) (3 INCH) CENTER-HOLE DIAMETER REEL.

The General Services Administration has authorized the use of this federal specification, by all federal agencies.

The complete requirements for procuring the instrumentation recording tapes described herein shall consist of this document and the latest issue in effect of W-T-1553.

1 Scope. This federal specification sheet covers the general requirements for 800 oersteds (Oe) coercivity magnetic oxide-coated, instrumentation recording tape with four dropouts per 100 foot (30 m) of tape.

2 Classification. This federal specification sheet uses a classification system which is included in the Part or Identification Number (PIN). The PIN shall be WT155304 (plus additional indicators from table I). Complete PIN example: WT155304BA046T (see table I).

3. Requirements.

3.1 Design and construction. Instrumentation recording tape supplied to this slash sheet shall be as specified herein.

3.2 Physical properties.

3.2.1 Base film material. The base film material shall be polyester.

3.2.2 Base film thickness. The base film thickness shall be 20.6 μm (0.810 mil) nominal.

3.2.3 Oxide coating thickness. The oxide coating thickness shall be 4.8 μm (0.190 mil) nominal.

3.2.4 Backcoat thickness. The backcoat thickness shall be 0.76 μm (0.030 mil) nominal.

Beneficial comments, recommendations, additions, deletions, clarifications, etc., and any data which may improve this document should be sent to: Defense Supply Center, Columbus, ATTN: DSCC-VAM, Post Office Box 3990, Columbus, OH 43216-5000, or telephone (614) 692-0548, or facsimile (FAX) (614) 692-6939.

AMSC N/A FSC 5835

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:34Z
Check the source to verify that this is the current version before use.

3.2.5 Tape width. The tape width shall be as specified in table I.

3.2.6 Tape length. The tape length shall be as specified in table I.

TABLE I. Characteristics of available PIN options.

Federal specification indicator	Tape width indicator: B: For a 1-inch (25.4 mm) nominal tape. (see 1.2.2 of W-T-1553)	Reel and hub indicator (see 1.2.3 of W-T-1553)	Tape length indicator (see 1.2.4 of W-T-1553)	Optional testing level indicator. (see 1.2.5 of W-T-1553)
WT155304	B	A	046	T or blank 1/
WT155304	B	B	072	
WT155304	B	C	092	

1/ In accordance with W-T-1553, to order standard qualified products list product leave this PIN code blank.

3.2.7 Magnetic layer material. The magnetic layer material shall be Cobalt doped Gamma Ferreric Oxide Fe_2O_3.

3.3 Magnetic properties.

3.3.1 Retentivity. The retentivity shall be 1,400 percent ±10 percent Gauss.

3.3.2 Coercivity. The coercivity shall be 800 percent ±10 percent Oe.

3.4 Performance specifications.

3.4.1 Saturated output. The saturated output shall be as specified in table II.

TABLE II. Saturated output.

Input frequency (kHz)	Wavelength (mil)	Wavelength response in decibels (dB).
500	0.240 mil (6.1 μm)	0 ±2.0
500	0.120 mil (3.05 μm)	0 ±2.0
500	0.060 mil (1.52 μm)	0 ±2.0
500	0.030 mil (0.76 μm)	0 ±3.5

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:34Z
Check the source to verify that this is the current version before use.

3.4.2 Output level uniformity, long term and short term. The long and short term output level uniformity at 1 megahertz shall be 2.0 dB maximum for both the center and the edge track.

3.4.3 Electrical resistance. The maximum electrical resistance of the conductive back coating surface shall be less than 1.8×10^5 ohms per square.

3.4.4 Instantaneous nonuniformity (dropouts per 100 foot (30 m)). The instantaneous nonuniformity shall be less than an average of 2 dropouts per 100 ft (30 m) per tape measured across the width and its entire working lengths, randomly distributed.

3.5 Temperature.

3.5.1 Operating temperature. The operating temperature shall be +4°C (40°F) to +49°C (120°F).

3.5.2 Storage temperature. The storage temperature shall be +4°C (40°F) to +32°C (90°F).

3.6 Humidity.

3.6.1 Operating humidity. The operating humidity shall be 50 percent relative humidity (RH) ±15 percent.

3.6.2 Storage humidity. The storage humidity shall be less than 40 percent RH.

3.7 Used or reconditioned material. A manufacturer shall not furnish any instrumentation recording tape which is used or reconditioned or is comprised of used or reconditioned material.

4. Quality assurance provisions. Quality assurance provisions shall be as specified in W-T-1553 except the instantaneous non-uniformity test shall be performed on 100 percent of the lot and as specified herein (see 3.4.4). Defective reels shall be removed from the lot and not be supplied to the specification. (NOTE: For T level product, the instantaneous non-uniformity test shall be performed on a sample basis by the government laboratory in accordance with W-T-1553.)

4.1 Tapes for qualification. PIN WT155304BA046 and WT155304BC092 shall be utilized for qualification of this specification sheet.

5. Packaging. Packaging shall be as specified in W-T-1553.

6. Notes.

6.1 PIN. The PIN should be used for Government purposes to buy instrumentation tapes to this federal specification sheet. See 1.2 for PIN format.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:34Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians

Army - CR
Navy - EC
Air Force - 99

Review activities

Navy - AS, NV, OM
Air Force - 80

CIVIL COORDINATING ACTIVITY:

NASA - NPPO

Preparing Activity:
DLA-ES

(Project 5835-0112-04)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:34Z
Check the source to verify that this is the current version before use.