[METRIC]
A-A-2627A
December 28, 1990
SUPERSEDING
A-A-2627
October 1, 1989

COMMERCIAL ITEM DESCRIPTION

PLATE, LITHOGRAPHIC, PRESENSITIZED

The General Services Administration has authorized the use of this commercial item description.

This description covers presensitized lithographic offset plates used in the printing industry.

Salient characteristics.

Description. 20 millimeter plate thickness, water start, presensitized, negative-working lithographic plate with a pigmented plastic printing surface. Minimum of 5000 impressions. The high-speed subtractive coating shall produce a violet visible image when exposed to ultraviolet light.

Plate size. See Table of Available Plate Sizes.

Coating. The sensitized coating shall be uniform and free from coating streaks, pinholes, dirt, abrasion marks, spots and mottling which may affect the printing quality of the plates.

Instruction sheet. An instruction sheet giving complete details regarding the handling of the plates shall be furnished with each package of plates.

Expiration date. The expiration date of the sensitized plates shall be not less than 24 months from the date of manufacture.

Workmanship. The sensitized plates shall be free from dents, kinks and waves. The edges of the plates shall be straight and the corners shall be square and true. The plates shall be free from any defects which may affect the durability, appearance or serviceability of the plates.

QUALITY ASSURANCE PROVISIONS.

Responsibility for inspection and testing. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein.

First article testing and approval. As prescribed by Federal Acquisition Regulation (FAR), Chapter 9, Part 3, the contractor shall furnish plates as specified for examination and testing within the time frame specified to prove prior to starting production that his production methods and choice of design detail will produce plates that comply with the requirements of the CID.

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Examination and tests specified shall be subject to surveillance and approval by the Government.

Any changes or deviations of subsequently produced plates from the approved plates during production will be subject to the approval of the contracting officer. Approval of the first approved plates will not relieve the contractor of his obligation to furnish plates conforming to the CID.

Sampling. Sampling for examination and tests shall be in accordance with MIL-STD-105. Unless otherwise specified, the general inspection level II AQL - 2.5 percent defective for visual examination, level S-2 AQL - 1.5 percent for performance testing shall apply.

Visual examination. Samples selected shall be examined for the following defects.

1. Size of plates not as specified.
2. Thickness of plates not as specified.
3. Plate coating not as specified.
4. Workmanship not as specified.

The presence of any of the defects may be considered as grounds for rejection.

Performance testing. The samples selected in accordance with the requirements of the CID shall be tested to verify the print quality specified herein. Prior to actual testing, the samples shall be conditioned through high-low temperature cycling per environmental conditions requirements of the following paragraph. At the end of the cycling period the samples shall be brought to room temperature and examined for discoloration or other damage, evidence of which may constitute failure of this test. Samples which passed the temperature cycling test shall then be tested to verify print quality. Testing shall be performed as delineated in the following paragraph. Nonconformance with the requirements of the CID for printing quality shall be regarded as a test failure.

Environmental conditions. The plates, in their original unopened package, shall not be damaged under the following storage conditions: A high of plus 49 $\pm$ 2 degrees C. for 4 hours daily for 2 days to minus 10 $\pm$ 2 degrees C. for 12 consecutive hours with negligible air movement.

Print quality. The sample plates, containing a combination of solids, line, and 150 line halftone images, shall be placed in an offset press and not less than the number specified herein shall be printed. The printed sheet shall have a fine highlight dot and a clean open-shadow dot on 150 line halftone images. A comparison of the first and last sheets shall show no deterioration of the image or evidence of scumming in the non-printing area.

Regulatory requirements. In accordance with Section 23.403 of the Federal Acquisition Regulations, the Government's policy is to

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing the supplier's employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling and marking. The preservation, packaging, packing, labeling and marking shall be as specified in the contract or purchase order.

Note: Purchaser shall specify plate size and NSN.

Plate size	Edge type	NSN
22.9 X 30.5	Punched	3610-01-306-4971
22.9 X 30.5	Straight	3610-01-306-4972
23.8 X 40.0	Notched	3610-01-306-4969
24.3 X 40.0	Straight	3610-01-306-4970
25.4 X 38.1	Straight	3610-01-306-4973
25.4 X 38.1	Punched	3610-01-306-4974
25.4 X 39.4	Straight	3610-01-306-8343
25.4 X 40.6	Straight	3610-01-306-4975
27.3 X 47.0	Punched	3610-01-306-4976
27.9 X 45.1	Punched one end	3610-01-306-4977
27.9 X 45.7	Punched	3610-01-306-4978
27.9 X 47.0	Punched	3610-01-306-4979
29.8 X 45.7	Punched	3610-01-306-4980
32.4 X 47.0	Punched	3610-01-306-4981
39.4 X 46.7	Punched	3610-01-306-4982
40.6 X 44.5	Straight	3610-01-306-4983
45.7 X 38.1	Straight	3610-01-306-4984
48.9 X 57.5	Straight	3610-01-306-4985
48.9 X 58.1	Straight	3610-01-306-4986

TABLE OF AVAILABLE PLATE SIZES
Dimensions in centimeters (cm)
Tolerances on plate sizes shall be ± 0.3 cm.

Copies of MIL-STD-105 can be obtained from the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

(MAS 36 II, SIN 51-2002b)

MILITARY INTERESTS:

NONE

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.