[METRIC]

A-A-304B
November 27, 1991
SUPERSEDING
A-A-304A
May 10, 1985

COMMERCIAL ITEM DESCRIPTION

BAG, PAPER (FOIL LAMINATED, FLAME RESISTANT, MOISTURE RESISTANT)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Federal Specification UU-B-23, which has been canceled.

This description covers foil laminated, flame resistant, moisture resistant paper bags with pressure sensitive adhesive attachment tabs.

1. SALIENT CHARACTERISTICS:

A) Construction. Bags furnished under this description shall be made from paper containing not less than 5 percent post consumer recovered material, as defined by 40 CFR Part 250, laminated to aluminum foil with a water and heat resistant adhesive. Before the paper is laminated, it shall be tested for Flame Resistance in accordance with TAPPI test method T 461 as Type I paper. The Char Length determined by this test shall be not more than 110 mm. The laminated material shall have an Internal Tearing Resistance in the machine direction of not less than 52 g when tested in accordance with TAPPI test method T 414. Bags shall be formed with a lip not less than 13 mm wide across the entire width of the back face. The aluminum foil side of the laminate shall be on the inside of the bags. Seams, made with a water resistant adhesive, shall be located on the back face and, if needed, on the bottom of the bags. Two pressure sensitive adhesive tabs shall be attached at the top of the back face with their center lines 65 $\pm$ 15 mm apart. Each tab shall extend beyond the top edge of the bag to provide an area of not less than 325 mm^2 for attaching the bag to horizontal surfaces. The adhesive in the attachment area shall be protected with an easily removable piece of release paper. Bags shall have 2 legends printed on them in an easily legible color. On the back face, below each tab, an arrow pointing up and the legend: "PULL TAB UPWARD" shall be printed. The front face shall have the legend: "THIS BAG MADE OF ALUMINUM FOIL AND FLAME RESISTANT PAPER" printed on it. Bags shall be no more than 2 months old when delivered to the Government. Bags shall pass the Holding Strength and Leakage Test specified in Section 2.

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:06Z
Check the source to verify that this is the current version before use.

B) Style and capacity. Bags shall be square style or self opening style, at the option of the supplier. The face width shall be not less than 145 mm. The gusset width or the bottom width, which equals 1/2 the perimeter of the top of the bag minus the face width, shall be not less than 83 mm. The overall height shall sufficient to give a bag capacity of not less than 4.01 Liters. Bag capacity shall be determined through the following equations:

F = face width,
P = perimeter of the top of the bag,
H = overall height of the bag, excluding the lip.

Capacity of square bags = $F[0.5P - F][H - (0.25P - 0.5F)]$

Capacity of self opening bags = $F(0.5P - F)(H)$

C) Workmanship. Bags shall be uniformly constructed, free from holes, tears, cuts, splits or defects that might impair their usefulness or appearance. Bags shall not adhere together. All seams shall adhere firmly throughout their area.

2. QUALITY ASSURANCE:

A) Responsibility for Inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

B) Sampling. Bags and shipping containers shall be sampled in accordance with MIL-STD-105.

C) Examination of Bags for Construction and Workmanship. The lot size shall be expressed in units of bags. The sample unit shall be 1 bag. The Inspection Level shall be S-2, the AQL shall be 2.5 percent defective.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:06Z
Check the source to verify that this is the current version before use.

D) Examination of Bags for Style and Capacity. The lot size shall be expressed in units of bags. The sample unit shall be 1 bag. The Inspection Level shall be S-2, the AQL shall be 2.5 percent defective.

E) Testing of Bags for Holding Strength and Leakage. The lot size shall be expressed in units of bags. The sample unit shall be 1 bag. The Inspection Level shall be S-1, the AQL shall be 2.5 percent defective.

Holding Strength and Leakage Test. Attach the bag firmly to the edge of a smooth horizontal surface so that the bag hangs freely from the edge supported only by the pressure sensitive adhesive tabs. Place 225 ± 5 g of commercial type facial tissues in the bag and carefully pour 225 ± 5 milliliters of water over the tissues. Let the bag hang undisturbed for not less than 16 hours, then examine the bag. If the attachment tabs no longer support the bag, or if water has leaked through the bag, the bag is defective.

E) Examination of Packaging, Packing, Marking, and Palletization. The lot size shall be expressed in units of issue of bags. The sample unit shall be one fully prepared shipping container. The Inspection Level shall be S-2, the AQL shall be 4.0 percent defective.

3. PACKAGING, PACKING, MARKING, AND PALLETIZATION:

Packaging, packing, marking, and palletization shall be as specified in the contract or order.

4. REFERENCED DOCUMENTS:

The issues of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:06Z
Check the source to verify that this is the current version before use.

A) Industry Standards

TAPPI T 414 - Internal tearing resistance of paper (Elmendorf-type method)

TAPPI T 461 - Flame resistance of treated paper and paperboard

These documents are available from TAPPI, 15 Technology Parkway South, P. O. Box 105113, Norcross, GA 30092.

B) Code of Federal Regulations

40 CFR Part 250

The Code of Federal Regulations is available from the Superintendent of Documents, U. S. Government Printing Office, Washington, DC 20402

C) Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

This document is available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

5. NOTES:

Purchasers shall specify packaging, packing, marking and palletization required.

MILITARY INTERESTS:

No official DOD interest in this Commercial Item Description has been registered.

CIVIL AGENCY COORDINATING ACTIVITY:

VA - OSS

PREPARING ACTIVITY:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:06Z
Check the source to verify that this is the current version before use.