INCH-POUND

MIL-W-5665K
AMENDMENT 1
25 April 1990

MILITARY SPECIFICATION

WEBBING, TEXTILE, COTTON WARP

This amendment forms a part of Military Specification MIL-W-5665K, dated 4 September 1987, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 5

Table I, opposite "Type VIII", under "Breaking strength, warp full width (pounds), min": Delete "2700" and substitute "2000".

PAGE 7

Table III: Add the following requirements following type IV in their respective columns:

"Type	Width (inches)	Thickness (inches)	Weight (oz/yd), max.	Breaking strength, warp full width (pounds), min	Ply of warp ends, min
V	5±1/8	0.050 - 0.100	4.3	2750	3

No of warp ends full width, min	Filling (yarns per inch), min 2/	Catch-cord yarn size		Filling yarn size (±5 percent)
		Bobbin 3/	Latch needle 3/	
350	32	8/2	----	8/2"

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T05:29Z
Check the source to verify that this is the current version before use.

Table III, opposite "Type VIII", under "Breaking strength, warp full width (pounds), min": Delete "2700" and substitute "2000".

PAGE 10

3.9: Delete and substitute:

"3.9 Length and put-up Unless otherwise specified (see 6.2), webbing shall be furnished in rolls containing not more than 110 yards nor less than 90 yards per roll, except for types V, VII, X, XV, and XIX webbing, which shall be furnished in rolls containing no more than 55 yards nor less than 45 yards per roll. Unless otherwise specified, each roll shall contain no more than three pieces, and no piece shall be less than 10 yards in length."

Custodians.

Army - GL
Navy - AS
Air Force - 99

Preparing activity:

Army - GL

(Project 8305-0335)

Review activities:

Army - MD
Navy - NU, MC
Air Force - 82
DLA - CT

User activity:

Army - ME

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T05:29Z
Check the source to verify that this is the current version before use.