SS-S-001534(GSA-FSS)
December 2 1968
(See Section 6)

INTERIM FEDERAL SPECIFICATION

SHINGLES, ASPHALT (MINERAL SURFACED, CLASSES A, B, AND C FIRE RATING)

This Interim Federal Specification was developed by the General Services Administration, Federal Supply Service, Washington, D. C. 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the general requirements for asphalt shingles class A, B, and C fire ratings. These shingles are square butt type and are applied with a double coverage of material in addition to the two-inch headlap (see 6.6).

1.2 Classification.

1.2.1 Class and type. The shingles furnished under this specification shall be designated according to their resistance to relative degrees of fire exposure and wind resistance, as specified (see 6.2):

Class A - Asphalt shingles, effective against severe fire exposures.

Type I - Wind Resistant (see 6.4).
Type II - Nonwind Resistant (see 6.4).

Class B - Asphalt shingles, effect against moderately severe fire exposures.

Type I - Wind Resistant (see 6.4).
Type II - Nonwind Resistant (see 6.4).

Class C - Asphalt shingles, effective against average fire exposure.

Type I - Uniform Thick, Wind Resistant (see 6.4).
Type II - Thick Butt, Wind Resistant (see 6.4).
Type III - Uniform Thick, Nonwind Resistant (see 6.4).
Type IV - Thick Butt, Nonwind Resistant (see 6.4).

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification to the extent specified herein.

Federal Specifications:

PPP-C-650 - Crates, Wood, Open and Covered.
PPP-F-320 - Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes.

Federal Standard:

Fed. Std. No. 123 - Marking for Domestic Shipment (Civilian Agencies).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a sbuscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.)

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.)

(Federal Government activities may obtain copies of Federal Specifications, Standards and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials Standards:

A 239 - Method of Test for Uniformity of Coating by the Preece Test (Copper Sulfate Dip) on Zinc Coated (Galvanized) Iron or Steel Articles.
D 228 - Methods of Testing Asphalt Roll Roofing, Cap Sheets, and Shingles.
D 225 - Shingles, Asphalt, Surfaced with Mineral Granules.
E 108 - Methods of Fire Testing Roof Coverings.

(Application for copies should be addressed to the American Society for Testing and Materials 1916 Race Street, Philadelphia, Pa. 19105.)

Underwriters' Laboratories, Inc. Publications:

UL 55B - for Class C Asphalt Organic Felt Sheet Roofing and Shingles.
UL 790 - Test Methods for Fire Resistance of Roof Covering Materials.

(Application for copies should be addressed to the nearest Underwriters' Laboratories, Inc. 207 East Ohio St., Chicago, Ill. 60611; 2550 Dundee Road, Box 247 Northbrook, Ill. 60062; Walt Whiteman Road, Melville, Long Island, N. Y. 11749; 1655 Scott Blvd., Santa Clara, Calif. 95050.)

3. REQUIREMENTS

3.1 Material. All class of shingles shall consists of asphalt together with organic or inorganic felt or any combination of these materials at the manufacturer's option and surfaced with mineral surfacing materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

3.2 Fire and Casualty Hazards.

3.2.1 When specified (see 6.2), each contractor shall submit to the contracting agency proof that the shingles he proposes to supply under this specification conform to the applicable requirement of UL 790 or ASTM E-108 for the class of shingle specified by the contracting authority. The label, or listing with re-examination, of the Underwriters' Laboratories, Inc. may be accepted as evidence that the shingles conform to this requirement.

3.2.2 In lieu of the label, or listing with reexamination, the contractor may submit independent proof satisfactory to the contracting agency that the shingles conform to the applicable requirements of the published standards, including Methods of Test of UL 790 or ASTM E-108.

3.3 Minimum weights. The minimum weight per square shall be one of the following:

Class A

(a) 270 lbs. organic felt-based shingle.
(b) 200 lbs. for inorganic mat-based shingles.

Class B

(a) 235 lbs. organic felt-based shingles.
(b) 185 lbs. inorganic mat-based shingles.

Class C

(a) The shingles shall conform to the requirements of UL 55B or ASTM D-225.

3.4 Wind resistance. To be classified as Type I, shingles must have either an adhesive or locking device which secures the exposed edge of the shingle to the underlying layers of roofing. The adhesive or other device must enable the shingle to meet the requirements of the Underwriters' Laboratories as explained in 6.4.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Unless otherwise specified, inspections by the supplier may be performed on a statistical or production lot basis to assure that the quality of manufacture is equal to the standards set by Underwriters' Laboratories, Inc., and need not be performed on the particular lot purchase. The records of such inspections shall be kept complete and available to the Government.

4.2 Sampling.

4.2.1 Lot. Unless otherwise specified (see 6.2), a lot shall consists of all bundles of the same class and type shingles offered for delivery at the same time.

4.2.2 Sampling for visual examination. Sampling shall be in accordance with MIL-STD-105, using inspection level S-3. The sample unit shall be one bundle of shingles.

4.2.3 Samples for tests. Sampling of lots for fire resistance shall be in accordance with UL 790 (see 3.2 and 3.4). Sampling of lots for weight determination shall be in accordance with ASTM D 228 for lots consisting of more than 1000 bundles. Sampling for lots of 1000 bundles and less shall be in accordance with level S-2 in MIL-STD-105. The sample unit shall be one bundle of shingles.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

4.3 Examination.

4.3.1 Defects. Both types of shingles shall be examined for defects listed in table I. The acceptable quality levels (AQL's) shall be 2.5 percent defective for major defects and 4.0 percent defective for minor defects.

TABLE I. Classification of defects, end item

Defects	Major	Minor
Shingles not of like description	X	
Shingles cracked	X	
Edges torn	X	
Corners crushed	X	
Areas not mineral surfaced		X
Damage or defects affecting function or serviceability	X	
Damage or defects not affecting function or serviceability		X

4.3.2 Examination of preparation for delivery. An examination shall be made to determine that packaging, packing, and marking requirements of the applicable contract or order are complied with. Defects shall be scored in accordance with table II. The lot size shall be the number of bundles or shipping containers fully prepared for delivery, with the exception that containers need not be closed if containers are required. Examination shall be made in two phases; first an examination of bundles in process of packaging, and second an examination of containers fully prepared for delivery. The sample unit for each of the two phases shall be one bundle or container prepared for delivery as set forth above. The inspection level shall be S-2 of MIL-STD-105, with an AQL of 4.0 percent defective.

TABLE II. Classification of preparation for delivery defects.

Examine	Defects
Marking (bundles and container, as applicable)	Omitted; incorrect, illegible, of improper size, location, sequence, or method of application.
Materials	Component missing, damaged, defective, or as not as specified.
Workmanship (as applicable)	Inadequate or improper packaging or packing, such as closure or sealing of bundles; improper or incomplete closure of containers; loose strapping or number or positioning of strapping not as specified; inadequate stapling; bulging or distortion of containers.
Bands of steel wire ties or steel strapping on bundles, as applicable	Missing, loose or not secure or not number specified.

4.4 Test methods.

4.4.1 Weight. The weight of each type of shingle shall be determined in accordance with ASTM D 228 (see 3.3 and 4.2.3).

4.4.2 Fire resistance. Both types of shingle shall be tested in accordance with UL-790 or ASTM E-108 (see 3.2 and 4.2.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Shingles of like description shall be packaged together in a bundle whose weight does not exceed 90 pounds. The ends, sides, top, and bottom of each bundle shall be enclosed in a continuous sheet of fiberboard meeting the requirements of PPP-F-320, type CF, class-weather resistant. The fiberboard shall be scored to insure a compact load. The bundle shall be secured with not less than 2 bands of steel wire ties or flat steel strapping to form a nonshifting load.

5.1.2 Level B. Shingles of like description shall be packaged as specified in 5.1.1, except the fiberboard shall be type CF, class domestic. Alternatively, the shingles may be packaged by wrapping each bundle in a continuous sheet of kraft paper having a basis weight of not less than 90 pounds. The wrap shall be sealed along the top seam and ends.

5.1.3 Level C. The shingles shall be packaged in accordance with the supplier's commercial practice.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 Level A. Bundles of shingles of like description shall be packed together in a crate conforming to PPP-C-650, style A, type optional.

5.2.2 Level B. Unless otherwise specified (see 6.2), shingles packaged as specified in 5.1.1 or 5.1.2, shall not require additional packing.

5.2.3 Level C. The shingles shall be packed to insure carrier acceptance and safe delivery to destination in containers complying with the rules and regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 Civil agencies. In addition to markings required by the contract or order, the bundles and shipping container shall be marked in accordance with Fed. Std. No. 123.

5.3.2 Military agencies. In addition to markings required by the contract or order, the bundles and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. Shingles covered by this specification are intended for roofing on decks with a positive drain and a slope exceeding 2 inches in 12 with a specification, and 4 inches in 12 with a general specification.

6.2 Ordering data. The purchaser should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, symbol, and date of this specification.
(b) Class and type of shingle required (see 1.2).
(c) If certification of compliance is required (see 3.2.1).
(d) Size of lot if different from 4.2.

6.3 Supersession data. This specification includes the requirements of Fed. Spec. SS-S-294a, December 7, 1966; Fed. Spec. SS-S-295a, December 7, 1966; Fed. Spec. SS-S-298b, November 26, 1962; and Fed. Spec. SS-S-300b, November 26, 1962.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

6.4 Underwriters' Laboratories have developed a guide specification for roof coverings which establishes criteria for definition and determination of wind resistant shingles (see 1.2.1 and 3.4). This information may be obtained directly from U. L.

6.5 Nails. Nails are not included with these shingles and should be purchased separately.

6.6 Headlap is defined as the minimum distance from a line formed by cutting off the exposed tab to the nearest underlying area of the substrate not covered by the preceding course of shingles. A shingle whose exposure area exceeds 5 inches in width must be qualified for a wind resistance rating in addition to the fire classification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.