TT-P-30E
AMENDMENT-1
March 21, 1984

FEDERAL SPECIFICATION

PAINT, ALKYD, ODORLESS, INTERIOR, FLAT
WHITE AND TINTS

This amendment, which forms a part of Federal Specification TT-P-30E, dated June 30, 1977, was approved by the Assistant Administrator, Federal Supply and Services, General Services Administration, for the use of all Federal agencies.

PAGE 1

Paragraph 2.1, under Federal Specifications, add:

TT-T-291 - Thinner, Paint, Mineral Spirits, Regular and Odorless
TT-T-390 - Tinting Medium, Concentrate, General-Purpose

Paragraph 2.2, under American Society for Testing and Materials (ASTM) Standards, add:

D 523 - Specular Gloss
D 1729 - Visual Evaluation of Color Differences of Opaque Materials
D 1849 - Package Stability of Paint
D 2698 - Pigment Content of Solvent-Type Paints by High-Speed Centrifuging
D 2805 - Hiding Power of Paints
D 3335 - Low Concentrations of Lead, Cadmium, and Cobalt by Atomic Absorption Spectroscopy

Add: South Coast Air Quality Management District

Rule 102 - Definition of Terms

(Application for copies should be made to South Coast Air Quality Management District, 9150 Flair Drive, El Monte, CA 91731.)

Paragraph 3.2.2 and Table I, delete in their entirety and substitute:

"3.2.2. Vehicle. The vehicle shall be a drying-oil alkyd in an odorless solvent that is nonphotochemically reactive as defined in Rule 102 of South Coast Air Quality Management District."

PAGE 3

Paragraph 3.3.4, delete in its entirety and substitute:

"3.3.4 Odor. When tested as specified in 4.3.4, the odor of the paint in the can and during application shall be similar to odorless mineral spirits. The paint shall have no residual odor 72 hours after application.

PAGE 5

Table IV. Color, delete "4250"; add "D 1729" under ASTM.

Storage stability, delete "3022"; add "D 1849" under ASTM.

Roller coating properties, change "4335" to "2112".

Washability properties, add "6141" under Fed. Test Method Std. No. 141.

Pigment, delete "4021"; add "D 2698" under ASTM.

Nonvolatile vehicle, delete "4053"; add "D 2698" under ASTM.

Gloss, delete "6103"; add "D 523" under ASTM and "4.3.15" under Paragraph Reference.

Lead content, add "D 3335" under ASTM.

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:14Z
Check the source to verify that this is the current version before use.

PAGE 6

Paragraph 4.3.2, lines 4 and 5, change "method 4250 of Fed. Test Method Std. No. 141" to "ASTM D 1729".

Paragraph 4.3.3.2, lines 1 and 2, change "method 3022 of Fed. Test Method Std. No. 141" to "ASTM D 1849".

Paragraph 4.3.4, delete in its entirety and substitute:

"4.3.4 Odor. Compare the odor of the paint with odorless mineral spirits conforming to TT-T-291, type III in accordance with ASTM D 1296. Allow the sample to air-dry 72 hours and evaluate for residual odor."

Paragraph 4.3.7, line 2, change "4335" to "2112".

Paragraph 4.3.8, delete in its entirety and substitute:

"4.3.8 Flexibility. Apply the paint with a film applicator to obtain a 25 ± 2 um (0.001 ± 0.0001 inch) thick dry film on a tin panel complying with method 2012 of Fed. Test Method Std. No. 141. Air dry 18 hours, bake 5 hours at 105 ± 2°C (121 ± 4°F), cool at 23 ± 1°C (73 ± 2°F) and 50 ± 4 percent relative humidity for 1/2 hours and bend over a 12.7 mm (1/2 inch) mandrel in accordance with method 6221 of Fed. Test Method Std. No. 141.

Paragraph 4.3.9, change the body of the paragraph to read:

"4.3.9 Washability properties. Prepare and test two panels in accordance with method 6141 of Fed. Test Method Std. No. 141 with the exceptions: The paint shall be applied over dried films of enamel conforming to TT-E-545 and (1) through (6) below.

Paragraph 4.3.9 (5), change the exception to read:

"(5) Measure the 85° gloss in accordance with ASTM D 523."

PAGE 7

Paragraph 4.3.12, line 15, change "method 6103 of Fed. Test Method Std. No. 141" to "ASTM D 523".

Paragraph 4.3.13, change the paragraph to read:

"4.3.13 Lead content. Determine lead content in accordance with ASTM D 3335 or as specified below. In case of dispute, the following procedure shall be used.

PAGE 8

Add new paragraph 4.3.15:

"4.3.15 Specular gloss. Draw down the paint on plane, opaque, white glass panels specified in 2.1.5 of method 2021 of Fed. Test Method Std. No. 141. Use a film applicator which will produce a wet film thickness of 76 ± 2 um (0.003 ± 0.0001 inch). Dry the panels 48 hours at 23 ± 1°C (73 ± 2°F) and 50 ± 4 percent relative humidity in a dust-free environment. Determine 85° gloss in accordance with ASTM D 523.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.