INCH-POUND

MIL-DTL-17/228A
27 MAY 2016
SUPERSEDING
MIL-DTL-17/228
26 August 1998

DETAIL SPECIFICATION SHEET

CABLE, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 50 OHMS, LOW SMOKE, LOW LOSS DIAMETER 1.670

This specification is approved for use by all Departments and Agencies of the department of Defense.

The requirements for acquiring the cable described herein shall consist of this specification and MIL-DTL-17.




FIGURE 1. General configuration.

TABLE I. Description.

Components	Construction details	Diameters
Inner conductor	Bare copper tube	.527±.003 inch (13.39 ±0.08 mm)
Dielectric core	Cellular polyethylene	1.350 ±.012 inch (34.29 ±0.30 mm)
Inner shield	.003 inch bonded aluminum tape	1.356 ±.012 inch (34.44 ±0.30 mm)
Outer conductor	Single braid of 30 AWG, tinned copper wire. Coverage: 90.9 percent, nominal. Carriers: 48 Ends: 10 Picks/inch: 4.2	1.401 ±.012 inch (35.59 ±0.30 mm)
Jacket	Type XIV, crosslinked polyolefin	1.670 ±.025 inch (42.42 ±0.64 mm)
Armor	Single braid of aluminum alloy wire.	1.77 inch (44.96 mm) maximum.

AMSC N/A

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.

ENGINEERING INFORMATION:

Continuous working voltage: 5,625 V rms, maximum.

Operating frequency: 2.5 GHz, maximum.

Velocity of propagation: 83 percent, nominal.

Power rating: See figure 2.

Operating temperature range: -30° to +105°C.

Inner conductor properties: DC resistance, maximum, at 20°C: .027 ohms per 100 feet.

REQUIREMENTS:

Dimensions, configuration and description: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Out-of-roundness: Not applicable.

Eccentricity: 10 percent, maximum.

Adhesion of conductors:

Inner conductor to core: 40 pounds, minimum; 250 pounds maximum.

Aging stability: +98° ±2°C.

Cold bend: -30°C ±2°C.

Dimensional stability: +85°C ±2C.

Inner conductor from core: 0.62 inch (mm), maximum.

Inner conductor from jacket: .125 inch (mm), maximum.

Contamination: Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Halogen content: 0.2 percent, maximum.

Immersion test:

Tensile strength, percent of unaged minimum, 50.

Elongation, percent of unaged minimum: 50.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness (type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles minimum (jacket only).

Tear strength: 35 pounds per inch.

Heat distortion: 30 percent maximum.

Physical tests on unaged jacket.

Tensile strength: 1,300 psi, minimum.

Elongation: 160 percent, minimum.

Physical tests on aged jacket:

Air oven:

Tensile strength, percent minimum: 60.

Elongation: percent minimum: 60.

Hot oil immersion:

Tensile strength, percent minimum: 50.

Elongation, percent minimum: 50.

Tensile strength and elongation: 1,300psi, 160 percent minimum.

Weight: 1020 Lbs/1000 ft, maximum.
1200 Lbs/1000 ft (armored), maximum.

Electrical:

Spark test: 8,000 V rms, minimum.

Voltage withstanding: 10,000 V rms, minimum.

Corona extinction voltage: 7,500 V rms, minimum.

Characteristic impedance: 50 $\pm$2 ohms.

Attenuation: See figure 2.

Structural return loss: See figure 3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.

Capacitance: 27.0 pF per feet, maximum.

Capacitance unbalance: Not applicable.


Transmission unbalance: Not applicable.

Mechanically induced noise: Not applicable.

Time delay: Not applicable.

Part or Identifying Number (PIN): M17/228-00001 (unarmored)
M17/228-00002 (armored).

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.



Tabulated values are for reference only. The values on the graph represent the requirements for attenuation. The data regarding power rating are for information only.

Frequency MHz	Attenuation dB	Power Watts
50	.28	13,200
150	.48	7400
450	.87	3750
900	1.34	2500
1500	1.80	1900
2000	2.28	1500
2500	2.57	1300

FIGURE 2. Power rating and attenuation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.




FIGURE 3. Structural return loss.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.

CONCLUDING MATERIAL

Custodians:
Army – CR
Navy – EC
Air Force – 85
DLA – CC

Preparing activity:
DLA - CC

(Project: 6145-2016-038)

Review activities:
Army - AR, AT, CR4, MI
Navy - AS, MC, OS, SH
Air Force - 19, 99
NASA - NA

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:37Z
Check the source to verify that this is the current version before use.