INCH-POUND

MIL-DTL-17/233C
w/AMENDMENT 2
12 June 2026
SUPERSEDING
MIL-DTL-17/233C
w/AMENDMENT 1
6 September 2024

DETAIL SPECIFICATION SHEET

CABLES, RADIO FREQUENCY, FLEXIBLE, COAXIAL, 72 OHMS, LOW NOISE, LOW SMOKE, ENHANCED INSULATION RESISTANCE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-17.




FIGURE 1. General configuration.

TABLE I. Description.

Components	Construction details
Inner conductor	Seven strands of tinned, copper wire. Each strand .0159 inch diameter. Overall diameter: .0477 inch ± .0020 concentric stranding centered within 10 percent of dielectric diameter.
Dielectric core	Composite of three layers. Diameter: .295 inch ± .007.
Inner layer	Type A-5: Semiconducting polyethylene; .003 inch nominal thickness.
Middle layer	Type A-1: Solid polyethylene.
Outer layer	Type A-5: Semiconducting polyethylene; .005 inch nominal thickness.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

TABLE I. Description – Continued.

Components	Construction details
Outer conductor Outer conductor	Single braid of AWG size 34, tinned copper wire. Diameter: .340 inch, maximum. Coverage: 97.7% inch, maximum. Carriers: 24 Ends: 7 Picks/inch: 16.3 ±10%
Barrier tape	A .001 inch thick polyester tape faced with a .002 inch thick layer of aluminum. The tape will be applied with a 50% lap, nominal. Aluminum face toward the outer conductor. Diameter: .350 inch, maximum.
Jacket	Type XIV, cross linked optional. Diameter: .405 inch ±.010.
Magnetic shield	Single braid, 36 Gage, high permeability Nickel-Iron Alloy in accordance with ASTM-A753, type 4. Diameter: .455 inch, maximum. Coverage: 85% inch, minimum. Carriers: 24 Ends: 8 Picks/Inch: 13.5
Barrier tape	A .001 inch thick polyester tape faced with a.002 inch thick layer of aluminum. The tape will be applied with a 50% lap, nominal. Aluminum face toward the magnetic shield. Diameter: .475 inch maximum.
Overall jacket	Type XIV, cross linked polyolefin. Thickness, .050 inch, minimum. Diameter: .560 inch, maximum.

ENGINEERING INFORMATION:

Continuous working voltage: 3,700 V rms, maximum.

Operating frequency: 1 GHz, maximum.

Velocity of propagation: 62 percent, nominal.

Operating temperature range: -30° to +85°C.

Inner conductor properties:

DC resistance, maximum, at 20°C: 0.65 ohms per 100 feet.

Elongation: 15 percent, minimum.

Tensile strength: 60 $klb_f/inch^2$, minimum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

Engineering notes: This cable useful in applications where electrical noise generated within the coaxial cable, due to flexure or vibration, must be limited.

REQUIREMENTS (See table II)

Dimensions, configuration and description: See figure 1 and table I.

Environmental and mechanical:

Visual and mechanical examination: Applicable.

Diameter: Applicable.

Out-of-roundness: Applicable.

Eccentricity: Applicable.

Adhesion of conductors:

Inner conductor to core: 7 pounds, minimum; 50 pounds maximum.

Electrical and mechanical:

Continuity: Applicable.

Spark test: 5,000 Vrms, +25 percent, -0 percent.

Voltage withstanding: 10,000 Vrms, minimum.

Insulation resistance:

300,000 megohms, minimum per 1,000 feet (center conductor to outer conductor) at 1,000 V dc.
1,500,000 megohms, minimum per 200 feet (center conductor to outer conductor) at 1,000 V dc.
10 megohms, minimum per 1,000 feet (outer conductor to magnetic shield) at 500 V dc.
50 megohms, minimum per 200 feet (outer conductor to magnetic shield) at 500 V dc.
15 megohms, minimum per 1,000 feet (magnetic shield to outer jacket surface) at 500 V dc.
75 megohms, minimum per 200 feet (magnetic shield to outer jacket surface) at 500V dc.

Corona extinction voltage: 5,000 V rms, minimum.

Characteristic impedance: 72 $\pm$3 ohms.

RF transmission loss (attenuation): 15 dB per 100 feet, maximum at 400 MHz.

Standing wave ratio (return loss): Not applicable.

Capacitance: 23 $\pm$1 pF per foot, maximum.

Capacitance stability:	Not applicable.
Capacitance unbalance:	Not applicable.
Transmission unbalance:	Not applicable.
Inductance:	Not applicable

Mechanically induced noise voltage: 320 microvolts peak to peak, maximum.

Time delay: Not applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

Aging stability: +98° ±2°C.

Stress crack resistance: Not applicable.
Outer conductor integrity: Not applicable.

Cold bend: -40°C ±2°C.

Dimensional stability: +85°C ±2C.

Inner conductor from core: 0.062 inch, maximum.

Inner conductor from jacket: .125 inch, maximum.

Contamination: Not applicable.
Bendability: Not applicable.
Flammability: Not applicable.

Flame propagation: Applicable.

Acid gas generation: 2.0 percent, maximum.

Halogen content: 0.2 percent, maximum.

Immersion test:

Tensile strength, percent of unaged minimum: 50.

Elongation, percent of unaged minimum: 50.

Smoke index: 25 maximum.

Toxicity index: 5 maximum.

Durometer hardness (type A) 80 minimum.

Weathering: Applicable.

Abrasion resistance: 75 cycles minimum (jacket only).

Tear strength: 35 pounds per inch.

Heat distortion: 30 percent maximum.

Physical tests on unaged jacket:

Tensile strength: 1,300 psi, minimum.

Elongation: 160 percent, minimum.

Physical tests on aged jacket:

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

Air oven:

Tensile strength, percent minimum: 60.

Elongation: percent minimum: 60.

Hot oil immersion:

Tensile strength, percent minimum: 50.

Elongation, percent minimum: 50.

Tensile strength and elongation: 1,300 psi, 160 percent minimum.

Weight: 0.235 Lbs/ft, maximum.

Shielding effectiveness:

Frequency range: .00006 - .01 MHz.
Surface transfer impedance, 8.184 milliohms/meter, maximum.

Frequency range: .0101 – 100 MHz.
Surface transfer impedance, 11.296 milliohms/meter, maximum.

Surface transfer impedance measurements performed in accordance with SAE-AS85485. Testing performed with outer conductor shield and magnetic shield connected together on both ends and is considered the “Shield” in the test procedure.

Special requirements:

Magnetic shield continuity: One hundred percent of all finished cable shall be tested for shield continuity prior to shipment. To establish continuity, no more than 25V dc shall be applied across the shield through an appropriate indicator, such as an ohmmeter, light or buzzer.

Magnetic shield tension: To be applied to the maximum tension possible so as to prevent loosening or creeping but not cause broken ends. Braids shall have no irregularities or loose unwoven strands. There shall be no splices of the completed braid.

Marking: Applicable.

Marking Durability: 125 cycles (250 strokes), 1 pound.

Workmanship: Applicable.

Part or Identifying Number (PIN): M17/233-00001

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
I	In-process inspection:		4.5	Entire sample		
	Continuity	3.7.1	4.8.2	Entire sample		
	Spark test	3.7.2	4.8.3	Entire sample		
	Voltage withstanding	3.7.3	4.8.4	Entire sample		
	Insulation resistance	3.7.4	4.8.5	Entire sample		
	Visual and mechanical inspection	3.6	4.8.1	Entire sample	Per Table VIII	A
	Diameter measurements.	3.6.1	4.8.1.1	Entire sample	Per Table VIII	A
	Out-of-roundness	3.6.2	4.8.1.2	Entire sample	Per Table VIII	A
	Eccentricity of inner conductor	3.6.3	4.8.1.3	2	Per Table VIII	A
	Adhesion of conductors	3.6.4	4.8.1.4	4	Per Table VIII	A
	Marking	3.8	4.8.1	Entire sample	Per Table VIII	A
	Marking Durability	3.8.2	4.8.39	3	Per Table VIII	A
	Workmanship	3.10	4.8.1	Entire sample	Per Table VIII	A
II	Corona extinction voltage	3.7.5	4.8.6	1	Per Table VIII	B
	Characteristic impedance	3.7.6	4.8.7	1	Per Table VIII	A
	RF transmission loss (attenuation)	3.7.7	4.8.8	2	Per Table VIII	A
	Standing wave ratio (return loss)	N/A				
	Capacitance	3.7.9	4.8.10	1	Per Table VIII	B
	Capacitance stability	N/A				
	Capacitance unbalance	N/A				
	Transmission unbalance	N/A				
	Inductance	N/A				
	Mechanically induced noise voltage	3.7.13	4.8.14	1	Per Table VIII	B

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

TABLE II. Qualification and Group A, B, and C Table - Continued.

Group	Qualification inspection	Requirement paragraph	Test paragraph	Qual- # of Specimens	Conf - # of Specimens	Conformance inspection
II	Time delay	N/A				
	Aging stability	3.7.15	4.8.16	4	Per Table VIII	C
	Stress crack resistance	N/A				
	Outer conductor integrity	N/A				
	Cold bend	3.7.18	4.8.19	3	Per Table VIII	B
	Dimensional stability	3.7.19	4.8.20	1	Per Table VIII	C
	Contamination	N/A				
	Bendability	N/A				
	Flammability	N/A				
	Flame propagation	3.7.23	4.8.25	1		
	Acid gas generation	3.7.24	4.8.26	1		
	Halogen content	3.7.25	4.8.27	1		
	Immersion tests	3.7.26	4.8.28	1		
	Smoke index	3.7.27	4.8.29	1		
	Toxicity Index	3.7.28	4.8.30	1		
	Durometer hardness	3.7.29	4.8.31	1		
	Weathering	3.7.30	4.8.32	1		
	Abrasion resistance	3.7.31	4.8.33	5		
	Tear strength	3.7.32	4.8.34	6	Per Table VIII	B
	Heat distortion	3.7.33	4.8.35	1	Per Table VIII	C
	Physicals (aged)	3.7.34	4.8.36	1	Per Table VIII	C
	Tensile strength and elongation	3.7.35	4.8.37	1	Per Table VIII	C
	Weight	3.9	4.8.24	1	Per Table VIII	B
	Shielding effectiveness	This Specification Sheet	This Specification Sheet			
	Magnetic shield continuity	This Specification Sheet	This Specification Sheet			
	Magnetic shield tension	This Specification Sheet	This Specification Sheet			

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.

Amendment notations. The margins of this specification are marked with vertical lines to indicate modifications generated by this amendment. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations.

Referenced documents. In addition to MIL-DTL-17, this document references the following:
ASTM-A753
SAE-AS85485

CONCLUDING MATERIAL

Custodians:
Army - CR
Navy - EC
Air Force – 85
DLA - CC

Preparing activity:
DLA - CC

(Project: 6145-2026-019)

Review activities:
Army - AR, AT, CR4
Navy - AS, MC, OS
Air Force - 19

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T16:38Z
Check the source to verify that this is the current version before use.