MILITARY SPECIFICATION SHEET

BATTERY, STORAGE, SILVER-ZINC ALKALINE (EMERGENCY), POR DSV:

TYPE 27 V - 30 Ah (METRIC)

This specification sheet is approved for use by the Naval Sea Systems Command and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the battery described herein shall consist of this document and the latest issue of DOD-B-24531.

REQUIREMENTS:

Electrical rating: The rating of each 18-cell battery shall be not less than that shown in table I.

TABLE I. Electrical rating.

Rate ampere (A)	Time hours (h)	Capacity ampere-hour (Ah)	Minimum battery voltage (V)	Minimum average cell voltage[1/] (V)	Minimum cell voltage (V)
5	6	30	23.4	1.45	1.30
20	1	20	21.5	1.35	1.20
30	20 seconds	-----	20.0	1.20	1.11

[1/] The "average voltage" is defined as the average of voltage readings taken at 1/2-hour intervals, starting with the first reading taken between 1/2 and 1 minute after applying the load and including the cut-off voltage.

Life: 1500 Ah total output (or input) or 1 year, whichever occurs first, before the capacity drops to 70 percent of rated capacity at the 6-hour rate.

Dimensions (in millimeters) (mm) (maximum envelope):

Maximum length - 238
Maximum width - 103
Maximum height - 191
(including terminals)

Mass: Maximum 11.4 kilograms (wet).
Maximum 8.8 kilograms (dry).

Terminals:
Size: 5/16-24 (two nuts per terminal post for each cell are required).
Maximum height: 18 mm above the cell cover.

Zinc electrodes: Mercury shall not be used. A NAVSEC substitute will be specified.

Note: Battery case and cover not required. The cells shall be bussed with intercell connectors and banded together to form an 18-cell battery, series connected, to fit the maximum envelope dimensions. Conformance shall be checked in accordance with 4.3.1.1 of DOD-B-24531.

Preparing activity:
Navy - SH
(Project 6140-N472-5)

FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:24Z
Check the source to verify that this is the current version before use.