
METRIC
DOD-B-24541/2A(SH)
24 November 1982
SUPERSEDING
DOD-B-24541/2(SH)
10 August 1976

MILITARY SPECIFICATION SHEET

BATTERY CELLS AND ELEMENTS, LEAD-ACID, MAIN STORAGE, SUBMARINE, TYPE GUPPY I, MOD C (METRIC)

This specification sheet is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the battery cells and elements described herein shall consist of this document and the latest issue of DOD-B-24541.



FSC 6140

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:29Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Electrolyte specific gravity:	1.285 nominal.
Measurement of capacity:	Capacity, in ampere-hours (Ah), is based on an initial electrolyte temperature of 26.7 degrees Celsius, specific gravity of 1.285, and shall be not less than as specified in table I.
Water cooling:	Not required.

TABLE I. Electrical characteristics.

Capacity Ah	Time hours	Discharge current A	Minimum battery voltage		Minimum cell voltage	
			126-cell			
			Average	Final	Average	Final
4000	1	4000	207	180	1.46	1.28
5250	3	1750	228	201	1.61	1.51
5925	5	1185	236	207	1.65	1.57
6150	6	1025	238	208	1.66	1.58
6800	10	680	241	212	1.69	1.63
7400	20	370	244	215	1.71	1.66
7740	36	215	246	217	1.72	1.68
7920	48	165	247	217	1.72	1.68

Mass per cell (filled and charged):	Maximum - 502 kilograms (kg) Maximum average - 493 kg Minimum - 470 kg
Guaranteed service life: (equivalent cycle equals 5000 Ah of charge)	165 equivalent cycles or 66 months, whichever occurs first.
Demonstration of rated capacity:	Within 30 equivalent cycles.
Life test:	Accelerated float charge and ship float simulation regimes.
Hydrogen emission (maximum): (measurements recorded as cubic centimeters/hour/cell/1,000 Ah at the 10-hour rate)	5,000 at 200 A 3,000 at 100 A 100 on open circuit
Trickle discharge rate:	5A

NOTE: Positive plate thickness shall be not less than 4.8 millimeters.

Preparing activity:
Navy - SH
(Project 6140-N562)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:29Z
Check the source to verify that this is the current version before use.