MILITARY SPECIFICATION

CARPET, FIBERGLASS, TUFTED, SINGLE LEVEL LOOP PILE (WITHOUT ATTACHED CUSHIONING)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of single level loop pile fiberglass carpeting tufted without attached cushioning.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL
- UU-P-268 - Paper, Kraft, Wrapping.
- PPP-B-35 - Bags, Textile, Shipping, Burlap, Cotton and Waterproof Laminated.
- PPP-B-576 - Box, Wood, Cleated, Veneer, Paper Overlaid.
- PPP-B-591 - Boxes, Shipping, Fiberboard, Wood-Cleated.
- PPP-B-601 - Boxes, Wood, Cleated-Plywood.
- PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
- PPP-B-636 - Boxes, Shipping, Fiberboard.
- PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple Wall.
- PPP-T-45 - Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

MILITARY
- MIL-L-10547 - Liners, Case, and Sheet Overwrap, Water-Vaporproof or Waterproof, Flexible.

STANDARDS

FEDERAL
- FED-STD-191 - Textile Test Methods.

MILITARY
- MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
- MIL-STD-129 - Marking for Shipment and Storage.
- MIL-STD-1623 - Fire Performance Requirements and Approved Specifications for Interior Finish Materials and Furnishings (Naval Shipboard Use).

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

RULES AND REGULATIONS UNDER THE TEXTILE FIBERS PRODUCTS IDENTIFICATION ACT

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D.C. 20580.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

UNIFORM CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules.

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION INCORPORATED, AGENT
National Motor Freight Classification Rules.

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., 1616 P Street, N.W., Washington, D.C. 20036.)

U.S. POSTAL SERVICE MANUAL

(Copies of the manual may be obtained from the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)
D 418-68 - Woven and Tufted Pile Floor Coverings, Testing.
D 1335-67 - Tuft Bind of Pile Floor Coverings, Test for.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS
AATCC-8 Colorfastness to Crocking

(Application for copies should be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, North Carolina 27709.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Sample for first article inspection. Prior to beginning production, a sample shall be tested as specified in 4.3 (see 6.3).

3.2 Materials. The component materials shall conform to the requirements specified in 3.2.1, 3.2.2 and 3.2.3 when tested as specified in 4.4.2.

3.2.1 Pile yarn. The pile yarn shall be made from 100 percent carpet type continuous filament fiberglass and shall be 100 percent pigment colored. Individual filament size shall average no less than 0.00015 inch diameter. The finished yarn shall be 150 - 4/3/2 and shall comply with the other requirements of table I. The finished yarn shall contain at least 8 ounces per square yard of an acrylic finish.

Table I - Physical requirements[1/]

Description	Single level loop pile
Tufts/sq in	80
Pile yarn weight, ozs/sq yd	45
Total weight ozs/sq yd	65
Finished yarn, twist or turns per inch	3.0
Pile height, inch	
Minimum	0.170
Maximum	0.220
Tuft bind (ozs)	90

1/ The weights given in the table are exclusive of back coating, except for total weight. Tolerance of minus 4.0 percent will be allowed for the pile weight only. All other requirements shown, except as specified, are minimum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

3.2.2 Backing material. The backing material shall be a woven fabric of 100 percent fiberglass weighing not less than 7.0 ounces per square yard.

3.2.3 Back coating. The back coating shall be a chloroprene latex or an equivalent type fire retardant latex and shall be applied uniformly at a weight not less than 10.0 ounces per square yard.

3.3 Color and matching. The color of the carpet shall be as specified (see 6.2) and shall match the standard sample, when available, under natural (north sky) daylight or artificial daylight having a color temperature of 7500 Kelvin (K) and shall be a good approximation to the standard sample under incandescent lamplight at 2800 K when tested as specified in 4.5.

3.3.1 Colorfastness. The carpet shall show fastness to light, wet cleaning, and wet and dry crocking equal to or better than the standard sample. When no standard is established, the carpet shall show good fastness to light, wet cleaning, and dry crocking, and fair fastness to wet crocking. They shall show a rating of good after 40 standard fading hours (8000 Langleys). Testing shall be as specified in 4.5.

3.4 Physical requirements. The finished carpet shall conform to the physical requirements specified in table I when tested as specified in 4.5.

3.5 Shrinkage. The shrinkage shall not exceed 2.0 percent in either the length or the width when tested as specified in 4.5.

3.6 Construction. Carpeting shall be of loop pile construction with backing and coating as specified in 3.2.2 and 3.2.3. Construction shall conform to requirements specified in table I. All carpet edges shall be straight.

3.6.1 Seaming. Seams, if required for special orders of non-standard sizes, are to be sewn or taped. Seams on carpet shall have a breaking strength of not less than 100 pounds when tested as specified in 4.5. The tape used in making seams shall be a minimum of 2-1/2 inches wide. Seams on rugs not installed wall to wall shall be made with carpet style single face adhesive tape with a minimum width of 3 inches. The tape used shall be that recommended by the carpet manufacturer. In addition, adhesive shall be applied to both edges of the carpet at the joint. These edges should be brought together to assure direct contact of the adjoining edges at the application of the adhesive. The finished seams shall be secure and able to withstand conventional commercial rug-cleaning processes.

3.7 Size and pattern. The length, width, and pattern of the carpets shall be as specified (see 6.2).

3.7.1 Dimensional tolerance. The dimensional tolerance shall be as follows:

(a) Cut to size - width or length shall not be less than 1 percent of that specified.

(b) Rolls - width shall not be less than 1 percent of that specified; length not less than specified nor more than 10 percent longer than specified.

(c) Single roll - shall not be more than 1 yard less than that indicated on piece ticket.

(d) Total yardage in sample - total gross length of all rolls in the order shall be not less than the total gross length of the individual rolls as indicated.

3.8 Safety requirements.

3.8.1 Flamespread rating. Carpeting shall meet the flamespread rating requirements specified in MIL-STD-1623 (see 4.6.6).

3.9 Fiber identification. Carpets shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3.10 Workmanship. Carpets shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQL's).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

(a) First article inspection (see 4.3).
(b) Quality conformance inspection (see 4.4).

4.3 First article inspection. First article inspection shall consist of the examination of 4.4 and the tests specified in 4.6.

4.4 Sampling for quality conformance inspection.

4.4.1 Sampling for examination. Examination shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated herein. The sample shall be as specified in table II. The lot shall be unacceptable if one or more samples fail to meet any specified requirement.

Table II - Sampling

Lot size, sq yd	Sample, sq yd
800 or less	2
801 to 22,000	3
22,001 and over	5

4.4.2 Inspection of component materials. Testing shall be performed on the components listed in table III, as applicable. Except as otherwise specified, test methods referenced are specified in FED-STD-191.

Table III - Component testing[1/]

Component	Characteristic	Requirement paragraph	Test method of FED-STD-191
Pile yarn (lbs)	Material identification	3.2.1	2/
	Diameter	3.2.1	4021
	Turns per inch (twist)	Table I	4054
	Finish (acrylic)	3.2.1	2/
Backing material (yds),	Material identification	3.2.2	2/
	Weight	3.2.2	5041
Back coating compound	Material identification	3.2.3	2/

1/ May be accepted based on supplier's certificate of compliance for all characteristics listed. The supplier shall prepare a certificate of compliance in accordance with the data ordering documents included in the contract or order (see 6.2.1).

2/ Standard commercial.

4.4.2.1 Quality conformance inspection. Quality conformance inspection shall consist of the examination specified in 4.4.3.1 and tests specified in 4.6.1, 4.6.2, and 4.6.3.

4.4.3 Examination of the end item. Defects found during the visual examination shall be classified in accordance with 4.4.3.1, 4.4.3.2, and 4.4.3.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

4.4.3.1 Visual examination. The defects listed in table IV shall be counted regardless of their proximity to one another, except where two or more defects represent a single local condition of the carpet, in which case only the more serious defect shall be counted. Continuous defects shall be counted as one defect for each yard or fraction thereof in which they occur. The sample unit shall be 1 linear yard. The acceptable quality levels (AQL's) shall be 2.5 major and 6.5 total defects (major and minor combined) per hundred units (linear yards). The sample size shall be based on inspection level II of MIL-STD-105. The lot size shall be expressed in units of 1 linear yard. When examination is made of full rolls, not more than one third of the total sample yardage shall be examined in any one roll. When the lot consists of less than 5 rolls, an approximate equal number of yards shall be examined on each roll to yield the sample yardage. When examination is made on carpets cut to size, the number of units selected shall be sufficient to yield the sample yardage. The visual examination shall be made at a distance of approximately six feet.

Table IV - Classification of defects.

	Defects
Critical	None
Major	
101	Marks across carpet.
102	Any obviously objectionable streak lengthwise of weave.
103	Length of pieces or width not as specified.
104	Tufts missing in pile.
105	Cut, hole or tear through to back.
106	Seams (when specified) not properly sewed or taped.
Minor	
201	Spot or stain.
202	Not evenly constructed, affecting appearance.
203	Discolored areas affecting appearance.
204	Any noticeable unevenness on top surface affecting appearance.
205	Imbedded foreign matter.

4.4.3.2 Overall examination. Each defect listed shall be counted not more than once in each unit examined. The sample unit for this examination shall be one roll or cut piece. The number of rolls or cut pieces examined for visual examination shall be the sample size. The lot shall be unacceptable if one or more of the following defects are found:

Overall uncleanness
Color or pattern other than specified
Rancid or otherwise objectionable odor
Type not as specified
Edges not finished as required

4.4.3.3 Length examination (rolls only). Each roll shall be examined for gross length. Any gross length found to be less than the gross length marked on the roll ticket shall be considered a defect with respect to length. The sample unit shall be one roll. The rolls used for visual examination shall be used for this examination. The lot shall be unacceptable if one or more defects are found in the sample.

4.5 Testing of the end item. Tests shall be performed for the characteristics specified in table V. Except as otherwise specified, test methods referenced are specified in FED-STD-191. Unless otherwise specified, the physical and chemical values specified in section 3 apply to the average of the determinations made on a sample unit for test purposes in the applicable test method. The sample unit shall be 1 square yard for the rolls or one carpet cut to size, as applicable. The lot size for purposes of end item testing shall be expressed in units of square yards for rolls and pieces of carpet, as applicable. The sample size shall be as listed in table III. The lot shall be unacceptable if one or more units fail to meet any requirement specified.

4.6 Tests.

4.6.1 Tufts per square inch. Tufts per square inch shall be determined by multiplying the pitch per inch or pile yarn ends by the rows of pile per inch, or the equivalent thereof. Pitch and rows per inch shall be determined in accordance with ASTM D 418-68. Pitch is defined as the number of pile yarn ends per inch of width in the carpet. Rows is defined as the number of rows of tufts per inch of length (also referred to as stitches per inch for tufted).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

Table V - End item testing.

Characteristic	Requirement reference	Test mehtod
Tufts per square inch	Table I	4.6.1
Weight of pile yarn	Table I	4.6.2
Total weight	Table I	5040 or 5041 1/
Pile height	Table I	4.6.3
Tuft bind	Table I	ASTM D-1335-67
Color matching	3.3	4.6.5
Colorfastness to:		
Light	3.3.1	5660
Wet and dry crocking	3.3.1	AATCC-8
Wet cleaning	3.3.1	5610 2/
Shrinkage	3.5	4.6.4
Seam strength	3.6.1	5100
Flame spread rating	3.8.1	4.6.6

1/ When Method 5041 is used, one specimen with an area of at least 16 square inches shall be used.

2/ Only the change in shade or color of the test specimen shall be considered.

4.6.2 Weight of pile yarn. The weight of pile yarn shall be determined on a conditioned sample in accordance with ASTM D 418-68.

4.6.3 Pile height. The pile height shall be determined in accordance with ASTM D 418-68.

4.6.4 Shrinkage test. A 12 by 12 inch sample of the specified carpet shall be conditioned under standard conditions as defined in section 4 of FED-STD-191 for a period of 24 hours. Specimen shall then be marked and measured at three different locations in the length and width directions; immerse sample in 110°F water for 15 minutes; mix 2 grams (g) of sodium alkylsulfate type of detergent with 50 g of water at 110°F and apply to pile surface of carpet. Scrub sample with a soft bristle brush by stroking back and forth 20 times (10 times in each unilateral direction), and in both length and width directions; rins well to remove majority of detergent; squeeze and dry at 125°F until dry; again condition under standard conditions for 24 hours.

4.6.4.1 Shrinkage evaluation. The specimen shall be remeasured and the shrinkage computed using the following formula:

$$\text{Shrinkage} = \frac{A-B}{A} \times 100$$

where:
A = Average of initial measurement
B = Average measurements after shampooing

The shrinkage in both the length and width directions shall be reported to the nearest 0.1 percent and shall conform to the requirement set forth in 3.5.

4.6.5 Color matching test. A test specimen at least 8 inches square shall be mounted at an angle of 45 degrees to the horizontal and compared with the standard sample, or the approved color sample furnished, similarly mounted under the light conditions specified in 3.3. When an artificial light source is used, it shall be placed so that its rays strike the sample normal to its surface. The viewing distance shall be 18 to 24 inches.

4.6.6 Flamespread rating. Carpeting shall be tested in accordance with MIL-STD-1623 (see requirement for fibrous glass carpet).

4.7 Inspection of preparation for delivery. The packaging, packing and marking shall be inspected for compliance with Section 5 of this document.

5. PREPARATION FOR DELIVERY

(The preparation for delivery requirements specified herein apply only for direct Government procurements.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Level A. Carpets, of one description only, shall be rolled tightly on a convolute or spiral wound chip board tube or a pole. The tube shall have a minimum inside diameter of 2 inches. For rolls weighing 200 pounds or more, regardless of width, the tube shall have a minimum wall thickness of 0.375 inch, with a minimum inside diameter of 3 inches. The ends of the tube shall extend not more than 1 inch beyond the rolled carpet. The rolled carpet shall be secured with cotton tape, or twine; wrapped with paper conforming to UU-P-268, grade B, minimum bursting strength not less than 60 pounds (24 by 36-500) and the paper wrap sealed with tape conforming to PPP-T-45, grade B.

5.1.2 Level B. The carpets shall be packaged as specified in 5.1.1.

5.1.3 Level C. Carpets, in size and pattern specified (see 3.7), shall be individually packaged. Packaging shall afford protection against environmental and physical damage during shipment from the supply source to the first receiving activity for immediate use. The supplier's normal packaging procedure may be used when such meets the requirements of this level.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Carpets, of one size and pattern (see 3.7), packaged as specified, shall be packed in containers conforming to any one of the following specifications at the contractor's option:

Specification	Container	Type or Class
PPP-B-576	Wood-Cleated Veneer Paper Overlaid	Class 2
PPP-B-591	Fiberboard, Wood-Cleated	Class II
PPP-B-601	Wood, Cleated-Plywood	Class II
PPP-B-621	Wood, Nailed and Lock-Corner	Class 2
PPP-B-636	Fiberboard	Weather-Resistant, Style FOL
PPP-B-640	Fiberboard, Corrugated, Tripple Wall	Class 2, Style A

Each shipping container except as specified herein shall be provided with a caseliner conforming to MIL-L-10547, type I, grade C. Container closure and reinforcing shall be in accordance with the applicable container specification or appendix thereto. Caseliners for containers conforming to PPP-B-636 and PPP-B-640 may be omitted when all seams and the manufacturer's joint of the container are sealed with pressure sensitive waterproof tape in accordance with the appendix to the applicable container specification. Containers shall not exceed the gross weight limitations of the applicable container specification. Wood, wood-cleated and plywood containers exceeding 200 pounds gross weight shall be modified by the addition of wood skids.

5.2.2 Level B. Carpets packaged as specified shall not require additional packing. When specified (see 6.2), carpets shall be packed in bags conforming to PPP-B-35, type III, class 2, style B with waterproof sewn seams. The bag shall be closed with two double looped wire ties on each open end. The ties shall be not less than 6 inches long.

5.2.3 Level C. Carpets, packaged as specified in 5.1.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the supplier for retail distribution. Containers shall comply with the U.S. Postal Service Manual, Uniform Freight Classification Rules, or National Motor Freight Classification Rules, as applicable.

5.3 Marking. In addition to any special marking required by the contract or order or herein, unit packages and shipping containers shall be marked in accordance with MIL-STD-129.

5.3.1 Special Marking. Unit packages not packed for shipment or packed in bags (see 5.2.2) shall be marked "USE NO HOOKS" including the hook symbol (see MIL-STD-129, figure entitled "USE NO HOOKS" precautionary marking.

6. NOTES

6.1 Intended use. The carpeting is intended for use as a floor covering comprised of high-temperature resistant fiberglass face fiber to provide low flammability and smoke generation under thermal degradation conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Color required (see 3.3).
(c) Length, width, and pattern of carpet (see 3.7).
(d) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(e) When packing of carpets in bags is required (see 5.2.2).
(f) Type of marking required (see 5.3).

6.2.1 Contract data requirements. When this specification is used in a procurement invoking the data requirement clause of the Armed Services Procurement Regulations (ASPR) paragraph 7-104.9(n) and which incorporates a DD Form 1423 Contract Data Requirements List (CDRL), the data requirements identified below will be developed as specified in the cited Data Item Description (DID) and delivered in accordance with such CDRL. When the ASPR provisions are not invoked, the data specified below shall be delivered in accordance with the contract requirements.

Specification paragraph	Data requirements	Service	Applicable DID	Options
4.4.2 (Table III)	Certificate of Compliance	SH	DI-E-2121	-------

(Copies of DID's required by the supplier in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.)

6.3 First article inspection.

6.3.1 Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection as to those bidders offering a product which has been previously procured or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending procurement.

6.4 Tufts per square inch. The term "tufts per square inch," is used in the table of physical requirements in lieu of other designations of constructions such as "pitch per inch" and "rows per inch" in order to allow for variations in these factors of pitch and rows between individual company fabrics offered to meet requirements. The use of this designation for construction elements should result in broader industry wide participation, more competitive bidding, greater style and selectivity and increased flexibility in procurement. A tuft is considered a cut loop or two fibril or filament clusters of one pile yarn.

6.5 Guide sample. Samples, when furnished, by the Government are solely for guidance and information to the supplier. Variations from this specification may appear in the sample, in which case this specification shall govern. For access to the guide samples, when available, address the procuring office issuing the invitation for bids.

Custodians:
Army - GL
Navy - SH
Air Force - 84

Preparing acitivity:
Navy - SH
(Project 7220-0078)

* U.S. GOVERNMENT PRINTING OFFICE: 1975—603-766:1618

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

FOLD

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124
PRINCE GEORGES CENTER
HYATTSVILLE, MARYLAND 20782

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEPARTMENT OF NAVY

DOD 316

U.S.MAIL

COMMANDER
NAVAL SHIP ENGINEERING CENTER
CENTER BUILDING - SEC 6124
PRINCE GEORGES CENTER
HYATTSVILLE, MARYLAND 20782

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED S/N 0102-014-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T22:22Z
Check the source to verify that this is the current version before use.