MIL-F-36901A
3 June 1974
SUPERSEDING
MIL-F-36901
18 October 1972

MILITARY SPECIFICATION

FABRICS, NONWOVEN, SURGICAL PACKS, DISPOSABLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for thirteen types of disposable, surgical packs, nonwoven fabrics.

1.2 Classification. The disposable, surgical packs, nonwoven fabrics shall be furnished in the following types, as specified (See 6.2):

1.2.1 Types.

I	Nonwoven fabric
IA	Anti-static treated polyethylene film
IB	Laminate, Type I fabric and polyethylene film
II	Nonwoven fabric, water repellent treated and polyethylene film area coated
IIA	Laminate, Type I fabric and co-extruded polyethylene film
IIB	Laminate, Type III fabric and co-extruded polyethylene film
III	Nonwoven fabric, water repellent treated
IIIA	Nonwoven fabric, water repellent treated
IIIB	Laminate, Type III or IIIA fabric with a 24 inch strip of polyethylene on one side and polypropylene on the other side
IV	Laminate, Type III or IIIA fabric and polyethylene film
V	Nonwoven fabric, Type III or IIIA, not water repellent treated
VA	Nonwoven fabric, calendered medium weight paper stock

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

STANDARDS

Federal

Fed. Test Method Std. No. 191 - Textile Test Methods

FSC 6530

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

Military

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of specifications, standards, drawings and publications required by supplier in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.).

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified the issue in effect on date of invitation for bids or request for proposal shall apply.

TECHNICAL MANUAL OF THE AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS

(Application for copies should be addressed to AATCC National Headquarters, P.O. Box 12215, Research Triangle Park, N.C. 27709.)

NATIONAL FIRE CODES

(Application for copies should be addressed to National Fire Protection Association, International (NFPA), 470 Atlantic Avenue, Boston, Mass. 02110)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

3.1 Construction.

3.1.1 Type I. The Type I nonwoven fabric shall be manufactured from cellulosic or synthetic fiber or a combination thereof; and may be wet or dry formed, or scrim or fiber reinforced at the manufacturer's option. The nonwoven fabric shall be resin bonded and shall conform to the requirements specified in Table I.

3.1.1.1 Type IA. The Type IA fabric shall be a low density anti-static treated polyethylene film and shall conform to the requirements specified in Table I.

3.1.1.2 Type IB. The Type IB fabric shall be a laminate composed of Type I fabric and a 1.5 mil polyethylene coating and shall conform to the requirements of Table I.

3.1.1.3 Type IC. The Type IC fabric shall be a minimum 3 mil co-extruded polyethylene on which is laminated a strip of Type I fabric of a specified size. The Type IC fabric shall conform to the requirements of Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

3.1.2 Type II. The Type II nonwoven fabric shall be manufactured from cellulosic or synthetic fiber or a combination thereof; and may be wet or dry formed, or scrim, or fiber reinforced at the manufacturer's option. The nonwoven fabric shall be resin bonded, creped or non creped, and water repellent treated. The treated fabric shall be abrasion resistant and have a good drape. The treated fabric shall be area coated with polyethylene and shall conform to the requirements specified in Table I. As an alternate, a strip of plastic may be edge bonded to the nonwoven material. The edge-bonding shall be along the 2 long sides of the plastic strip/nonwoven material for the table cover and along the 4 sides of the plastic strip for the Mayo Stand Cover.

3.1.2.1 Type IIA. The Type IIA fabric shall be a minimum 3 mil co-extruded polyethylene on which is laminated a strip of Type I fabric of a specified size. The Type IIA fabric shall conform to the requirements of Table I.

3.1.2.2 Type IIB. The Type IIB fabric shall be a tubular constructed, 4 mil minimum, co-extruded polyethylene on which is laminated a strip of Type III fabric of a specified size. The Type IIB fabric shall conform to the requirements of Table I.

3.1.3 Type III. The Type III nonwoven fabric shall be fully bleached pulp and synthetic fiber shall be certified as having no known irritating or toxic elements, lint or objectionable noise or odors when used. The nonwoven fabric shall be wet formed, scrim or fiber reinforced with tissue. The fabric shall be reinforced with synthetic fiber or scrim and over-all bonded. The nonwoven fabric may be creped or non-creped and shall be water repellent treated. The water repellent treated fabric shall be used in all the specified components. The bonded synthetic reinforced fabric shall not separate in normal handling and use. The finished and treated fabric shall be abrasion resistant and have a good drape and shall conform to the requirements specified in Table I.

3.1.3.1 Type IIIA. The Type IIIA nonwoven fabric shall be manufactured from cellulosic or synthetic fiber or a combination thereof, and may be wet or dry formed, or scrim, or fiber reinforced at the manufacturer's option. The nonwoven fabric shall be bonded and water repellent treated and shall not separate in normal handling and use. It shall have no known irritating or toxic elements, lint or objectionable noises or odors. The finished and treated fabric shall be abrasion resistant and have good drape, and shall conform to the requirements specified in Table I.

3.1.3.2 Type IIIB. The Type IIIB nonwoven fabric shall be a laminate composed of Types III or IIIA fabric with a 24 inch wide strip of polyethylene on one side and polypropylene on the other side. The polyethylene and polypropylene shall have a nominal thickness of one mil and shall conform to the requirements specified in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

3.1.4 Type IV. The Type IV reinforcement fabric for the "T" -Sheet shall be an impervious laminate composed of either Types III or IIIA fabric, on which is extruded a virgin polyethylene film of at least 1 mil thickness. At the manufacturer's option, the "T-Sheet tail" shall be reinforced with either Types III or IIIA fabric, which has been laminated between a 2 ply 28/24 gauze screen covering the larger of the two fenestrated areas. The Type IV fabric shall conform to the requirements of Table I.

3.1.5 Type V. The Type V nonwoven fabric shall be either Type III or IIIA fabric without the water repellent treatment and shall conform to the requirements of Table I.

3.1.5.1 Type VA. The Type VA nonwoven fabric shall be a calendered, medium weight paper stock with wet strength properties produced from bleached chemical pulp and shall be certified as having no known irritating or toxic elements, lint or objectionable noise or odors when used. The nonwoven fabric construction shall be tissue bonded to synthetic reinforcing yarns, cotton or rayon scrim. The nonwoven fabric shall not separate in normal handling and use. The finished fabric shall be abrasion resistant and have good drape, and shall conform to the requirements specified in Table I.

3.2 Color. The color of the fabrics shall be a pastel shade of misty-green, blue-green, grey-green, or blue on one or both faces, except that Types I, IA, IB, IC and V may be white on both surfaces. Both surfaces as well as the aseptic surface shall be dull and free from glare.

3.3 Workmanship. The nonwoven fabrics shall be clean, free from any break, tear, hole, cut, wrinkle, uneven or ragged edge, spot, stain, lint, or other foreign matter which could affect serviceability or appearance. The finished cloth shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

TABLE I - AS RECEIVED PROPERTIES

	REQUIREMENTS												
	TYPES												
	I	IA	IB	IC	II	IIA	IIB	III	IIIA	IIIB	IV	V	VA
CHARACTERISTICS													
Breaking strength, pounds minimum:													
Machine direction	1.5	3			4			4	4	=		4	7
Cross direction	1.5	3			4			4	4	-		4	7
Ounces per square yard, minimum	1.0				1.25 3/			1.4	1.4	-		1.4	2.0
Surface resistivity, ohms per unit square maximum	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$ 1/	$1x10^{11}$ 2/	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$ 4/	$1x10^{11}$	$1x10^{11}$	$1x10^{11}$
OR													
Static decay, seconds maximum	0.5	0.5	0.5 1/	0.5 2/	0.5	0.5	0.5	0.5	0.5	0.5 4/	0.5	0.5	0.5
Gauge of polyethylene, inches minimum		0.003	0.0015	0.003	0.0015	0.003	0.004			0.001 4/	0.001		
Hand of fabric (softness), grams maximum (nonwoven fabric only):													
Machine direction					35			35	35			35	
Cross direction					35			35	35			35	
Flame resistance, seconds minimum					3.5			3.5	3.5		3.5	3.5	3.5
Water repellency, polyethylene coated side					Impervious								
Water repellency, minutes minimum								20	20				
OR													
Spray rating, minimum								70,70,70	70,70,70				
Dry abrasion resistance, 2.5 pound load cycles minimum:													
End point filling								10	10			10	
End point failure (destruction								25	25			25	
OR													
Weight loss, percent maximum								10	10			10	

1/ Applicable to both sides of the fabric.
2/ Applicable to the polyethylene surface.
3/ Weight of the fabric without the polyethylene coating.
4/ Applicable also to the polyethylene and polypropylene surfaces.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of quality. Where certificates of quality are submitted, they shall contain verifiable actual tests and inspection data. The Government reserves the right to inspect and test the fabrics to verify the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Visual examination of the base fabric. The required yardage of each roll shall be visually examined and the defects clearly noticeable at normal inspection distance (3 feet) shall be scored. The list of defects below shall be used to enumerate the defects found. The defects found shall be counted regardless of their proximity to each other, except when two or more defects represent a single local condition of the fabric, in which case only the most serious defect shall be scored. A continuous defect shall be counted as one defect for each lengthwise yard or fraction thereof. The sample unit shall be one linear yard, full width of the finished fabric. The acceptable quality level shall be 6.5 defects per 100 units (yards). The sample size shall be in accordance with Inspection Level I of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls to be selected shall be in accordance with Table II. An approximately equal number of yards shall be examined from each roll in the sample.

Defects

a. Any tear, hole, or cut through the base fabric.
b. Any unbonded area, delamination, splices.
c. Any color not as specified.
d. Any spot, streak, stain, grease, dirt, insect, hair, metal or other foreign matter.
e. Any unattached or loose material which cannot be readily removed from the surface.
f. Objectionable odor.
g. Material wrinkled - affecting serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

Table II. Sample size

Lot size (total yards)	Sample size 1/ (rolls)
Up to 1200	3
1201 up to and including 3200	5
3201 up to and including 10,000	8
10,001 up to and including 35,000	13
35,001 up to and including 150,000	20
150,001 and over	32

1/ If a lot contains fewer than three rolls, each roll in the lot shall be examined.

4.3 Testing of the base fabric - physical characteristics. The physical characteristics of the base fabrics shall be determined in accordance with the test methods of FED-Test Method-STD-No. 191, AATCC, NFPA as listed in Table III, 4.3.1 4.3.2, 4.3.3 and 4.3.4, as applicable. Except as otherwise indicated, the physical requirements specified in section 3 shall apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The sample unit shall be 3 continuous yards, full width, of the finished fabric. The lot shall be unacceptable if one or more sample units fail to meet any test requirement specified. Each 3 yard sample shall be taken from a different roll and shall be taken from the beginning of the roll. All test reports shall contain the individual values utilized in expressing the final results. The sample size (number of sample units) shall be in accordance with the following:

Lot Size (total yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table III. Test Methods

Characteristic	Test Method
Breaking strength	5100
Flame resistance	5908 1/
Surface resistivity:	
Nonwoven fabric	NFPA-56A
Polyethylene	NFPA-56A
or	
Static decay:	
Nonwoven fabric	NFPA-56A
Polyethylene	NFPA-56A
Abrasion resistance	par. 4.3.2
Abrasion resistance	93-1970-AATCC 2/
Water repellency	par. 4.3.3
Spray rating	5526
Weight	par. 4.3.4 or 5041
Hand of fabric	par. 4.3.1

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

1/ Burning rate - 45 degree angle.
2/ Test run for 20 seconds at 3,000 RPM

4.3.1 Hand of fabric.

This method is applicable to the determination of the hand of non-woven fabrics in the weight of 1.0 - 4.0 oz./sq. yd..

Principle of Method. The prepared specimen is placed on a slotted plate and the force required to push it through a slot of known width is recorded. This force can be related to the surface friction and flexual resistance of the specimen under test.

Conditioning. Samples shall be conditioned for at least 2 hours at a relative humidity of 65% ± 2% at 70° F. ± 2° F..

Apparatus. Model 211-4 or 211-5 Handle-O-Meter.

STANDARDIZATION:

a. Set the slot width to 10 mm. unless otherwise specified.

b. Standardize the instrument in accordance with the manufacturer's calibration procedure.

SAMPLE PREPARATION:

a. Cut sample 4"x 4" square (unless otherwise specified) taking care to ensure the edges are parallel or perpendicular to the machine direction. Five samples shall be taken randomly across the width of the material with the machine direction identified. (NOTE: Crease free areas of fabric should be selected, and care exercised to ensure that all edges are parallel or perpendicular to the machine direction.)

PROCEDURE:

a. Place the sample on the plate with the direction that is being tested perpendicular to the slot. The sample should extend across the slot with the far edge parallel to the beam and exactly three inches from the edge of the slot.

b. Actuate the penetration beam and record maximum reading.

c. The sample is rotated 90 degrees and a second reading taken which expresses hand in the opposite direction of the fabric.

d. The sample is turned over and readings are taken of the other 2 ends which gives a total of 2 MD and 2 CD readings per 4" x 4" square.

e. Five specimens shall be tested giving a total of ten readings in the MD and ten in the CD.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

CALCULATIONS:

The hand of the sample in each direction shall be the average of the ten readings and shall be reported to the nearest gram.

4.3.2 Abrasion Resistance.

This method is applicable to determining the abrasion resistance of a reinforced disposable fabric.

Principle of Method. A sample is abraded with Lytron 80 x 56 finished cloth and the resultant damage noted.

Apparatus. Stoll Quartermaster Abrasion Tester with Frosting Method Attachement, High intensity light, Magnifying glass.

Material. 80 x 56 Lytrol finished cloth.

SAMPLE PREPARATION:

a. Cut strips of Lytrol finished cloth 3" wide x 10" long, with the long dimension in the warp direction, to be used as the abradant.

b. Cut 5" squares of the material to be tested.

PROCEDURE:

a. Secure the abradant to the face of the top plate. Fresh abradant is used for each sample.

b. Fasten the test sample on the foam pad of the bottom plate.

c. Place a 2-1/2 lb. weight on the top plate.

d. Focus the high intensity lamp on the sample.

e. Set the counter at zero, lower the top face until the abradant is in contact with the sample, and turn on the tester.

f. Inspect the sample every 5 cycles from 5-30 cycles, and every 10 cycles from 30 until failure. If failure has not occurred at 100 cycles the test may be terminated.

CONCLUSIONS:

Results are reported at two different stages of the test:

a. The number of cycles when pilling is first noted. Pilling is defined as the breaking off of fibers which start to form clumps or beads.

b. The number of cycles necessary for a hole to start to appear in the top surface of the test material.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:32Z
Check the source to verify that this is the current version before use.

4.3.3 Water Repellency. This procedure is applicable to the determination of the repellency of a yarn reinforced disposable fabric.

Principle of Method

The fabric to be tested is used to seal an inverted vented mason jar containing a saline solution and the penetration of the solution through the fabric noted.

Apparatus

a. 2-11/16 inch diameter circular cutting die.

b. Mason jars (1 qt.) with holes drilled in the bottom and metal rings with openings 2-3/16 inch in diameter and fitted with gaskets. Gasket size is outside diameter 2-3/4 inch, inside diameter 2-3/16 inch. The gaskets are to be cut from a coated fabric No. ES-555-B.

c. One glass plate.

d. One mirror.

e. A lamp to place between glass and mirror to shine on sample during test. (Tensor high intensity lamp).

Reagents

0.9% Saline Solution.

Sample Preparation

Die cut 5 samples randomly across the width of the fabric or cut 5 - 5 inch squares randomly across the width of the fabric.

Procedure

a. Hold a finger on the vent hole, pour enough saline solution into a jar to give a 4-1/2 inch head (approx. 600 mls.).

b. Place the test sample on the mouth of the jar and screw the metal ring with gasket in place with sufficient torque to prevent leakage.

c. Invert the jar onto the glass plate which is mounted six to eight inches above the mirror.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:32Z
Check the source to verify that this is the current version before use.

d. Start the timing of the test as soon as the jar is inverted onto the glass plate and terminate it at the first sign of penetration. Penetration is evidenced when saline penetrates the fabric and wets the glass plate. Occasionally some condensation (a light "fog") will be observed on the surface of the glass and care must be taken that this is not confused with a testing failure.

4.3.4 Weight per square yard. This method is applicable to the determination of weight per square yard of a reinforced disposable fabric.

Principle of Method	Samples are to be conditioned. After conditioning, an accurately measured sample is weighed and weight per square yard calculated.
Conditioning	Samples shall be conditioned for at least four hours at a relative humidity of 65% ± 2%, at 70° ± 2° F..
Accuracy	Approximately 1% of the true value.
Apparatus	Balance weighing accurately to 0.01 grams or 1 grain. Scissors. Steel Rule, graduated in 1/32 inch.
Procedure	Lay the fabric on a smooth horizontal surface and draw a line across the full width perpendicular to the edge. Draw another line parallel to the first line and at such a distance from the first line that approximately 2/3 of a square yard (864 sq. in.) in area of sample is defined. Cut out the area laid out above and weigh.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

Calculations

$$W^1 = \frac{W_e \times 1296}{L \times I}$$

or

$$= \frac{W_m \times 1296 \times 15.43}{L \times I}$$

or

$$W^2 = \frac{W^1}{437.5}$$

W^2 = ounces per square yard

W^1 = Weight, grains per square yard.
W_e = Weight of specimen, grains.
W_m = Weight of specimen, grams.
I = Width of specimen in inches.
L = Length of specimen in inches.
15.43 = grains/gram.
437.5 = grains/ounce.

5. PREPARATION FOR DELIVERY

5.1 Packaging and packing. The fabrics shall be packaged and packed in a manner to afford the minimum degree of protection necessary to prevent deterioration or damage during shipment under normal environmental conditions and commercial modes of transportation.

6. NOTES

6.1 Intended use. This specification is for the basic nonwoven fabrics used in the fabrication of components for disposable surgical packs and drapes. The intended use of the individual types are as follows:

TYPE	INTENDED USE
I, IA, IB and IC	Outerwrap
II, IIA and IIB	Table Cover and Mayo Stand Cover
III, IIIA and IIIB	Leggings, Under Buttock Drapes, Abdominal Drape, Utility Drape, Special Purpose Sheet, and Drape Sheet
IV	"T" Sheet Reinforcement
V and VA	Towels

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:32Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.

(b) Type required (1.2.1).

6.3 Availability of testing equipment.

6.3.1 Handle-O-Meter. Handle-O-Meter Model 211-4 or 211-5 may be purchased from:

Thwing-Albert
10960 Dutton Road
Philadelphia, Pa. 19154

6.3.2 Stoll Quartermaster Abrasion Tester with Frosting Method Attachment. Stoll Quartermaster Abrasion Tester with Frosting Method attachment may be purchased from:

Custom Scientific Instruments, Inc.
Whippany, N. J.

6.3.3 Lytron finished cloth (80 x 56). Lytron finished cloth may be obtained from Johnson & Johnson, New Brunswick, N. J.

6.3.4 Coated fabric gaskets. Coated fabric No. ES-555-B for gaskets may be obtained from Permacel, U. S. Route 1, North Brunswick, N. J.

6.3.5 High Intensity Lamp. High intensity lamp may be obtained from:

Tensor Corp.
333 Stanley Avenue
Brooklyn, N. Y. 11207

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6530-1313

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

☆ U. S. GOVERNMENT PRINTING OFFICE: 1974-603-110/1879

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-F-36901A

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:32Z
Check the source to verify that this is the current version before use.