MIL-F-36943A
16 September 1987
SUPERSEDING
MIL-F-36943
3 May 1973

MILITARY SPECIFICATION

FORCEPS, HEMOSTATIC (Curved, Rochester-Pean)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a 6-1/4 inch hemostatic forceps of the Rochester-Pean design suitable for accomplishing hemostasis in delicate tissue.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. The following specifications and standards form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Headquarters, Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, DPSC-RST, 2800 S. 20th Street, Philadelphia, PA 19101, by using self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 6515
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

GG-I-526	- Instruments, Dental and Surgical; General Specifications.
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-601	- Boxes, Wood, Cleated-plywood.
PPP-B-621	- Boxes, Wood, Nailed and Lock-corner.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Boxes, Set-up.

MILITARY

MIL-P-116	- Preservation, Methods of.
MIL-L-10547	- Liners, Case and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.
MIL-STD-147	- Palletized Unit Loads.
MIL-STD-794	- Parts and Equipment, Procedures for Packaging of.

2.1.2 Drawing. The following drawing forms a part of this specification to the extent specified herein. Unless otherwise specified, the issue shall be that in effect on the date of the solicitation.

DRAWING

Defense Personnel Support Center (DPSC)

No. 20290	- FORCEPS. HEMOSTATIC, CURVED, Rochester-Pean, 6-1/4 Inch

(Copies of specifications, standards and drawing required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

as constructed and

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted shall be those listed in the issue of the DoDISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DoDISS shall be the issue of the nongovernment documents which is current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) STANDARDS

E 18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials, Tests for.

E 92 - Vickers Hardness of Metallic Materials, Tests for.

E 140 - Hardness Conversion Tables for Metals (Relationship Between Brinell Hardness, Vickers Hardness, Rockwell Hardness, Rockwell Superficial Hardness and Knoop Hardness).

F 899 - Stainless Steel Billet, Bar and Wire for Surgical Instruments.

F 921 - Standard Definitions of Terms Relating to Hemostatic Forceps

F 1026 - General Workmanship and Performance Measurements of Hemostatic Forceps.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services).

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General requirements. The hemostatic forceps shall be in accordance with the applicable requirements ASTM F1026 as specified herein. The terms used to describe the components and portions of the forceps described in this specification shall be in accordance with ASTM F921.

3.2 Material. The forceps shall be fabricated from Class 4, martensitic stainless steel in accordance with ASTM F899.

3.3 Hardness. The forceps shall have a Rockwell hardness of C40 to C47. This requirement shall not apply to the screw or pin. The requirements of Federal Specification GG-I-526 shall apply.

3.4 Style, design and dimensions. The forceps shall be of the Rochester-Pean design with a curved tip. The forceps shall be in accordance with DPSC Drawing Number 20290.

3.5 Locks. The forceps shall be as specified in ASTM F1026.

3.6 Finish. Finish shall be mirror, satin or matte. Should the forceps be of mirror finish, the locks and ratchet shall be polished smooth, but need not possess a mirror finish. The matte finish shall exhibit a uniform nondirectional surface texture equivalent to that produced by lightly blasting the prepared surface with fine abrasives under pressure.

3.6.1 Passivation. The forceps shall be properly passivated.

3.6.2 Corrosion resistance. The forceps shall show no sign of corrosion or plating of copper as specified in Federal Specification GG-I-526.

3.7 Jaws and ratchet operation. The forceps shall be tested as specified in ASTM F1026. Forceps which do not perform as specified shall be rejected.

3.8 Identification markings. In addition to the requirements specified in ASTM F1026, forceps of foreign manufacture shall be marked "stainless."

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection shall be in accordance with GG-I-526.

4.1.2 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.3 Certificate of quality. Certificate of quality supplied by the manufacturer of the corrosion-resistant steel, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number, the item identification, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.1.4 Metric products Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerance specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimemsions exceed the tolerance specified in the inch-pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in Table I. Unit of product for examination purposes shall be one forceps.

TABLE I. Sampling criteria for inspection.

Type of defect	Inspection level	AQL (percent defective)
Major	II	1.0
Minor	II	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as indicated in table II. The unit of product for test purpose shall be one forceps. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

TABLE II. Sampling criteria for tests

Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Hardness test	3.3 & GG-I-526	4.4.1	S-2	1.5
Dimensions	3.4	----	S-2	2.5
Distortion test	ASTM F1026	----	S-2	2.5
Copper sulfate test	GG-I-526	GG-I-526	S-2	1.0
Boil test	GG-I-526	GG-I-526	S-2	1.0
Jaw and ratchet operation test	3.7 & ASTM F1026		S-2	1.0

4.2.3 Raw materials. A sufficient quantity of each lot of metal used in the manufacture of the forceps shall be selected for chemical analysis.

4.3 Examination.

4.3.1 Examination of forceps. The forceps shall be examined to determine compliance with all the requirements contained in this specification. Examination shall be conducted as specified in tables I and III. Examination, however, shall not be restricted to defects listed in table III. Any forceps in the sample containing one or more defects shall be rejected and if the number of defective forceps in any sample exceeds the acceptance number for the sample, the lot represented by that sample shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

TABLE III. Classification of defects

Categories	Defects
Critical	None defined
Major	
101	Forceps not of the specified design for appropriate type, stock number and item identification.
102	Both jaws not serrated throughout full length.
103	Jaw serrations not of uniform depth and not well defined.
104	Jaw serrations not chamfered through full length.
105	Ratchet teeth not well defined.
106	Forceps not free from cracks, pits, burrs, sharp edges, scale, rough areas or corrosion.
107	Finish of forceps not uniform and not as specified.
108	Serrations of both jaws do not completely mesh in fully closed position.
109	Box lock performance not as specified in 3.5.
110	Jaws possess sharp tips.
111	Ratchet teeth do not completely engage in all positions.
112	Pin for box lock not flush with surface and not free from crevices.
Minor	
201	Forceps not free from dirt, polishing material or foreign matter.
202	Identification markings not present, not correct, not complete, or not legible.

4.3.2 Inspection of packaging. The sampling and inspection of the preservation and interior package marking shall be in accordance with groups A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Hardness test. Hardness shall be determined in accordance with ASTM Standards E 18 or E 92. Conversion of Vickers hardness values to Rockwell values shall be in accordance with ASTM Standard E 140.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or C as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Cleaning and drying. Forceps shall be cleaned and dried in accordance with MIL-P-116.

5.1.1.2 Preservative applications. Preservatives shall not be used.

5.1.1.3 Unit package. Each forceps shall be wrapped in neutral tissue paper or other suitable anticorrosive material. Each forceps shall be further packaged in accordance with MIL-P-116, method 1C-1.

5.1.1.4 Intermediate package. Twelve forceps shall be packaged in a box conforming to PPP-B-566, PPP-B-676 or PPP-B-636, Type CF, class domestic. Closure shall be as specified in the applicable box specification.

5.1.2 Level C.

5.1.2.1 Unit package. Presevation for forceps shall conform to the requirements of MIL-STD-794 for level C.

5.1.2.2 Intermediate package. Twelve forceps shall be packaged in accordance with the requirements of MIL-STD-794 for level C.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Two hundred and eighty-eight forceps shall be packed in designed for a type 2 load and conforming to PPP-B-601, overseas type, PPP-B-621, class 2 or PPP-B-636, class weather-resistant, grade V3c. Closure and strapping shall be as specified in the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall be as specified in the liner specification. Case liner shall not be required for fiberboard boxes. Each fiberboard box shall be waterproofed as specified in PPP-B-636.

5.2.2 Level B. Two hundred-eighty-eight forceps shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-601, domestic type, PPP-B-621, class 1 or PPP-B-636, class domestic. Closure shall be as specified in the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T09:37Z
Check the source to verify that this is the current version before use.

The name of the component/material, the lot number, the lot size, and

5.2.3 Level C. Two hundred eighty-eight forceps shall be packed in accordance with the requirements of MIL-STD-794 for level C.

5.2.4 Packing variation permitted. If the required number of units to be shipped is less than the number of units specified to be overpacked in a exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which will insure safe delivery to destination.

5.2.5 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantity for shipment to one destination exceeds 250 lbs (excluding the pallet) or 20 cubic feet. Loads shall be unitized as specified in MIL-STD-147, on Type IV or Type V 4-way entry pallets. Pallet shall have a length of 40 inches and a width of 48 inches. Pallet loads, including the pallet, shall not exceed 54 inches in height, 40 inches in length and 48 inches in width. Quantity for shipment to one destination of less than 250 lbs or 20 cubic feet need not be palletized.

5.2.5.1 Levels A and B. Forceps packed as specified in 5.2.1 and 5.2.2 shall be unitized on pallets conforming to MIL-STD-147.

5.2.5.2 Level C. Forceps packed as specified in 5.2.3 shall be unitized as specified in 5.2.5.

5.3 Marking.

5.3.1 Levels A, B and C. Each unit pack, intermediate package, exterior container and unitized load shall be marked as specified in MIL-STD-129.

5.4 General.

5.4.1 Exterior container. Exterior container (see 5.2.1, 5.2.2, and 5.2.3) shall be of minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be in accordance with 4.3.2.

6. NOTES

6.1 Intended use. Hemostatic forceps shall be used for accomplishing hemostasis in delicate tissue.

6.2 Ordering data.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number, and date of specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(c) Applicable National Stock Number.

6.3 National Stock Number Coverage. This specification covers the following National Stock Number:

National Stock No.	Item Identification
6515-00-334-4300	FORCEPS, HEMOSTATIC, CURVED, Rochester-Pean, 6-1/4 Inch

6.4 Matte and satin finish. It should be noted that matte finish specified herein can be distinguishable from mirror and satin finishes under high-power illuminated magnification. Forceps of matte finish shall have a reduced reflective surface that is more glare resistant than satin finish.

6.5 Subject term (key word) listing.

Curved forceps
Forceps
Hemostatic forceps

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

Preparing Activity:

DoD-MR

Agent:

DLA-DM

CIVIL AGENCY COORDINATION ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6515-3494

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:37Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE. This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-NSTS
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:37Z
Check the source to verify that this is the current version before use.

2 APPLICABLE DOCUMENTS

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-F-36943A	FORCEPS, HEMOSTATIC (Curved, Rochester-Pean)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION (Mark one)
	☐ VENDOR
b. ADDRESS (Street, City, State, ZIP Code)	☐ USER
	☐ MANUFACTURER
	☐ OTHER (Specify)

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER (Last, First, MI) - Optional	b. WORK TELEPHONE NUMBER (Include Area Code) - Optional
c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional	8. DATE OF SUBMISSION (YYMMDD)

DD FORM 82 MAR 1426

PREVIOUS EDITION IS OBSOLETE.

...M THIS FORM, CUT ALONG THIS LINE)

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:37Z
Check the source to verify that this is the current version before use.