MIL-F-10870G
30 September 1982
SUPERSEDING
MIL-F-10870F
29 May 1973

MILITARY SPECIFICATION

FOOD CONTAINER, INSULATED, WITH INSERTS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a rectangular shaped insulated metal container with removable inserts and gaskets for transportation of hot or cold foods or liquids (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

| | | |
|---|---|---|
| QQ-A-250/2 | - | Aluminum Alloy 3003, Plate and Sheet |
| TT-E-529 | - | Enamel, Alkyd, Semigloss |
| TT-P-1757 | - | Primer Coating, Zinc Chromate, Low Moisture-Sensitivity for Aluminum Surfaces |
| PPP-B-636 | - | Boxes, Shipping, Fiberboard |

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Laboratories, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 7330

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

MILITARY

| | | |
|---|---|---|
| MIL-R-3065 | - | Rubber, Fabricated Products |
| MIL-P-4861 | - | Packing, Preformed, Rubber, Packaging Of |
| MIL-C-5541 | - | Chemical Conversion Coatings on Aluminum and Aluminum Alloys |
| MIL-W-6858 | - | Welding, Resistance, Spot and Seam |
| MIL-P-21929 | - | Plastic Material, Cellular Polyurethane, Foam-in-Place, Rigid, (2 and 4 pounds per cubic foot). |

STANDARDS

FEDERAL

| | | |
|---|---|---|
| FED-STD-141 | - | Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing |
| FED-STD-595 | - | Colors |

MILITARY

| | | |
|---|---|---|
| MIL-STD-105 | - | Sampling Procedures and Tables for Inspection by Attributes |
| MIL-STD-129 | - | Marking for Shipment and Storage |
| MIL-STD-1188 | - | Commercial Packaging of Supplies and Equipment |

DRAWINGS

US ARMY NATICK RESEARCH AND DEVELOPMENT LABORATORIES

| | | |
|---|---|---|
| 2-9-109 | - | Food Container, Insulated, with Inserts; Assembly Complete |
| 2-9-110 | - | Cover and Body Assembly |
| 2-9-111 | - | Cover and Body Details |
| 2-9-112 | - | Insert Assembly and Details |
| 5-13-143 | - | Food Container, Insulated, with Inserts; Method of Placing Top and Bottom Pads, Corner Cells and Separator in Fiberboard Container |

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A-167 - Stainless and Heat-Resisting Chromium-Nickel Steel Plate, Sheet, and Strip

A-276 - Stainless and Heat-Resistant Steel Bars and Shapes

D-2000 - Elastomeric Materials for Automotive Applications

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

3. REQUIREMENTS

3.1 First article. When specified, a sample shall be subjected to first article inspections (see 4.3, 6.2 and 6.3).

3.2 Materials and components. Materials (see 6.5) and components shall be as specified on Drawing 2-9-110.

3.3 Description. The item covered by this document shall consist of an insulated container with three uninsulated inserts. The container shall be provided with an insulated cover held in closed position by over-center type latch assemblies. Drop



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the currentversion before use.

handles shall be provided on the ends of the container for ease in handling. Each insert shall be provided with a bail handle serving the dual purpose of transport and retaining the insert cover in place. The container cover and each insert cover shall be provided with a molded rubber gasket to prevent leakage.

3.4 Construction. The construction shall conform in all respects to the drawings listed in 2.1 and as specified herein.

3.4.1 Welding. Spot welds for aluminum components shall conform to class C of MIL-W-6858.

3.4.2 Application of insulation. Before final assembly, the space between container outer and inner shells and between cover top and cover liner shall be completely filled with insulation, by foaming in place, as specified in MIL-P-21929, except minimum overall density shall be 1.8 pound per cubic foot when tested as specified in paragraph 4.4.2.3.2. Body and cover shall be heated to 130 degrees Fahrenheit (F.), plus or minus 10 F., immediately prior to pouring the polyurethane foam mix from the mixing machine. When foamed and cured, the insulation shall be firmly bonded to surrounding metal and to underside of phenolic body-collar. The body bottom and cover liner shall be installed after the polyurethane mix has foamed and completely filled the body and cover cavities. Voids and blow holes (1/4 inch or less) covering less than 25 percent of the exposed insulation surfaces shall not be cause for rejection.

3.4.3 Inner shell. The container inner shell shall be formed from one piece of sheet aluminum as specified in QQ-A-250/2.

3.4.4 Body collar. The exposed surface of the body collar shall be black.

3.4.5 Gaskets. The compressibility of the container gasket and the insert gasket shall be such that they form a tight seal when container and insert covers are closed (see 3.6.1 and 3.6.2). Rubber shall conform to the requirements of class, grade and suffix letters SC515A, B, S, of MIL-R-3065 and ASTM D-2000.

3.5 Finish.

3.5.1 Exterior surface of container. Exterior aluminum surfaces including handles shall be prepared for painting by application of a chemical film conforming to class 2 of MIL-C-5541. Corrosion-resisting steel hardware shall be thoroughly



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

cleaned (it will be permissible to treat attached corrosion-resisting steel hardware by the same process specified for the aluminum parts). After thorough drying, the treated surfaces shall be coated with primer as specified in TT-P-1757. Dry film thickness shall be not less than 0.4 mil. The primer coat, when thoroughly dry, shall be followed by a coat of enamel as specified in TT-E-529. The color shall be olive drab No. X24087 of FED-STD-595. Dry film thickness of the combined primer and enamel coats shall be not less than 1.2 mils. Gaskets shall not be subjected to baking. The final exterior finish shall be free from imprints when tested as specified in 4.5.2.

3.5.2 Interior surfaces and inserts. The inside of the container, except cover liner, and all surfaces of the inserts shall be given a frosted finish produced chemically to result in a uniform frosted appearance, free from finger marks and discoloration, except that light water marks will not be objectionable. Light stains on insert exteriors in the bail retainer area caused by bleeding of cleaning solutions after washing and rinsing and light grey to white stains on insert cover exterior shall be acceptable.

3.6 Water tightness.

3.6.1 Container. When tested as specified in 4.5.1.1, not more than one fluid ounce of water shall leak through the cover gasket. Moisture on the gasket will not be regarded as a test failure.

3.6.2 Inserts. When tested as specified in 4.5.1.2, not more than 6 fluid ounces of water shall leak from the three inserts.

3.7 Closing and latching the container cover. The pressure required to close the four latches shall be substantially uniform.

3.8 Special marking. Waterproof label or decalcomania shall be printed with waterproof ink and securely attached on the outside of the container cover. The label or decalcomania shall contain the title and headings printed in 12- or 14-point bold face type and the text shall be printed in 10-point bold face type as follows:

FOOD CONTAINER, INSULATED, WITH INSERTS

Rough handling or lost gaskets will reduce efficiency of this container. To prevent leakage, see that gaskets are in place and that container, inserts and covers are not deformed.

INSTRUCTIONS FOR USE

If the inserts and interior of the container are cold, warming them with hot water before filling with food will keep foods hot longer.



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

DO NOT WARM CONTAINER OVER AN OPEN FLAME

When cleaning the containers or inserts, remove all gaskets and wash them thoroughly with soap and water. Replace container gasket with open side down immediately after cleaning and drying. Replace insert gasket immediately after cleaning and drying.

NOMENCLATURE OF PARTS

Food Container, Insulated, Without Inserts.
Insert, Food Container, Insulated, Complete.
Gasket, Outer Cover, Food Container, Insulated.
Gasket, Insert Cover, Food Container, Insulated.

3.9 Marking for identification.

3.9.1 Container. The letters "U.S.", manufacturer's name, trade name or trademark, of such known character as to be easily identified with said manufacturer, contract number, and the year of contract shall be embossed in the size and location shown on Drawing 2-9-109. The surface exhibiting these embossed marks shall show no signs of fracture or distortion. At the option of the contractor, the embossed marks may be placed on both the front and back of the food containers.

3.9.2 Insert. The letters "U.S.", manufacturer's name, trade name or trademark of such known character as to be easily identified with said manufacturer, contract number, and the year of contract shall be indented in the size and location shown on Drawing 2-9-112. The surface opposite these indentation marks shall show no signs of penetration or unevenness, nor shall the marks cause distortion.

3.10 Workmanship. The finished food container shall be clean, well made, suitable for the intended use. All components shall be carefully assembled, adjusted, and aligned. Welds shall be sound, without pits, undercuts, cracks, burnholes, or fractures. Holes for rivets shall be correctly punched or drilled, and all burrs that would prevent proper seating of rivets removed. Rivet heads shall make full contact with riveted surfaces, shall be peened and set tightly. Sharp edges, projections, and slivers shall be removed. The container finish shall be smooth and uniform, without runs, wrinkles, drops, streaks, or areas of thin film or no film, and shall be free from grit or coarse particles.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for defects specified in 4.4.3.1, 4.4.3.2, and 4.4.3.3. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 Process inspection.

4.4.2.1 Process examination. Inspection shall be made of the following processes to establish conformance with specified requirements. Whenever a non-conformance is noted, correction shall be made to affected items and lots in process.

| Requirement | Reference paragraph |
|---|---|
| Insulation of cover and body, following pre-heating | 3.4.2 |
| Surface treating in preparation for painting. | 3.5.1 |
| Application of primer to treated surfaces prior to enameling. | 3.5.1 |
| Interior reinforcements (latch and handle). Interior brackets (side and end). | Drawing Number 2-9-110 |



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the currentversion before use.

4.4.2.2 Intermediate examination. Examination shall be performed after making a complete longitudinal cut through the vertical centerline of the container to expose the insulation and reinforcements. Two examinations shall be made for the first 500 units produced. If no defects are noted, one examination shall be made for the next 1000 units. If no defects are noted, then one examination shall be made for each remaining 2000 units produced. If defects are noted during any of the above examinations, two examinations shall be made from the next 500 units and the entire procedure shall be repeated. Examinations shall be made for the defects listed below. The Government reserves the right to exclude from acceptance, lots for which intermediate examinations report noncompliance.

| Examine | Defect |
|---|---|
| Insulation | Contains voids or blowholes deeper than 1/4 inch or covering more than 25 percent of exposed area.<br>Cover or body cavities not completely filled.<br>Not firmly bonded to metal walls or underside of phenolic collar.<br>Not completely foamed.<br>Contains accumulations of unexpanded resin or other inclusions. |
| Reinforcement | Any missing, not formed, or not attached as shown on drawing.<br>Not securely fastened, or not in specified location.<br>Fastened with less than required number of spot welds. |

4.4.2.3 Intermediate testing.

4.4.2.3.1 Primer. Testing of the primer shall be performed on each sample unit for thickness of primer coat as specified in 3.5.1. The sample unit shall consist of one container after the application of primer but before the enamel application. The lot shall consist of the number of containers offered for inspection at one time. Any deviation from the requirements shall be classified as a defect. The inspection level shall be S-2 and the acceptable quality level (AQL) shall be 4.0, expressed in terms of defects per hundred units.

4.4.2.3.2 Insulation density. Cut a 36-cubic-inch sample from each container body and each container cover bisected for intermediate examination (see 4.4.2.2). Each sample shall be checked for 0.6 ounce weight requirements as specified in MIL-P-21929.

4.4.3 End item inspection. The lot shall consist of all complete containers, inserts, insert gaskets, or container gaskets offered for inspection at one time. The sample unit for visual and dimensional examination shall be one complete container, insert, insert gasket, or container gasket, as applicable.



Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

4.4.3.1 Visual examination. The complete container, insert, insert gasket, or container gasket, as applicable, shall be examined for defects listed in table I. The inspection level shall be II with an AQL of 2.5 for major defects and 6.5 for total defects expressed in terms of defects per hundred units.

TABLE I. Classification of defects

| Examine | Defect | Classification Major | Minor |
|---|---|---|---|
| | Food Container (complete) | | |
| Finish | | | |
| Exterior surface of body and cover | Not enameled. | X | |
| | Color not olive drab. | | X |
| | Color not uniform or surface not smooth. | | X |
| | Chipped, peeled, or blistered (except rubbing surfaces of hardware). | X | |
| | Wet or tacky. | | X |
| | Hard or soft sags or runs. | | X |
| Interior surface of body and all surfaces of inserts and covers | Does not have frosted finish (except corrosion-resisting steel cover liner). | | X |
| | Not smoothly surfaced - marks or dirt in finish. | | X |
| | Discolored (see 3.5.2). | | X |
| Construction and workmanship (general) | Part missing. | X | |
| | Part cracked, broken, punctured, or malformed. | X | |
| | Any part designed to move that jams or requires abnormal force to operate. | X | |
| | Part not securely fastened. | X | |
| | Part not located or aligned as specified. | X | |
| | Any irregularity that impairs function, i.e., depressions in surfaces that cause poor sealing. | X | |
| | Any sharp edges, corners, slivers, or burrs. | X | |
| | Any distortion of container body or cover or insert body or cover. | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects (cont'd)

| Examine | Defect | Classification Major | Minor |
|---|---|---|---|
| Welding | Spot welds not located as shown or as specified. | X | |
| | Spot welds not diameter specified. | | X |
| | Less than specified number of spot welds. | X | |
| | Incomplete fusion of spot welds. | X | |
| Riveting | Rivet(s) loose or not fully peened. | X | |
| | Rivet head(s) broken or damaged or not properly seated. | X | |
| | Rivet(s) not vertically aligned with riveted surfaces. | | X |
| | Rivets not as specified. | X | |
| Container body and cover | Metal beads of body and cover butt at any point in locked position. | X | |
| | Tension on latch bails not uniform; or not enough tension for good seal. | X | |
| | Latch bail too tight - required abnormal force to open. | X | |
| | Body and bottom flanges not tight fit in bottom channel. | X | |
| | Inner shell not formed from one sheet of aluminum. | X | |
| | Distortion of body or cover. | X | |
| Gaskets | Gasket retained in position by fastening device or adhesive. | X | |
| | Surface imperfections that could cause leakage. | X | |
| Inserts | Poor fit of insert cover to body of insert. | X | |
| | End of bail not headed to prevent removal from bail retainer. | | X |
| | Body and cover each not formed from one sheet of aluminum. | X | |
| | Distortion of body or cover. | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects (cont'd)

| Examine | Defect | Classification Major | Classification Minor |
|---|---|---|---|
| Marking | Special markings not as specified (see 3.8). | | X |
| | Identification marking not as specified (see 3.9). | | X |
| | Embossed marking shows signs of | | X |
| | a. Distortion | X | |
| | b. Metal fracture | | |
| | Inserts (applicable when purchased separately) | | |
| Finish | Do not have frosted finish. | | X |
| | Not smoothly surfaced - marks or dirt in finish. | | X |
| | Discolored. | | X |
| Construction and workmanship (general) | Part missing. | X | |
| | Part cracked, broken, fractured or malformed. | X | |
| | Any part designed to move that jams or requires abnormal force to operate. | X | |
| | Parts not securely fastened. | X | |
| | Part not located or aligned as specified. | X | |
| | Any sharp edges, corners or burrs. | X | |
| | Any distortion of insert body or cover. | X | |
| Welding | Spot welds not located as shown or specified. | X | |
| | Spot welds not diameter specified. | | X |
| | Less than specified number of spot welds. | X | |
| | Incomplete fusion of spot welds. | X | |
| | Poor fit of insert cover to body of insert. | X | |
| | End of bail not headed to prevent removal from bail retainer. | | X |
| | Body and cover each not formed from one sheet of aluminum. | X | |
| | Distortion of body or cover. | X | |



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects (cont'd)

| Examine | Defect | Classification Major | Classification Minor |
|---|---|---|---|
| Marking | Identification marking not as specified. | | X |
| | Embossed marking shows signs of | | |
| | a. Distortion. | | X |
| | b. Metal fracture. | X | |
| | Insert gaskets and container gaskets (applicable when purchased separately) | | |
| Gaskets | Any irregularity that impairs function i.e., depressions in surface that cause poor sealing. | X | |
| | Surface imperfections that could cause leakage. | X | |

4.4.3.2 Dimensional examination. Dimensional examination shall be made of the complete container, insert, insert gasket, or container gasket, as applicable, to determine compliance with this document. Any dimension not within the specified requirements shall be classified a defect. The inspection level shall be S-2 with an AQL of 4.0 expressed in terms of defects per hundred units.

4.4.3.3 End item testing. When a first article is not required, the first unit of production shall be tested in accordance with 4.2. Tests listed in table II shall be performed on the end item as applicable.

TABLE II. End item testing

| Characteristic | Requirement paragraph | Test method | Inspection | AQL |
|---|---|---|---|---|
| Leakage of container | 3.6.1 | 4.5.1.1 | S-2 | 2.5 |
| Thickness of combined primer and enamel | 3.5.1 | Standard commercial | S-2 | 2.5 |
| Leakage of inserts | 3.6.2 | 4.5.1.2 | S-2 | 2.5 |
| Imprint test on exterior finish | 3.5.1 | 4.5.2 | S-2 | 2.5 |



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

4.4.4 Packaging inspection. An examination shall be made to determine that preservation, packing and marking requirements comply with the section 5 requirements. Defects shall be scored in accordance with table III. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Examination of closure defects shall be made on shipping containers fully packaged. The lot size shall be the number of containers in the inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

TABLE III. Packaging inspection

| Examine | Defect |
|---|---|
| Markings | Missing; incorrect; illegible; of improper size, location, sequence, or method of application. |
| Materials | Component missing or damaged. |
| Contents | Contents per containers is more or less than required. |

4.5 Tests.

4.5.1 Leak tests.

4.5.1.1 Container. Thirty-two pounds of tap water at a room temperature between 65 F. and 70 F. shall be poured into a container without the inserts. With cover locked tightly, the container shall be turned upside down for a period of fifteen minutes, and right-side-up for an additional fifteen minutes. The container shall be examined during and after this test to determine compliance with the requirements as specified in 3.6.1. Inability to comply with requirements shall constitute failure of this test.

4.5.1.2 Insert. Ten pounds of tap water at a room temperature between 65 F. and 70 F. shall be poured into each of the three inserts. With the insert covers on, the inserts shall be placed in the container and the container cover locked tightly. The container shall then be turned upside down for a period of fifteen minutes. During and after this test, the inserts shall be examined to determine compliance with the requirements as specified in 3.6.2. Inability to comply with requirements shall constitute failure of this test.

4.5.2 Imprint test. The final finish of the exterior surface of the container shall be given the print test specified in Method 6211 of FED-STD-141, except commercial cheesecloth and a 2-pound weight shall be used. After pressing for 15 minutes, the final finish shall be examined visually to determine compliance with the imprint requirements as specified in 3.5.1. A determination shall be made on each surface. Inability to comply with requirements shall constitute failure of this test.



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Food container, insulated, with inserts. The three inserts complete with covers shall be positioned within the well of the food container. A sheet of parchment paper having a basis weight of 26 pounds per ream (24 by 36-500) shall be placed to cover all points of contact between the container body and the rubber gasket. The parchment paper shall be vegetable parchment and shall not impart any objectionable odor or flavor, or add any toxic substance to any part of the food container which will affect food to be stored in the container. The cover of the food container shall then be closed and latched tightly in place.

5.1.1.2 Gasket, food container and gasket, insert, food container. The gaskets for the food container or inserts shall be packaged in accordance with the level A packaging requirements of MIL-P-4861.

5.1.1.3 Insert, food container. Each insert shall be unit packed in a snug-fitting fiberboard box conforming to style RSC, type CF, variety SW, or type SF, class domestic of PPP-B-636. Box closure shall be in accordance with the appendix of PPP-B-636.

5.1.2 Commercial. The complete food containers, gaskets, or inserts shall be preserved in accordance with MIL-STD-1188.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing.

5.2.1.1 Food container, insulated, with inserts. Two food containers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V2s of PPP-B-636. The food containers shall be packed in the fiberboard shipping container as shown on Drawing 5-13-143. Corner cells, top and bottom pads, and the separator shall be fabricated from fiberboard conforming to W6c or W6s of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

5.2.1.2 Gasket, food container and gasket, insert, food container. The gaskets for the food container or inserts, preserved as specified in 5.1, shall be packed in accordance with the level A packing requirements of MIL-P-4861.



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

5.2.1.3 Insert, food container. Eight inserts preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V2s of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

5.2.2 Level B packing.

5.2.2.1 Food container, insulated, with inserts. Two food containers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF, variety SW, or type SF, class domestic, grade 275 of PPP-B-636. The food containers shall be packed in the fiberboard shipping container as shown on Drawing 5-13-143. Corner cells, top and bottom pads, and the separator shall be fabricated from materials as specified for the fiberboard shipping container. Closure shall be in accordance with method II of the appendix of PPP-B-636.

5.2.2.2 Gasket, food container and gasket, insert, food container. The gaskets for the food container or inserts, preserved as specified in 5.1, shall be packed in accordance with the level B packing requirements of MIL-P-4861.

5.2.2.3 Insert, food container. Eight inserts, packaged as specified in 5.1, shall be packed upright in a snug-fitting fiberboard shipping container conforming to style RSC, type CF, variety SW, or type SF, class domestic, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.4 Weather-resistance fiberboard containers. When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of the container specification.

5.2.3 Commercial packing. The complete food containers, gaskets, or inserts, preserved as specified in 5.1 shall be packed in accordance with MIL-STD-1188.

5.3 Marking. In addition to any special marking required by the contract or purchase order, unit packs and shipping containers shall be marked in accordance with MIL-STD-129 or MIL-STD-1188, as applicable.

6. NOTES

6.1 Intended use. The insulated food container is used to maintain the desired temperature of foods and beverages while transporting them from the kitchen to troops in the field. It is suitable for keeping the contents palatably warm for at least three hours at ambient temperatures down to minus 20 F. Removable components (inserts, insert gaskets and container gaskets) can be procured separately.



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Acquisition documents should specify the following:

(a) Title, number, and date of this document.
(b) When a first article is required (see 3.1, 4.3 and 6.4).
(c) Number of inserts, insert gaskets or container gaskets, if procured separately.
(d) Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
(e) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).

6.3 Samples. For access to samples and the transceiver required for the fit examination in 4.4.3.2, address the procuring activity issuing the invitation for bids.

6.4 First article. When a first article sample is required, it shall be inspected and approved under the appropriate provisions of DAR 7-104.55. The first article should be a preproduction sample consisting of one food container with inserts. The contracting officer should include specific instructions in acquisition documents regarding arrangements for inspection and approval of the first article.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document (see 3.2).

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - SA
Air Force - 99

Preparing activity:

Army - GL

Project No. 7330-0473

Review activities:

Army - MD
Navy - MC, MS, YD, SA, CG
Air Force - 84
DSA - GS



Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-F-10870G Food Container, Insulated, With Inserts

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

**DD FORM 1 OCT 76 1426** EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

**BUSINESS REPLY CARD**

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Command
ATTN: DRDNA-ES
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.