MIL-H-10868F
25 March 1988
SUPERSEDING
MIL-H-10868E
25 March 1984

MILITARY SPECIFICATION

HOSE ASSEMBLY, RUBBER, UTILITY, GASOLINE (1/4-INCH INSIDE DIAMETER)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers a gasoline utility hose assembly used to transfer fuel from the source to the stove adapter.

1.2 Classification. The hose assemblies shall be of the following lengths as specified (see 6.2).

Length 1 - 6 feet
Length 2 - 12 feet

* 1.2.1 Part identification number. The part identification number is definitive and formatted to identify each item covered by this specification. The part identification number shall consist of the letter M, the basic number of the specification and the appropriate numbering sequence as specified below:

M10868- X

- X: Length (example: M10868-1)
- 10868: Specification number. Do not include the revision letter or activity symbol.
- M: An item defined by inch-pounds

* Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 4720

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

QQ-B-626 - Brass, Leaded and Nonleaded Rod Shapes, Forgings and Flat Product TH Finished Edges (Bar and Strip).

MILITARY

MIL-P-775 - Packaging of Hose, Hose Assemblies; Rubber, Plastic, Fabric or Metal (Including Tubing); and Fittings, Nozzles and Strainers

STANDARDS

FEDERAL

FED-STD-601 - Rubber; Sampling and Testing

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and storage

* (Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

DRAWINGS

* US ARMY NATICK RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

5-13-1953 - Hose Assembly, Rubber, Utility, Gasoline (1/4-Inch Inside Diameter)

* (Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

* 2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 412	-	Rubber Properties in Tension
D 573	-	Rubber-Deterioration in An Air Oven
D 1053	-	Rubber Property - Stiffening at Low Temperatures Using a Torsional Wire Apparatus Measuring
D 3951	-	Standard Practice for Commercial Packaging
F 607	-	Adhesion of Gasket Materials to Metal Surfaces, Test for

(Copies may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

* (Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

* 2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2 and 6.3).

* 3.2 Material and components. Material and components shall conform to applicable documents and requirements specified herein and on the applicable drawings. Materials and components not specifically defined shall be of the quality normally used by the manufacturer provided the complete item complies with all the provisions of this document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

* 3.2.1 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the document.

3.3 Design and construction. The hose assembly shall consist of hose and fittings (swivel, fixed and splice couplings) as specified on Drawing 5-13-1953. The male (fixed coupling) and female (swivel coupling) shall be firmly installed in the hose so that the hose assembly shall not leak when tested as specified in 4.5.1. The female fitting shall be attached so that the nut shall revolve freely. The splice fitting and the two hose clamps shall be secured to the hose assembly with soft, galvanized, steel, tie-wire, commercial grade, located 6 to 10 inches from the male fitting. The tie-wire shall be tightened so that it shall not be depressed in the hose.

3.3.1 Hose. The hose shall be made from a compounded rubber inner tube, a cotton or synthetic fiber reinforcement and a compounded rubber cover.

* 3.3.1.1 Tube. The tube shall be of uniform thickness and shall be not less than 0.030 inches in thickness. The material shall be a synthetic rubber utilizing a copolymer of epichlorohydrin and ethylene oxide as the sole elastomeric component.

* 3.3.1.2 Cover. The cover shall be black. The cover thickness shall be not less than 0.025 inches. The material shall be a synthetic rubber utilizing a copolymer or epichlorohydrin and ethylene oxide as the sole elastomeric component.

3.3.1.3 Reinforcement. The reinforcement shall consist of a single braid of cotton or synthetic yarn, a circular woven ply of cotton or suitable yarn or equivalent plies of woven fabric. The reinforcement shall be applied so that the cover shall be smooth with no visual evidence of lumps on the cover due to kinking of the reinforcement or embedded foreign matter.

3.3.1.4 Bursting strength. The bursting strength of the hose shall be not less than 400 pounds per square inch (psi) when tested as specified in 4.5.2.

3.3.1.5 Tensile strength and ultimate elongation.

3.3.1.5.1 Rubber hose (as received). The tensile strength of the hose tube shall be not less than 1200 psi; the tensile strength of the cover shall be not less than 1100 psi; and the ultimate elongation of the tube and cover shall be not less than 200 percent of the initial length of the tube and cover, when tested as specified in 4.5.3.1.

3.3.1.5.2 Rubber hose (after aging). The rubber hose tube and cover after aging shall not lose more than 25 percent of the "as received" tensile strength of the cover and 40 percent of the "as received" elongation when tested as specified in 4.5.3.2.

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

3.3.1.6 Volume swell. The volume increase of the tube and cover of the hose, after immersion, shall not exceed 30 percent, when tested as specified in 4.5.4.

3.3.1.7 Flammability. The cover of the hose shall be self-extinguishing within 60 seconds when tested as specified in 4.5.5.

3.3.1.8 Low temperature flexibility. The relative torsional modulus for the tube and cover of the hose shall be no greater than 5 at -40°C, when tested as specified in 4.5.6.

3.3.1.9 Corrosion resistance. The hose tube shall have a corrosion resistance rating of no more than II in accordance with ASTM F 607 when tested as specified in 4.5.7.

3.4 Identification marking. Each hose assembly shall be identified with an aluminum tag. The manufacturer's identification along with the following information shall be indented on the aluminum tag in accordance with commercial practice:

Size: 1/4 Inch Inside Diameter
Cure date: (quarter and year)
Part identification number (see 1.2.1)
After three years in storage, samples of these hoses should be tested for low temperature flexibility and leakage.

The tag shall be attached on the outside of the rubber hose by tie-wire, halfway between the ends of the hose assembly. The tie-wire shall be soft, galvanized steel wire, commercial grade. The tie-wire shall be tightened so that the wire shall not be depressed in the hose.

* 3.5 Workmanship. The hose assembly shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels (AQL). The hose assembly shall conform to the following workmanship requirements:

a. Hose assembly components shall not be fractured, broken, bent, dented or malformed.

b. Hose fittings and tie-wire shall be free from burrs, slivers, sharp edges or harmful projections.

c. Plated parts shall be free from rust areas, areas of no plating or visual evidence of embedded foreign matter.

d. Rubber hose shall be free of visual evidence of deterioration or separation of hose cover from inner tube, or surface cuts, cracks, pits, nicks, blisters, lumps, embedded foreign matter and shall be clean.

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.2.1 and tested as specified in table II. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

* 4.4.2 End item visual examination. The end item shall be examined for the defects listed in table I. The lot size shall be expressed in units of hose assemblies. The sample unit shall be one hose assembly. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 2.5 for major defects and 6.5 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Finish	Not as specified	X	
	Clamps, coupling and wrenches not zinc plated	X	
Design, construction and workmanship	Component missing, not as specified, fractured, broken, bent, dented or malformed	X	
	Hose fittings and tie-wire not free of burrs, slivers, sharp edges, or harmful projections		X
	Swivel coupling nut not free to rotate	X	
	Tie-wire twisted too tightly on rubber hose		X
	Splice fitting not located from 6 to 10 inches from male fitting		X
	Plated parts not free of rust areas, areas of no plating or visual evidence of embedded foreign matter	X	
	Rubber hose cover not free of visual evidence of deterioration, such as discoloration or dried-out appearance with surface cracks, or of separation of hose cover from inner tube by appearance of wrinkled surface	X	
	Not free of cuts, cracks, pits nicks, blisters, lumps, or deep bruises that expose reinforcement braid	X	
	Not free of light bruises that do not expose reinforcement braid, or hose not clean		X
Identification marking tag	Omitted; illegible; incomplete; incorrect, not spaced as specified, not secured with tie-wire on the outside of the rubber hose halfway between the ends of the hose assembly		X

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

* 4.4.2.1 End item dimensional examination. The first article or first produced hose assembly, when a first article is not required, shall be examined for conformance to the dimensions specified in this document and on the drawing. Prior to cutting test strips from the hose specimen of the first article or first produced hose assembly, the thickness of the cover and inner tube shall be measured using the reinforcement braid as the boundary line between the cover and inner tube. Any dimensions not within the specified tolerance shall be cause for rejection of the first article or first produced hose assembly.

* 4.4.2.2 End item testing. The hose assemblies shall be tested as specified in 4.4.2.3 and 4.4.2.3.1. For quality conformance testing, the lot size shall be expressed in units of hose assemblies. The sample unit shall be one completely assembled hose. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

* 4.4.2.3 First produced item testing. When a first article is not required, the first produced hose assembly shall be tested as specified in table II. Any nonconformance shall be cause for rejection of the first produced item. Any nonconformance shall be investigated as to cause, corrections made, and the next produced item shall be tested.

* 4.4.2.3.1 Lot by lot leak and burst testing. The hose assemblies shall be subjected to the test marked "X" in column 3 of table II.

* 4.4.3 Packaging examination. The fully packaged end items shall be examined in accordance with MIL-P-775 and for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling. Bulged or distorted container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

* 4.5 Methods of inspection. The test schedule shall be in accordance with table II. The first article or first produced hose assembly will be subjected to tests 4.5.1 and 4.5.2, leak and bursting tests, first. Test strips of inner tube or cover from the sample hose will then be cut lengthwise from 4 inches long hose specimens and will be tested in accordance with 4.5.3 through 4.5.7, as applicable.

TABLE II. Test methods

Test sequence	First article	Quality conformance	First produced item	Test	Test paragraph	Requirement paragraph
1	2	3	4	5	6	7
1	X	X	X	Leak	4.5.1	3.3
2	X	X	X	Burst Tensile strength and elongation	4.5.2	3.3.1.4
3	X		X	(a) Rubber hose (as received)	4.5.3.1	3.3.1.5.1
4	X		X	(b) Rubber hose (after aging)	4.5.3.2	3.3.1.5.2
5	X		X	Volume swell	4.5.4	3.3.1.6
6	X		X	Flammability	4.5.5	3.3.1.7
7	X		X	Low-temperature flexibility	4.5.6	3.3.1.8
8	X		X	Corrosion resistance	4.5.7	3.3.1.9

4.5.1 Leak test. The hose assembly shall be sealed at one end and attached to any air hose at the other end. A pressure of fifty (50) psi ± 5 psi shall be applied and the assembly immersed in water for not less than 3 minutes and observed for leaks to determine compliance with 3.3. Any nonconformance shall constitute failure of this test.

4.5.2 Bursting test. The bursting strength of the hose assembly shall be determined in accordance with Method 10011 of FED-STD-601 to determine compliance with the bursting strength requirements of 3.3.1.4. Any nonconformance shall constitute failure of this test.

Source: https://assist.dla.mil -- Downloaded: 202640-17T14:30Z
Check the source to verify that this is the current version before use.

4.5.3 Tensile strength and elongation tests.

4.5.3.1 Rubber hose (as received). Test strips of cover and tube of the rubber hose "as received" shall be tested for tensile strength and ultimate elongation in accordance with the tensile strength and ultimate elongation methods of ASTM D 412 to determine compliance with 3.3.1.5.1, as applicable. The test strips shall be free of pricker punch marks. Any nonconformance shall constitute failure of this test.

4.5.3.2 Rubber hose (after aging). Test strips of cover and inner tube of rubber hose shall be aged at 212° for 70 hours, plus or minus 1/4 hour in accordance with the air heat method of ASTM D 573. The aged strips shall be tested for tensile strength and ultimate elongation in accordance with ASTM D 412 to determine compliance with the tensile strength and elongation requirements of 3.3.1.5.2. Any nonconformance shall constitute failure of this test.

4.5.4 Volume swell test. Volume swell in terms of volume increase of test strips of cover and tube of the rubber hose (as received) shall be determined in accordance with Method 6211 of FED-STD-601 to determine compliance with the applicable volume swell requirements of tube and cover of 3.3.1.6. The immersion shall be a test fluid conforming to medium No. 6 of Method 6001 of FED-STD-601. The temperature of the fluid during immersion shall be 75°F ± 5°F. Any nonconformance shall constitute failure of this test.

4.5.5 Flamability test. A test specimen of the cover shall be held, outer surface up, in a clamp. The specimen shall be held in a bunsen burner flame, 1-1/2 inch inside the cone flame, until about 1/2 inch of the specimen is burning. The specimen shall then be removed from the flame and held horizontally, outer surface up, to determine compliance with flammability requirements of 3.3.1.7. Any nonconformance shall constitute failure of this test.

4.5.6 Low-temperature flexibility test. Test strips of the cover and tube of the rubber hose shall be tested for low-temperature flexibility in accordance with "the stiffness measurement in liquid media" of ASTM D 1053. The low temperature for starting the test shall be -55°C to determine compliance with the torsion modulus requirements of 3.3.1.8. Any nonconformance shall constitute failure of this test.

4.5.7 Corrosion test. Test plates shall be 1-inch by 2-inches by 1/4-inch of brass composition, half-hard, alloy 360 conforming to QQ-B-626. The plates shall be polished to a smooth finish. A tube specimen (1-inch by 1/4-inch by 0.030 inch, maximum) shall be placed between the plates, bolted and compressed from 0.005 to 0.009 inch. The assembly shall be heated in an oven for 1 hour at 100°F and then placed in a humidity test chamber at 100 percent relative humidity and 100°F for for 96 hours. A 10-inch dessicator containing 500-1000 milliliters of water placed in the oven at 100°F shall be an acceptable humidity

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.

chamber. After cooling and separation of the plates, the corrosion resistance rating shall be determined for compliance with the corrosion resistance requirements of 3.3.1.9. Any non-conformance shall constitute failure to pass this test.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Hose assemblies shall be preserved in accordance with the applicable level A requirements of MIL-P-775.

5.1.2 Commercial. Hose assemblies shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Level A hose assemblies shall be packed in accordance with level A requirements of MIL-P-775.

5.2.2 Level B packing. Level B hose assemblies shall be packed in accordance with level B requirements of MIL-P-775.

5.2.3 Commercial packing. Hose assemblies preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

* 5.3 Marking. In addition to any special marking required by the contract or purchase order, shipping containers shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable. The marking on the container shall also include the following in 1/4 inch letters:

Length
Cure date (quarter and year)
Part identification number (see 1.2.1)
After three years of storage, samples of these hoses shall be tested for low temperature flexibility and leakage

6. NOTES

6.1 Intended Use. The hose assemblies are for use with Heater, Space - MIL-H-12340, Burner, Oil - MIL-B-2029 and Adapter, Gravity Feed - MIL-A-10957.

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

* 6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number and date of this document.
b. Length of hose assembly and part identification number required (see 1.2 and 1.2.1).
c. When a first article is required (see 3.1, 4.3 and 6.3).
d. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).

* 6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

* 6.4 Subject term (key word) listing.

Hose
Rubber, Utility, Gasoline

* 6.5 Changes from previous issue. The margins of this document have been marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirments of this document based on the entire content as written, irrespective of the marginal notations and relationship to the previous issue.

Custodians:

Army - GL
Navy - YD
* Air Force - 99

Review activities:

Army - MD, ME
DLA - CS
* Air Force - 82

Preparing activity:

Army - GL

Project No. 4720-0761

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US ARMY NATICK RESEARCH
and DEVELOPMENT CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

STRNC-ES

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research
and Development Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:30Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-H-10868F	Hose Assembly, Rubber, Utility, Gasoline (1/4-Inch Inside Diam

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK/OP, 20 Nov 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:30Z
Check the source to verify that this is the current version before use.