MIL-I-10901H
28 March 1984
SUPERSEDING
MIL-I-10901G
7 March 1979

MILITARY SPECIFICATION

INSECT BAR: FIELD TYPE, NYLON NETTING

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This documents covers one type and size insect bar made from nylon netting.

2. APPLICABLE DOCUMENTS

* 2.1 Government documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

SPECIFICATIONS

FEDERAL

V-T-280	-	Thread, Gimp, Cotton, Buttonhole
V-T-285	-	Thread, Polyester
UU-P-268	-	Paper, Kraft, Wrapping
DDD-L-20	-	Label: for Clothing, Equipage, and Tentage (General Use)
PPP-B-636	-	Boxes, Shipping, Fiberboard

MILITARY

MIL-C-508	-	Cloth, Oxford, Nylon, 3 Ounce
MIL-C-3395	-	Cloth, Netting, Nylon

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research and Development Center, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 7210

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

MIL-T-3530 - Thread and Twine; Mildew Resistant or Water Repellent Treated
MIL-T-5038 - Tape, Textile and Webbing, Textile, Reinforcing, Nylon

STANDARDS

FEDERAL

FED-STD-751 - Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

DRAWINGS

U.S. ARMY NATICK RESEARCH AND DEVELOPMENT CENTER

5-4-502 - Insect Bar, Field Type, Nylon Netting; Assembly, Details and Sections

(Copies of documents required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Other publications. Unless otherwise specified, the following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this document to the extent specified herein.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Guide samples. Samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from the document may appear in the sample, in which case, the document shall govern.

3.2 First article. When specified, a sample shall be subjected to first article inspection and approval (see 4.3, 6.2 and 6.5).

3.3 Materials.

* 3.3.1 Cloth, netting, nylon. The basic material shall be woven nylon netting, 1.6 ounce, Olive Green 106, conforming to type I; or knitted nylon netting, 2.0-ounce, Olive Green 106, conforming to type II of MIL-C-3395.

* 3.3.2 Cloth, oxford, nylon. The material for the buttonhole stay and tie tape reinforcements shall be nylon oxford, 3-ounce Olive Green 106, conforming to type I, class 1 of MIL-C-508.

3.3.3 Tape, nylon. The nylon tape for the tie tapes shall be 3/4 inch wide conforming to type III, Olive Drab 7 of MIL-T-5038.

3.3.4 Thread, polyester. The polyester thread shall be sizes A and B, conforming to type I or II, any class, subclass A of V-T-285.

3.3.4.1 Color. The thread shall be dyed OD Shade S-1, C.A. 66022 and shall show fastness to weathering equal to or better than the standard sample (see 6.3). When no standard sample is available, the thread shall show good fastness to weathering.

3.3.5 Gimp. The gimp for reinforcing the buttonholes shall be cotton, No. 8, conforming to type I or II of V-T-280. The gimp shall be treated for mildew resistance in accordance with type I, class 1 of MIL-T-3530, and the color shall be that naturally imparted by the treatment.

* 3.3.6 Identification label. The identification label shall measure 3-1/2 ± 1/8 inches by 2-1/2 ± 1/8 inches and shall conform to type VI, class 5 of DDD-L-20.

3.4 Patterns. Patterns shall be made by the contractor and shall provide a 1/2-inch seam allowance for the nylon netting and nylon oxford. The measurements of the finished insect bar shall be as specified on Drawing 5-4-502. Allowance shall be incorporated into the patterns for the seams, hems and seaming take-up.

3.5 Construction. The construction shall conform in all respects to Drawing 5-4-502, table I and as specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

3.5.1 Stitches, seams and stitchings. All stitches, seams and stitching types, except bartacks, shall conform to FED-STD-751. The type of seam, stitching, and stitches per inch shall be as specified in table I. When two or more methods, seam or stitch types are given for the same part of the operation, any one of them may be used. Seam allowances shall be maintained and seams shall be sewn without raw edges, runoffs, twists, pleats, puckers or open seams.

3.5.1.1 Type 301 stitching. Unless otherwise specified, ends of all type 301 stitching shall be backstitched or overstitched 1 inch minimum except where ends are turned under in a hem or held down by other stitching. Thread tension shall be maintained so that there will be no loose stitching resulting in loose bobbin or top thread, or excessively tight stitching resulting in puckering of the materials sewn. The lock shall be embedded in the materials sewn.

3.5.1.1.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1 inch back of the end of the stitching. 1/

b. Thread breaks or two more consecutive skipped or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch in back of the defective area, and continue over the defective area and continue a minimum of 1 inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and restitching in the required manner. 1/

1/ When making the above repairs the ends of the stitching are not required to be backstitched.

3.5.1.2 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching. The chain portion of the stitching shall be on the inside of the insect bar. All repairs shall be in accordance with 3.5.1.1.1.a and 3.5.1.1.1.b.

3.5.1.3 Automatic stitching. Automatic machines may be used to perform any of the required stitch patterns provided the requirements for the stitch pattern, stitches per inch, and size and type of thread are met; and at least three or more tying, overlapping or backstitches are used to secure the ends of the stitching.

* 3.5.1.4 Bartacking. Bartacks shall be 1/2 ± 1/16 inch long, 1/8 ± 1/32 inch wide and shall contain 28 stitches. Bartacks shall be free from thread breaks and loose stitching.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

3.5.1.5 Thread ends. All thread ends shall be trimmed to a length of not more than 1/4 inch.

3.6 Repairs. Repairs such as mends, darns or patches are not allowed to be made to the insect bar.

3.7 Replacement of defective components. During the spreading, cutting and manufacturing process, components having material defects or damages that are classified as defects in 4.4.3 shall be removed from production and replaced with non-defective and properly matched components.

3.8 Manufacturing operations requirements. The insect bar shall be manufactured in accordance with the operations specified in table I. The contractor is not required to follow the exact sequence of operations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

TABLE I.

NO.	MANUFACTURING OPERATIONS REQUIREMENTS	STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
1.	Cutting.						
	a. The material shall not be stretched or subjected to tension during the laying up or cutting operation.						
	b. The insect bar shall consist of two to four panels of equal dimensions, four reinforcement stay pieces and ten tie tape reinforcements of nylon cloth and fourteen tie tapes (see Drawing 5-4-502).						
	c. Remnant ends and triangular pieces of netting produced in the cutting operation may be utilized by joining the parts with a vertical seam using the same seam type as for joining the four main panels. Not more than two splices on each insect bar, and not more than one splice on each panel are permitted.	301 or 401	LSc-2 LSc-2	12--16 12--16	B B	B A	
	d. Each tie tape shall be cut in one piece 24 ± 1 inches long.						
	e. Cut four reinforcement stays, with not less than 1/2 inch added allowance for hem, in accordance with the design and finished measurements shown on Drawing 5-4-502. As an alternate method, reinforcement stays may be cut to finished dimensions shown on Drawing 5-4-502, with edges pinked or fused without hemming.						
	f. Cut ten tie tape reinforcements 2 ± 1/8 inches square and pink edges.						

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-01-17T14:33Z
Check the source to verify that this is the current version before use.

TABLE I. (cont'd)

NO.	MANUFACTURING OPERATIONS REQUIREMENTS	STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
1.	Cutting. (cont'd)						
	g. Any part of the material containing a tear, hole or any other defect which may impair serviceability shall be replaced at time of cutting.						
2.	Stitch reinforcement stay pieces.						
	a. Position reinforcement stays on inside of netting as indicated on Drawing 5-4-502.						
	b. Turn edges of reinforcement stays (except the edge to be caught in the joining seam) 3/8 to 1/2 inch and stitch edge of stay pieces 1/8 to 3/16 inch from turned edge to inside of insect bar.	301	LSd-1	12-16	B	B	
	or						
	c. Reinforcement stays with pinked or fused edges shall be stitched directly to inside of insect bar with 1/8 to 3/16 inch stitch margin.	301	SSbd-1	12-16	B	B	
3.	Make buttonholes.						
	Make a well-worked 1/2 inch eyelet end taper bar buttonhole over No. 8 gimp. Buttonhole shall be positioned so that it will be parallel to ridge seam 1/4 to 1/2 inch from center to ridge seam, with the eyelet end aligned as shown on Drawing 5-4-502 for each buttonhole.	Buttonhole	---	48 per buttonhole	B	A	

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

NO.	TABLE I. (cont'd) MANUFACTURING OPERATIONS REQUIREMENTS	STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
4.	Joining component parts.						
	The panels shall be joined with a double-lapped double-stitched seam 3/16 to 5/16 inch gage with the buttonhole reinforcement pieces caught in the ridge seam. An identification label shall be sewn on the inside of the insect bar in the ridge seam 4 ± 1 inches from the end of the insect bar as shown on Drawing 5-4-502.	301 or 401	LSc-2 LSc-2	12-16 12-16	B B	B A	
5.	Hem bottom edge of insect bar.						
	Turn bottom edge of insect bar to the inside with raw edges turned in and single stitch. Hem to measure 3/8 to 1/2 inch wide. Selvage edge (see Drawing 5-4-502) shall not be hemmed.	301	EFb-1	12-16	B	B	
6.	Attach tie tapes.						
	a. Position the fourteen tie tapes on the outside of the insect bar as indicated on Drawing 5-4-502.						
	b. Four tie tapes shall be positioned on the ridge seam with the free ends of equal length ± 1 inch. Each tape shall be secured with a 1/2 inch bartack. The bartacks shall be approximately centered between the double rows of stitching. Bartacks shall not run off the edge of the tape.	Bartack	---	28 per bartack	B	B	

NATICK Form 903
1 Dec 76 EDITION OF 1 OCT 76 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-01-17T14:33Z
Check the source to verify that this is the current version before use.

NO.	TABLE I. (cont'd) MANUFACTURING OPERATIONS REQUIREMENTS	STITCH TYPE	SEAM AND STITCHING TYPE	STITCHES PER INCH	THREAD		
					NEEDLE	BOBBIN/ LOOPER	COVER
6.	Attach tie tapes. (cont'd)						
	c. Ten tie tapes shall be positioned on the body of the insect bar, (five on each half of body) in the location shown on Drawing 5-4-502. Fold tape evenly in half, ± 1 inch catching the netting material and the tie tape reinforcement in the fold and bartack with a 1/2 inch bartack, 1/4 to 5/16 inch from folded edge; through the double thickness of the tie tape, the double thickness of the netting and the double thickness of the tie tape reinforcement. Tie tape reinforcements shall be approximately centered under the point of attachment of the tie tapes. Bartacks shall not run off the edge of the tape.	Bartack	---	28 per bartack	B	B	
7.	Clean insect bars.						
	Trim, and remove, all thread ends to a length of not more than 1/4 inch. Remove all spots and stains.						
8.	Finished measurements.						
	The finished measurements of insect bar, including stay pieces, and the location of tie tapes, shall conform to the measurements shown on Drawing 5-4-502.						

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

3.9 Workmanship. The insect bar shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing operation to determine whether operations or sub-assemblies are accomplished as specified. Whenever nonconformance is noted, corrections shall be made to the parts affected and lot in-process. Parts which cannot be corrected shall be removed from production.

4.4.3 End item visual examination. The end item shall be for the defects listed below. The lot size shall be expressed in units of insect bars. The sample unit shall be one insect bar. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major and 15.0 for total (major and minor combined) defects.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor
Nylon oxford	Any hole, cut, tear, or smash	X	
	Abrasion mark or open place		X
Nylon netting	Any cut or tear	X	
	Mesh opening more than three times normal size	X	
Tape	Any hole, cut, or tear	X	
Seams and stitching:			
Open seams	Up to and including 1 inch on a single row of stitching		X
	More than 1 inch on single row of stitching	X	
	Any seam open on both rows of stitching	X	
NOTE:	A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more consecutive skipped or runoff stitches occur. On double stitched seams, a seam shall be considered open when or both sides of the seam are open.		
Raw edges	More than 1/2 inch when securely caught in stitching		X
NOTE:	Raw edges not securely caught in stitching shall be classified as open seams.		
Seam and stitch type	Wrong seam or stitch type	X	
	Seam pleated or puckered		X
Stitch tension	Loose tension resulting in loose top or bobbin thread		X
	Excessively tight tension resulting in puckering of material on seams		X

Source: https://assist.dla.mil -- Downloaded: 202610-17T14:33Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Classification Minor
Seams and stitching: (cont'd)			
Stitches per inch (except buttonholes and bartacks)	One to two stitches less than minimum specified 1/		X
	Three or more stitches less than minimum specified 1/	X	
	One or more stitches in excess of maximum specified 1/		X
	NOTE: Variation in the number of stitches per inch caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams shall be classified as follows:		
	Within the Major defect classification - Minor defect		
	Within the Minor defect classification - No defect		
	1/ Defect to be scored when condition exists on any one seam for a length of 5 inches or more, or when the combined length of several areas exceeds 8 inches.		
Stitching ends (on type 301 stitching)	Not secured as specified (except when caught in other stitching or turned under in a hem)		X
Thread breaks, skipped stitches or runoffs	Overstitched less than 1 inch in each direction beyond the defective stitching area		X
	NOTE: Thread breaks or two or more consecutive skipped or runoff stitches not overstitched shall be classified as open seams.		

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Minor
Components and assembly	Any required component or part of insect bar omitted (unless otherwise classified herein)	X	
	Any required operation omitted or not preformed as specified	X	
	Needle chews	X	
	Mend, darn, or patch	X	
	Any unauthorized repair	X	
	Any required row of stitching omitted	X	
	Looper thread (type 401 stitching) showing on outside of insect bar		X
Cutting	Any component part not cut in conformance with specification requirements	X	
Body	Either side of body constructed with more than one horizontal seam	X	
	Constructed with more than two vertical splices or more than one vertical splice in any panel		X
Hems	Constructed with a single turn-under instead of double		X
Tie tapes	Body tapes attached through single thickness of netting or through single thickness of tie tape reinforcement	X	
	Ridge tapes not attached through seam	X	
	Ends of tapes not fused		X
	Any tape spliced or not cut in one piece as specified		X
Buttonholes	Not constructed as specified	X	
	Any omitted or uncut	X	
	Stitching incomplete, loose, or broken		X
	Not parallel to ridge seam		X
	Eyelet end reversed, i.e., facing body		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

Examine	Defect	Classification Major	Classification Minor
Bartacks	Any bartack omitted		X
	Number of stitches not as specified		X
	Stitching loose, incomplete, or broken		X
	End of bartack runs off edge of tie tape		X
Cleanness	Dirt, grease, or oil stains clearly noticeable; thread ends not trimmed as specified throughout		X
Identification label	Omitted, illegible, incorrect or size of characters and label not as specified		X
	Located on incorrect side of insect bar		X

4.4.4 End item dimensional examination. The end item shall be examined for the defects listed below. The lot size shall be expressed in units of insect bars. The sample unit shall be one insect bar. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 4.0 for major defects and 25.0 for total (major and minor combined) defects.

Examine	Defect	Classification Major	Classification Minor
Overall dimensions	Any smaller than specified dimension less the applicable minus tolerance indicated on drawing	X	
	Any larger than specified dimension and applicable plus tolerance indicated on drawing		X
Dimensions other than overall including stitch margin and gage	Any not within specified tolerance		X

4.4.5 Packaging inspection. An examination shall be made to determine that the preservation, packing, and marking comply with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

shall be one shipping container fully packaged with the exception that it need not be closed. Examination of closure defects listed below shall be made on shipping containers fully packaged. The lot size shall be the number of shipping containers in the inspection lot. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and unit packs)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as incomplete closure of container flap, inadequate stapling, improper taping, or loose strapping. Bulged or distorted container.
Content	Number of unit packs per container is more or less than required. Number of insect bars per unit pack is more or less than required. 1/

1/ For this defect, one unit pack shall be examined from each shipping container in the sample.

* 4.4.6 Palletization examination. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully packaged. The lot size shall be the number of palletized unit loads in the inspection lot. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each insect bar shall be laid out flat as shown on Drawing 5-4-502. The two triangular ends shall each be folded over to the center forming a rectangle. The width (approximately 68 inches) shall be folded over in thirds, with the last fold overlapping the first fold, to measure approximately 23 inches. The length (approximately 74 inches) shall then be folded over in fifths, starting at one end, to a dimension of approximately 14-1/2 inches. Ten folded insect bars shall be evenly stacked to form a bundle measuring approximately 23 x 14-1/2 x 7-1/2 inches. Each bundle shall be securely crosstied with cotton tape or twine.

* 5.1.2 Commercial. The insect bars shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. Twenty insect bars, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15C of PPP-B-636. Level A unit packs shall be packed flat, two in depth within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.2.2 Level B packing. Twenty insect bars, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container, conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Level A unit packs shall be packed flat, two in depth within a shipping container. Inside dimensions of each container shall approximate 23-1/2 inches in length, 15 inches in width, and 15 inches in depth. Approximate dimensions are furnished as a guide only. Each container shall have the contents completely covered on the top and bottom with a sheet of 30-pound

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.2.2.1 Weather-resistant fiberboard container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636 except the inspection shall be in accordance with 4.4.5.

* 5.2.3 Commercial packing. Insect bars, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951, as applicable.

5.3 Palletization. When specified (see 6.2), insect bars, packed as specified in 5.2, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. This document covers the requirements for insect bars to be used by personnel of the Department of Defense.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number and date of this document.
b. When a first article sample is required (see 3.2, 4.3 and 6.5).
c. Selection of the applicable levels of preservation and packing (see 5.1 and 5.2).
d. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
e. When palletization is required (see 5.3).

6.3 Samples. For access to samples address the contracting office issuing the invitation for bids.

6.4 Netting widths. All procurement of netting for this item should be made in 35-inch or 70-inch widths since the full width of the netting, including selvage; used in the insect bar, provides for economical cutting.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

6.5 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of DAR 7-104.55. The first article should be a preproduction sample consisting of at least one complete insect bar. The contracting officer should include specific instructions in all acquisition documents, regarding arrangements for inspection and approval of the first article.

6.6 Changes from previous issue. The margins of this document are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activities:

Army - MD
Air Force - 82
DLA - CT

User activities:

Navy - MC
Air Force - 45

Preparing activity:

Army - GL

Project No. 7210-0261

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY
US Army Natick Research and Development Center
Natick, Massachusetts 01760

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development Center
ATTN: STRNC-ES
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-I-10901H	Insect Bar: Field Type, Nylon Netting

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OPR 1 Apr 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:33Z
Check the source to verify that this is the current version before use.