COMMERCIAL ITEM DESCRIPTION

LABEL, PAPER, PRESSURE-SENSITIVE ADHESIVE

The General Services Administration has authorized the use of this Commercial Item Description in preference to Federal Specification UU-L-1644, which has been cancelled.

1. SCOPE

This Commercial Item Description covers pin-feed and slot-feed, non-removable, die cut pressure-sensitive adhesive coated, paper labels.

2. CLASSIFICATION

Pressure-sensitive adhesive paper labels covered by this specification shall be of the following classes, styles, types and forms.

Class A - General purpose labels, with marginal pin-feed holes.
Class B - General purpose labels, with slot-feed holes.

Style 1 - Rectangular, rounded corners.
Style 2 - Rectangular, square corners.

Type A - Solid (white or colored).
Type B - With a identification stripe.
Type C - With a border.

3. SALIENT CHARACTERISTICS

A. Paper: The labels shall be made of bleached chemical woodpulp which may contain a maximum of 25 percent unbleached or groundwood. The paper shall have a basis weight (before gumming) of 74.0 to 96.2 gms/m^2 (50 to 65 lb. 25 X 38-500) -5%, +unlimited, when tested in accordance with TAPPI test method T410. The paper shall be uniform in texture with a smoothly finished surface and shall be sized so that inked impressions from typewriter ribbons, ball point pens, and drawing ink will be well defined and will not feather.

B. Construction: The labels shall be furnished as specified in the contract or order, completely coated on one side with a uniform film of pressure-sensitive adhesive. The labels shall be mounted on a release liner or backing sheet.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Federal Supply Service, 26 Federal Plaza, New York, NY 10278 ATTN.: Engineering Branch (2FYEE).

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

C. Release liner: The release liner or backing sheet shall be coated with a release coating sufficient to allow manual peel off of the label, but will prevent peel off or separation of the label from the liner/sheet, when the carrier sheet with label is passed over the outside of a convex surface, having an outside diameter of one inch. The backing sheets shall be such that they will not tear in pin-feed or slot-feed operations and shall conform to the physical requirements of Paragraphs E and F.

D. Pressure-sensitive adhesive: The pressure-sensitive adhesive shall require no heat, moisture, or other preparation prior to application. Labels shall tack quickly to paper, wood, plastic, glass, and fiberboard, and shall adhere without wrinkling, curling, or lifting at any edge. The pressure-sensitive adhesive shall display a minimum adhesion of 66N/100mm width (60 oz./in.) when tested in accordance with paragraph 5B.

E. Dimensions: The labels shall be the dimensions as specified in the contract or ordering document. For Class A labels the backing sheet shall have the width indicated.

Label width* mm (inches)	Label length* mm (inches)	Width of backing sheet mm (inches)
88.9 mm (3-1/2 in)	23.8 mm (15/16 in)	114.3 mm ± 6.3 mm (4-1/2 ± 1/4 in)
101.6 mm (4 in)	36.5 mm (1-7/16 in)	127 mm ± 6.3 mm (5 in ± 1/4 in)
127 mm (5 in)	23.8 mm (15/16 in)	152.4 mm ± 6.3 mm (6 in ± 1/4 in)
101.6 mm (4 in)	36.5 mm (1-7/16 in)	335.7 mm ± 0.7 mm (13-7/32 in ± 1/32 in)

* Dimensional tolerances as specified in paragraph 1G shall apply.

F. Form: The labels shall be furnished in the form specified in the contract or ordering document. The purchaser shall specify if perforations are required and the location. For Class A labels the backing sheet shall have 3.96 mm (5/32 inch) diameter holes running vertically along each margin. The holes shall be spaced 12.7 mm (1/2 inch) apart from center to center and the centers of the holes shall be located 6.35mm +0, or -1.59 mm (1/4 inch +0, or -1/6 inches) from the edge of the backing sheet. Vertical lines passing through the centers of any two marginal holes on the same line shall be at 90° to the vertical lines through the centers of the holes. For Class B labels the backing sheet shall be 88.9 mm (3- 1/2 inches) wide and have horizontal slit perforations across its width every 57.15 mm (2-1/4 inches) of the length. Labels shall be centered between the width of the backing

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

sheet and the horizontal perforations. A horizontal feed slot, 3.17 mm (1/8 inch) high by 12.7 to 15.9 mm (1/2 to 5/8 inches) wide shall be centered on the horizontal slit perforations between labels.

G. Tolerances: A tolerance of +/- 0.794 mm (1/32 inch) shall be permitted for dimensions over one inch, and +/- 0.397 mm (1/64 inch) for dimensions under one inch for all label dimensions. A tolerance of +/- 1.588 mm (1/16 inch) shall be permitted for the identification stripe or border width on any one label.

H. Bleaching. To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Workmanship: The labels and backing sheets shall be clean, free from lint, dust, spots, scorches, folds, wrinkles, holes and any other defects which may affect the serviceability, durability, or appearance. Pin-feed and slot-feed holes shall be cleanly punched and free of confetti. There shall be no breaks in the fanfolded packs and no labels shall be missing from the backing sheet.

4. REGULATORY REQUIREMENTS:

The contractor shall certify that the minimum content standard shall be no less than 50% recovered materials including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definition of post consumer materials and recovered materials in sections 203 and (205). As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5. TABLES AND TESTS:

Table 1. Physical requirements for paper without adhesive.

	Requirement	Test Method
Basis Weight	74.0 to 96.2 g/m^2 (50 to 65 lb. 25 X 38-500) tolerance: -5%, +unlimited	T410

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

A. **Printing and writing qualities:** The labels shall be tested for printing and writing qualities as follows: Lines or characters shall be drawn or written on the writing surface of the label with a medium point "roller ball" type pen. To be considered satisfactory there shall be no feathering of the inked lines or characters.

B. **Adhesion:** The adhesive side of each of three labels shall be firmly pressed in contact with: 1) an 215.9 mm by 279.4 mm (8-1/2 X 11 inch) specimen of standard reference material, as specified in ASTM D 3654. 2) grade V3c or V3s fiberboard. Roll the labels once in each direction with a soft rubber covered hinged iron roller. To be considered satisfactory, the labels shall immediately tack to the surfaces without curling or tearing. After two hours elapsed time, the adhesive quality shall be considered satisfactory if: the labels cannot be removed from the test surfaces without fiber separation.

6. **QUALITY ASSURANCE:**

Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description, where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements (See Section 7, Ordering Data).

Each lot of Paper Labels shall be inspected for conformance to the requirements herein. Sampling for inspection shall be in accordance with ANSI/ASQC Z1.4 using the plans specified below.

A. Visual and Dimensional characteristics - Inspection Level S-2 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one box, book, fanfold or sheet of labels.

B. Sampling for end item testing - Inspection Level S-1 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one label selected at random from the issue unit. Not more than five labels shall be selected from any one issue unit. Characteristics of the component paper stock tested for conformance to the requirements in Section 1 do not have to be retested under end item testing. A certified test report is evidence that the paper has passed the required test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

7. PREPARATION FOR DELIVERY:

Packaging, packing and marking shall be as specified in the contract or purchase order.

8. REFERENCED DOCUMENTS:

The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, PO Box 105113
Atlanta, GA 30348
(404) 446-1400

ASTM test methods are available from:

American Society for Testing and Materials
ATTN.: Consumer Service
1916 Race Street
Philadelphia, PA 19103
(215) 299-5585

ANSI/ASQC Z1.4 is available from:

American National Standards Institute
11 West 42nd Street
New York, NY 10036
(212) 642-4900

40 CFR pt. 250 is available from:

The Code of Federal Regulations (CFR) and Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, US Government Printing Office, Washington, DC 20402.

9. NOTES:

A. Ordering Data:

Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Class, style, type and form.
(2) Dimensions.
(3) Color of label.
(4) Color of identification stripe or border.
(5) If bleaching with chlorine compound or hypochlorite is prohibited.
(6) Specific packaging, packing, palletization and, marking requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

B. **Item Identifiers/Reference Part Number System (For Cataloging Use Only)**

AA2832 - B1A: This example describes rectangular, solid colored labels with rounded corners and marginal punching. (Color as specified in the contract or order).

- TYPE A - Solid (white or colored).
  B - With a identification stripe.
  C - With a border.
- STYLE 1 - Rectangular, rounded corners.
  2 - Rectangular, square corners.
- CLASS A - General purpose labels (marginal pin-feed holes.)
  B - General purpose labels (slot-feed holes).

C. **National Stock Numbers (NSNs).** The following is a list of NSNs assigned which correspond to this CID. The list may not be indicative of all possible NSNs associated with the CID.

7530-00-007-2165	7530-00-577-4370	7530-00-982-0062
7530-00-054-1575	7530-00-577-4371	7530-00-982-0064
7530-00-082-2661	7530-00-577-4372	7530-00-982-0065
7530-00-082-2662	7530-00-577-4373	7530-00-982-0066
7530-00-082-2663	7530-00-577-4374	7530-01-015-6402
7530-00-194-9643	7530-00-577-4375	7530-00-576-5004
7530-00-577-4368	7530-00-577-4376	7530-01-239-6720
7530-00-577-4369	7530-00-781-6216	

Military custodians:

Army - GL
Navy - SA

Preparing activity:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.