6 June 1966
SUPERSEDING
MIL-T-12755B
22 June 1962

MILITARY SPECIFICATION

TAGS, BLANK, CABLE IDENTIFICATION

(CABLE MARKERS MX-892 ( )/G, MX-893 ( )/G, MX-894 ( )/G,

and MX-895 ( )/G)

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE AND CLASSIFICATION

1.1 Scope.- This specification covers one type and four colors of plastic tags.

1.2 Classification.-

1.2.1 Colors.- The tags shall be furnished in the following colors as specified (see 6.2).

(a) Red
(b) Yellow
(c) Green
(d) White

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

L-P-535	-	Plastic Sheet (Sheeting and Film); Vinyl Chloride Polymer and Vinly Chloride-Vinyl Acetate Copolymer, Rigid.
UU-T-111	-	Tape; Paper, Gummed (Sealing and Securing).
PPP-B-566	-	Boxes, Folding, Paperboard.
PPP-B-636	-	Box, Fiberboard.
PPP-B-676	-	Boxes, Setup.

/FSC 9905/

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-G-16491 - Grommet, Metallic.
MIL-B-43291 - Boxes: Fiberboard, Corrugated, Double-Wall, Weather Resistant.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

MUNSELL BOOK OF COLORS

(Application for copies should be addressed to the Munsell Color Company, 2441 No. Calvert St., Baltimore 18, Maryland).

STEEL PRODUCTS MANUAL, WIRE AND RODS, CARBON STEEL, dated December 1963

(Application for copies should be addressed to the American Iron and Steel Institution, 150 East 42nd Street, New York 17, New York).

3. REQUIREMENTS

3.1 Preproduction sample.- Unless otherwise specified (see 6.2), before production is commenced, six finished samples of each color tag (being procured) covered by this specification, shall be submitted or made available to the contracting officer or his authorized representative for approval in accordance with 4.2. The approval of the preproduction sample authorizes the commencement of production, but does not relieve the supplier of responsibility for compliance with all applicable provisions of this specification. The preproduction sample shall be manufactured in the same facilities to be used for the manufacture of the production items.

3.2 Material.-

Source: https://assist.dla.mil -- Downloaded: 202640-17T23:16Z
Check the source to verify that this is the currenversion before use.

* 3.2.1 Plastic.- The plastic sheet stock used in the manufacture of cable markers shall meet the requirements of L-P-535, composition A, type II or composition B, type I, grade A except thermal stability and volume resistivity requirements shall not be applicable.

3.2.2 Grommet.- The grommet shall conform to type I, class 3, size 00 of MIL-G-16491.

* 3.2.3 Wire.- The wire shall be fine manufacturers tag wire, 12 ± 1/16 inches in length, No. 23 steel wire gauge, 0.0258 inch nominal diameter, with a standard galvanized finish. It shall meet the requirements of the American Iron and Steel Institution's Products Manual, Wire and Rods, Carbon Steel.

3.3 Design, construction and dimensions.-

3.3.1 Corners.- The corners at one end of each tag shall be cut along diagonal lines running between each of two points, 1/4 inch in from the outer edges, along end (width of tag) and the corresponding adjacent points 3/16 inch in from end, along sides (length of tag). This cut end shall be the top of the tag. The cut edges shall be free from cracking, spalling and chipping.

3.3.2 Grommet (location).- The grommet specified in 3.2.2 shall be centered 7/16 inch from the top edge of each tag and midway between the two outer (lengthwise) edges at the top of the tag. The area around grommet shall be free from cracking, spalling and chipping.

3.3.3 Wire.- Each tag shall be furnished with the wire specified in 3.2.3 for securing the tag to wires and cables for which it is used. Half of a 12 inch length of this wire shall be passed through the grommet and bent 180° back on the other half. The two ends shall be twisted one full turn, close to the marker leaving two free ends of equal length.

TABLE I.- Tag Dimensions

Length	3-1/4 ± 1/16 inches
Width	1-5/8 ± 1/16 inches
Thickness	0.015 ± 0.0015 inch

3.4 Performance.-

3.4.1 Cold bend.- The tag shall not show breaks, or cracks, when tested as specified in table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

3.4.2 Heat stability of color.- The tag stock shall show not more than a slight change in color when tested as specified in table II. A slight color change is defined as one which is perceptible with difficulty.

3.4.3 Dimensional stability.- The tag stock shall show not more than a 5 percent dimensional change when tested as specified in table II.

3.5 Color.- The colors of the sheet stock shall approximate the following Munsell colors:

Cable marker identification	Requirement Munsell book notation
MX-892 ( )/G Red	5R 4/12 or brighter
MX-893 ( )/G Yellow	5Y 8/12 or brighter
MX-894 ( )/G Green	5G 5/8 or brighter
MX-895 ( )/G White	(Neutral) 9.0 or lighter

3.6 Finish.- The tags shall have a matte finish on both sides when tested as specificed in 4.4.3.

3.7 Workmanship.- The finished tags shall be clean, uniform in color and shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the specified acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Inspection responsibility.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Preproduction inspection.- When required, inspection and testing of the preproduction samples shall be made for all provisions of this specification applicable to end product examination and test.

4.3 Sampling for inspection.- Sampling for inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated.

* 4.3.1 Component and material inspection.- In accordance with 4.1 above, components and materials shall be inspected and tested in accordance with all requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

4.3.1.1 Testing of components.- Tests shall be performed on samples from each lot and type of components and materials used in the fabrication of the end item for the applicable characteristics listed in table II. The sample unit shall consist of 1 square foot of tag stock material, randomly selected throughout the lot. The sample size shall be three. There shall be no evidence of failure to meet the specified requirements. Test reports shall include all values on which results are based.

TABLE II.- Testing of components and materials

Characteristic and component	Specification reference		Instruction for testing Requirements applicable to		Number determinations per unit	Results reported as
	Requirement	Test method	Individual unit	Lot average		Pass or fail
Heat stability of color	3.4.2	4.4.2	X	---	1	X
Dimensional stability	3.4.3	4.4.2	X	---	2 (1 each direction)	--- Numerically to nearest 0.1 percent

4.3.2 Inspection of the end item.-

4.3.2.1 Examination of the end item.- The end item shall be examined in accordance with the classification of defects set forth herein. The lot size shall be expressed in units of tags of each color for examination in 4.3.2.1.1 and 4.3.2.1.2, in units of primary containers for examination in 4.3.2.1.3 and in units of shipping containers for examination in 4.3.2.1.4. The inspection levels for purpose of determining the sample size in accordance with the provisions of MIL-STD-105 and the acceptable quality levels (AQL's) expressed in defects per hundred units shall be as follows:

Examination paragraph	Inspection level	AQL
4.3.2.1.1	I	2.5
4.3.2.1.2	S-3	2.5
4.3.2.1.3	S-3	---
4.3.2.1.4	S-2	4.0

4.3.2.1.1 Examination of the end item for defects of finish, color and workmanship.- The sample unit for this examination shall be one tag of the specified color. No more than 10 tags shall be drawn from any one primary container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

Examine	Defect
Finish	Not matte finished on both sides. Not as specified.
Workmanship	Scratches on surface. Any dirt on foreign matter greater than 1/4 inch in largest dimension. Any rough or sharp edges. Any deep gouge. Any chipping, cracking or spalling. Any cuts, blisters, bubbles, tears, scuffs, cracks, pits or creases. Wire not as specified. Brass grommet missing or not rolled over as specified.
Color	Not as specified. Not uniform or readily distinguishable. Any spot, stain or other discoloration affecting appearance.

4.3.2.1.2 Examination of the end item for defects in dimensions.- The sample unit for this examination shall be one tag of the specified color. No more than 5 tags shall be drawn from any one primary container.

Examine	Defect
Tag size	Any dimension variation exceeding the tolerance specified.
Corners	Not cut as specified.
Grommet	Not size specified. Not located as specified.
Wire	Not size specified. Length not as specified.

4.3.2.1.3 Examination of the intermediate package for defects in count.- The sample unit for this examination shall be one intermediate package (see 5.1.1). The average count per container shall be not less than the specified count. When practicable no more than one sample unit shall be drawn from any shipping container.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

4.3.2.1.4 Examination of preparation for delivery.- An examination shall be made to determine that markings, materials, workmanship, contents and weights comply with the requirements of Section 5 of this specification. The sample unit shall be one shipping container, fully packed, selected just prior to closing operation. Closed shipping containers shall be examined for closure defects. The lot size shall be the number of shipping containers submitted for acceptance at one time.

Examine	Defect
Markings (exterior and interior)	Incorrect; incomplete; illegible; omitted; of improper size, location, sequence or method of application.
Materials	Any nonconforming component; component missing, damaged or otherwise defective.
Workmanship	Inadequate application of components: such as incomplete closure of container flaps, loose or inadequate sealing, strapping or stapling, bulged or distorted container.
Contents	Number of intermediate packages per shipping container is more or less than required.

4.3.3 Testing of the end item.- The end item shall be tested for the characteristics indicated in table III, herein, from each lot presented for examination. The sample unit shall be two tags of the specified color. Five sample units randomly selected, shall be tested from each lot with no failure to meet the specified requirements.

TABLE III.- Instruction for testing

Characteristic	Specification reference		Requirement applicable to individual unit	Number determinations per unit	Results reported as Pass or fail
	Requirement	Test method			
Finish	3.6	4.4.3	X	1	X
Cold bend	3.4.1	4.4.1	X	1	X

4.4 Test methods.-

4.4.1 Cold bend.- The tag, together with a 1/4 inch diameter mandrel, shall be stored in a cold chamber at a temperature of -40° ± 2°F. for 24 hours. Then, while still at -40°F, the tag shall be bent across its lesser axis one half turn around the mandrel at a rate of 5 seconds per half turn. Examine for breaks or cracks.

Source: https://assist.dla.mil -- Downloaded: 202610-17T23:16Z
Check the source to verify that this is the current version before use.

4.4.2 Heat stability of color and dimensional stability.- Two tags, premeasured to the nearest 1/16 inch in length and width and 0.0015 inch in thickness, prior to heating, shall be subjected to a temperature of 212° ± 2°F. for 5 minutes in a circulating air oven. Examine for color change and dimensional change.

4.4.3 Finish.- A mark made with a 2H grade lead pencil using a pressure of ordinary writing shall be legible when viewed with the naked eye at a distance of 18 inches.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Packaging shall be level A or C as specified (see 6.2).

* 5.1.1 Level A.- Fifty tags of one color only, shall be tied, banded or wired together. One thousand tags of one color only, bundled as specified, shall be packaged in a snug-fitting fiberboard box conforming to style RSC, type CF, class domestic, variety SW, minimum grade 125 of PPP-B-636; folding paperboard box conforming to variety 1, style III, type B, class a of PPP-B-566; or setup paperboard box conforming to type I, variety 1, class A, style 4 of PPP-B-676. Box closure shall be secured with 2 inch minimum width gummed paper tape conforming to class 1 of UU-T-111. The full telescope style paperboard boxes shall have the tape applied at the center of the length opening and extend along the bottom and up each side at least 2 inches (see 6.3).

5.1.2 Level C.- Tags shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing.- Packing shall be level A, B or C as specified (see 6.2).

* 5.2.1 Level A.- Eight thousand tags of one color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V3c or V3s of PPP-B-636. Alternatively, shipping containers shall conform to style RSC, V15c of MIL-B-43291. Each container shall be waterproofed in accordance with the Appendix of PPP-B-636. Each shipping container shall be closed and reinforced with flat steel strapping or tape banding in accordance with the appendix of the applicable container specification.

5.2.2 Level B.- Eight thousand tags of one color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF or SF, class domestic, variety SW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II in the appendix of the container specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

5.2.2.1 When specified, shipping containers shall be fabricated from V3c or V3s fiberboard (see 6.2).

5.2.3 Level C.- Tags, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation.

5.3 Marking.- In addition to any special marking required by the contract or order, interior boxes and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.- The tags covered by this specification are intended for tactical use for line identification on field wires and cables.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Color required (see 1.2.1).
(c) Requirement for preproduction sample (see 3.1).
(d) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(e) Whether V-board shipping containers are required for level B shipments (see 5.2.2.1).

* 6.3 The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - GL
Navy - YD
Air Force - 69

Preparing activity:
Army - GL
Project No. 9905-0107

Review activities:
Army - GL, EL
Navy - YD, SA
Air Force - 69

User activity:
Navy - MC

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing Of DOD Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost Comments and the return of this form will be appreciated Fold on lines on reverse side, staple in corner, and send to preparing activity

SPECIFICATION Tags, Blank, Cable Identification (Cable Markers MX-892 ( )/G, MX-893 ( )/G, MX-894 ( )/G, and MX-895 ( )/G) - MIL-T-12755C

ORGANIZATION | CITY AND STATE

CONTRACT NO | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1 HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A GIVE PARAGRAPH NUMBER AND WORDING

B RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2 COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3 IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 202640-17T23:16Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01762

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRE-SS
Natick, Massachusetts 01762

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T23:16Z
Check the source to verify that this is the current version before use.