INCH-POUND

A-A-51186B
4 November 2005
SUPERSEDING
A-A-51186A
5 September 1996

COMMERCIAL ITEM DESCRIPTION

FILES, ROTARY, TAPERED, 14 DEGREE CONE SHAPE, RADIUS NOSE, HIGH SPEED STEEL OR TUNGSTEN CARBIDE

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers the requirements for tapered, cone shape, high speed steel or tungsten carbide type rotary files having an included angle of 14 degrees.

1.1 Intended use. The rotary files covered by this CID are intended for general-purpose machining and deburring.

2. CLASSIFICATION. The rotary files shall be of the following types, styles, sizes, and classes.

2.1 Type. The type to be furnished shall be as specified (see 7.3(b)).

Type I - High speed steel
Type II - Tungsten carbide

2.2 Style. The style to be furnished shall be as specified (see 7.3(c)).

Style A - Right-hand spiral fluting
Style B - Right-hand spiral fluting with chip breaker
Style C - Double cut fluting
Style D - Diamond cut fluting

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: STDZNMGT@dla.mil or Defense Supply Center Richmond (DSCR), ATTN: DSCR-VEB, 8000 Jefferson Davis Highway, Richmond, VA 23297-5616.

AMSC N/A FSC 3455

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

2.3 Size. Unless otherwise specified the size shall be one of the sizes listed in tables I and II (see 7.3(d)). If a rotary file is to be furnished with a shank diameter or cutter head diameter and length different from those listed in tables I and II, the shank diameter and cutter head diameter and head length shall be specified in the acquisition order (see 7.3(e)).

TABLE I. Type I, high speed steel rotary files, sizes, and characteristics.

Size	Characteristics		
	Shank diameter (inch)	Cutter head diameter (inch)	Cutter head length (inch)
1	1/4	1/4	5/8
2	1/4	1/4	3/4
3	1/4	5/16	7/8
4	1/4	5/16	1
5	1/4	3/8	1
6	1/4	1/2	1-1/8
7	1/4	5/8	1-5/16
8	1/4	3/4	1-1/2

TABLE II. Type II, tungsten carbide rotary files, sizes, and characteristics.

Size	Characteristics		
	Shank diameter (inch)	Cutter head diameter (inch)	Cutter head length (inch)
1	1/8	1/8	1/2
2	1/4	1/4	5/8
3	1/4	5/16	7/8
4	1/4	3/8	1-1/16
5	1/4	1/2	1-1/8
6	3/8	1/2	1-1/8
7	1/4	5/8	1-5/16
8	3/8	5/8	1-5/16
9	1/4	3/4	1-1/2
10	3/8	3/4	1-1/2

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

2.4 Class. Unless otherwise specified (see 7.3(f)), the class of rotary file to be furnished shall be as listed in table III for type I and table IV for type II files.

TABLE III. Number of teeth per circumference, type I rotary files.

Cutting head diameter (inch)	Teeth per circumference			
	Class A coarse cut	Class B medium cut	Class C fine cut	Class D extra coarse cut
1/4	10-13	14-16	17-21	4-9
5/16	10-14	15-18	19-22	4-9
3/8	12-17	18-22	23-30	6-11
1/2	14-20	21-26	27-35	8-13
5/8	17-22	23-29	30-40	10-16
3/4	18-24	25-32	33-44	12-17

TABLE IV. Number of teeth per circumference, type II rotary files.

Cutting head diameter (inch)	Teeth per circumference			
	Class A coarse cut	Class B medium cut	Class C fine cut	Class D extra coarse cut
1/8	8-11	12-15	16-20	4-7
1/4	10-14	15-19	20-26	4-9
5/16	10-14	16-20	21-26	4-9
3/8	13-17	18-24	25-38	6-12
1/2	16-20	21-28	29-39	8-15
5/8	18-23	24-30	31-47	10-17
3/4	19-28	30-36	38-49	12-18

3. SALIENT CHARACTERISTICS

3.1 General requirements.

3.1.1 Type I cutting heads. The cutting heads of type I rotary files shall meet the minimum requirements for standard high-speed steel described in annex 92a of ASTM A 600, "Standard Specification for Tool Steel High Speed", when tested in accordance with ASTM A 370, "Standard Test Methods and Definitions for Mechanical Testing of Steel Products".

3.1.2 Type II cutting heads. The cutting heads of type II rotary files shall be manufactured from tungsten carbide with a hardness of not less than 91.2 and not greater than 92.5 on the Rockwell "A" scale when tested in accordance with ASTM B 294, "Standard Test Method for Hardness Testing of Cemented Carbides".

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

3.1.2.1 Density. The cutting heads of type II rotary files shall have a density of 14.6 to 15.1 grams per cubic centimeter when tested in accordance with ASTM B 311, "Test Method for Density Determination for Powder Metallurgy (P/M) Materials Containing Less Than Two Percent Porosity".

3.1.2.2 Rupture strength. Type II rotary files shall have a transverse rupture strength of 220,000 pounds per square inch when tested in accordance with ASTM B 406, "Standard Test Method for Transverse Rupture Strength of Cemented Carbides".

3.2 Taper angle. The angle of taper of the type I and type II rotary files shall be 14 degrees as measured along the length of the cone on opposite sides of the file.

3.3 Fluting. The fluting of the rotary file shall be either right-hand spiral, right-hand spiral with chip breaker, double cut, or diamond cut, depending upon the style specified.

3.3.1 Style A rotary files. The style A rotary files shall have right-hand spiral fluting consisting of a right-hand helix. The helix angle measured from the centerline of the cutter head shall be between 15 degrees and 35 degrees inclusive.

3.3.2 Style B rotary files. Style B rotary files shall have right-hand spiral fluting with a left-hand spiral chip breaker along the periphery of the cutting teeth.

3.3.3 Style C rotary files. Style C rotary files shall have double cut fluting consisting of a series of left-hand spirals in conjunction with right-hand spirals that results in a wedge or chisel form cutting tooth. The number of left-hand spirals shall be between 40 percent and 60 percent of the number of right-hand spirals.

3.3.4 Style D rotary files. Style D rotary files shall have diamond cut fluting consisting of a series of left-hand spirals in conjunction with right-hand spirals that result in a pyramidal form cutting tooth. The number of left-hand spirals shall be from 70 percent to 90 percent of the number of right-hand spirals.

4. REGULATORY REQUIREMENTS

4.1 Recovered materials. The offeror/contractor is encouraged to use recovered materials to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

5. PRODUCT CONFORMANCE PROVISIONS

5.1 Product conformance. The products provided shall meet the salient characteristics of this CID, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The government reserves the right to require proof of such conformance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.


5.2 Market acceptability. The product offered must have been previously sold either to the government or on the commercial market.

6. PACKAGING

6.1 Preservation, packing, and marking. Preservation, packing, and marking shall be as specified in the acquisition order (see 7.3(g)).

7. NOTES

7.1 Part or identification number (PIN). The following PIN procedure is for government purposes and does not constitute a requirement for the contractor.



AA51186-1A4C indicates a high speed steel, right-hand spiral fluted, 1/4 inch shank diameter, 5/16 inch cutter head diameter, 1 inch cutter head length, fine tooth spacing type rotary file.

7.2 Sources of documents.

7.2.1 FAR. The FAR may be obtained from the Superintendent of Documents, P.O. Box 371954, Pittsburgh, PA 15250-7954. Electronic copies of FAR documents may be obtained from http://www.arnet.gov/far/.

7.2.2 ASTM standards. Copies of ASTM standards may be obtained from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959. Electronic copies of ASTM standards may be obtained from http://www.astm.org/.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

7.3 Ordering data. The acquisition order should specify the following:

a. CID document number, revision, and CID PIN.
b. Type of rotary file (see 2.1).
c. Style of rotary file (see 2.2).
d. Size of rotary file (see 2.3).
e. Shank and cutter head diameters and length, if different (see 2.3).
f. Class of rotary file (see 2.4).
g. Preservation, packing, and marking (see 6.1).

7.4 Subject term (key word) listing.

cutting head
deburring
fluting
shank diameter

MILITARY INTERESTS:	CIVIL AGENCY COORDINATING ACTIVITY:
Custodian: Air Force - 99	GSA - FSS
Review Activity: Air Force - 84	Preparing Activity: DLA - GS6
	(Project 3455-0191)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.