A-A-51201
3 September 1986

COMMERCIAL ITEM DESCRIPTION

TUBE, CENTRIFUGE, ROUND STEM BOTTOM, GRADUATED, 100 ml.

This commercial item description shall be used in preference to Military Specification MIL-T-36430(DM)

This commercial item description covers a centrifuge tube suitable for use in the determination of water and sediment in crude mineral oils.

Salient characteristics:

The centrifuge tube shall have a round bottom, shall be graduated and made from transparent borosilicate glass. The tube shall be in accordance with design markings and dimensions shown for pear shaped centrifuge tubes in ASTM Designation D96, except that area for marking may be enameled and inner diameter of the top of the tube shall be 15 ± 3 millimeters.

When filled with water to its rated capacity, the centrifuge tube shall not break or crack when centrifuged at a relative centrifugal force indicated in ASTM Designation D96.

Ring strain when tested in accordance with ASTM Designation E671, shall not be greater than temper No. 1, and any longitudinal strain, if present, shall be faint and highly diffused.

Workmanship. Shall be first class throughout. The centrifuge tube shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Each (EA). One tube as specified, constitutes one unit.

Reference standards. Where standards are referenced herein, the issue of that standard in effect on the date of solicitation shall be used to determine compliance with stated requirements.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

FSC 6640

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AMSC N/A

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

Inspections. Inspections, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics. Each centrifuge tube shall be tested to demonstrate its capability for proper operation.

Resistance to centrifugal force. Tubes shall be filled to the 100-milliliter graduation with water, placed in a centrifuge, and spun for 15 minutes at the maximum relative centrifugal force indicated in the ASTM Designation D96.

Strain. Tubes shall be tested in accordance with ASTM Designation E 671.

Permanency of marking. Gloss on enameled area for marking may fade. If area can accept a pencil mark after testing, area shall be considered as having passed the test.

Resistance to alkali. The centrifuge tube shall be immersed completely in 1N sodium hydroxide at room temperature, covered, boiled for 1/2 hour, and allowed to stand in the alkali for an additional 1 hour. The centrifuge tube shall then be removed from the alkali, thoroughly rinsed with water, and dried by rubbing vigorously with a cloth.

Hydrochloric acid. The centrifuge tube shall be immersed completely in concentrated hydrochloric acid (specific gravity 1.18) at room temperature, covered, boiled for 1/2 hour, and allowed to stand in the acid for an additional 1 hour. The centrifuge tube shall then be removed from the acid, thoroughly rinsed with water, and dried by rubbing vigorously with a cloth.

Sulfuric acid. The centrifuge tube shall be immersed completely in concentrated sulfuric acid (specific gravity 1.84) at room temperature and allowed to stand 1 hour. The centrifuge tube shall then be removed, thoroughly rinsed with water, and dried by rubbing vigorously with a cloth.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of the description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The offeror/contractor shall comply, and be responsible for compliance by their subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act and regulations promulgated thereunder, and the requirements of all other applicable Federal and State statutes and regulations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.

Recovered materials. Offerors/contractors are encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practical.

Preservation, packaging, and packing. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and conforms to applicable carrier's rules and regulations.

For information only. The following product, as of the date of this document, are purported by the following companies to meet the salient characteristics of the item(s) described herein:

Kimble Products	-	Part No. 45244
Corning Glass Works	-	Part No. 8200

NOTE: The following National Stock Number is covered by this document: 6640-00-290-4428.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing Activity:
DoD - MB

Agent:
DLA - DM

54799

Project No. 6640-1113

Location: CID-S3-1-20

☆U.S. GOVERNMENT PRINTING OFFICE: 1986 — 605-036/46067

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:52Z
Check the source to verify that this is the current version before use.