MILITARY SPECIFICATION

INTERIM AMENDMENT
CELLULOSE, COTTON
(FOR USE IN EXPLOSIVES)

This Interim Amendment is issued for use by the U.S. Army Armament Command with Military Specification MIL-C-206A dated 24 August 1962 and is approved for use by all Departments and Agencies of the Department of Defense.

Paragraph 1.2 Classification,

Class 1, Delete "9.9" poises max
and substitute: "10.9" poises max

Add the following:

"Class 3 - Viscosity - 4.4 poises min and 15.4 poises max." (see 6.3)

2.1 Federal,Add the following:

"FEDERAL

UU-P-31	-	Paper General Specification and Method of Testing
UU-P-268	-	Paper, Kraft Untreated Wrapping
MMM-A-260	-	Adhesive, Water-Resistant (For Sealing Waterproof Paper)
PPP-T-76	-	Tape, Pressure Sensitive Adhesive, Paper Water-Resistant (for Carton Sealing)
PPP-T-45	-	Tape, Gummed Paper Reinforced and Plain For Sealing and Securing

PUBLICATIONS.-Delete "Publications - ORDNANCE CORPS
ORD-M-608-11 - Procedure and Tables for Continuous Sampling by Attributes" in its entirety.

Paragraph 3.2 - Table I - Delete the Table in its entirety and substitute the following Table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T06:40Z
Check the source to verify that this is the current version before use.

"TABLE I - CHEMICAL AND PHYSICAL PROPERTIES

Property	Classes 1	2	3 (see 6.3)	Applicable Paragraph
Alkali Soluble Matter, % max	5.0	5.0	5.0	4.3.4
Ether Extractive Matter, % max	0.4	0.4	0.4	4.3.5
Ash, % max	0.5	0.5	0.5	4.3.6
Moisture Content, % min			5.0	4.3.1
max	7.0	7.0	9.0	
Viscosity, poises				
min	4.4	10.0	4.4	4.3.3.1
max	10.9	36.0	15.4	4.3.3.3
Second in 20 centimeter drop				
min	20.0	46.0	20.0	4.3.3.2
max	50.0	165.0	70.0	
Ream Weight Pounds/3000 sq ft at 0% moisture				
min	-	-	333	4.3.8
max	-	-	387	
Width of Sheet			See 6.3	
Diameter of Roll, inches				
min	-	-	38.5	4.3.9
max	-	-	41.5	
Thickness of Sheet, inches				
min	-	-	0.040	4.3.10
max	-	-	0.055	

Para 4.2.2 Examination.-Delete "ORD-M608-11" in its entirety.

Add new paragraph:

"4.2.3.2 Sampling for Class III cellulose cotton sheets.

4.2.3.2.1 Sampling by lot. A sample of five (5) rolls of cellulose cotton shall be selected at random from each lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T06:40Z
Check the source to verify that this is the current version before use.

4.2.3.2.1.1 For determination of chemical properties. Samples shall be taken by boring into each roll to a depth of 3 inches, with a tool which cuts a plug 4 inches in diameter. The plug shall be withdrawn and ten of the discs which make up the plug shall be removed as follows:

a. One disc from the second sheet from wrapper.
b. Two discs 2 inches deep.
c. Three discs 2 inches deep.
d. Four discs 3 inches deep.

Each roll shall be bored but once. The edge of the hole bored in the first roll shall be 2 inches from one end. The holes in the succeeding rolls shall be spaced at intervals of one-fifth the distance across the roll and staggered so as to take in the entire circumference of the roll.

4.2.3.2.1.2 For determination of physical properties. A sheet 72 inches in length shall be cut from each roll before boring (see 4.2.3.2.1.1) and subjected to the tests specified in 4.3.8, 4.3.9 and 4.3.10.

4.3.8 Weight, Ream. The ream weight shall be determined in accordance with Specification UU-P-31 method 110 except that the result shall be reported in pounds per 3000 square feet at 0.0 percent moisture.

4.3.9 Width of Sheets and roll diameter. The width of sheet and roll diameter shall be measured with a gage.

4.3.10 Sheet thickness. The sheet thickness shall be determined in accordance with Specification UU-P-31, Method 173.

Add new paragraph:

5.3 Packing for Class III Cellulose Cotton Sheets

5.3.1 Level A. Unless otherwise specified, cellulose cotton shall be furnished in rolls approximately 30 inches wide (max) and 42 inches diameter (max) Each roll shall have a center void of approximately 3 inches inside diameter with a 3 inch plug. Rolls shall be suitably restrained from unwinding. Each roll

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T06:40Z
Check the source to verify that this is the current version before use.

shall be completely wrapped and headed with at least one thickness of Kraft paper, Grade B, 60 pound basis weight in accordance with Specification UU-P-268. The paper shall be sealed with Grade B adhesive in accordance with Specification MMM-A-260 or with four inch wide water-resistant tape complying with Specification PPP-T-45 or 3 inch wide water-resistant tape complying with Specification PPP-T-76, centered along the edge of the paper and applied across the full width of the roll.

5.3.2 Level C. Unless otherwise specified, rolls, shall be packed to afford protection against damage during direct shipment from the supply source to the first receiving activity for immediate use. Shipment shall comply with Uniform Freight Classification Rules and Container Specification for truck shipments, as applicable.

5.4 Marking. Unless otherwise specified, marking shall be in accordance with MIL-STD-129.

6.1 Add "c width of sheet required"

6.3 Add a new paragraph - Class 3 material shall be supplied in sheet form with a nominal width of 30 inches unless otherwise specified in the contract or purchase order.

Custodian:
Army-PA

Preparing Activity:
Army-PA

Project Number: 9420-A007

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T06:40Z
Check the source to verify that this is the current version before use.